Room Temperature Reactivity Of Silicon Nanocrystals With Solvents: The Case Of Ketone And Hydrogen Production From Secondary Alcohols: Catalysis?

Jehad El-Demellawi, Christopher R. Holt, Edy Abou-Hamad, Zeyad A. Al-talla, Youssef Saih, and Sahraoui Chaieb

ACS Appl. Mater. Interfaces, **Just Accepted Manuscript** • DOI: 10.1021/acsami.5b01231 • Publication Date (Web): 29 May 2015

Downloaded from <http://pubs.acs.org> on May 31, 2015

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.

ACS Publications
High quality. High impact.

ACS Applied Materials & Interfaces is published by the American Chemical Society.
1155 Sixteenth Street N.W., Washington, DC 20036
Published by American Chemical Society. Copyright © American Chemical Society.
However, no copyright claim is made to original U.S. Government works, or works
produced by employees of any Commonwealth realm Crown government in the course
of their duties.

Room Temperature Reactivity Of Silicon Nanocrystals With Solvents: The Case Of Ketone And Hydrogen Production From Secondary Alcohol: Catalysis?

Jehad K. El-Demellawi,¹ Christopher R. Holt,¹ Edy Abou-Hamad,² Zeyad A. Al-Talla,³ Youssef Saih,² and Sahraoui Chaieb^{1*}

¹Physical Sciences and Engineering Division, King Abdullah University of Science and Technology, Thuwal 23955-6900, Saudi Arabia

²KAUST Catalysis Center, King Abdullah University of Science and Technology, Thuwal 23955-6900, Saudi Arabia

³Analytical Core Laboratory, King Abdullah University of Science and Technology, Thuwal 23955-6900, Saudi Arabia

KEYWORDS: Silicon Nanocrystals; Heterogenous Catalysis; NMR; Mass Spectroscopy; Hydrogen Production; Alcohol Dehydrogenation

ABSTRACT

Although silicon nanoparticles dispersed in liquids are used in various applications ranging from bio-labeling to hydrogen production, their reactivities with their solvents and their catalytic properties remain still unexplored. Here, we discovered that, because of their surface structures and mechanical strain, silicon nanoparticles react strongly with their solvents and may act as catalysts for the dehydrogenation, at room temperature, of secondary alcohols (e.g. isopropanol) into ketones and hydrogen. This catalytic reaction was monitored by gas chromatography, pH measurements, mass spectroscopy and solid-state NMR. This discovery provides new understanding of the role played by silicon nanoparticles, and nanosilicon in general, in their reactivity in solvents in general as well as being candidates in catalysis.

INTRODUCTION

Nanoparticles are unique for two reasons: A large proportion of their atoms lie on the surface and these atoms do not necessarily order themselves in a similar fashion as those in bulk materials do.^{1,2} Because of their high surface-to-volume ratio, nanoparticles are used in a gamut of applications such as chemical sensors,³ optical devices⁴ in which size is important,⁵ energy harvesting⁶ as well as flexible devices⁷ and many more. One of their most extensive usages is in chemical synthesis and in particular their catalytic properties. Their sizes and shapes are indeed important to optimum catalytic activity.^{8,9-11} The size of nanoparticles can be finely tuned and their surface can be modified at the atomic level, which makes them ideal in heterogeneous catalysis. Apart from zeolites,¹² mostly zerovalent metallic nanoparticles are used in heterogeneous catalysis.¹³⁻¹⁹ Whereas HF-treated silicon nanowires were used as a photocatalyst in the reduction of Rhodamine B,²⁰ or to catalyze p-nitrophenol reduction in the presence of a reducing agent NaBH₄,²¹ or playing the role of an enzyme such as a reductase during the reduction of MTT used

1
2
3 in cells viability studies²² as well as used to enhance the photo-oxidation of water when com-
4
5 bined with TiO₂,²³ silicon nanoparticles on the other hand, are still mostly used for sensing and
6
7 photonic applications. To our best knowledge, there has been no report as yet on the use silicon
8
9 nanoparticles (SiNPs) in any catalytic reaction, although it is known that silicon react strongly
10
11 with oxygen (ΔH of Si-O bond formation is 452 kJ/mol.).²⁴ Reactivity in general and Catalysis in
12
13 particular is essentially a surface property. In order to detect any catalytic reaction on silicon one
14
15 must be able to synthesize mono-dispersed nanoparticles because catalysis requires high surface
16
17 area materials of very small size. Evidently this is a simplification of the catalytic phenomenon,
18
19 which is dependent not only on the dispersion but also on specific activity of the exposed crystal-
20
21 line planes and on morphology parameters (i.e. structures with corners versus spheres). For ex-
22
23 ample real breakthrough for this particle size-effect has been made by *Haruta* in the case of gold
24
25 for which dramatic increase of catalytic properties has been detected for small Au nanoparticles
26
27 (NPs).²⁵
28
29
30
31
32
33

34 We have been using an inexpensive method, through colloidal etching,⁵ to fabricate sili-
35
36 con nanoparticles whose size is around 2.5 nm (Figure 1 and description in supporting infor-
37
38 mation). It was therefore interesting to explore the possible catalytic properties of these nanopar-
39
40 ticles. The dehydrogenation of alcohols to aldehydes or ketones is a well-known industrial pro-
41
42 cess, and these reactions are primarily carried out on copper or palladium catalysts at high tem-
43
44 peratures because of their high selectivity to the dehydrogenation product. The principal catalyst
45
46 that has been used in these reactions is copper chromite,^{26,27} however, new EPA restrictions now
47
48 prohibit the disposal of chromite in landfills. The production of acetone for example is also usu-
49
50 ally performed at high temperature, which is not cost effective when done at large scales. Thus,
51
52 there is an incentive to develop new replacement catalysts, which contain no heavy metals and
53
54 which could be used at standards conditions of temperature and pressure. The simplest model
55
56
57
58
59
60

1
2
3 reaction chosen was the dehydrogenation of secondary alcohols (such as Isopropanol) to ketones
4 (Acetone) in water. (One of the reasons that spurred this interest is that silicon nanoparticles are
5 often stored for long periods of time in alcohols.) We want to disclose here that, to our surprise,
6
7
8
9
10 such reaction can now occur at room temperature and low pressure. Although such reaction is
11
12 known but it usually occurs at relatively high temperature with the usage of often-toxic cata-
13
14
15 lysts.²⁸
16

38
39 **Figure 1.** High Resolution TEM of a 2.5 nm SiNPs in the [111] directions.
40

41 42 **EXPERIMENTAL SECTION**

43
44
45 Colloidal silicon nanoparticles (SiNPs) were fabricated through *electrolytic stain etching*
46 and *electro-etching* of p-type single crystal (100-oriented) boron doped silicon wafers (Addison
47 Electronics).⁵ The silicon wafers were cleaved into 2.5 x 4.5 cm strips, and immersed in 50:1 so-
48
49 lution of deionized water and hydrofluoric acid (49%, Fluka) for 3-4 minutes for native oxide
50
51 removal. The silicon was then laterally anodized while being dipped into a 3:2:1 solution of hy-
52
53 drogen peroxide, H₂O₂, (30% by volume), methanol ($\geq$ 98% purity), and HF (49%, Fluka). A
54
55
56
57
58
59
60

current of 50-60 mA was supplied to each strip by a current supply through a platinum wire cathode. The strips were lowered into the etchant at a rate of 4 mm/hr and etched for 1 hour. To prevent excess heating due to the electric current, a heat exchanger was mounted underneath the etching bath. Temperatures in the bath were monitored by a thermocouple imbedded in the bath wall and were kept below 25°C while etching. Following etching, wafer strips were cleaned through brief dipping in deionized water followed by rinsing in absolute ethanol and then dried under a N₂ stream. The nanoparticles were dispersed into an organic solvent by sonicating the strips for 15 minutes. Unlike Belomoin *et al.*,⁵ no post-processing steps were used to break down larger structures and recover larger crystals. We were very careful to perform all experiments in controlled atmosphere. Hydrogen passivation is demonstrated in FTIR (Figure S1) and NMR spectra as seen below in the text.

High resolution transmission electron microscopy (HRTEM) images were recorded using a FEI Krios CT-TEM at an operating voltage of 120 kV. Fluorescence spectra were determined using a Horiba Fluoromax-4 spectrofluorometer. Absorbance measurements were carried out using a Genysis 10S UV-Vis Spectrometer (Thermo Scientific). FT-IR spectra were recorded using a Thermo Nicolet iS10 FT-IR spectrometer. Samples were prepared for FT-IR measurements by drying suspensions in KBr salts and pressing them into pellets.

Production of hydrogen was studied using micro- gas chromatography (Varian CP4900). The analysis of H₂ evolution was performed using a molecular sieve (5A) equipped with a pre-column and a backflush system to protect the molecular sieve. The amount of H₂ produced was determined using a thermal conductivity detector (TCD) with Argon as a reference gas (see supporting information for more details). Formation of ketones was detected using gas chromatography mass spectrometry (GC-MS) and flame ionization detection (GC-FID). Stock solutions containing 1.5 µg/ml of crystalline SiNPs were prepared in various secondary alcohols and

1
2
3 mixed with water in volume proportions from 1% to 30% (description in supporting infor-
4 mation). The solutions were mixed in the static headspace (SHS) of the gas chromatograph (GC)
5 where the analysis was performed. A two-way splitter was used to split the signal between the
6 mass spectrometry detector and the flame ionization detector for peak identification, detection,
7 and confirmation of the amounts of ketone produced. A Thermo Scientific glass Ag/AgCl double
8 junction semi-micro tip pH electrode connected to an Omega microprocessor pH meter with ATC
9 was used for pH measurements.
10
11
12
13
14
15
16
17
18

19 One-dimensional ^1H MAS, ^{13}C and ^{29}Si CP/MAS solid-state NMR spectra were recorded
20 on Bruker AVANCE III spectrometers operating at 900 MHz resonance frequencies for ^1H with
21 a conventional double resonance 3.2 mm CP/MAS probe at a spinning frequency of 20 KHz for
22 ^1H and ^{13}C and 10 KHz for ^{29}Si . Dry nitrogen gas was utilized for sample spinning to prevent
23 degradation of the samples. NMR chemical shifts are reported with respect to the external refer-
24 ences, TMS and adamantane, for ^1H and ^{13}C . For ^{13}C CP/MAS NMR experiments, the following
25 sequence was used: 90° pulse on the proton (pulse length 2.4 s), and then a cross-polarization
26 was achieved using a linear ramp of RF field amplitude on the ^1H channel, with a contact time of
27 2 ms for ^{13}C , 1 and 10 ms for ^{29}Si . The RF field strength was chosen for optimum transfer effi-
28 ciency. There was additional acquisition of the NMR signal under SPINAL-64 proton decoupling
29 at a RF field of 100 KHz. The delay between the scans was set to 4 s for ^{13}C and 5s for ^{29}Si to
30 allow the complete relaxation of the ^1H nuclei and the number of scans was 25,000 for ^{13}C ,
31 20,000 for ^{29}Si and 8 for ^1H . An exponential apodization function corresponding to a line broad-
32 ening of 40 Hz for ^{13}C and 100 Hz for ^{29}Si was applied prior to Fourier transformation.
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52

53 ^{29}Si direct polarization DP/MAS solid-state NMR spectra were recorded on Bruker
54 AVANCE III spectrometers operating at 900 MHz resonance frequencies for ^1H with a conven-
55
56
57
58
59
60

tional double resonance 3.2 mm probe at a spinning frequency of 10 KHz with an excitation pulse of 30° and a recovery time of 120 s and the number of scans was 10,000.

^1H - ^1H multiple-Quantum Spectroscopy: Two-dimensional double-quantum (DQ) and triple-quantum (TQ) experiments were recorded on a Bruker AVANCE III spectrometer operating at 900 MHz with a conventional double resonance 3.2 mm CPMAS probe, according to the following general scheme: excitation of DQ coherences, t_1 evolution, Z-filter, and detection. The spectra were recorded in a rotor synchronized fashion in t_1 ; that is, the t_1 increment was set equal to one rotor period (4.545 μs). One cycle of the standard back-to-back (BABA) recoupling sequence was used for the excitation and reconversion period. Quadrature detection in w_1 was achieved using the States-TPPI method. A spinning frequency of 22 KHz was used. The 90° proton pulse length was 2.5 μs , while a recycle delay of 5 s was used. A total 32 t_1 increments with 32 scans each were recorded. Double (DQ)- and Triple (TQ)-quantum proton spectroscopies under fast MAS have recently been shown to be powerful techniques to probe the structural information and dynamics inherent proton-proton dipolar couplings. The DQ frequency in the w_1 dimension corresponds to the sum of two single quantum (SQ) frequencies of the two coupled protons and correlates in the w_2 dimension with the two corresponding proton resonances. The TQ frequency in the w_1 dimension corresponds to the sum of the three SQ frequencies of the three coupled protons and correlates in the w_2 dimension with the three individual proton resonances. Conversely, groups of less than three equivalent spins will not give rise to diagonal signals in the spectrum. Two-dimensional DQ and TQ correlations experiments can thus be applied to determine in a reliable way the number of attached equivalent protons.

RESULTS AND DISCUSSION

In a typical experiment, 1.5 μg of SiNPs that are 2.5 nm in diameter are mixed with a water solution of isopropanol (33 mmol). Hydrogen is evolved²⁹ (Figure 2 and see Figure S6 in SI) and detected by micro-GC (micro- gas chromatography), acetone is formed and is detected by GC-MS (Figure 3 and see supporting information) in equimolecular amounts.

Figure 2. The amount of hydrogen produced during the reaction of 30% SiNPs suspended in isopropanol mixed with H₂O as a function of time. Water and IPA are mixed in the 7:3 proportions. The amount of Si in this experiment is 4.5×10^{-6} g.

Figure 2 shows hydrogen evolution during the catalytic reaction where Isopropanol containing Si-NPs is mixed with water. The molar amount of hydrogen produced at any given time is equal to the molar amount of acetone produced at the same time. Using a high resolution GC-MS we measured the amount of Acetone produced right after the nanoparticles are mixed with the water and alcohol solution. The amount produced as a function of SiNPs present in solution is plotted in figure 3. (The details of the detection is given in the supporting information.)

Figure 3. Amount of acetone in ppm produced during the catalytic reaction as a function of the concentration of SiNPs, in ppb by weight, contained in the IPA solution. Blue circles correspond to GC-FID results and the red squares correspond to GC-MS results. The line is a fit to a power law: $[\text{Acetone}] \sim [\text{Si}]^{3/2}$. There is a ratio of 1000 to 1 between the numbers of acetone molecules and silicon NPs. These data were retrieved from kinetics experiments (Figure S7 in SI).

The fit to the data shown in Figure 3 is captured by the following power law, which shows that only surface atoms interacted with the solvent atoms: $[\text{Acetone}] \sim [\text{Si}]^{3/2}$, where $[\text{Acetone}]$ is the concentration of acetone in mg/ml and $[\text{Si}]$ is the concentration of silicon nanoparticles in $\mu\text{g/l}$. A heuristic model of a surface reaction within a shell around the particles explains this reaction. Let ρ_{Si} be the density of silicon atoms that participate in the reaction. Since these atoms are fixed on the surface, they are related to the surface of the particles by the surface density given by $\rho_{\text{Si}} \sim M/l^2$, where l^2 is the surface of the nanoparticle. On the other hand, the density of acetone is given by $\rho_{\text{Acetone}} \sim M/L^3$, where L^3 is the volume at which the acetone is produced. If

these length scales are equal ($l=L$), meaning that the acetone exists in the same volume around the particles, then the densities are related by $\rho_{Acetone} \sim \rho_{Si}^{3/2}$ which is the correct fit of the data represented by the line. This simple argument enforces the idea that only surface silicon atoms contribute to the reaction and that only chemisorbed alcohols contribute to this process as demonstrated below using NMR.

To demonstrate the recyclability of the SiNPs we measured the rate of the reaction and found that, after the plateau value (Figure S7) we could start a new reaction by adding more water and we notice that more acetone is produced: The particles are recycled. We chose one ratio of water concentration to IPA containing the nanoparticles and performed GC-FID. Figure 4 shows the renewed activity when more water is added and when the kinetics reach a plateau (kinetic figures are depicted in Figure S7 in SI). This proves that the nanoparticles are *not consumed* during the reaction.

Figure 4. GC-FID chromatogram of 1.5ml of SiNPs-containing IPA in 3ml of water (black), the concentration of Si in this experiment is 1.5 $\mu\text{g/ml}$ of IPA. The peak response is directly propor-

tional to the amount of acetone produced. Notice the increase in the peak response when 1.5ml of water is added, successively (blue, red and green spectra), to the original suspension (black spectrum). Water is added when the kinetics curve flattens out and no more acetone is produced (Figure S7)

When increasing the amount of SiNPs, the pH drops exponentially with the amount of SiNPs added (Figure 5 shows the amount of protons produced when assuming that the mixture behave like a weak acid.). Notice that IPA mixed with water gives away more protons than any other solvent tested. Furthermore, the photoluminescence of these SiNPs are only slightly affected by this catalytic phenomenon (no variation of the structure as described in Figure S4 in supporting information). We are obviously dealing with a catalytic phenomenon, for which we tried to investigate the mechanism ^1H , ^{13}C and ^{29}Si -NMR

Figure 5. H^+ ions (protons) produced as a function of the addition of silicon nanoparticles (SiNPs) suspended in solvents and mixed with water at different volume fractions. The volume fraction of water to IPA varies from 100% to 90%. The initial concentration of silicon nanoparti-

cles is 1.5 $\mu\text{g/ml}$. The inset shows the dramatic decrease in the pH after adding SiNPs contained in IPA.

To determine and confirm that the surface silicon atoms react with IPA, we conducted extensive solid-state NMR experiments in which we observed the disappearance of the OH peaks of isopropanol and the appearance of a new resonances corresponding to protons on the surface of the particles. The ^1H magic-angle spinning (MAS) solid-state NMR spectrum of SiNPs suspended in IPA exhibits three signals at 1.5, 4.3 and 5.6 ppm (Figures 6A and Figure S14 in supporting information). The signal at 1.5 ppm in Figure 6B auto-correlates in the double-quantum (DQ) NMR experiment under 22 KHz MAS,^{30,31} which can be assigned to CH_3 of isopropanol. The peak at 4.3 ppm exhibits no autocorrelation in the DQ experiment and is assigned to the proton CH of isopropanol. Figure S14 shows that the solution ^1H NMR spectrum of isopropanol has the same chemical shifts. Furthermore, a correlation in the DQ/single-quantum (SQ) NMR spectrum between CH and CH_3 confirms the assignment of these two kinds of protons to IPA (Figure 7B). The ^{13}C CP/MAS NMR spectrum shows two peaks at 63 and 25 ppm corresponding to CH and CH_3 of isopropanol, respectively (Figure S15 in supporting information). In Figure 7A, we observe that the peak at 2.1 ppm, characteristic of OH (Figure S16 in supporting information), is absent in the 1D ^1H MAS spectrum, suggesting that a bond-forming reaction taking place between isopropanol and the SiNP surface. The new peak at 5.6 ppm exhibits no autocorrelation in the DQ spectrum that can be assigned to an isolated proton on the surface of the SiNPs.

Figure 6. (A) One-dimensional (1D) ^1H spin-echo MAS solid-state NMR spectrum of SiNPs suspended in isopropanol acquired at 900 MHz with a 22 KHz MAS frequency, a repetition delay of 5 s, and 8 scans. (B) Two-dimensional (2D) ^1H - ^1H double-quantum (DQ)/Single-Quantum (SQ) NMR spectra of SiNPs suspended in isopropanol acquired with 32 scans per t_1 increment, 5 s repetition delay, 32 individual t_1 increments.

To understand this proton coordination, we prepared two concentrations (30 and 15%) of SiNPs with IPA in H_2O and evaporated them at 50 mbar and room temperature for 85 minutes using a Vacuum RapidVap (Labconco, Inc.). The ^1H NMR spectra in Figure 7A and 7B show a clear increase in intensity and a small shift in the peak at 5.3 ppm in both concentrations. The ^1H NMR spectra of water shows a sharp peak at 4.2 ppm (Figure S17 in supporting information) and

the line fittings of the ^1H MAS NMR spectra of the 30% concentration (Figure S18 in supporting information) and the 15% concentration (Figure S19 in supporting information) ruled out the possibility of the presence of water. The autocorrelation in the DQ and Triple-Quantum (TQ) spectra for the peak at 5.3 ppm (Figure 7), however, in the 15% concentration of IPA containing SiNPs in water, suggests that the density of protons at the surface of the NPs is higher than when no water is added (Figure 6). This suggests an increase in the population of Si-H on the surface.

Figure 7. 1D ^1H spin-echo MAS solid-state NMR spectrum of (A) 30% (B) 15% SiNPs suspended in isopropanol in H_2O acquired at 900 MHz with a 22 KHz MAS frequency, a repetition delay of 5 s, and 8 scans. (C) 2D ^1H - ^1H double-quantum (DQ)/Single-Quantum (SQ) (D) 2D ^1H - ^1H Triple-quantum (TQ)/Single-Quantum (SQ) NMR spectra of 15% SiNPs suspended in isopropanol in H_2O acquired on 900 MHz NMR spectrometer under 22 KHz MAS frequency with

32 scans per t_1 increment, 5 s repetition delay, 32 individual t_1 increments. The mass of SiNPs is the same as above.

To confirm the existence of protons at the surface of the NPs and the existence of the Si-H species, we used direct-polarization (DP) and cross-polarization (CP) ^{29}Si NMR on SiNPs suspended in isopropanol (Figure 8) and 30% of SiNPs suspended in isopropanol in H_2O after evaporation (Figure 9). The ^{29}Si T_1 was reported to be 12,000 s for crystalline silicon nanoparticles.³² Therefore, in the DP experiment, an excitation pulse of 30° and a recovery time of 120 s were used to give us a qualitative but not quantitative signal, especially between the bulk and the surface silicon atoms. The DP MAS spectrum of SiNPs suspended in isopropanol (Figure 8) reveals a distribution of peaks between -30 and -70 ppm and centered around -50 ppm and largely unaffected by the removal of ^1H decoupling. These peaks are therefore due to silicon atoms that are not directly bonded to hydrogen atoms and can be assigned to crystalline silicon nanoparticles.

Figure 8. ^{29}Si NMR spectrum of SiNPs suspended in isopropanol using the direct-polarization (DP/MAS) acquired on a 900 MHz NMR spectrometer at 10 KHz MAS frequency with an excitation pulse of 300 and a recovery time of 120 s and 10,000 scans. The cross-polarization (CP/MAS) NMR spectrum of the same sample with two different contact times (10 and 1 ms) acquired at 900 MHz with a 10 kHz MAS frequency. The number of scans was 20,000, and the recycle delay was set to 5 s. An exponential line broadening of 100 Hz was applied prior to the Fourier transform.

Another peak distribution between -90 and -120 ppm and centered around -100 ppm was detected. It was affected by ^1H - ^{29}Si CP/MAS decoupling with different contact times, suggesting that this peak was due to the silicon atoms on the surface.³³ The CP technique is based directly upon dipole-dipole ^1H - ^{29}Si interactions and favors ^{29}Si signals of silicon atoms that are directly bonded to hydrogen atoms or close to each other because of the short contact time. We used a long contact time to probe if the Si atoms were attached to other Si atoms by Si-Si bonds or by Si-O-Si bonds. The difference between DP and CP can be understood on the basis that only DP can probe if the surface Si atoms are bonded to hydrogen. The CP/MAS spectra of SiNPs suspended in isopropanol using a long contact time (10 ms) shows the disappearance of the peaks around -50 ppm and a clear distribution at -82, -91, -100 and -110 ppm, indicating that the surface atoms are bonded exclusively to hydrogen atoms. However, the CP/MAS with a short contact time (1 ms) showed a few distributions with a higher intensity at -91 ppm that can be attributed to silicon atoms directly bonded to hydrogen. The DP for the 30% concentration of SiNPs suspended in IPA and mixed with H_2O shows higher intensities for the peak distributions around -100 ppm, suggesting an increased population of protons on the surface (Figure 9).

Figure 9. ^{29}Si NMR spectra of the 30% concentration of SiNPs suspended in isopropanol mixed with H_2O (black) and SiNPs suspended in isopropanol (red) using direct-polarization (DP/MAS) acquired on a 900 MHz NMR spectrometer using 10 KHz MAS frequency with an excitation pulse of 30° and a recovery time of 120 s, and 10,000 scans.

The “dissociative chemisorption” of isopropanol occurs on the SiNPs to produce an Si-H and an Si-isopropoxy radical. There are two possible mechanisms (Figure 10) for isopropanol chemisorption depending on the nature of the surface chemistry: if the SiNPs is covered by oxygen (e.g. bridging oxygen probably from water) dissociative chemisorption of isopropanol occurs as in mechanism A in Figure 10. However this does not explain the formation of protons (decrease of pH) and the formation of Si-H demonstrated by NMR.

In contrast and given the NMR results as well as the FTIR spectra (Figure S1) we can safely assume that the SiNPs are not fully covered by oxygen, and one can tentatively propose mechanism B where the surface of the SiNPs contains disilene and monohydride (Si-H) species as in Figure 10-mechanism B. (Si-H being electron-deficient could serve as electron sinks) First isopropanol dissociated on a highly electron deficient “Si=Si” with formation of isopropoxy sili-

con detected by NMR and a proton detected by pH measurements. Once the isopropoxy is chemisorbed, the next step of the mechanism is the beta-H elimination with formation of acetone and silicon hydride that was detected by NMR. This silicon hydride can react with protons to give hydrogen. There would be two competitive reactions with the silicon hydride: A reaction with protons to give hydrogen or simple adsorption.

Mechanism A **Mechanism B**

Figure 10. The two possible mechanisms for Acetone production, but only the mechanism B reproduce our results that were probed by NMR and pH measurements where the surface the nanoparticles is made of disilene bonds. The oxygen from Isopropoxy radical is a Hapto-2 Oxygen.

CONCLUSION

We have demonstrated the ability of silicon nanoparticles to be an efficient and recyclable catalyst for the dehydrogenation of a series of secondary alcohols. Ketones are produced (acetone in the case of Isopropyl alcohol) and hydrogen is evolved. The catalytic activity and performance is related solely to the surface composition. The presence of the Si-H bonds on the surface that are electron sinks may be necessary for the ketone production but our preliminary results show that the presence of disilene or Si=Si is necessary for the hydrogen evolution.

ASSOCIATED CONTENT

Supporting Information Available

Fourier Transform Infrared Spectroscopy (FTIR). Study of the effect of water on luminescence of silicon nanoparticles; along with the corresponding photoluminescence emission spectra. Discussion about the evidence of charge transfer; supported by pH measurements of silicon nanoparticles colloidal/water solutions. Gas chromatography for ketone production (GC-MS and GC-FID) from various secondary alcohols. ^1H liquid-state and solid-state magnetic resonance (NMR) spectroscopy as well as ^{13}C and ^{29}Si solid-state NMR. This material is available free of charge via the Internet at <http://pubs.acs.org>.

AUTHOR INFORMATION

Corresponding Author

* sahraoui.chaieb@kaust.edu.sa

Author Contributions

J.E. prepared all samples, did the GC-MS and micro-GC experiments as well as FT-IR, assisted with the photoluminescence, UV-Vis absorption measurements and the NMR experiments, and formatted the paper. C.H. prepared samples and did the pH as well as the UV-Vis absorption measurements. E.A. performed solid-state NMR experiments and analysis. Y.S. assisted with the micro-GC-TCD for the hydrogen detection. Z.E. assisted with GC-MS for the ketones detection. S.C. designed the experiments, wrote the paper and analyzed the data. All authors have given approval to the final version of the manuscript.

ACKNOWLEDGMENT

S.C. thanks J.-M. Basset for fruitful discussions and critical reading of the manuscript. We thank N. Kharbatia for his assistance with the GC-MS, and A. Emwas for his work on liquid NMR but not discussed in this paper. S.C. thanks Kun Li for assisting in acquiring the HRTEM image. We also thank King Abdullah University of Science and Technology (KAUST) for financial support.

REFERENCES

1. Alivisatos, A. P. Semiconductor Clusters, Nanocrystals and Quantum Dots. *Science* **1996**, *271*, 933-937.
2. Roduner, E. Size Matters: Why Nanomaterials are Different. *Chemical Society Reviews* **2006**, *35*, 583-592.
3. Elghanian, R.; Storhoff, J. J.; Mucic, R. C.; Letsinger, R. L.; Mirkin, C. A. Selective Colorimetric Detection of Polynucleotides Based on the Distance-Dependent Optical Properties of Gold Nanoparticles. *Science* **1997**, *277*, 1078-1081.
4. Colvin, V. L.; Schlamp, M. C.; Alivisatos, A. P. Light-Emitting Diodes made from Cadmium Selenide Nanocrystals and a Semiconducting Polymer. *Nature* **1994**, *370*, 354-357.

5. Belomoin, G.; Therrien, J.; Smith, A.; Rao, S.; Twesten, R.; Chaieb, S.; Nayfeh, M. H.; Wagner, L.; Mitas, L. Observation of a Magic Discrete Family of Ultrabright Si Nanoparticles. *Appl. Phys. Lett.* **2002**, *80*, 841-843.
6. Weigele, P.; Noren, C. J. Photocatalysts: Splitting Water with Viruses. *Nature Nanotechnology* **2010**, *5*, 313-314.
7. Segev-Bar, M.; Haick, H. Flexible Sensors Based on Nanoparticles. *ACS Nano* **2013**, *7*, 8366-8378.
8. Valden, M.; Lai, X.; Goodman, D. W. Onset of Catalytic Activity of Gold Clusters on Titania with the Appearance of Nonmetallic Properties. *Science* **1998**, *281*, 1647-1650.
9. Narayanan, R.; El-Sayed, M. A. Catalysis with Transition Metal Nanoparticles in Colloidal Solution: Nanoparticle Shape Dependence and Stability. *J. Phys. Chem. B* **2005**, *109*, 12663-12676.
10. Burda, C.; Chen, X.; Narayanan, R.; El-Sayed, M. A. Chemistry and Properties of Nanocrystals of Different Shapes. *Chem. Rev.* **2005**, *105*, 1025-1102.
11. Xia, Y.; Xiong, Y.; Lim, B.; Skrabalak, S. E. Shape-Controlled Synthesis of Metal Nanocrystals: Simple Chemistry Meets Complex Physics. *Angew. Chem., Int. Ed.* **2009**, *48*, 60-103.
12. Corma, A. State of the Art and Future Challenges of Zeolites as Catalysts. *J. Catal.* **2003**, *216*, 298-312.
13. Zhou, K.; Li, Y. Catalysis Based on Nanocrystals with Well-Defined Shapes. *Angew. Chem., Int. Ed.* **2012**, *51*, 602-613.
14. Aiken III, J. D.; Finke, R. G. A Review of Modern Transition-Metal Nanoclusters: their Synthesis, Characterization, and Applications in Catalysis. *J. Mol. Catal. A: Chem.* **1999**, *145*, 1-44.

15. Hughes, M. D.; Xu, Y.; Jenkins, P.; McMorn, P.; Landon, P.; Enache, D. I.; Carley, A. F.; At-
tard, G. A.; Hutchings, G. J.; King, F.; Stitt, E. H.; Johnston, P.; Griffin, K.; Kiely, C. J. Tun-
able Gold Catalysts for Selective Hydrocarbon Oxidation under Mild Conditions. *Nature*
2005, *437*, 1132-1135.
16. Lin, Y.; Finke, R. G. Novel Polyoxoanion- and Bu₄N⁺-Stabilized, Isolable, and Redissolva-
ble, 20-30-Å. Ir₃₀₀₋₉₀₀ Nanoclusters: The Kinetically Controlled Synthesis, Character-
ization, and Mechanism of Formation of Organic Solvent-Soluble, Reproducible Size, and
Reproducible Catalytic Activity Metal Nanoclusters. *J. Am. Chem. Soc.* **1994**, *116*, 8335-
8353.
17. Burch, R. Gold Catalysts for Pure Hydrogen Production in the Water-gas Shift Reaction:
Activity, Structure and Mechanism. *Phys. Chem. Chem. Phys.* **2006**, *8*, 5483-5500
18. Reetz, M. T.; Breinbauer, R.; Wanninger, K. Suzuki and Heck Reactions Catalyzed by Per-
formed Palladium Clusters and PalladiumNickel Bimetallic Clusters. *Tetrahedron Lett.*
1996, *37*, 4499-4502.
19. Lewis, L. N.; Lewis, N. Platinum-Catalyzed Hydrosilation-Colloid Formation as the Essen-
tial Step. *J. Am. Chem. Soc.* **1986**, *108*, 7228-7231.
20. Shao, M.; Cheng, L.; Zhang, X.; Duo Ma, D. D.; Lee, S. Excellent Photocatalysis of HF-
treated Silicon Nanowires. *J. Am. Chem. Soc.* **2009**, *131*, 17738-17739.
21. Xu, Y.; Wang, L.; Jiang, W.; Wang, H.; Yao, J.; Guo, Q.; Yuan, L.; Chen, H. Silicon Nan-
owire Arrays – A New Catalyst for the Reduction of Nitrobenzene Derivatives. *Chem-*
CatChem **2013**, *5*, 3788-3793.
22. Wang, H.; Jiang, W.; Yuan, L.; Wang, L.; Chen, H. Reductase-like Activity of Silicon Nan-
owire Arrays. *ACS Appl. Mater. Interfaces* **2013**, *5*, 1800-1805.

23. Hwang, Y. J.; Boukai, A.; Yang, P. High Density n-Si/n-TiO₂ Core/Shell Nanowire Arrays with Enhanced Photoactivity. *Nano Lett.* **2009**, *9*, 410-415.
24. Raabe G.; Michl J. Multiple Bonding to Silicon. *Chem. Rev.* **1985**, *85*, 419-509.
25. Haruta, M. Size- and Support Dependency in the Catalysis of Gold. *Catal. Today* **1997**, *36*, 153-166.
26. Nondek, L.; Seldlacek J. Mechanism of Dehydrogenation of Secondary Alcohols on Chromia. *J. Catal.* **1975**, *40*, 34-39.
27. Rioux, R.; Vannice, M. Hydrogenation/Dehydrogenation Reactions: Isopropanol Dehydrogenation over Copper Catalysts. *J. Catal.* **2003**, *216*, 362-376.
28. Cunningham, J.; Al-Sayyed, G. H.; Cronin, J. A.; Healy, C.; Hirschwald, W. Surface Synergisms between Copper and its Oxides in Catalytic Isopropanol/Acetone Interconversions at 430-523 K. *Appl. Catal.* **1986**, *25*, 129-138.
29. Chaieb, S.; Holt, C. Silicon Hydride Nanocrystals as Catalysts for Proton Production in Water-organic Liquid Mixtures. U.S. Patent 8,795,906 B2 (5 August 2014).
30. Geen, H.; Titman, J. J.; Gottwald, J.; Spiess, H. W. Solid-State Proton Multiple-Quantum NMR Spectroscopy with Fast Magic Angle Spinning. *Chem. Phys. Lett.* **1994**, *227*, 79-86.
31. Bendjeriou-Sedjerari, A.; Azzi, J. M.; Abou-Hamad, E.; Anjum, D. H.; Pasha, F. A.; Huang, K.-W.; Emsley, L.; Basset, J.-M. Bipodal Surface Organometallic Complexes with Surface N-Donor Ligands and Application to the Catalytic Cleavage of C-H and C-C Bonds in N-Butane. *J. Am. Chem. Soc.* **2013**, *135*, 17943-17951.
32. Shao, W. L.; Shinar, J.; Gerstein, B. C.; Li, F.; Lannin, J. S. Magic-Angle Spinning Si²⁹ NMR Study of Short-Range Order in *a*-Si. *Phys. Rev. B* **1990**, *41*, 9491-9494.
33. Faulkner, R. A.; DiVerdi, J. A.; Yang, Y.; Kobayashi, T.; Maciel, G. E. The Surface of Nanoparticle Silicon as Studied by Solid-State NMR. *Materials* **2013**, *6*, 18-46.

TABLE OF CONTENTS/ABSTRACT GRAPHIC