Investigating the Influence of Mesoporosity in Zeolite Beta on its Catalytic Performance for the Conversion of Methanol to Hydrocarbons

Zhaohui Liu, Xinglong Dong, Yihan Zhu, Abdul-Hamid Emwas, Daliang Zhang, Qiwei Tian, and Yu Han

ACS Catal., Just Accepted Manuscript • DOI: 10.1021/acscatal.5b01350 • Publication Date (Web): 26 Aug 2015

Downloaded from <http://pubs.acs.org> on August 31, 2015

Just Accepted

“Just Accepted” manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides “Just Accepted” as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. “Just Accepted” manuscripts appear in full in PDF format accompanied by an HTML abstract. “Just Accepted” manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). “Just Accepted” is an optional service offered to authors. Therefore, the “Just Accepted” Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the “Just Accepted” Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these “Just Accepted” manuscripts.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Investigating the Influence of Mesoporosity in Zeolite Beta on its Catalytic Performance for the Conversion of Methanol to Hydrocarbons

Zhaohui Liu,[†] Xinglong Dong,[†] Yihan Zhu,[†] Abdul-Hamid Emwas,[‡] Daliang Zhang,[‡] Qiwei Tian,[†] and Yu Han^{†,*}

[†]Advanced Membranes and Porous Materials Center, Physical Sciences and Engineering Division, [‡]Imaging and Characterization Core Lab, King Abdullah University of Science and Technology, Thuwal 23955-6900, Saudi Arabia.
E-mail: yu.han@kaust.edu.sa

ABSTRACT

Hierarchically porous zeolite Beta (Beta-MS) synthesized by a soft-templating method contains remarkable intra-crystalline mesoporosity, which reduces the diffusion length in zeolite channels down to several nanometers and alters the distribution of Al among distinct crystallographic sites. When used as a catalyst for the conversion of methanol to hydrocarbons (MTH) at 330 °C, Beta-MS exhibited a 2.7-fold larger conversion capacity, a 2.0-fold faster reaction rate, and a remarkably longer lifetime than conventional zeolite Beta (Beta-C). The superior catalytic performance of Beta-MS is attributed to its hierarchical structure, which offers full accessibility to all catalytic active sites. In contrast, Beta-C was easily deactivated because a layer of coke quickly deposited on the outer surfaces of the catalyst crystals, impeding access to interior active sites. This difference is clearly demonstrated by using electron microscopy combined with electron energy loss spectroscopy to probe the distribution of coke in the deactivated catalysts. At both low and high conversions, ranging from 20% to 100%, Beta-MS gave higher selectivity towards higher aliphatics (C₄-C₇) but lower ethene selectivity compared to Beta-C. Therefore, we conclude that a hierarchical structure decreases the residence time of methylbenzenes in zeolite micropores, disfavoring the propagation of the aromatic-based catalytic cycle. This conclusion is consistent with a recent report on ZSM-5 and is also strongly supported by our analysis of soluble coke species residing in the catalysts. Moreover, we identified an oxygen-containing compound, 4-methyl-benzaldehyde, in the coke, which has not been observed in the MTH reaction before.

Keywords

Hierarchical zeolite, Methanol-to-hydrocarbons, Electron energy loss spectroscopy, Dual-cycle mechanism, Coke formation

INTRODUCTION

Zeolites are microporous aluminosilicates with regular intra-crystalline cavities and channels of molecular dimensions. The small pore sizes of zeolites (0.3—1 nm) render unique size- and shape-selectivity in catalysis,¹⁻² but give rise to constraints for molecular diffusion within zeolite crystals.³ As a consequence, zeolite-catalyzed reactions are often limited by slow diffusion. Decreasing the size of zeolite crystals could reduce the diffusion length, but this method is not favorable because it is difficult to synthesize zeolite crystals smaller than 100 nm, and furthermore, ultrafine catalyst particles are difficult to handle and thus, undesirable for practical applications.⁴⁻⁵ An alternative and perhaps more effective method to circumvent the diffusion limitation imposed by small pores is to create a large number of mesopores (> 2 nm) in zeolite crystals.⁶⁻⁸ With this strategy, it is possible to significantly reduce the diffusion length (down to several nanometers), because mesopores break the microporous zeolitic framework into small domains. The resulting materials are usually referred to as “hierarchical zeolites” or “mesoporous zeolites,” in which mesopores allow rapid diffusion and enhanced accessibility for bulky molecules, while zeolitic micropores enable catalytic activity and selectivity.⁹⁻¹¹

Conventional methods for preparing hierarchical zeolites are based on various post-synthesis processes such as steaming,¹² acid (or base) leaching,¹³⁻¹⁴ and chemical treatments.¹⁵⁻¹⁷ Recently, more efforts have been made towards the “direct synthesis” of hierarchical zeolites through soft-templating routes,¹⁸⁻²¹ which can achieve greater mesoporosity, more precise control of pore size, and higher zeolite structure integrity compared with “post-treatment” methods. Hierarchical zeolites prepared by different methods have been tested as catalysts for various reactions, and typically, they exhibit higher catalytic activities (especially when the reactant molecules are bulky),²²⁻²³ longer lifetimes,²⁴⁻²⁵ slower coke formation rates,²⁶ and altered product selectivities²⁷ compared to conventional zeolites with the same framework types. For example, we recently reported that a non-surfactant cationic polymer can act as a dual template to synthesize hierarchical zeolite Beta.²⁸ The obtained material (Beta-MS) featured remarkable mesoporosity, single crystallinity, excellent stability, and superior catalytic activity over conventional zeolite Beta in several liquid-phase reactions. Although there is a bulk of evidence for the superior catalytic properties of hierarchical zeolites, a systematic

comparison between a hierarchical zeolite and its bulk (non-mesoporous) counterpart for a particular reaction on the basis of detailed catalyst characterization and a careful analysis of the full products is lacking.

The conversion of methanol to hydrocarbons (MTH) has attracted considerable attention in the past few decades because it provides an alternative way to produce fuels and chemicals that are currently mainly produced by petroleum-based synthetic routes. Acidic zeolites are the most commonly used catalysts for MTH reactions.²⁹ It is generally accepted that MTH reactions on zeolites follow an indirect “hydrocarbon pool” mechanism,³⁰⁻³¹ in which the active intermediates repeatedly undergo methylation or cracking reactions to produce complex hydrocarbons, and that there are two catalytic cycles coexisting in the process: an aromatic-based cycle and an olefin-based cycle, in which polymethylbenzenes and olefins act as the active hydrocarbon pool species, respectively (Scheme 1).³²⁻³⁴ This dual-cycle mechanism may explain the observed product selectivity of MTH on different zeolites by considering how the pore structure of the zeolite catalyst affects the relative propagation of the two cycles.²⁹ For example, ZSM-22 has one-dimensional non-interacting 10-member-ring channels that are too small to form polymethylbenzene intermediates; consequently, the aromatic-based cycle is suppressed while the olefin-based cycle dominates the conversion process, giving rise to high selectivity for branched C₅+-fraction alkenes.³⁵⁻³⁶ In contrast, SAPO-34 has large 12-member-ring cavities with small (3.8 × 3.8 Å) pore openings that enrich aromatic intermediates, promoting the aromatic-based cycle to produce more ethene³⁷ (a termination product of this cycle, see Scheme 1). Likewise, the MTH product distribution over ZSM-5 can be tuned by varying the reaction conditions (e.g., feed compositions³⁸⁻⁴⁰ and zeolite crystal sizes^{4, 41-42}) to adjust the relative propagation of these two catalytic cycles.

Hierarchical zeolites have been used for MTH, mainly based on the ZSM-5 system. Schmidt *et al.*⁴³ prepared hierarchical ZSM-5 zeolite *via* the desilication reassembly technique for MTH conversion. They found that in addition to a longer lifetime, hierarchical ZSM-5 shows a distinctively different deactivation/reactivation behavior from that of conventional ZSM-5. During successive deactivation/reactivation cycles, conventional ZSM-5 showed a near constant reaction rate and an increasing deactivation rate, while hierarchical ZSM-5 showed the opposite

behaviors (a decreased reaction rate but a constant deactivation rate). Aramburo *et al.*¹² reported that mesoporous ZSM-5 prepared by steaming treatment exhibited similar activity and selectivity but better stability in MTH than did untreated ZSM-5, and that different coke species formed in the two catalysts. Ryoo *et al.*⁴⁴ synthesized ZSM-5 nanosheets with only one unit cell thickness that exhibited a 5-fold longer lifetime compared to the conventional ZSM-5 catalyst when used for MTH conversion. Most recently, Bhan's group⁴² systematically investigated the effect of ZSM-5 crystallite size on product selectivity in MTH conversion. Their results showed that larger crystallites favor the aromatic-based cycle to give higher light-olefin selectivity, because of the prolonged intra-crystalline residual time of methylbenzenes. In this study, hierarchically structured (self-pillared) ZSM-5, with a diffusion length as short as ~ 1 nm, was used as a representatively smallest crystallite.

Here, we endeavor to explore the influence of mesoporosity in zeolite Beta on its catalytic performance for the MTH reaction by systematically comparing highly mesoporous zeolite Beta (Beta-MS) with conventional zeolite Beta (Beta-C). We analyzed the full products and probed the coke species and their distributions in the catalysts with the assistance of electron microscopy and electron energy loss spectroscopy. The data we obtained explains the difference between the two catalysts and provides important insights into the influence of intra-crystalline mesoporosity on the catalytic properties of zeolites.

EXPERIMENTAL SECTION

Preparation of the Catalysts Beta-MS was hydrothermally synthesized from an aluminosilicate gel using a cationic polymer (polydiallyldimethylammonium chloride) as a template; a detailed description of its synthesis can be found in our recent publication.²⁶ Beta-C was synthesized according to a previously reported method.⁴⁵ To convert zeolites to the H-form, the as-synthesized zeolite was overnight ion-exchanged with a 0.5 M NH_4NO_3 solution (20 mL per gram of zeolite) for three times, dried in air at 70 °C, and then calcined at 550 °C in air for 4 h.

Characterizations of the Catalysts Scanning transmission electron microscopy (STEM) images were acquired on a FEI Titan ST Microscope operated at 300 KV using a high-angle annular dark field (HAADF) detector. High-resolution TEM was performed on a JEOL JEM-3010 TEM at 300 KV.

Inductively coupled plasma-optical emission spectroscopy (ICP-OES) was conducted on a Varian 720-ES spectrometer, and the powder X-ray diffraction (XRD) patterns were recorded on a Bruker D8 Advance diffractometer using Cu K α radiation. Ar adsorption-desorption isotherms were measured on a Micromeritics ASAP 2420 apparatus at 87 K. Thermogravimetric analysis (TGA) was performed on a Netzsch TG 209 F1 machine as the temperature increased from 150 °C to 850 °C under flowing air at a rate of 25 mL/min and a constant ramping rate of 10 K/min. Temperature-programmed desorption (TPD) measurements using NH₃ as the probe molecule were performed on a Micromeritics AutoChem II 2950 apparatus. Before measurements, 0.15 g of the sample was pretreated in He gas (25 mL/min) for 1 h at 500 °C and then cooled to 100 °C. Next, the sample was exposed to a mixed gas (10 mol% NH₃ and 90 mol% He) flow of 20 mL/min for 1 h to ensure the sufficient adsorption of NH₃. Prior to desorption, the sample was flushed in He gas for 3 h. Subsequently, NH₃ desorption was performed in the range of 100–600 °C at a heating rate of 10 °C /min under a He flow of 20 mL/min. *In situ* Fourier transform infrared spectroscopy (FTIR) spectra of pyridine adsorbed were recorded on a Nicolet iS10 FTIR spectrometer, operating in the transmission mode. The samples were pre-treated at 450 °C in a vacuum for 8 h before adsorbing pyridine at room temperature. Before collecting the spectrum, desorption of pyridine was performed at the desired temperatures for 2 hours. Magic-angle spinning (MAS) ²⁷Al single-pulse nuclear magnetic resonance (NMR) spectra were recorded on a Bruker Advance 900 WB NMR spectrometer operating at a magnetic field of 21.1 T. The hydrated samples were packed into a 3.2 mm ZrO₂ rotor. Spectra were recorded at a resonance frequency of 234.56 MHz, a spinning rate of 20 KHz, a pulse length of 2.0 μ s, and a recycle delay of 1 s for 5000 scans. The chemical shift is referred to an external standard of Al(Cl)₃·6H₂O (δ = 0 ppm).

Catalytic Reactions MTH conversion was performed in a stainless steel fixed-bed reactor (i.d. 11 mm) packed with 0.5 g of zeolite catalyst. The catalyst bed was activated in a pure air flow (50 mL/min) at 550 °C for 60 min prior to each run, after which the temperature was decreased to 330 °C, and the air flow was switched to N₂ (50 mL/min) gas flow mixed with 0.01 mL/min methanol using a HPLC pump. The desired methanol conversions were achieved by adjusting the weight hourly space velocity (WHSV) in the range of 0.94 to 12 g_{MeOH} g_{Cat}⁻¹ h⁻¹. The reactions

were all performed under atmospheric pressure, and the product was analyzed using online gas chromatography. Composition of the effluent was determined by gas chromatography (GC) with a flame ionization detector equipped with Agilent HP-PLOT/Q column (30 m*0.53 mm*40 μ m). The following temperature programming was applied: 6 $^{\circ}$ C /min from 50 $^{\circ}$ C (5 min at the initial temperature) to 230 $^{\circ}$ C (20 min at the final temperature). The liquid products (C_{6+}) were also collected using an ice bath, and then analyzed by a HP-5 column with the following temperature programming: 5 $^{\circ}$ C /min from 40 $^{\circ}$ C (1 min at the initial temperature) to 140 $^{\circ}$ C, and then 10 $^{\circ}$ C /min to 280 $^{\circ}$ C (1 min at the final temperature). The results showed that there was only a trace amount (< 2%) of C_{8+} aliphatics in the liquid products, which were therefore ignored in the discussion. Dimethyl ether was not considered as a product for the calculation.

Analysis of the Residual Organic Species in Used Catalysts Residual soluble organic species from catalysts were extracted following a commonly used procedure.⁴⁶⁻⁴⁸ Specifically, the catalyst was taken out of the reactor after the desired reaction time, and 200 mg of this used catalyst was transferred to a capped Teflon vial and dissolved in 6 mL of 24% HF for 3 h. Then, 6.0 mL of CH_2Cl_2 was added to the solution to extract the liberated organic species from the water phase. After 3 h, the organic phase was separated from the mixture, and analyzed using GC and GC-MS equipped with the same HP-5 column (30 m*0.32 mm*0.25 μ m).

Elemental Carbon Mapping and EELS Spectroscopy The focused ion beam (FIB) technique was used to cut a thin slice from a deactivated catalyst crystal for carbon mapping and electron energy loss spectroscopy (EELS). FIB sample preparation was conducted on an FEI Helios NanoLab 400S FIB/SEM dual-beam system. Before cross sectioning by FIB and the ion milling process, crystals were pre-sputtered by a thin gold layer with a thickness of 5 ~ 10 nm. This layer acted as both a marker and a separator between the coke species inside the crystal, and the Pt/C layer outside the catalyst crystal that was deposited prior to FIB cross sectioning served to protect the sample from being damaged by the ion beam. This step is essential to identify the intrinsic distribution of coke species throughout the cross-section specimen of zeolites and to avoid surface damage by the ion beam and the diffusion of deposited carbonaceous species into the specimen. STEM imaging and EELS were performed on a cubed Titan G2 electron microscope with a probe-corrector operated at 300 kV. A Cs-corrected and

monochromated STEM probe was used for site-specific characterization of the coke species in zeolites as it offers both high-spatial ($< 1.4 \text{ \AA}$) and high-energy resolution ($\sim 0.2 \text{ eV}$).

RESULTS AND DISCUSSION

The two catalysts investigated in this study, hierarchically structured mesoporous zeolite Beta (denoted as Beta-MS) and conventional zeolite Beta (denoted as Beta-C), have comparable particle sizes (300-500 nm and 400-600 nm for Beta-MS and Beta-C, respectively) and are both phase pure, as shown by STEM and XRD (Figures 1a-c). Analysis of the XRD shows that the peaks of Beta-MS are broadened relative to Beta-C, suggesting smaller crystallite sizes of the former (Figure 1c). STEM images of higher magnification clearly indicate that unlike Beta-C, which consists of dense crystals, Beta-MS contains crystals with hierarchical structures and remarkable intra-crystal mesoporosity (insets in Figures 1a and b and Figure S1). This difference is confirmed by the Ar sorption isotherms collected at 87 K. Beta-C exhibits a type-I isotherm characteristic of a microporous zeolite, while Beta-MS shows an isotherm with combined type-I and type-IV isotherm features, indicating the coexistence of micropores and mesopores (Figure 1d). Beta-MS has a slightly larger BET surface area ($686 \text{ m}^2/\text{g}$ vs. $623 \text{ m}^2/\text{g}$) and a significantly higher total pore volume ($0.84 \text{ cm}^3/\text{g}$ vs. $0.27 \text{ cm}^3/\text{g}$) than Beta-C. The mesopores in Beta-MS have a relatively narrow size distribution centered at about 8.5 nm, as determined from the adsorption isotherm using the Barrett-Joyner-Halenda model (Figure S2). High-resolution TEM images of Beta-MS show the existence of disordered mesopores that break the microporous zeolite framework into very small but continuous domains, where the smallest crystalline domain is about 3-nm thick (Figure S3). This means that Beta-MS has diffusion lengths of only a few nanometers, two orders of magnitude smaller than those of Beta-C. A more detailed structural characterization of Beta-MS, including its single crystalline nature and three-dimensional interconnection of the mesopores, can be found in our recent publication.²⁸ Despite the same Si/Al ratio (21) in the synthetic precursors, as-synthesized Beta-MS and Beta-C have slightly different Si/Al ratios (18 and 15, respectively), as determined by ICP-OES. Pyridine adsorption/desorption experiments monitored by FTIR spectra revealed nearly identical Brønsted acidity in the two catalysts (Figures 2a and 2b). The results of the

temperature programmed desorption of ammonia experiments show that Beta-MS has slightly fewer acid sites compared to Beta-C (Figure 2c), possibly due to its lower Al content.

The locations of tetrahedrally coordinated Al sites (Al T-sites) in the zeolite lattice determine their stability and accessibility and impact the acidity of the zeolite.⁴⁹⁻⁵¹ It is interesting to explore whether the fabrication of a hierarchical structure (i.e., the incorporation of mesopores) can cause Al T-site distribution to vary for a given zeolite type. Recently, Vjunov *et al.* used ultrahigh-field ²⁷Al MAS NMR to probe the distribution of Al among the nine crystallographically distinct T-sites in zeolite Beta (T1-T9 sites, see Figure 3), and their analysis was based on the deconvolution of the spectra according to the DFT-predicted ²⁷Al NMR chemical shifts.⁵²⁻⁵³ Using this established method, we probed the Al distribution in Beta-MS and Beta-C. Figure 3 shows the ²⁷Al NMR spectra measured at 900 MHz, where by fitting the experimental spectra using the DFT-calculated NMR chemical shifts,⁵²⁻⁵³ the relative Al occupancies at different T-sites were determined. Results show that Al preferentially occupies the T2 site and disfavors the T4, T5, T6, and T8 sites in both Beta-C and Beta-MS. The major difference between the two samples appears in the fraction of the T7 site, which is considerably higher in Beta-MS (0.25) than in Beta-C (0.09). The T7 site is part of 5- and 6-member rings but unassociated with 4-member rings. The observed distribution of Al depends on the occupation probability of Al at each T site as well as the quantity of each T site in the zeolite framework. Assuming that the occupation probabilities are identical for Beta-MS and Beta-C, we conclude that the generation of mesopores (by our direct-synthesis method) results in a large number of surface terminations, and consequently, a change in the relative quantities of different T-sites in zeolite Beta. These results indicate that despite having the same framework type, Beta-MS and Beta-C are substantially different in their distribution of Al T-sites. Exploring the subtle influences of this difference on the acid strength of each catalyst is beyond the scope of this study, where we presume that their different catalytic behaviors are mainly associated with their transport properties.

We tested Beta-MS and Beta-C with the MTH reaction using a fix-bed reactor at 330 °C and 101 KPa total feed pressure. The initial conversion of methanol was controlled by varying the

WHSV. Product analysis was performed at steady-state conversions. The details of the reaction conditions and the product analysis methods are elaborated on in the Experimental Section.

First, we investigated the intrinsic selectivity of the catalysts at low conversions. To achieve iso-conversion of methanol, a larger WHSV was needed for Beta-MS because of its higher activity compared to Beta-C. Specifically, Beta-MS and Beta-C gave ~20% conversion of methanol (30 min time on stream) at the WHSV of $12 \text{ g}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1} \text{ h}^{-1}$ and $5 \text{ g}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1} \text{ h}^{-1}$, respectively. Figure 4a shows product selectivity toward ethene, propene, C₄-C₇ aliphatics, methylbenzenes (MBs), and “others” that include ethane, propane, and C₈+ hydrocarbons excluding MBs. It is generally accepted that ethene is a termination product of the aromatic-based cycle in MTH. Therefore, ethene selectivity can be used as an indicator for the degree of propagation of this catalytic cycle.^{34, 39-40} Likewise, higher-hydrocarbon (e.g., C₄-C₇) selectivity is often used to describe the propagation of the olefin-based cycle (Scheme 1).^{34, 39-40} Note that because propene can be produced from both cycles, and aromatics act as the intermediates of the aromatic-based cycle, their selectivities are not suitable for describing the propagation of the two cycles. Thus, we use the ratio of ethene to C₄-C₇ (ethene/C₄-C₇) yield as a “descriptor” for the relative propagation of the two catalytic cycles. As shown in Figure 4a, Beta-MS produced less ethene but more C₄-C₇ olefins than Beta-C, giving a smaller ethene/C₄-C₇ yield value (0.095 vs. 0.15). Reducing the WHSV to $7 \text{ g}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1} \text{ h}^{-1}$ for Beta-MS and to $3 \text{ g}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1} \text{ h}^{-1}$ for Beta-C resulted in the methanol conversion increasing to ~55%, while Beta-MS still exhibited a lower ethene selectivity, a higher C₄-C₇ selectivity, and accordingly a smaller ethene/C₄-C₇ yield (0.11 vs. 0.16) than did Beta-C (Figure 4b). These results suggest that incorporating mesopores in zeolite Beta favors the olefin-based cycle over the aromatic-based cycle. Earlier this year, Bhan’s group observed that ethene selectivity decreased while C₄-C₇ hydrocarbon selectivity increased with decreasing crystallite size of the ZSM-5 catalyst. They proposed that the aromatic-based cycle is suppressed by short diffusion lengths because the produced methylbenzene intermediates can easily exit micropores without undergoing further dealkylation reactions that are integral for the aromatic-based cycle that produces ethene.⁴² Because our results are in good agreement with these observations, we can infer that although the 12-member-ring channels of zeolite Beta are sufficiently large for most molecules involved

in MTH conversion without restriction, the creation of intra-crystalline mesoporosity imposes a similar impact on the product selectivity as has been reported for ZSM-5.⁴² We note that the effect of crystallite size on the product selectivity is more significant for ZSM-5 than for Beta, likely because ZSM-5 has narrower pores (more severe transport restriction).

We also evaluated the catalytic performance of Beta-MS and Beta-C in terms of conversion capacity, reaction/deactivation rate, selectivity, and lifetime at high conversions of methanol. For this purpose, we adjusted the WHSV to be $0.94 \text{ g}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1} \text{ h}^{-1}$ for both catalysts to ensure that they handled the same quality of feed. Under this condition, Beta-MS and Beta-C gave 100% and 97% conversions, respectively, at the beginning of the reaction. With prolonged time-on-stream, conversions of methanol gradually decreased due to catalyst deactivation. Notably, Beta-MS exhibited a significantly slower deactivation rate than Beta-C. As shown in Figure 5, the lifetime before the conversion dropped to 50% was 24.5 h for Beta-MS and 9.0 h for Beta-C.

A model developed by Janssens was used to derive the conversion capacity R , the rate constant k , and the deactivation coefficient α from the lifetime plots.⁵⁴ The results clearly show that Beta-MS has a greater conversion capacity R (0.72 vs. 0.27 $\text{mol}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1}$), a higher rate constant k (1.2 vs. 0.6 $\text{mol}_{\text{MeOH}} \text{ g}_{\text{Cat}}^{-1} \text{ h}^{-1}$), and a lower deactivation coefficient α (0.139 vs. 0.378 $\text{g}_{\text{Cat}} \text{ mol}_{\text{MeOH}}^{-1}$) compared to Beta-C (Table 1). Given that the two catalysts have an identical framework type with comparable crystal sizes and Si/Al ratios, the superior catalytic performance of Beta-MS can be attributed to its unique hierarchical structure. The highly interconnected mesoporous network within Beta-MS crystals allows all acid sites in the catalyst particles to be fully accessible, and thus, gives a high conversion rate and a large conversion capacity; meanwhile, it reduces the probability of coke formation (by promoting molecular transport) and increases the coke tolerance capacity, which accounts for the long lifetime of the catalyst. In contrast, due to diffusion constraints, the conversion of methanol over Beta-C mainly takes place on the outer layer of catalyst particles where coke is easily accumulated, subsequently blocking reacting molecule access to the interior acid sites and quickly deactivating the catalyst. The insufficient use of active sites explains the inferior catalytic performance of Beta-C compared to Beta-MS. We verified these hypotheses by observing the distribution of coke in the deactivated catalysts (*vide infra*).

We monitored the changes of product selectivity with time-on-stream until the catalysts were essentially deactivated (conversion < 20%). As illustrated in Figures 6a and 6b, Beta-MS and Beta-C show a similar evolution trend of product selectivity. At the beginning of the reaction, both catalysts gave C₄-C₇ aliphatics as the main products (butene dominating in this fraction), but their selectivity quickly decreased as the reaction proceeded. Propane was the other product with decreased selectivity, while all other identified products, including aromatics, propene, ethene, and methane, showed gradually increased or constant selectivity with prolonged time on stream (Figures 6a and 6b). These results suggest that over both catalysts, the olefin-based cycle dominates in the initial stage of the reaction, but the aromatic-based cycle is gradually boosted as the reaction proceeds. Meanwhile, certain marked differences in selectivity were evident between the two catalysts. Beta-MS produced more C₄-C₇ aliphatics than Beta-C throughout the whole lifetime: selectivity decreased from 61% to 38% over 30 h for Beta-MS but from 46% to 31% within 12 h for Beta-C (Figure 6c). As the major product of this fraction, butene followed the same trend of selectivity over the two catalysts (Figure S5). Alternatively, over the entire reaction period, Beta-MS had lower ethene selectivity and methane selectivity than Beta-C (Figure 6c). Because ethene and methane are both termination products of the aromatic-based cycle *via* the dealkylation of MBs,^{34, 39-40} we can conclude that Beta-MS favors the olefin-based cycle over the aromatic-based cycle, compared with Beta-C. These results are consistent with the discussion about low methanol conversions from above, and can be attributed to the easy molecular transport in Beta-MS that reduces opportunities for MBs to undergo multiple methylation/dealkylation reactions.

Next, we investigated the coke species formed by each catalyst to help further explain their catalytic behaviors. Thermogravimetric analysis of the used catalyst determined the coke content according to weight loss between 300 and 800 °C. Interestingly, despite converting more methanol (Figure 5), Beta-MS produced less coke than Beta-C at the same reaction time; for example, after 5 h, coke contents were measured for Beta-MS and Beta-C at 8.7 wt% and 11.7 wt%, respectively (Figure 7a). The slower coke formation in Beta-MS can be attributed to its hierarchical structure, which provides better molecular diffusion to depress the polymerization of aromatic hydrocarbons. However, when completely deactivated, more coke

accumulated in Beta-MS (16.8 wt%) than in Beta-C (13.5 wt%), indicating that Beta-MS has a higher tolerance capacity to coke (Figure 7b). We used the FIB technique to cut ultrathin cross-section specimens (60 ~ 80-nm thick) out of completely deactivated catalyst crystals. From these specimens, we were able to probe the distribution of the coke in the two catalysts using STEM and EELS. Elemental carbon (K-edge) mapping by EELS reveals an obvious difference between the two catalysts: Beta-MS has a fairly uniform coke distribution throughout the entire crystal, while Beta-C exhibits an inhomogeneous distribution of coke that is concentrated at the outer layer and scarce in the inner region of the crystal (Figure 8). This result is consistent with the TGA analysis showing that Beta-MS can tolerate more coke than Beta-C. More importantly, it reveals the different reaction sites of the two catalysts. With Beta-C, due to the diffusion restriction imposed by the microporous system, the conversion essentially takes place at the outer surface of catalyst crystals, where once a dense layer of coke is formed, the interior acid sites are blocked and become useless for catalysis. In the case of Beta-MS, all acid sites of the catalyst are accessible because the hierarchical structure circumvents the diffusion constraints. This difference explains the greater conversion capacity, the faster reaction rate, and longer lifetime of Beta-MS compared to Beta-C.

In addition to the overall distribution of coke, high-resolution EELS (energy resolution of ~ 0.2 eV along with a small focal depth of < 10 nm) allowed us to probe the chemical nature of coke species at specific locations in the catalyst crystals. From another two FIB-cut specimen (the two FIB-cut specimen used for Figure 8 were contaminated after the scanning for carbon mapping), we acquired two EELS spectra for Beta-MS by focusing the electron beam on a mesopore region (site 1) and a zeolite domain (site 2), respectively, and one EELS spectra for Beta-C (site 3) (see Figure 9). By comparing the EELS fine structures of the three sites, we learn that site 1 has a $1s \rightarrow \pi^*$ excitation at 285.1 eV, which is conventionally assigned to large aromatics with high degrees of graphitization⁵⁵⁻⁵⁶ and does not appear in the EELS spectra of sites 2 or 3 (Figure 9). Sites 2 and 3 both show a peak of higher energy loss (288.6 eV for site 2 and 288.4 eV for site 3) that is absent from site 1's spectrum. This peak can be attributed to the C-H $1s-3p/\sigma^*$ resonance and thus, reasonably considered to be indicative of the existence of H-rich carbon species.⁵⁶ These results suggest that for conventional zeolites, the coke residues in

the micropores are low-molecular-weight H-rich species (e.g., MBs and long-chain aliphatics), while heavier graphite-like coke deposits are formed on only the outer surfaces of the catalyst particles. This is conceivable considering the small dimensions of zeolitic micropores. In the case of Beta-MS, however, the intra-crystalline mesopores are sufficiently large to accommodate heavy coke with high degrees of graphitization. More interestingly, we observed another $1s \rightarrow \pi^*$ excitation at ~ 286.5 eV in the EELS spectra for both Beta-MS and Beta-C (Figure 9), which is a sign of the presence of aromatic C=O sp^2 carbon species in the coke.⁵⁶ It was recently proposed that oxygen-containing species may be a possible cause for the deactivation of MTH catalysts, especially in the initial period of the reaction.⁵⁷ However, no specific oxygen-containing species have yet been identified, and their formation mechanism remains unclear. Our EELS results provide evidence for the presence of oxygen-containing species in the coke and specifies that they contain aromatic C=O bonds.

To gain more information about the coke, we extracted the organic species retained in the catalysts after different reaction times by using the standard method, dissolution of the zeolite aluminosilicate framework with HF solution followed by extraction of the organic species with CH_2Cl_2 from the water phase.⁴⁶⁻⁴⁸ The extracted (soluble) species, which are essentially the H-rich compounds residing in the zeolitic micropores and account for ~ 5 wt% of the total coke, were analyzed with GC and GC-MS. In good agreement with the EELS results, an oxygen-containing compound was identified by GC at the retention time of 26 min as C_8H_8O ($m/z=120$). Based on the fragmentation pattern, the most plausible molecule is 4-methyl-benzaldehyde (see Figure 10, Figures S6 and S7). This compound was detected in the residues of both Beta-MS and Beta-C at different reaction times (Figure 10). 4-methyl-benzaldehyde was only detected in the coke but not in the effluent products of the reaction, suggesting that once produced, this compound strongly adsorbs on the active sites of zeolite catalysts or is quickly converted into other products (most likely aromatics). It is worth noting that we also identified two oxygen-containing compounds (di- and tri-methyl-2-cyclopenten-1-one) in the coke when zeolite ZSM-5 was used for MTH conversion. A detailed investigation of these unreported coke species, including their content, formation mechanism, and influences on the catalyst activity, will be reported elsewhere shortly.

With the exception of 4-methyl-benzaldehyde, the residual organic species can be classified into MBs (dominated by hexamethylbenzene and pentamethylbenzene) and long-chain aliphatics (C_{10} , C_{11} , C_{12} , C_{14} , etc.). As shown in Figure 10, the relative proportions of MBs and long-chain aliphatics differ greatly between Beta-MS and Beta-C. With the increase of reaction time from 5 h to 15 h, the content of MBs in Beta-C gradually accumulated. In comparison, an apparently smaller fraction of MBs remained in Beta-MS, even when the catalyst was nearly completely deactivated (after 34 h of reaction). On the other hand, there was a larger fraction of long-chain aliphatics in Beta-MS than in Beta-C regardless of the reaction time (Figure 10). These results provide additional evidence for our aforementioned conclusions that Beta-MS allows for the easy diffusion of MBs out of the microporous channels due to the hierarchical structure, subsequently suppressing the propagation of the aromatic-based cycle relative to the olefin-based cycle; the opposite effect applies to Beta-C.

Conclusions

In summary, we systematically compared the catalytic properties between hierarchically porous Beta-MS with conventional microporous Beta-C for MTH conversions. Our results show that the significant intra-crystalline mesoporosity is indeed advantageous for improving the accessibility of acid sites in the catalyst crystals, and thus give rise to a larger conversion capacity, a faster conversion rate, and a longer catalyst lifetime. It also enables Beta-MS to afford more coke than Beta-C before complete deactivation. On the other hand, the two orders of magnitude difference in diffusion length results in different product selectivity between Beta-MS and Beta-C. Methylbenzenes, which are the intermediates of the aromatic-based cycle in MTH reaction, can easily diffuse out of the zeolite channels in Beta-MS, limiting the propagation of this catalytic cycle, while relatively promoting the olefin-based cycle. As a consequence, Beta-MS gave lower ethene selectivity but higher selectivity towards C_4 - C_7 aliphatics with respect to Beta-C in a wide range of methanol conversion (20% to 100%). We analyzed the residual coke species in the used catalysts and found a smaller ratio of MBs: long-chain aliphatics in Beta-MS compared to Beta-C regardless of the reaction time. This result provides further evidence for the suppressed aromatic-based cycle in Beta-MS. Using FIB, STEM, and EELS techniques, we were able to visualize the distribution of coke in the deactivated catalysts. The results verify our

hypothesis that all the acid sites in Beta-MS were fully used for catalysis whereas a large fraction of acid sites in Beta-C was blocked (useless for catalysis) by a layer of coke that formed on the crystal's outer surfaces. Results from EELS implied the presence of oxygen-containing compounds in the coke and accordingly 4-methyl-benzaldehyde was identified in the residual organic species by GC-MS. The formation mechanism of such a compound in MTH reactions has little exposure in the literature and its role in deactivating the catalyst may be worthy of careful investigations in the future.

References

- (1) Calero, S.; Schenk, M.; Dubbeldam, D.; Maesen, T. L. M.; Smit, B., *J. Catal.* **2004**, *228*, 121-129.
- (2) Jae, J.; Tompsett, G. A.; Foster, A. J.; Hammond, K. D.; Auerbach, S. M.; Lobo, R. F.; Huber, G. W., *J. Catal.* **2011**, *279*, 257-268.
- (3) Primo, A.; Garcia, H., *Chem. Soc. Rev.* **2014**, *43*, 7548-7561.
- (4) Rownaghi, A. A.; Rezaei, F.; Hedlund, J., *Catal. Commun.* **2011**, *14*, 37-41.
- (5) Qin, Z.; Lakiss, L.; Tosheva, L.; Gilson, J.-P.; Vicente, A.; Fernandez, C.; Valtchev, V., *Adv. Funct. Mater.* **2014**, *24*, 257-264.
- (6) Zhang, X.; Liu, D.; Xu, D.; Asahina, S.; Cychosz, K. A.; Agrawal, K. V.; Al Wahedi, Y.; Bhan, A.; Al Hashimi, S.; Terasaki, O.; Thommes, M.; Tsapatsis, M., *Science* **2012**, *336*, 1684-1687.
- (7) Serrano, D. P.; Escola, J. M.; Pizarro, P., *Chem. Soc. Rev.* **2013**, *42*, 4004-4035.
- (8) Chen, L. H.; Li, X. Y.; Rooke, J. C.; Zhang, Y. H.; Yang, X. Y.; Tang, Y.; Xiao, F. S.; Su, B. L., *J. Mater. Chem.* **2012**, *22*, 17381-17403.
- (9) Parlett, C. M. A.; Wilson, K.; Lee, A. F., *Chem. Soc. Rev.* **2013**, *42*, 3876-3893.
- (10) Perez-Ramirez, J.; Christensen, C. H.; Egeblad, K.; Christensen, C. H.; Groen, J. C., *Chem. Soc. Rev.* **2008**, *37*, 2530-2542.
- (11) Holm, M. S.; Taarning, E.; Egeblad, K.; Christensen, C. H., *Catal. Today* **2011**, *168*, 3-16.
- (12) Aramburo, L. R.; Teketel, S.; Svelle, S.; Bare, S. R.; Arstad, B.; Zandbergen, H. W.; Olsbye, U.; de Groot, F. M. F.; Weckhuysen, B. M., *J. Catal.* **2013**, *307*, 185-193.
- (13) Groen, J. C.; Moulijn, J. A.; Pérez-Ramírez, J., *Micropor. Mesopo. Mater.* **2005**, *87*, 153-161.
- (14) Ogura, M.; Shinomiya, S.-y.; Tateno, J.; Nara, Y.; Kikuchi, E.; Matsukata, M., *Chem. Lett.* **2000**, *29*, 882-883.
- (15) Pérez-Ramírez, J.; Abelló, S.; Bonilla, A.; Groen, J. C., *Adv. Funct. Mater.* **2009**, *19*, 164-172.
- (16) Verboekend, D.; Pérez-Ramírez, J., *Chem.-Eur. J.* **2011**, *17*, 1137-1147.
- (17) Wang, D. R.; Zhang, L.; Chen, L.; Wu, H. H.; Wu, P., *J. Mater. Chem. A* **2015**, *3*, 3511-3521.
- (18) Choi, M.; Cho, H. S.; Srivastava, R.; Venkatesan, C.; Choi, D.-H.; Ryoo, R., *Nat. Mater.* **2006**, *5*, 718-723.
- (19) Wang, H.; Pinnavaia, T. J., *Angew. Chem. Int. Ed.* **2006**, *45*, 7603-7606.
- (20) Na, K.; Jo, C.; Kim, J.; Cho, K.; Jung, J.; Seo, Y.; Messinger, R. J.; Chmelka, B. F.; Ryoo, R., *Science* **2011**, *333*, 328-332.
- (21) Xu, D.; Ma, Y.; Jing, Z.; Han, L.; Singh, B.; Feng, J.; Shen, X.; Cao, F.; Oleynikov, P.; Sun, H.; Terasaki, O.; Che, S., *Nat. Commun.* **2014**, *5*, 4262-4270.
- (22) Wang, L.; Zhang, J.; Yi, X.; Zheng, A.; Deng, F.; Chen, C.; Ji, Y.; Liu, F.; Meng, X.; Xiao, F.-S., *ACS Catal.* **2015**, *5*, 2727-2734.

- (23) Xi, D.; Sun, Q.; Xu, J.; Cho, M.; Cho, H. S.; Asahina, S.; Li, Y.; Deng, F.; Terasaki, O.; Yu, J., *J. Mater. Chem. A* **2014**, *2*, 17994-18004.
- (24) Wang, C.; Yang, M.; Tian, P.; Xu, S.; Yang, Y.; Wang, D.; Yuan, Y.; Liu, Z., *J. Mater. Chem. A* **2015**, *3*, 5608-5616.
- (25) Sun, Q.; Wang, N.; Xi, D.; Yang, M.; Yu, J., *Chem. Commun.* **2014**, *50*, 6502-6505.
- (26) Kim, J.; Choi, M.; Ryoo, R., *J. Catal.* **2010**, *269*, 219-228.
- (27) Mei, C.; Wen, P.; Liu, Z.; Liu, H.; Wang, Y.; Yang, W.; Xie, Z.; Hua, W.; Gao, Z., *J. Catal.* **2008**, *258*, 243-249.
- (28) Zhu, J.; Zhu, Y.; Zhu, L.; Rigutto, M.; van der Made, A.; Yang, C.; Pan, S.; Wang, L.; Zhu, L.; Jin, Y.; Sun, Q.; Wu, Q.; Meng, X.; Zhang, D.; Han, Y.; Li, J.; Chu, Y.; Zheng, A.; Qiu, S.; Zheng, X.; Xiao, F. S., *J. Am. Chem. Soc.* **2014**, *136*, 2503-2510.
- (29) Olsbye, U.; Svelle, S.; Bjorgen, M.; Beato, P.; Janssens, T. V.; Joensen, F.; Bordiga, S.; Lillerud, K. P., *Angew. Chem. Int. Ed.* **2012**, *51*, 5810-5831.
- (30) Dahl, I., M.; Kolboe, S., *J. Catal.* **1994**, *149*, 458-464.
- (31) Dahl, I., M.; Kolboe, S., *J. Catal.* **1996**, *161*, 304-309.
- (32) Svelle, S.; Joensen, F.; Nerlov, J.; Olsbye, U.; Lillerud, K. P.; Kolboe, S.; Bjorgen, M., *J. Am. Chem. Soc.* **2006**, *128*, 14770-14771.
- (33) Bjørgen, M.; Svelle, S.; Joensen, F.; Nerlov, J.; Kolboe, S.; Bonino, F.; Palumbo, L.; Bordiga, S.; Olsbye, U., *J. Catal.* **2007**, *249*, 195-207.
- (34) Ilias, S.; Bhan, A., *ACS Catal.* **2013**, *3*, 18-31.
- (35) Teketel, S.; Svelle, S.; Lillerud, K.-P.; Olsbye, U., *ChemCatChem* **2009**, *1*, 78-81.
- (36) Teketel, S.; Olsbye, U.; Lillerud, K. P.; Beato, P.; Svelle, S., *Micropor. Mesopo. Mater.* **2010**, *136*, 33-41.
- (37) Hereijgers, B. P. C.; Bleken, F.; Nilsen, M. H.; Svelle, S.; Lillerud, K. P.; Bjorgen, M.; Weckhuysen, B. M.; Olsbye, U., *J. Catal.* **2009**, *264*, 77-87.
- (38) Ilias, S.; Bhan, A., *J. Catal.* **2012**, *290*, 186-192.
- (39) Sun, X. Y.; Mueller, S.; Liu, Y.; Shi, H.; Haller, G. L.; Sanchez-Sanchez, M.; van Veen, A. C.; Lercher, J. A., *J. Catal.* **2014**, *317*, 185-197.
- (40) Sun, X. Y.; Mueller, S.; Shi, H.; Haller, G. L.; Sanchez-Sanchez, M.; van Veen, A. C.; Lercher, J. A., *J. Catal.* **2014**, *314*, 21-31.
- (41) Sugimoto, M.; Katsuno, H.; Takatsu, K.; Kawata, N., *Zeolites* **1987**, *7*, 503-507.
- (42) Khare, R.; Millar, D.; Bhan, A., *J. Catal.* **2015**, *321*, 23-31.
- (43) Schmidt, F.; Hoffmann, C.; Giordanino, F.; Bordiga, S.; Simon, P.; Carrillo-Cabrera, W.; Kaskel, S., *J. Catal.* **2013**, *307*, 238-245.
- (44) Choi, M.; Na, K.; Kim, J.; Sakamoto, Y.; Terasaki, O.; Ryoo, R., *Nature* **2009**, *461*, 246-249.
- (45) Cambor, M. A.; Pérez-Pariente, J., *Zeolites* **1991**, *11*, 202-210.
- (46) M. Guisnet; P. Magnoux; Canaff, C., *Stud. Surf. Sci. Catal.* **1986**, *28*, 701-707.
- (47) P. Magnoux; P. Roger; C. Canaff; V. Fouche; N.S. Gnep; Guisnet, M., *Stud. Surf. Sci. Catal.* **1987**, *34*, 317-330.
- (48) Bjørgen, M.; Olsbye, U.; Kolboe, S., *J. Catal.* **2003**, *215*, 30-44.
- (49) Pariente, J. P.; Sanz, J.; Fornes, V.; Corma, A., *J. Catal.* **1990**, *124*, 217-223.
- (50) Maier, S. M.; Jentys, A.; Lercher, J. A., *J. Phys. Chem. C* **2011**, *115*, 8005-8013.
- (51) Yu, Z.; Zheng, A.; Wang, Q.; Chen, L.; Xu, J.; Amoureux, J. P.; Deng, F., *Angew. Chem. Int. Ed.* **2010**, *49*, 8657-8661.
- (52) Vjunov, A.; Fulton, J. L.; Huthwelker, T.; Pin, S.; Mei, D.; Schenter, G. K.; Govind, N.; Camaioni, D. M.; Hu, J. Z.; Lercher, J. A., *J. Am. Chem. Soc.* **2014**, *136*, 8296-306.
- (53) Vjunov, A.; Fulton, J. L.; Huthwelker, T.; Pin, S.; Mei, D.; Schenter, G. K.; Govind, N.; Camaioni, D. M.; Hu, J. Z.; Lercher, J. A., *J. Am. Chem. Soc.* **2015**, *137*, 2409.

- (54) Janssens, T. V. W., *J. Catal.* **2009**, *264*, 130-137.
- (55) Klein, R. J.; Fischer, D. A.; Lenhart, J. L., *Langmuir* **2008**, *24*, 8187-8197.
- (56) Haberstroh, P. R.; Brandes, J. A.; Gélina, Y.; Dickens, A. F.; Wirick, S.; Cody, G., *Geochim. Cosmochim. Acta* **2006**, *70*, 1483-1494.
- (57) Müller, S.; Liu, Y.; Vishnuvarthan, M.; Sun, X.; van Veen, A. C.; Haller, G. L.; Sanchez-Sanchez, M.; Lercher, J. A., *J. Catal.* **2015**, *325*, 48-59.

Table 1. Factors of catalytic performance derived from Janssens’ model ^a

Catalyst	t _{0.5} (h) ^b	t _{0.8} (h) ^c	R (mol _{MeOH} g _{Cat} ⁻¹) ^d	k (mol _{MeOH} g _{Cat} ⁻¹ h ⁻¹) ^e	a (g _{Cat} mol _{MeOH} ⁻¹) ^f
Beta-C	9	2.5	0.27	0.6	0.378
Beta-MS	24.5	16	0.72	1.2	0.139

^a refer to reference 53 for the details of this model; ^b time until 50% of conversion;
^c time until 80% of conversion; ^d methanol conversion capacity calculated at t_{0.5}: $R = WHSV_{MeOH} * t_{0.5}$;
^e rate constant k derived from Janssens’ model at t_{0.8}.
^f deactivation coefficient: $a = \tau_0 / t_{0.5}$ (contact time: $\tau_0 = 3.4 \text{ g}_{cat} \text{ h mol}_{MeOH}^{-1}$).

Scheme 1. The proposed dual-cycle mechanism for methanol-to-hydrocarbon conversions over zeolite catalysts. Although this mechanism was proposed for the ZSM-5 systems (references 30-32), it can also be used to explain the catalytic behaviors of other types of zeolites. The major intermediate species of the aromatic-based cycle (methylbenzenes) may differ in different zeolites due to pore size differences.

Figure 1. STEM images of (a) Beta-MS and (b) Beta-C. (c) XRD patterns of Beta-MS and Beta-C. (d) Ar adsorption-desorption isotherms of Beta-MS and Beta-C collected at 87K. The insets in (a) and (b) are enlarged STEM images for individual crystals.

Figure 2. FTIR spectra of the characteristic ring vibrations of pyridine adsorbed on Brønsted (B) and Lewis (L) acid sites over Beta-MS (a) and Beta-C (b) catalysts upon desorption treatment at different temperatures. (c) NH₃-TPD profiles of Beta-MS and Beta-C.

Figure 3. MAS ^{27}Al single-pulse NMR spectra of Beta-MS (a) and Beta-C (b) with the according distribution of different T sites on the right-hand side. The chemical shifts of different T sites used for fitting were adopted from ref. 51, which were predicted by DFT calculations. The fitting procedure was similar to that described in ref. 51. The black dots and red curves represent the experimental and fitted spectra, respectively. See Figure S4 in the Supporting Information for the nine crystallographic T sites in the zeolite BEA framework.

Figure 4. Product selectivity over Beta-MS and Beta-C at two isoconversion (of methanol) conditions: (a) ~20% and (b) ~55%. C₂=, C₃=, C₄-C₇, and MBs stand for ethylene, propylene, C₄-C₇ aliphatics, and methylbenzenes, respectively. The percentages in the horizontal axis specify the exact conversion values given by the corresponding catalyst.

Figure 5. Catalytic lifetime in MTH reactions over Beta-MS and Beta-C catalysts at 330 °C and a WHSV of 0.94 g_{MeOH} g_{Cat}⁻¹h⁻¹.

Figure 6. Evolution of product selectivity during the MTH conversion reaction over (a) Beta-MS and (b) Beta-C. In (c), the selectivities towards C_4 - C_7 aliphatics, ethene, and methane shown in (a) and (b) are isolated for direct comparison between the two catalysts.

Figure 7. (a) TGA analysis of Beta-MS and Beta-C catalysts after 5 h of reaction. (b) TGA analysis of the completely deactivated Beta-MS and Beta-C catalysts. The weight losses indicated in the Figure correspond to the coke contents.

Figure 8. Spectra images including HAADF-STEM images (left), carbon K-edge intensity maps (middle), and line profiles (right) of Beta-MS (a-c) and Beta-C (d-f). Yellow contour lines in (b) and (e) mark the Au-layers, which show sharp bright contrast in (a) and (d). The intensity maps in (b) and (e) were rendered using a temperature color scheme as indicated by the color bar. Red arrows indicate where the line profiles were extracted.

Figure 9. HAADF-STEM images of cross sections of (a) Beta-MS and (b) Beta-C. Local regions are enlarged to show the locations where EELS spectra (on the right) were collected. An irregular mesopore in Beta-MS is outlined in yellow in the zoomed image. Carbon K-edge EELS spectra collected from sites 1, 2, and, 3 are shown on the right, in which different characteristic energy loss peaks are marked by dashed lines with different colors (red: ~285.1 eV; blue: ~286.5 eV and green: ~288.4 eV).

Figure 10. Residual hydrocarbon species extracted from the used catalysts after different reaction times (5h, 10h, and 15 h for Beta-C; 5h, 15 h, and 34 h for Beta-MS).

TOC graph