Accepted Manuscript

Title: Understanding the risk of scaling and fouling in hollow fiber forward osmosis membrane application

Author: Tahir Majeed Sherub Phuntsho Sanghyun Jeong
Yanxia Zhao Baoyu Gao Ho Kyong Shon

PII: S0957-5820(16)30109-4
DOI: <http://dx.doi.org/doi:10.1016/j.psep.2016.06.023>
Reference: PSEP 811

To appear in: *Process Safety and Environment Protection*

Received date: 3-2-2016
Revised date: 11-6-2016
Accepted date: 15-6-2016

Please cite this article as: Majeed, T., Phuntsho, S., Jeong, S., Zhao, Y., Gao, B., Shon, H.K., Understanding the risk of scaling and fouling in hollow fiber forward osmosis membrane application, *Process Safety and Environment Protection* (2016), <http://dx.doi.org/10.1016/j.psep.2016.06.023>

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Understanding the risk of scaling and fouling in hollow fiber forward osmosis membrane application

Highlights:

- Driving force in FO does not remain constant unlike in pressured membrane processes.
- UF/RO fouling assessment method may not be suitable for FO.
- An alternate fouling evaluation process is suggested for FO membrane application.
- In active layer–draw solution, rapid flux decline is not linked to FO fouling.
- The crossflow rate plays an important role for varying fouling effects for FO.

Understanding the risk of scaling and fouling in hollow fiber forward osmosis membrane application

Tahir Majeed^a, Sherub Phuntsho^a, Sanghyun Jeong^b, Yanxia Zhao^c, Baoyu Gao^c, Ho Kyong
Shon^{a*}

^a School of Civil and Environmental Engineering, Faculty of Engineering and Information Technology,
University of Technology, Sydney (UTS), PO Box 123, Broadway, NSW 2007,

^b King Abdullah University of Science and Technology (KAUST), Water Desalination and Reuse Center
(WDRC), Biological and Environmental Science & Engineering (BESE), Thuwal 23955-6900, Saudi Arabia,

^c Key Laboratory for Special Functional Aggregated Materials of Education Ministry, School of Chemistry and
Chemical Engineering, Shandong University, Jinan 250100, China

* Corresponding author: E-mail: Hokyong.Shon-1@uts.edu.au; phone: (61) 2 9514 2629

Abstract

Fouling studies of forward osmosis (FO) were mostly conducted based on fouling evaluation principals applied to pressure membrane processes such as reverse osmosis (RO)/nanofiltration (NF)/ microfiltration (MF)/ ultrafiltration (UF). For RO/NF/MF/UF processes, the single flux driving force (hydraulic pressure) remains constant, thus the fouling effect is easily evaluated by comparing flux data with the baseline. Whilst, the scenario of fouling effects for FO process is entirely different from RO/NF/MF/UF processes. Continuously changing driving force (osmotic pressure difference), the changes in concentration polarization associated with the varying draw solution/feed solution concentration and the fouling layer effects collectively influence the FO flux. Thus, usual comparison of the FO flux outcome with the baseline results can not exactly indicate the real affect of membrane fouling, rather presents a misleading cumulative effect. This study compares the existing FO

1 fouling technique with an alternate fouling evaluation approach using two FO set-ups.
2 Scaling and fouling risk for hollow fiber FO was separately investigated using synthetic
3 water samples and model organic foulants as alginate, humic acid and bovine serum albumin.
4 Results indicated that FO flux declines up to 5% and 49% in active layer-feed solution and
5 active layer-draw solution orientations respectively.

6

7 **Keywords:** Concentration polarization; Flux; Hollow fiber forward osmosis membrane;
8 Inorganic scaling; Organic fouling

9

1

2 **1. Introduction**

3 Forward osmosis (FO) is a new low cost desalination approach utilizing natural osmotic
4 pressure gradient between draw solution (DS) and feeding solution (FS) (Cath et al., 2006,
5 McCutcheon et al., 2005, Sahebi et al., 2015). Due to its low pressure operation and low
6 energy process requirement, FO has been gaining wide popularity and effectively used for
7 water desalination, juice concentration, oil and gas wastewater treatment and energy
8 production (Elimelech, 2007, Kessler and Moody, 1976, Bamaga et al., 2009, Chung et al.,
9 2012, Warczok et al., 2007). At present, the FO process is being evaluated for commercial
10 applications after gone through early lab-scale test.

11

12 Membrane fouling is the accumulations of the inorganic, organic or microbiological
13 impurities on the membrane surface, which significantly affect the membrane performances
14 in terms of flux and salt rejection. It not only influences the quality of the product water but
15 also directly affects the operating cost such as downtime, cleaning chemical costs, labour
16 requirements, production loss and frequent membrane replacements (Peng et al., 2004). The
17 fouling is a very complex phenomena as it is determined by various physical and chemical
18 interactions between different foulants and membrane materials (Kim et al., 2010, Saffarini et
19 al., 2012). Since fouling is considered as a serious operational issue for all membrane based
20 systems, the FO fouling studies are also important to evaluate the risks associated with
21 commercial operations of the FO system. Various studies have been published with the
22 evaluation of the fouling potential for various types of FO membranes under different feed
23 and draw solution combinations (Cornelissen et al., 2008, Mi and Elimelech, 2008, Achilli et
24 al., 2009, Mi and Elimelech, 2010, Gu et al., 2013). Fouling may occur on the membrane
25 surface, at the pore openings and within the pores (Arkhangelsky et al., 2012). Some of the

1 key factors controlling fouling mechanism are foulant characteristics, DS and FS chemistry
2 (pH, ionic strength, and divalent cation concentration), membrane properties (surface charge,
3 hydrophobicity, and roughness), and hydrodynamic conditions (permeate flux, and crossflow
4 velocity) (Bellona et al., 2004, Peng et al., 2004, Greenlee et al., 2009, Radu et al., 2012,
5 Pérez-González et al., 2012).

6
7 Earlier studies on FO fouling found that the severity of the fouling potential for FO
8 membranes was not so intensive. FO, being a process governed by the osmotic pressure
9 gradient, has been hypothesized to have a lower fouling propensity than other pressure driven
10 membrane processes, such as reverse osmosis (RO)/nanofiltration (NF) (Li et al., 2012,
11 Zhang et al., 2012). Mi et al. (2010) evaluated the FO fouling potential with alginate and
12 found that FO fouling is fully reversible with simple rinsing (without any cleaning reagents).
13 In addition, fouling reversibility in FO was attributed to the less compact organic fouling
14 layer formed on the membrane surface due to the lack of hydraulic pressure (Zhao et al.,
15 2012, Park et al., 2013).

16 Gu et al. (2013) assessed FO fouling potential with opposite charged foulant mixtures and
17 suggested that membrane surface properties played a less important role in fouling due to the
18 dominance of foulant-foulant interaction. Further, under mild fouling conditions, the thin film
19 composite (TFC) membrane was more prone to fouling due to the much rougher membrane
20 surface. Tang et al. (2010) indicated that the flux loss in active layer-feed solution (AL-FS)
21 orientation was likely due to the combined effects of (1) the internal clogging of the FO
22 support structure as well as (2) the enhanced internal concentration polarization (ICP) caused
23 mainly by the reduced porosity and mass transfer coefficient in the support layer (SL). Peng
24 et al. (2004) found that biofouling layer is more stable and difficult to remove by flushing as
25 crossflow rate was increased from 4 cm/s to 33 cm/s for 1 h of operation.

1

2 Most of these studies identified that FO showed consistent performances at AL-FS
 3 orientation and avoid severe fouling (She et al., 2012, Valladares Linares et al., 2014). FO
 4 test by Yip et al. (2011) in activ2e layer–draw solution (AL-DS) orientation when used to
 5 harvest salinity gradient power noticed that osmotic backwash facilitated the FO flux
 6 restoration.

7

8 It is however observed in these studies that the FO fouling was evaluated following the
 9 fouling principles of RO, NF, ultrafiltration (UF), or microfiltration (MF), where the
 10 performance of these systems is compared with the baseline outcome and the deviation in
 11 their flux performance is referred as to fouling effects. The RO/NF/MF/UF is operated for a
 12 fixed driving force (hydraulic pressure). However, the FO process differs from the other
 13 membrane-based processes, mainly in terms of the non-existence of a constant driving force
 14 during the experiment run. Unlike RO or NF, FO may not be operated at a fixed driving
 15 force. Further, permeate flux and trans-membrane pressure is the best indicator of
 16 RO/NF/MF/UF membrane fouling applications but not used for FO process at all.
 17 Comparisons of the resultant flux trend with the baseline outcome easily figured out any
 18 performance variations for RO/NF/MF/UF, which clearly indicated the resultant fouling
 19 effect on the membrane performance.

20

21 However, at any fixed time, as the FO does not show the same driving force for any two flux
 22 data curves, the standard flux curves comparison is hardly able to identify the portion of flux
 23 change that is influenced by fouling (**Fig. 1**). For FO, at any particular point, the continuously
 24 changing driving force (due to the varying FS and DS concentrations) with their simultaneous
 25 effects on the concentration polarization (CP) make it really hard to operate two FO processes

1 having similar driving force. For particular FO applications, the FO membrane is also used in
 2 AL-FS and AL-DS orientations with varying nature of performances. Additionally, as FO
 3 manages the simultaneous flow of two different solutions as FS and DS on either side of the
 4 membrane it carries varying fouling risks for different sides of the membrane. FS coming

Fig. 1 Comparison of the fouling scenario between FO and RO/NF/MF/UF processes. FO operates under the influence of constantly varying driving forces whereas for RO/NF/MF/UF processes, the main flux driving force (hydraulic pressure) remains constant for the whole test run. Hence the existing fouling experimental protocol may not be used to evaluate fouling effects for FO membrane as it gives misleading outcome.

5 from various sources carry different impurities which pose severe threats for fouling
 6 development on the FO membrane surface, whereas the risk of fouling on the DS side is
 7 found to be minimal

because the DS is usually prepared in a controlled working environment by dissolving suitable draw solute in high quality treated water. Thus, FO fouling in AL-DS orientation has not been fully evaluated in previous FO studies (Holloway et al., 2007, Mi and Elimelech, 2008, Cornelissen et al., 2008, Zhang et al., 2012).

The comparison of the fouling evaluation approach for FO and RO/NF/MF/UF indicated that these basic differences between the FO and other membrane system and their approach towards their fouling processes were not realized in earlier studies. Thus, the existing comparison of the flux performances for FO fouling which rely on the comparison of the flux performance curves with the baseline failed to indicate actual fouling potential for any FO operation. To overcome this issue, this study suggests a modified approach, referred as (Tahir approach). Tahir approach takes all forces affecting the flux in the hollow fiber FO membrane fouling process into account and clearly indicates actual flux loss by fouling.

This study evaluated and compared the risks of scaling and fouling in the hollow fiber FO (HFFO) membrane application using two different fouling approaches: 1) the existing commonly used approach and 2) Tahir approach. The fouling of FO membrane was also evaluated using various synthetic FSs mixed with model organic foulants such as sodium alginate, humic acid (HA) and bovine serum albumin (BSA).

2. Materials and Methods

2.1 FO setup

Fig. 2 shows the sequence of experiments performed to investigate the effect of fouling for FO membrane. Two identical bench scale HFFO set-ups, similar to the one reported by

Majeed et al. (2013) were used. Each set-up used two Cole-Parmer variable speed pumps to circulate DS and FS through the membrane module. A temperature controller unit linked to a water bath was used to maintain the temperature of the DS and FS sides at $25 \pm 0.5^\circ\text{C}$. All fouling tests were performed at FO set-up # 2 for similar crossflow rates representing a Reynolds number (Re) of 1900 and 700 for the lumen side and shell side, respectively. Set-up # 1 was used to evaluate the performances of the new membrane and effect of fouling on HFFO membrane.

2.2 Membrane

HFFO lumens manufactured by Samsung Cheil Industries, Korea were used to construct different modules for the study, each carrying a membrane area of 25 cm^2 . FO lumens were made up of aromatic polyamide (PA) thin film composite (TFC) active layer (inside) on hydrophilic sulphonated polysulphone (SPSf) substrate (Chen et al., 2014, Majeed et al., 2013). The PA membrane carried a negative charge of -9.30 mV at $\text{pH}=7$ with contact angle of 55° (Majeed et al., 2013). FO membrane properties such as pure water permeability (A) and salt rejection (B) have been reported in another earlier study (Majeed et al., 2013). The fouling performances of the HFFO membrane modules were evaluated in both AL–DS and AL–FS membrane orientations. For AL–FS orientation, the FS passed through the inner side of lumens and the DS run outside the lumens, while the FS and DS run the opposite way for AL–DS membrane orientation.

Fig. 2 Sequence of operations performed to evaluate the effect of scaling and fouling on HFFO membrane at two side by side FO units (set-up # 1 and set-up # 2).

1

2 **2.3 Chemicals**3 **2.3.1. DS and FS**

4 KCl and NaCl were used as DS. To assess the effect of DS on scaling, KCl was initially used
5 in 1, 2 and 3 M concentrations for baseline tests and the flux was evaluated separately against
6 deionized (DI) water as FS and specific organic foulant loaded DI water as FS, respectively.
7 Based on the results, further studies for the inorganic scaling and organic fouling were made
8 with 2 M KCl DS. FSs, which have various brackish ground water (BGW) qualities
9 representing total dissolved solids (TDS) of 5, 10, 20 and 35 g/L, were prepared from
10 different analytical grade chemicals and reported as B5, B10, B20 and B35, respectively.
11 NaCl, Na₂SO₄, CaCl₂·2H₂O, MgCl₂·6H₂O, NaHCO₃ and KCl reagents (supplied by Chem-
12 supply, Australia) were used to prepare various BGW qualities FS and their constituent
13 details are summarized in **Table 1**. These synthetic BGW represent water samples at various
14 salt interception scheme locations in Murray Darling Basins of Australia. All FS and other
15 DS were prepared by dissolving respective salts into DI water. DI water was also used as FS
16 for baseline (reference line) tests.

17

1

2 Table 1 Detailed composition of various synthetic BGW qualities evaluated for the FO
 3 fouling study. Osmotic pressure (π , atm) was calculated using OLI Stream Analyser 3.2
 4 software.

Compounds/Concentration	B5	B10	B20	B35
	mmol	mmol	mmol	mmol
NaCl	31.8	63.5	127.1	222.5
Na ₂ SO ₄	6.3	12.6	25.3	44.2
KCl	0.9	1.8	3.6	6.3
CaCl ₂ .2H ₂ O	1.1	2.2	4.3	7.6
MgCl ₂ .6H ₂ O	9.7	19.4	38.8	68
NaHCO ₃	0.6	1.1	2.3	3.9
π (atm)	2.74	5.35	10.56	18.56

5

6 2.3.2. Organic foulants

7 Three different model organic foulants were used to evaluate their fouling potential on FO
 8 membrane: sodium alginate (Sigma-Aldrich), being polysaccharides that constitute a major
 9 fraction of soluble microbial products in wastewater (Mi and Elimelech, 2010), BSA being
 10 proteins and amino acids, and HA (Sigma-Aldrich) being natural organic carbon (NOC)
 11 produced by biodegradation of dead organic matter. Alginate represents the hydrophilic
 12 fraction of organic foulants and the molecular weight of sodium alginate ranges from 12 to 80
 13 kDa. Other characteristics of alginate can be found elsewhere (Jin et al., 2012). Alginate is
 14 negatively charged within the fouling study pH range (6–8) (Wang et al., 2010). Humic

substances are refractory anionic macromolecules and consist of both aromatic and aliphatic components primarily with phenolic and carboxylic functional groups.

For each of these model foulants, a stock solution was prepared by separately mixing 2.4 g of individual foulants in 1 L of DI water. Alginate and BSA (received in powder form) were dissolved in DI water and mixing was continued for 24 h to ensure complete dissolution. HA stock solution was prepared by dissolving HA powder in DI water and adjusting the pH to 8.2 with 0.01N NaOH. The HA stock solution was mixed continuously for 24 h to ensure complete dissolution and then stored in amber glass bottles at 4 °C for further use. FS used in fouling studies was individual foulants and following combinations: HA+Alginate, HA+BSA, Alginate+BSA, and HA+Alginate+BSA. These model foulants were used in 60 mg/L each concentration to prepare various FS qualities.

2.4 Water flux measurement

Water flux was evaluated by continuously measuring the loss of FS tank weight placed on a digital weighing scale (Model: CUW 4200H by CAS, Korea), which was directly connected to a computer. It was recorded every 1 min. FO experiments were carried out for 4–10 h based on targeted evaluation of the FO membrane for scaling or organic fouling. Some experiments were run for up to 36 h for long time operations.

2.5 Performance checks

At the end of each fouling test, as indicated in **Fig. 2**, performance checks were carried out for all membranes with 2 M NaCl as DS and DI water as feed. After the fouling experiment a normal flush (using Re of 1900 and 700 on FS and DS side, respectively) was done with 1 L of DI water to gently remove any additional DS/FS solutes from the membrane and FO module was moved to set-up # 1. The performance of the fouled FO membrane was initially

evaluated with 2M NaCl DS against DI water FS using the existing FO fouling evaluation approach and later with the new Tahir approach.

3. Results and discussion

3.1. Influence of FS and DS concentration on flux behaviour

FO was initially evaluated using set-up # 1 with 2 M NaCl as DS and DI water as FS in both AL-FS and AL-DS membrane orientations. Baseline flux was also obtained. After baseline tests, HFFO modules were shifted to set up # 2 and FO was operated for 1, 2 and 3 M KCl as DS and various BGW quality FS (B5, B10, B20 and B35) for AL-FS and AL-DS.

Fig. 3 Effect of changing FS (for inorganic fouling) and DS concentration on HFFO flux a) in AL-FS and b) AL-DS.

3.1.1 Flux behaviour in AL-FS orientation

Fig. 3(a) presents the flux outcomes for AL-FS orientation when the HFFO was evaluated for two different FS concentrations (B10 and B35) with various DS concentrations of 1–3 M

1 KCl. It was observed that the flux inconsistently changed by the change in FS and DS
 2 concentrations. With the changing DS concentration, water flux increased with the increase in
 3 osmotic pressure of the DS, nevertheless; the increase of experimental flux was non-linear
 4 with the changes in DS concentration (Phuntsho et al., 2013, Lotfi et al., 2015). Results
 5 indicated that, for an increase of DS concentration from 1 and 3 M KCl, the flux increased by
 6 32% for B10 FS, whereas for B35 FS, it showed a flux increase of 26%. However, the flux
 7 reduced by 8 % for 1 M KCl DS and 14% for 3 M KCl DS when FS quality was increased
 8 from B10 to B35. The flux curves for various DS and FS concentrations behaved differently
 9 and showed two distinct performance ranges along the test run. In all cases, the flux declined
 10 rapidly in the initial 30 min followed by a steady state flux level. For 1 M KCl DS, the flux
 11 changed by 21–28% for various FS concentrations in the initial 30 min, whereas the flux
 12 changes by only 3–8% in the 30–200 min. These results indicated that, during the initial
 13 period, DS and FS built ICP and ECP interactions on the AL and SL of the membrane and
 14 this affected the flux outcome. Further, the observed flux changes during the initial period
 15 were higher than the apparent effect of possible DS dilution and FS concentration with time.
 16 For this reason, it is suggested that, during the initial experimental time, the higher flux
 17 decline was due to the strong interactions between the solute particles and membrane surfaces
 18 that helped ICP/ECP build up and rapidly reduced the flux. Later, as the development of FS
 19 and DS solute's association reached the cusp, the build-up became uniform and the flux
 20 changed in the remaining test run only appear to be due to the subsequent dilution of the DS
 21 and the concentration of the FS side. To confirm this hypothesis, a few experiments were run
 22 for 36 h, but no serious change was observed in the flux patterns.

23

24 3.1.2 Flux behaviour in AL–DS orientation

1 FO performances were further evaluated in AL–DS membrane orientation using the same
2 experiment protocols. The 1-3 M KCl was used as DS against B5, B10, B20 and B35 as FS,
3 and the resultant flux variation is presented in **Fig. 3(b)**. It should be noted that the flux
4 curves for these DS and FS combinations showed a different order from the AL–FS
5 orientation, which indicated that the ICP and ECP build-up differently at AL–FS and AL–DS
6 membrane orientations. Similar to the AL–FS membrane orientation, the flux patterns
7 showed two distinct parts, with the flux declined quickly in the initial test time followed by
8 gradual decline for DS dilution. However, in the AL–DS orientation, the flux reduced quickly
9 in a shorter time of 20 min and the flux-declining trend became nearly linear. The flux curve
10 at the later stage indicated insignificant flux changes in FO operations because the driving
11 force did not change remarkably with the changes in DS dilution and FS concentration.

Fig. 4 Effect of changes in FS concentration on FO flux a) for AL-FS and b) for AL-DS membrane orientation.

3.2 Effect of inorganic FS concentration on flux behaviour

Based on the flux patterns in earlier tests using various DS concentrations, 2 M KCl DS was selected for rest of the study. Baseline water flux was first evaluated with 2 M KCl DS against DI (Reference), B10, B20 and B35 quality FS (**Fig. 4**). FO in the AL-FS orientation showed a flux drop of only 12% as the flux declined from 15.02 LMH to 14.23 LMH when the FS concentration was changed from DI water to 10 g/L BGW (**Fig. 4(a)**). However, for AL-DS orientation, FO initially showed a sharp decline in water flux as the FS concentration was changed from DI water to B10, B20 and B35. The water flux dropped from 48.2 LMH to 12.7 LMH indicating a flux drop of 73% when FS concentration was changed from DI water to B10 (**Fig. 4(b)**). Later, for the changes in the FS concentration of B10 to B20 (10 g/L) did

not produce similar effect as flux declined by 9.95% and 20% for AL–FS and AL–DS orientation, respectively.

Earlier studies have shown that the flux decline is attributed to the enhanced ICP/ECP effect developed by the high FS concentrations (Suh and Lee, 2013, Tang et al., 2010, McCutcheon et al., 2006, McCutcheon and Elimelech, 2006). For higher FS concentration, ECP development begins as water permeation starts from FS to DS. As the pure water permeate through the membrane, depending upon the FO membrane orientation, the FS solute enrichment increases at the FS and AL or SL interface. This enhanced FS solute concentration causes a reduction of the net effective osmotic pressure difference for the FO process and as a result, a resultant lower FO flux output is derived. However, the flux outcome for the AL–DS membrane orientation (**Fig. 4(b)**) indicated that the flux declined immediately from the start of the experiment, before the FS solutes concentration could start to rise due to water permeation towards DS. This indicated that apart from the possible ICP and ECP effects, some other forces, developed with the possible association of FS and the membrane surface material, also played a significant role for the drastic reduction of water flux in AL–DS orientation. It is suggested that the divalent FS solutes components, such as Ca^{2+} and Mg^{2+} , developed additional interactions with the functional groups of the membrane SL or at the SL–AL interface were mainly responsible for the water permeation through osmosis. The rapid flux changing phenomena may be further attributed to the SL pore blocked by FS solutes (Majeed et al., 2013). These outcomes stressed the need for further studies in this area to track membrane functional groups influencing FO flux outcome for changes in FS concentration.

To check the effect of fouling on FO membrane, few membrane modules were alternatively collected after 20 min of fouling tests, gently rinsed and placed on FO setup # 2. The membrane performance was checked using 2 M NaCl DS and DI water FS. All of these membranes showed performances similar to baseline (within $\pm 2.12\%$ range). Results indicated that the initial flux declines shown in **Fig. 3 and 4** were not due to fouling, but to some interactions between FS solutes and AL or SL of the membrane.

3.3 Effect of organic foulants on FO flux performances

Three model foulants, such as alginate, HA and BSA were studied to investigate the effect of organic fouling on the FO process. The 2 M KCl was used as DS for these experiments. Alginate, HA and BSA were initially evaluated in individual concentrations of 60 mg/L with DI water FS for organic fouling potential. Later FO was also tested with all possible combination of 60 mg/L each of alginate, HA and BSA with varying BGW FS concentrations to assess the synergic effect of organic foulants and FS solutes on FO performances.

3.3.1 Flux performance in AL–FS orientation

Fig. 5 illustrates the effect of alginate, HA and BSA on flux when the FO was operated at AL–FS orientation using DI water and B35 FS. It was observed that FO showed higher flux with FS carrying alginate, HA and BSA in DI water than DI water DS (**Fig. 5(a)**). Compared to 2 M KCl DS and DI water FS baseline, the FS carrying each of alginate, HA and BSA in DI water even showed 5.6% higher flux outcome (**Fig. 5(a)**). Foulants build-up on the FO membrane increased the negative charges of the membrane surface and resulted a higher flux outcome (Tiraferri and Elimelech, 2012). The results also indicated that once the fouling layer started to develop on the FO membrane surface, the net ionic charges and the functional groups of these foulants facilitated the permeation of water molecules. This further confirmed

that, compared to pressure driven processes, FO in AL-FS orientation shown more stability in flux and this result was in good agreement with the earlier findings (Tang et al., 2010, Achilli et al., 2009).

Fig. 5 Effect of model organic foulants on flux performance of FO process with a) DI water FS in AL-FS; b) B35 in AL-FS; c) DI water FS in AL-DS; and d) B35 in AL-DS orientation.

2M KCl was used as DS for both AL-FS and AL-DS orientation, crossflow Reynolds number for FS and DS were 1900 and 700, respectively and temperature was 25 ± 0.5 °C.

Fig. 5(b) also showed a similar trend when alginate, HA and BSA were used with B35 FS. After 30 min of operation, FS carrying organic foulants showed a 9.11% higher flux than that of the B35 FS. Interactions between the foulant species and membrane surface helped the negative charges on the membrane surface to rise, which enhanced the flux through the membrane. Divalent Ca^{2+} and Mg^{2+} ions also attached to negatively charged fouling layers but did not show their effect on flux reduction.

3.3.2 Flux performance in AL-DS orientation

Figs. 5 (c) and (d) further show the performance of the HFFO membrane in the AL-DS orientation for various organic foulants and the changing FS qualities. **Fig. 5(c)** represents the flux outcome when HFFO was operated with various combinations of alginate, HA and BSA in DI water FS. It was found that, in comparison to FO operations in AL-FS, the flux is affected with model foulants in varying order. In contrary to the results in AL-FS orientation, the FS carrying combined (alginate + HA + BSA) foulants did not show a higher flux in AL-DS orientation, while the FS loaded with alginate/HA showed a higher flux. FS carrying only alginate initially showed a lower flux, followed by a higher flux after 300 min of operation.

FO flux was evaluated in AL-DS orientation for B35 FS carrying organic foulant and the results are presented in **Fig 5(d)**. Similar to **Fig. 4(b)**, FO showed a very low flux when operated for organic foulant loaded B35 FS. Organic foulants with B35 FS showed a similar flux behaviour as shown with the DI water FS. Alginate carrying FS showed a higher flux whereas alginate/HA/BSA loaded FS showed a lower flux outcome. These outcomes indicated that the developing fouling layers played an important role for the changes of FO

performance. Initially, the fouling layer association with the membrane modify the osmotic behaviour of the membrane and resulted flux increase. Later, it supports pore-blocking phenomena to reduce flux performances of the membrane. **Fig. 5** shows that the water flux in both the AL-FS and AL-DS membrane orientation enhanced slightly with the development of the organic foulant layer. **Figs. 5 (c) and (d)** further indicated that, for AL-DS orientation, FS carrying foulants drastically reduced the flux outcome possibly due to the induced severe internal clogging on the SL. It was different from the AL-FS orientation, where fouling phenomena was dominated by cake layer formation on the relatively smooth rejection layer (Mi and Elimelech, 2010).

During the fouling process, the organic and particulate matter accumulates inside the porous structure of the support layer and reduces membrane permeability. Reverse salt flux can be built up in the support layer and reduce the effective osmotic driving force (Cath et al., 2013). These results further indicated that the water flux loss due to fouling on the FO membrane was collectively caused by a combination of (1) the physical blocking of the active pores associated with the AL or SL structure by the FS components; 2) enhanced concentrative ICP which reduced the mass transfer coefficient of the SL; 3) internal clogging in the support structure of the FO membrane which likely reduced the porosity and mass transfer rate, enhancing the structural parameter which resulted in additional hydraulic resistance; and 4) the enhanced CP development in the attached fouling layer [30]. The impact of initial fouling layer on flux behaviour can mainly be attributed to pore plugging and CP effects at the AL and SL of the membrane. Later attachments of the new layers to the initial fouling layer did not enhance this combination effect.

1

2

3 Fig. 6 Effect of membrane orientation and FS concentration on FO flux. Conditions: DS=
 4 2M KCl, FS=DI and BGW35 carrying alginate, HA and BSA were used in 60 mg/L
 5 concentration each. Membrane orientation: evaluated for both AL-FS and AL-DS,
 6 temperature = 25 ± 0.5 °C.

7

8 **Fig. 6** illustrates the effect of membrane orientation and the combined effect of inorganic and
 9 organic components of the FS on HFFO membrane flux. Paralleling the earlier results for
 10 BGW FS outcome as shown in **Fig. 4**, for alginate/HA/BSA loaded FS with DI, the HFFO
 11 membrane showed high flux in AL-DS orientation whereas the FO showed the lowest flux
 12 for alginate/HA/BSA loaded FS with B35. These results reflected the serious pore blocking
 13 and CP affected by the FS carrying inorganic solutes which restricted the flux outcomes in
 14 AL-DS orientation (Majeed et al., 2015). The higher flux outcome with organically fouled
 15 membrane indicated that higher negative charged of the FO membrane helped to facilitate the
 16 quick and easy penetration of water molecules. It further indicated that the water permeation

1 through membrane starts with the association of the positively charged (H^+) part of water
2 molecule with the negatively charged sites of the membrane functional groups. These
3 associations facilitated water molecules to come closer and passed quickly through the
4 membrane pores.

5
6 These results further indicated that depending on the type of membrane orientation, newly
7 formed fouling layer on the FO membrane produced different CP effects. It provided an extra
8 thick layer on either the AL or SL of the membrane and resulted additional ICP or ECP build-
9 up on FO membrane and affected FO flux. **Fig. 7** shows the varying effect of ICP and ECP
10 on FO membrane due to the newly developed fouling layer. For the developed fouling layer
11 on FO membrane, ECP showed higher effects on flux in AL-FS than ICP effects on AL-DS
12 orientation. The thickness of the fouling layer also helped to enhance the ICP effects which
13 reduced the flux attributed to cake layer formation (Mi and Elimelech, 2008). These results
14 suggested that the higher portion of the flux decline for FO fouling in AL-DS was caused by
15 the pore blocking or cake enhanced resistance, whereas for AL-FS, the CP resistance mainly
16 contributed to a flux drop.

1

2

a)

3

4

b)

Fig. 7 Effects of fouling layer on the ICP and ECP for FO operations a) at AL–FS and b) at AL–DS.

Figs. 4 and 5 have already indicated that when DS and FS qualities are changed, the flux does not change linearly to reflect the changes in the osmotic pressure difference. Some portion of the osmotic pressure increase is offset by the possible changes in the ICP/ECP effects (**Fig. 7**). For higher DS concentrations, the effectiveness of the net osmotic pressure decreases with the higher concentrations of FS. CP quickly builds-up with high BGW solute concentration in FS and this results in a lowering of the net osmotic pressure at the membrane interface (Majeed et al., 2015). For this reason, difference of flux outcome increases more at high FS concentration.

3.4. Delusion behind the scaling and fouling approach for hollow fiber forward osmosis membrane

Figs. 3-6 presented flux behaviour for HFFO membrane using FS carrying BGW and organic foulants. Apparently all curves directed reducing flux trends and indicated occurrence of possible fouling phenomena. Following the existing fouling approach, these fouling judgements were made by comparing any flux curve behaviour with the baseline curve at any particular time and the difference between these two points was referred as to fouling effect. These fouling observations were made considering the presence of constant driving force acting on FO process, thus Figs. 3-6 indicated significant differences in the flux for fouling, and however, the actual fouling potential seems different from the apparent one.

Opposite to RO/NF/MF/UF systems, the changes in the FO driving forces are extremely dynamic as they continuously affect the FO flux performance. Multiple flux driving forces simultaneously act on FO, which do not remain fixed during the FO operation rather keep

changing constantly. In FO, no two points show the similar driving force while comparing any two FO flux curves; hence the flux outcome did not provide a reliable comparison of any two such performances at any particular time. The same flux declining curves using different driving forces cannot be used to ascertain the fouling potential on the FO membrane surface for any DS and FS. Hence, from the existing methodology of FO flux data curve comparison, it is difficult to find how much of the flux is affected individually by the changing driving forces and the fouling and scaling or ICP/ECP issues (**Fig. 1**). For these reasons, the standard flux curves comparison for FO operation, may not be reasonably used for evaluating the fouling potential of the FO membrane.

To accommodate the issue of constantly changing flux-driving forces for FO fouling as summarized in **Fig. 1**, Tahir approach is used ahead to evaluate the fouling risk for FO process. To check the absolute effect of FO fouling on the flux performance, the FO membrane was initially evaluated at FO set-up # 1 with a different DS (2 M NaCl) and DI water FS and the baseline flux was recorded for an average 10 min of test run. FO fouling experiments were conducted on set-up # 2 for specific DS (2 M KCl) and varying FS concentration carrying different combinations of BGW and organic foulants (**Fig. 2**). On completion of each fouling test run, a 10 min slow rinsing with DI water was carried out on both sides to remove excessive DS and FS from the fouling experiment. The module is then moved to set-up # 1 and the FO was evaluated for the same initial driving force using 2 M NaCl DS and DI water FS to indicate any changes in the FO membrane flux performance. The average of the initial 10 min flux was evaluated to compare the membrane performances.

3.4.1 Real effects of inorganic fouling on FO performances

1 Using the experimental protocol outlined in **Fig. 2** for Tahir fouling approach, the water flux
2 was monitored for HFFO membrane in AL-FS and the AL-DS orientations and results are
3 presented in **Fig. 8**. The results indicated that the FO flux performance was barely affected by
4 the changing BGW FS quality. FO in AL-FS orientation showed a smaller flux decline than
5 in the AL-DS orientation. For B35 FS, the results showed that the HFFO flux declined by
6 0.25 LMH (3%) in AL-FS orientation. However, in AL-DS orientation, up to a 2.16 LMH
7 (5.6%) flux drop was observed for similar FS (**Fig. 8(a)**).

8
9 **Fig. 8(b)** showed the flux outcome for step-1 and step-5 following Tahir fouling protocol
10 where the FO was operated for 2 M KCl DS and B35 FS in both AL-FS and AL-DS
11 membrane orientations. Results show that, in AL-FS orientation, for a longer test run with
12 B35 FS, the FO flux dropped by 0.38 LMH (2.64%), which indicated a minimal effect in
13 terms of fouling. However, HFFO showed a higher flux decline of 2.59 LMH (5.92%) when
14 operated in AL-DS membrane orientation. These results were different from the results
15 presented above in **Figs. 4 and 5**, which failed to clearly indicate fouling effect for various
16 DS and FS combinations as they shown flux behaviour influenced by various forces. Thus it
17 did not demonstrate real flux changes specifically for scaling.

a)

b)

Fig. 8 Effect of scaling on HFFO membrane performance: a) for AL-FS and AL-DS membrane orientation with 2 M KCl DS and B10, B20 and B35 as FS, b) flux performance for step-1 and step-5. 2 M KCl was used as DS against B35 FS for both AL-FS and AL-DS membrane orientation, Temp=25 ± 0.5 °C.

1

2 **3.4.2 Real Effect of combined fouling on HFFO performances**

3 Following the **Fig. 2** experimental protocol, the HFFO was evaluated for fouling issues using
 4 2 M KCl DS and DI water and B35 FS carrying alginate, HA and BSA and results were
 5 summarized in **Fig. 9**. **Fig. 9(a)** presented the performance of the FO membrane when
 6 operated at AL–FS orientation. The outcomes showed varying fouling effect for FO in
 7 relation to different FS. The results indicated higher fouling for the HFFO membrane for
 8 organic foulants/DI water FS than organic foulants/ BGW FS. Flux with FS carrying 60 mg/L
 9 each of HA and Alginate in DI dropped to 12.18 LMH indicating a flux drop of up to 9% due
 10 to fouling. On the other hands, when used with B35, they showed little flux decline. FO
 11 indicated lower fouling potential for organic foulants/BGW FS. A flux drop of up to 4% was
 12 also observed for B35 FS carrying 60 mg/L each of HA and BSA.

13

14 Different fouling effects with similar FS and DS for AL-FS and AL-DS membrane
 15 orientation suggest that apart from effects of the membrane properties and foulant
 16 characteristics, flux potential is also driven by some other forces. In the current design of
 17 HFFO module, similar cross flow velocity indicated varying Re flow within and outer side of
 18 lumens and exerts varying shear force. High crossflow shear forces resist fouling layer
 19 development process by overcoming the foulant-membrane attractive forces. The crossflow
 20 shear force acting within the HF lumen does not allow any fouling layer development and
 21 reduces the HFFO fouling risk for AL-FS orientation. Further, any foulant attached to inner
 22 lumen surface is easily pushed out by the sheer force generated by the crossflow velocity
 23 especially for FS flowing through the fiber lumens (**Fig. 10**). Hence, in AL–FS orientation,
 24 little or no flux loss was observed with the combined fouled FS. Lower fouling results with

B35 indicates that the bridging of divalent Ca^{2+} and Mg^{2+} ions with the foulants functional groups depressed the adhesion potential of the fouling layer.

a)

b)

Fig. 9 Effect of the combine organic fouling on the performances of HFFO membrane a) flux in AL-FS membrane orientation b) flux in AL-DS membrane orientation.

Furthermore, when FO was evaluated in AL–DS orientation using alginate, HA and BSA foulants in DI water and BGW FS, the flux dropped by 16–49%, indicated high fouling risk for HFFO membrane at AL–DS (**Fig. 9(b)**). Similar to AL–FS orientation, FO in AL–DS orientation also indicated high fouling for FS carrying organic foulants in DI water. However, for few cases, it showed high fouling with BGW FS. B35 DS carrying 60 mg/L each of HA, alginate and BSA foulants showed high fouling and indicated a flux drop of 49% for fouling. The lower flux outcomes indicated that, in AL–DS orientation, the FO membrane is highly prone to a greater risk of fouling. Among the three model foulants, the BSA loaded FS showed much apparent flux decline than HA and alginate.

The observed differences in the fouling rate at different membrane orientations reflected the influence of varying associations among the foulants and surface charge, hydrophilicity and zeta potential of the associated layers of the FO membrane influenced by the flow shear forces. These results also suggested that the different flow shear forces acting on FO seem primarily responsible for varying fouling behaviour for AL–FS and AL–DS membrane orientations. **Fig. 10** indicated the consequences of DS and FS streams flowing with varying Re through the HFFO membrane for scale development and deposition. In AL–FS membrane orientation, FS passed through HFFO lumens. The given FS crossflow rate produced a high shear force inside of the HF lumens, generating swirling movements that left fewer opportunities for scale build-up on inner surface of the FO lumens. Thus, a lower flux decline was observed for AL–FS orientation. Higher cross-flow velocity led to reduction of aggregation of the feed solids to form the fouling layer. The sheer force turbulence overcame the membrane–foulants interaction force and avoid fouling layer development on the membrane surface in AL–FS orientation. Reduced hydrophobicity and increased electrostatic

repulsion led to a lower deposition rate of these foulants onto the membrane surface and thus less fouling (Hong and Elimelech, 1997).

Fig. 10 Graphical presentation for effects of varying crossflow shear forces within and outside HFFO lumens affecting fouling behaviours of HFFO membrane in a) AL-FS and b) AL-DS orientation.

On the contrary, due to the HFFO module design issues, the similar working crossflow rate was unable to deliver the similar swirling effect on the HF outer surface. The feeble shear force left a more favourable environment for the deposits build-up and results comparatively higher flux drop in the AL-DS membrane orientation.

Figs. 4-6 indicated fouling using existing methodology for FO fouling whereas **Figs. 8 and 9** showed FO fouling potential using Tahir approach. Comparing the FO performance curves presented in **Figs. 4-6** with **Figs. 8 and 9** for two different fouling evaluation approaches, it can be seen that the results presented by the existing approach showed a better flux outcome or less fouling for alginate, HA and BSA loaded FS. This stood true for AL-FS but indicated misleading outcome for AL-DS orientation. These comparisons further indicated that for the FO process, as the existing fouling approach did not indicate true fouling risks for FO membranes rather directed toward misleading outcome, it may not be used effectively to identify the real fouling issues for the FO membrane. This comparison highlighted the severe interference of the interacted forces with the FO performance especially in relation to internal concentration polarization (ICP)/external concentration polarization (ECP). The effect of possible ICP and ECP intensification with fouling layer growth on FO membrane was still unclear, however, the possibilities in relation to the ICP and ECP intensification of the fouling layer should not be ruled out.

3.5 Fouling development process during FO combined fouling

The development of fouling on FO membrane was also assessed with reference to the duration of the operation. FO was evaluated in AL-DS orientation for FS carrying 60 mg/L each of alginate, HA and BSA in DI water and 2 M KCl DS for a period of 2 and 10 h separately. At the end of experiments, resultant flux was also evaluated on FO set-up # 1 and the flux performance was recorded. The results shown nearly similar flux of 36.58 LMH and 36.56 LMH for the two tests operated for 2 and 10 h respectively (**Fig. 11**), indicated a flux loss of about 18% due to HFFO fouling. The similar flux outcomes for FO membrane operated for different times indicated that the fouling layer on the FO membrane developed during the initial stage of FO test run contributing to the reduction in the FO flux

performance. This also indicated that the initial fouling layer blocked the membrane pores, which mainly affected flux for the membrane process. The later deposition of the other fouling layer seemed loose which did not appear to contribute to the further plugging of membrane pore. Accordingly, no or lower flux decline was observed with subsequent fouling for longer FO test run. More detailed studies are required to further evaluate how these FS characteristics affect the FO flux driving force at the initial stages.

Fig. 11 Fouling development progress with time (AL-DS)

FO showed mixed flux trends with all model organic foulants evaluated in this study. The formation of a cross-linked gel layer is also observed when the FO was operated in AL-DS orientation for alginate, HA and BSA loaded FS (**Fig. 12**). These prominent and easily distinguishable fouling layers are observed in all experiments using FS carrying dark brown

- 1 coloured HA. This fouling layer is found firmly stuck to the membrane surface and found
- 2 really hard to separate it from the membrane outer surface by vigorous shaking.
- 3

Accepted Manuscript

Fig. 12 Fouling layer developed on HFFO lumen fiber module used for a) AL-FS and b) AL-DS respectively

4. Conclusions

The HFFO membrane was evaluated to investigate the effects of fouling for two different fouling evaluation protocols using various BGW FS qualities carrying model organic foulants such as alginate, HA and BSA. The following conclusions are drawn from the outcomes of this study:

- An immediate flux drop at AL-DS orientation in a very short time test run does not follow the existing CP concept. This indicates role of possible associations between the FS solutes and active and support layer of FO membrane. These cause a drop in the net osmotic pressure at the membrane interface and resultant flux outcome, which is independent of the general CP. This reduced flux may not be classified as either scaling or fouling.

- Due to continuous changes in FO driving force and their associated effects on flux outcome, the fouling effects for FO cannot be worked out using routine FO fouling experimental approaches used similar to RO/NF/MF/UF.
- The fouling process for FO is reviewed and an alternative approach is suggested to evaluate the actual loss of the FO flux due to scaling and fouling which successfully shown the real impact of the fouling on the FO flux.
- It is found that paralleling other membrane systems, the HFFO membrane also carries nearly the same risk for fouling, however, the crossflow rates leave different results for FO fouling in AL-F and AL-DS orientation.
- The respective influence of foulants on the FO flux is different for both the AL-FS and AL-DS membrane orientation. HFFO showed a higher fouling risk at AL-DS orientation.
- The crossflow rate seems to play an important role for varying fouling outcomes for the HFFO membrane in both the AL-DS and AL-FS membrane orientation. Further studies may easily lead to some adjustments in the appropriate process conditions for effective fouling control in FO process.

Acknowledgements

This research is funded by the National Centre of Excellence in Desalination, Australia (NCEDA). The authors also thank Samsung Cheil Industries, Korea for graciously providing membrane materials for the current study.

1

2 **References**

- 3 Achilli, A., Cath, T. Y., Marchand, E. A. & Childress, A. E. 2009. The forward osmosis
4 membrane bioreactor: A low fouling alternative to MBR processes. *Desalination*,
5 239, 10-21.
- 6 Arkhangelsky, E., Wicaksana, F., Chou, S., Al-Rabiah, A. A., Al-Zahrani, S. M. & Wang, R.
7 2012. Effects of scaling and cleaning on the performance of forward osmosis hollow
8 fiber membranes. *J. Membr. Sci.*, 415–416, 101-108.
- 9 Bamaga, O., Yokochi, A. & Beaudry, E. 2009. Application of forward osmosis in
10 pretreatment of seawater for small reverse osmosis desalination units. *Desal. Wat.*
11 *Treat.*, 5, 183-191.
- 12 Bellona, C., Drewes, J. E., Xu, P. & Amy, G. 2004. Factors affecting the rejection of organic
13 solutes during NF/RO treatment—a literature review. *Water Res.*, 38, 2795-2809.
- 14 Cath, T. Y., Childress, A. E. & Elimelech, M. 2006. Forward osmosis: Principles,
15 applications, and recent developments. *J. Membr. Sci.*, 281, 70-87.
- 16 Cath, T. Y., Elimelech, M., McCutcheon, J. R., McGinnis, R. L., Achilli, A., Anastasio, D.,
17 Brady, A. R., Childress, A. E., Farr, I. V. & Hancock, N. T. 2013. Standard
18 methodology for evaluating membrane performance in osmotically driven membrane
19 processes. *Desalination*, 312, 31-38.
- 20 Chen, G., Lu, Y., Krantz, W. B., Wang, R. & Fane, A. G. 2014. Optimization of operating
21 conditions for a continuous membrane distillation crystallization process with zero
22 salty water discharge. *J. Membr. Sci.*, 450, 1-11.
- 23 Chung, T.-S., Li, X., Ong, R. C., Ge, Q., Wang, H. & Han, G. 2012. Emerging forward
24 osmosis (FO) technologies and challenges ahead for clean water and clean energy
25 applications. *Curr. Opin. Chem. Eng.*, 1, 246-257.
- 26 Cornelissen, E., Harmsen, D., De Korte, K., Ruiken, C., Qin, J.-J., Oo, H. & Wessels, L.
27 2008. Membrane fouling and process performance of forward osmosis membranes on
28 activated sludge. *J. Membr. Sci.*, 319, 158-168.
- 29 Elimelech, M. 2007. Yale constructs forward osmosis desalination pilot plant. *Memb. Tech.*,
30 2007, 7-8.
- 31 Greenlee, L. F., Lawler, D. F., Freeman, B. D., Marrot, B. & Moulin, P. 2009. Reverse
32 osmosis desalination: water sources, technology, and today's challenges. *Water Res.*,
33 43, 2317-2348.
- 34 Gu, Y., Wang, Y.-N., Wei, J. & Tang, C. Y. 2013. Organic fouling of thin-film composite
35 polyamide and cellulose triacetate forward osmosis membranes by oppositely charged
36 macromolecules. *Water Res.*, 47, 1867-1874.
- 37 Holloway, R. W., Childress, A. E., Dennett, K. E. & Cath, T. Y. 2007. Forward osmosis for
38 concentration of anaerobic digester centrate. *Water Res.*, 41, 4005-4014.
- 39 Hong, S. & Elimelech, M. 1997. Chemical and physical aspects of natural organic matter
40 (NOM) fouling of nanofiltration membranes. *J. Membr. Sci.*, 132, 159-181.
- 41 Jin, X., She, Q., Ang, X. & Tang, C. Y. 2012. Removal of boron and arsenic by forward
42 osmosis membrane: Influence of membrane orientation and organic fouling. *J.*
43 *Membr. Sci.*, 389, 182-187.
- 44 Kessler, J. O. & Moody, C. D. 1976. Drinking water from sea water by forward osmosis.
45 *Desalination*, 18, 297-306.
- 46 Kim, S. J., Ko, S. H., Kang, K. H. & Han, J. 2010. Direct seawater desalination by ion
47 concentration polarization. *Nat Nano*, 5, 297-301.

- 1 Li, Z.-Y., Yangali-Quintanilla, V., Valladares-Linares, R., Li, Q., Zhan, T. & Amy, G. 2012.
2 Flux patterns and membrane fouling propensity during desalination of seawater by
3 forward osmosis. *Water Res.*, 46, 195-204.
- 4 Lotfi, F., Phuntsho, S., Majeed, T., Kim, K., Han, D. S., Abdel-Wahab, A. & Shon, H. K.
5 2015. Thin film composite hollow fibre forward osmosis membrane module for the
6 desalination of brackish groundwater for fertigation. *Desalination*.
- 7 Majeed, T., Lotfi, F., Phuntsho, S., Yoon, J. K., Kim, K. & Shon, H. K. 2013. Performances
8 of PA hollow fiber membrane with the CTA flat sheet membrane for forward osmosis
9 process. *Desal. Wat. Treat.*, 53, 1744-1754.
- 10 Majeed, T., Sahebi, S., Lotfi, F., Kim, J. E., Phuntsho, S., Tijing, L. D. & Shon, H. K. 2015.
11 Fertilizer-drawn forward osmosis for irrigation of tomatoes. *Desal. Wat. Treat.*, 53,
12 2746-2759.
- 13 McCutcheon, J. R. & Elimelech, M. 2006. Influence of concentrative and dilutive internal
14 concentration polarization on flux behavior in forward osmosis. *J. Membr. Sci.*, 284,
15 237-247.
- 16 McCutcheon, J. R., McGinnis, R. L. & Elimelech, M. 2005. A novel ammonia—carbon
17 dioxide forward (direct) osmosis desalination process. *Desalination*, 174, 1-11.
- 18 McCutcheon, J. R., McGinnis, R. L. & Elimelech, M. 2006. Desalination by ammonia—
19 carbon dioxide forward osmosis: Influence of draw and feed solution concentrations
20 on process performance. *J. Membr. Sci.*, 278, 114-123.
- 21 Mi, B. & Elimelech, M. 2008. Chemical and physical aspects of organic fouling of forward
22 osmosis membranes. *J. Membr. Sci.*, 320, 292-302.
- 23 Mi, B. & Elimelech, M. 2010. Organic fouling of forward osmosis membranes: Fouling
24 reversibility and cleaning without chemical reagents. *J. Membr. Sci.*, 348, 337-345.
- 25 Park, M., Lee, J., Boo, C., Hong, S., Snyder, S. A. & Kim, J. H. 2013. Modeling of colloidal
26 fouling in forward osmosis membrane: Effects of reverse draw solution permeation.
27 *Desalination*, 314, 115-123.
- 28 Peng, W., Escobar, I. C. & White, D. B. 2004. Effects of water chemistries and properties of
29 membrane on the performance and fouling—a model development study. *J. Membr.*
30 *Sci.*, 238, 33-46.
- 31 Pérez-González, A., Urriaga, A. M., Ibáñez, R. & Ortiz, I. 2012. State of the art and review
32 on the treatment technologies of water reverse osmosis concentrates. *Water Res.*, 46,
33 267-283.
- 34 Phuntsho, S., Sahebi, S., Majeed, T., Lotfi, F., Kim, J. E. & Shon, H. K. 2013. Assessing the
35 major factors affecting the performances of forward osmosis and its implications on
36 the desalination process. *Chem. Eng. J.*, 231, 484-496.
- 37 Radu, A., Vrouwenvelder, J., van Loosdrecht, M. & Picioreanu, C. 2012. Effect of flow
38 velocity, substrate concentration and hydraulic cleaning on biofouling of reverse
39 osmosis feed channels. *Chem. Eng. J.*, 188, 30-39.
- 40 Saffarini, R. B., Summers, E. K., Arafat, H. A. & Lienhard V, J. H. 2012. Technical
41 evaluation of stand-alone solar powered membrane distillation systems. *Desalination*,
42 286, 332-341.
- 43 Sahebi, S., Phuntsho, S., Kim, J. E., Hong, S. & Shon, H. K. 2015. Pressure assisted fertiliser
44 drawn osmosis process to enhance final dilution of the fertiliser draw solution beyond
45 osmotic equilibrium. *J. Membr. Sci.*, 481, 63-72.
- 46 She, Q., Jin, X., Li, Q. & Tang, C. Y. 2012. Relating reverse and forward solute diffusion to
47 membrane fouling in osmotically driven membrane processes. *Water Res.*, 46, 2478-
48 2486.

- 1 Suh, C. & Lee, S. 2013. Modeling reverse draw solute flux in forward osmosis with external
2 concentration polarization in both sides of the draw and feed solution. *J. Membr. Sci.*,
3 427, 365-374.
- 4 Tang, C. Y., She, Q., Lay, W. C. L., Wang, R. & Fane, A. G. 2010. Coupled effects of
5 internal concentration polarization and fouling on flux behavior of forward osmosis
6 membranes during humic acid filtration. *J. Membr. Sci.*, 354, 123-133.
- 7 Tiraferri, A. & Elimelech, M. 2012. Direct quantification of negatively charged functional
8 groups on membrane surfaces. *J. Membr. Sci.*, 389, 499-508.
- 9 Valladares Linares, R., Bucs, S. S., Li, Z., Abughdeeb, M., Amy, G. & Vrouwenvelder, J.
10 2014. Impact of spacer thickness on biofouling in forward osmosis. *Water Res.*, 57,
11 223-233.
- 12 Wang, R., Shi, L., Tang, C. Y., Chou, S., Qiu, C. & Fane, A. G. 2010. Characterization of
13 novel forward osmosis hollow fiber membranes. *J. Membr. Sci.*, 355, 158-167.
- 14 Warczok, J., Gierszewska, M., Kujawski, W. & Güell, C. 2007. Application of osmotic
15 membrane distillation for reconcentration of sugar solutions from osmotic
16 dehydration. *Sep. Purif. Technol.*, 57, 425-429.
- 17 Yip, N. Y., Tiraferri, A., Phillip, W. A., Schiffman, J. D., Hoover, L. A., Kim, Y. C. &
18 Elimelech, M. 2011. Thin-film composite pressure retarded osmosis membranes for
19 sustainable power generation from salinity gradients. *Environ. Sci. Technol.*, 45,
20 4360-4369.
- 21 Zhang, J., Loong, W. L. C., Chou, S., Tang, C., Wang, R. & Fane, A. G. 2012. Membrane
22 biofouling and scaling in forward osmosis membrane bioreactor. *J. Membr. Sci.*, 403,
23 8-14.
- 24 Zhao, S., Zou, L., Tang, C. Y. & Mulcahy, D. 2012. Recent developments in forward
25 osmosis: Opportunities and challenges. *J. Membr. Sci.*, 396, 1-21.
- 26