Journal of Materials Chemistry C

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: Y. Zhang, S. WUSTONI, A. Savva, A. Giovannitti, I. McCulloch and S. Inal, *J. Mater. Chem. C*, 2018, DOI: 10.1039/C8TC00370J.

This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [author guidelines](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the ethical guidelines, outlined in our [author and reviewer resource centre](#), still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

PAPER

Lipid Bilayer Formation on Organic Electronic Materials

Yi Zhang,^a Shofarul Wustoni,^a Achilleas Savva,^a Alexander Giovannitti,^b Iain McCulloch^{b,c} and Sahika Inal^{a,*}Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

The lipid bilayer is the elemental structure of cell membrane, forming a stable barrier between the interior and exterior of the cell while hosting membrane proteins that enable selective transport of biologically important compounds and cellular recognition. Monitoring the quality and function of lipid bilayers is thus essential and can be performed using electrically active substrates that allow for transduction of signals. Such a promising electronic transducer material is the conducting polymer poly(3,4-ethylenedioxythiophene) doped with poly(styrene sulfonate) (PEDOT:PSS) which has provided a plethora of novel bio transducing architectures. The challenge is however in assembling a bilayer on the conducting polymer surface, which is defect-free and has high mobility. Herein, we investigate the fusion of zwitterionic vesicles on a variety of PEDOT:PSS films, but also on an electron transporting, negatively charged organic semiconductor, in order to understand the surface properties that trigger vesicle fusion. The PEDOT:PSS films are prepared from dispersions containing different concentrations of ethylene glycol included as a formulation additive, which gives a handle to modulate surface physicochemical properties without a compromise on the chemical composition. The strong correlation between the polarity of the surface, the fusion of vesicles and the mobility of the resulting bilayer aides extracting design principles for the development of future conducting polymers that will enable the formation of lipid bilayers.

Introduction

Biomembranes act as an essential barrier that separates tissues or cells from their surrounding environment. For instance, a number of toxins secreted by pathogenic bacteria attack the biomembranes by disrupting the integrity of their lipid structure, causing various diseases.¹ The biomembrane integrated with its proteins is also essential in maintaining cellular communication and function by enabling selective transportation of certain compounds and ions in and out of the cell. Investigating the integrity and the function of a biomembrane is therefore not only crucial to understand biological phenomena but also to develop diagnostic tools for pharmaceutical screening and in designing therapeutics against pathogen attack. As the natural biomembrane is highly complex, its major structural component, i.e. phospholipid bilayer, has provided a framework to access information regarding cellular

machinery including critical membrane interactions among constituents and properties of membrane proteins.²⁻⁶ Particularly, planar lipid bilayers supported by substrates provide a stable and robust platform. These supported lipid bilayers (SLBs) are self-assembled upon adsorption and fusion of lipid vesicles on hydrophilic and smooth surfaces such as glass,⁷ mica,⁸ and silica.⁹ The SLBs assembled on such surfaces are compatible with a variety of surface sensitive characterization techniques including total internal reflection fluorescence microscopy (TIRF),¹⁰ atomic force microscopy (AFM),¹¹ quartz crystal microbalance with dissipation monitoring (QCM-D),¹² and surface plasmon resonance (SPR).¹³

Electrical methods can allow for high-throughput and label-free sensing of the integrity of the bilayer and the functionality of biological membrane receptors or channels using chip-based arrays.¹⁴ They rely on the intrinsically high electrical resistance of the bilayer and as such can monitor changes in membrane conductance associated with the transport of ions through ion channels or in membrane surface potential associated with membrane function and protein binding events.¹⁵ SLBs have been formed on conducting or semiconducting substrates such as single-walled carbon nanotubes (SWNTs),¹⁶ gold,¹⁷ indium tin oxide (ITO)¹⁸ or polypyrrole.¹⁹ In a recent example, Zhou *et al.* recorded currents from individual ion channels using transistors based on SWNTs functionalized with polymeric cushions, relying on the ion channel current charging directly the quantum capacitance of a single NT in a network of purified semiconducting NTs.¹⁶ Despite the high potential of electrical methods to monitor lipid bilayers, the challenge remains in generating high resistance SLBs on

^a Biological and Environmental Sciences and Engineering Division, King Abdullah University of Science and Technology (KAUST), Building 2, Level 4, Room 4276, Thuwal 23955-6900, Kingdom of Saudi Arabia *Email - sahika.inal@kaust.edu.sa

^b Department of Chemistry and Centre for Plastic Electronics, Imperial College London, London SW7 2AZ, UK

^c Physical Science and Engineering Division, KAUST, Thuwal 23955-6900, Kingdom of Saudi Arabia

Electronic Supplementary Information (ESI) available: synthesis of p(OH-gNDI-gT2), NMR spectrum of p(OH-gNDI-gT2), FRAP images of a bilayer formed on glass, QCM-D signals of bilayers formed on various PEDOT:PSS surfaces, impedance spectra of PEDOT:PSS before and after vesicle fusion, water contact angle of a PEDOT:PSS film before and after fusion treatment, additional FRAP and AFM images of the electropolymerized PEDOT:PSS, and a summary of XPS results. See DOI: 10.1039/x0xx00000x

electronic surfaces which can efficiently transduce signals across the membrane while allowing for integration with functional transmembrane proteins.

A major drawback of traditional metal or metal oxide materials is in fact related to the limited space between the lipids and the substrate surface, which inhibits the insertion of large membrane proteins or leads to their denaturation due to the direct contact with the rigid surface and therefore limiting the biomimetic properties of the SLB.¹⁵ A promising material to interface the SLB is the conducting polymer, poly(3,4-ethylenedioxythiophene) doped with poly(styrene sulfonate) (PEDOT:PSS). PEDOT:PSS is not only an efficient ion-to-electron transducer,²⁰ but can also act as a hydrated polymer cushion providing a fluid environment for the bilayer. In fact, due to its compatibility with biological systems and good electrochemical stability in aqueous electrolytes, PEDOT:PSS has been the material of choice for a variety of electronic devices applied at the interface with biological systems. Examples include PEDOT:PSS based microelectrodes and organic electrochemical transistors (OECTs) for recording electrophysiological signals,^{21–23} monitoring cell coverage,²⁴ as well as barrier tissue formation.²⁵ The OECT is an electrolyte-gated transistor with record high transconductance, implying amplification of small biological signals into electronic current.²⁶ Owens and co-workers have recently shown, for the first time, the formation of a SLB on a PEDOT:PSS film and organic electrochemical transistor (OECT) using PEDOT:PSS in its channel via vesicle fusion.²⁷ These bilayers were characterized with QCM-D, fluorescence recovery after photobleaching (FRAP) and impedance spectroscopy. Due to the inherent amplification of the OECT, the integrity of the bilayer and the effects of a pore-forming toxin (α -hemolysin) on the bilayer integrity could be monitored.²⁷ However, the resistance of the SLB was much lower than the state-of-the-art, indicating that vesicles did not completely transform into a bilayer. Instead, a mixed population of vesicles and bilayers existed on the conducting polymer surface.²⁷ In order to achieve high sensitivity and obtain high throughput electrical measurements, a high resistivity and defect-free structure of the bilayer are prerequisites.

With recent advances in the microfabrication and patterning technologies of conducting polymers,²⁸ assembling transmembrane protein incorporated lipid bilayers on PEDOT:PSS surfaces show great promise for the development of highly sensitive bio transducers like the OECT. However, little is known about what triggers vesicles to form SLBs on these surfaces. Surface structures and the physicochemical properties of the substrate play an important role on vesicle fusion, the structure and property of the SLB.^{29–32} The interactions of the vesicles with the substrate are susceptible to the properties of substrate such as surface charge, roughness and composition, as well as to the properties of vesicles (e.g. composition, charge and size) and the buffer environment (pH, ionic strength and composition). As the field of organic bioelectronics expands beyond PEDOT:PSS and lipid bilayers are extremely interesting for the development of diagnostic tools for cells as well as designing therapeutics, it is crucial to understand what type of

organic semiconductor surfaces are required to promote vesicle fusion. In this work, we investigate the fusion of zwitterionic vesicles on a variety of conjugated polymer films. We investigate PEDOT:PSS films, which have the same chemical composition but different surface physicochemical characteristics. We obtain these films via spin-casting dispersions of PEDOT:PSS containing different amounts of a solution additive, i.e., ethylene glycol (EG). Varying the EG content in the dispersion leads to different surface properties. We monitor vesicle fusion and subsequent lipid bilayer formation on these films using FRAP and QCM-D and find that the mobility of the bilayers depends strongly on the polarity of the surface, regulated by the EG content. Moreover, intact vesicles on an electropolymerized PEDOT:PSS and a negatively charged n-type organic semiconductor film reveal the importance of surface roughness and charge density on vesicle fusion, respectively. As such, we identify the surface properties that promote vesicle fusion and shed light into the vesicle fusion process on conjugated polymers as well as the factors controlling the resulting structure of the SLBs. These results will aid in extracting design rules for the development of future materials which will enable defect-free SLBs.

Experimental

Materials

PEDOT:PSS (Clevios PH 1000) was purchased from Heraeus Clevios GmbH. The n-type semiconducting polymer p(OH-gNDI-gT2) is based on the electron deficient 2,6-dibromonaphthalene-1,4,5,8-tetracarboxylic diimide (NDI) unit. The solubility of the polymer in polar solvents and its electrochemical activity is due to the glycol side chains.³³ This –OH terminated polymer was synthesized as described in the Supporting Information and its NMR spectrum is given in Fig. S1. 4-dodecylbenzenesulfonic acid (DBSA), (3-glycidyloxypropyl)trimethoxysilane (GOPS), ethylene glycol (EG), chloroform, phosphate buffered saline (PBS) and trifluoroacetic acid were purchased from Sigma-Aldrich. The lipids, 1,2-diphytanoyl-sn-glycero-3-phosphocholine (DPhPC) and 1,2-diphytanoyl-sn-glycero-3-phosphoethanolamine (DPhPE), were purchased from Avanti Polar Lipids (Alabaster, USA). N-(4,4-difluoro-5,7-dimethyl-4-bora-3a,4a-diaza-indacene-3-propionyl)-1,2-dihexadecanoyl-sn-glycero-3-phosphoethanolamine, triethylammonium salt (BODIPY-DHPE) was purchased from Thermo Fisher Scientific. The hydrodynamic diameter of vesicles was measured to be ca. 118 nm using dynamic light scattering measurements.

Film preparation

Microscope glass slides and cover glasses (24 × 32 mm; No. 1.5; VWR) were cleaned in piranha solution (75 % H₂SO₄ and 25 % H₂O₂, v/v) followed by O₂ plasma cleaning at 150 W for 2 min. PEDOT:PSS dispersions were prepared by mixing EG (between 0 and 20 % by volume of dispersion as noted in the text/figures), DBSA (0.002 % v/v), GOPS (1 % w/w) and Clevios PH 1000 before ultra-sonication (30 min) and filtration through 1 μ m glass fiber filters. PEDOT:PSS films were spin-cast on glass substrates at

3000 rpm for 45 seconds unless otherwise stated. After spin-coating, the films were baked at 140 °C for 1 hour.

The semiconducting polymer, p(OH-gNDI-gT2), was dissolved in trifluoroacetic acid to 2.5 mg/mL and drop-cast on parylene C-coated glass substrate. Parylene C was used as a hydrophobic coating to promote stability of the polymer in aqueous media.

For the preparation of the electropolymerized PEDOT:PSS, we used a three-electrode system of a PEDOT:PSS-coated glass substrate as working electrode, a platinum mesh counter electrode, and an Ag/AgCl reference electrode, all connected to a potentiostat (Metrohm Autolab). The monomer, EDOT, (10 mM) and the dopant PSS (0.8 wt%) were mixed in DI water in a glass cell. Electropolymerization of PEDOT:PSS was carried out by using the potentiostatic mode, where the sample was biased at 1 V vs Ag/AgCl for 300 s at room temperature. The polymer deposited electrode was then washed with DI water, followed by spraying with N₂.

Before incubating the polymer films with lipid vesicles, all samples were immersed in DI water for 24 hours and dried with N₂ spray, followed by O₂ plasma activation at 25 W for 2 min. PDMS wells were then assembled on top of the polymer-coated glass substrates and used to define the area for lipid bilayers.

Vesicle preparation

DPhPC and DPhPE were mixed in chloroform (molar ratio 7:3) with 0.5 mol% BODIPY-DHPE. Bulk chloroform was evaporated under a stream of N₂ and any remaining solvent was removed under vacuum for at least 3 hours. PBS was then added to the dried lipid film which was re-suspended in a sonication bath for 30 minutes. The resulting multi-lamellar vesicles were extruded through a polycarbonate membrane (Whatman Nucleopore) with a pore size of 50 nm using a mini-extruder (Avanti Polar Lipids).

Fluorescence recovery after photobleaching (FRAP)

FRAP experiments were performed with a Zeiss LSM 800 or LSM 880 inverted microscope (Zeiss Germany) to determine the mobility of the SLB. With the lipid mixture 0.5 mol % BODIPY was used as a fluorescent label. Formed bilayers were gently scratched with a needle to remove a small portion of the bilayer material. The scratches facilitated focusing at the plane of the bilayer for microscope imaging. Following this step, the bilayer was rinsed with PBS for at least 1 min to wash away the removed lipid material. A laser beam was used to bleach a circular spot in the bilayer membrane. The recovery of fluorescence intensity of the bleached spot was recorded to determine the mobility of the lipid bilayer.^{34, 35} After background subtraction and normalization, the recovery data was fit using a Bessel function following a Soumpasis method.³⁶ The diffusion coefficient (*D*) was calculated using the following equation:

$$D = \frac{w^2}{4t_{1/2}}$$

where *w* is the radius of the photobleached spot and *t_{1/2}* is the time required to achieve half of the maximum recovery intensity.

Electrochemical quartz crystal microbalance with dissipation monitoring (EQCM-D)

Combined QCM-D/electrochemical impedance spectroscopy measurements for PEDOT:PSS (dispersions with varying EG content)-coated SiO₂ sensors were performed on the QSense Analyzer system (Biolin Scientific AB, Sweden) equipped with an electrochemistry module. The measurements were carried out at 24 °C with a flow rate of 100 μL/min controlled by a peristaltic pump. After stabilization of the baseline in PBS, vesicles in PBS (0.5 mg/mL) were injected onto the sensors. The adsorption of vesicles was monitored through changes in resonance frequency (Δf) and energy dissipation (ΔD) as a function of time using several overtones. All QCM-D data presented in this work were recorded at the 7th overtone. During these measurements, we also simultaneously measured the impedance of the sensors placed in the electrochemistry module which was connected to a potentiostat (Autolab PGSTAT128N). The sensor was used as the working electrode while a platinum foil contained in the module acted as a counter electrode and a Ag/AgCl electrode was used as the reference electrode. The impedance spectra of the films were acquired during different stages of bilayer formation under an AC potential of 10 mV and a DC voltage that corresponds to open-circuit potential (*V_{oc}*) before sending vesicles. The impedance spectra of these samples were also recorded at -0.05V vs *V_{oc}* after the formation of lipid membranes. We performed a second set of measurements, this time for only PEDOT:PSS, without adding vesicles. The films were stabilized in PBS and then impedance spectra were recorded first at *V* = *V_{oc}* and then *V* = -0.05V vs *V_{oc}*. In order to exclude slight differences between the two PEDOT:PSS films studied for each EG content, we normalized the spectra at *V_{oc}* with that recorded for PEDOT:PSS (no lipids, at *V_{oc}*) and a calibration curve was obtained for each sample. This calibration curve was then used to derive the corresponding impedance spectra of the films at -0.05V vs *V_{oc}*.

Contact angle measurements

The wettability of polymer films was determined using a goniometer (KRÜSS, DSA100, Germany). The mean value was obtained by measuring water contact angles at three different locations of the substrate. Each measurement took place 15 s after a 5 μL of deionized water droplet was deposited on the substrate.

Surface zeta potential

The surface zeta potentials of spin-cast PEDOT:PSS films, electropolymerized PEDOT:PSS film and p(OH-gNDI-gT2) film were determined using Zetasizer Nano ZS (Malvern Instruments Ltd, UK) equipped with a surface zeta potential cell (ZEN1020). A small piece of the polymer-coated glass substrate was attached to the sample holder and placed in the measurement cell. Each measurement was performed at 25 °C in 10 mM KCl (pH 7.4) containing Coffeemate® (Nestle S.A.) as tracer particles. The electrophoretic mobility of the tracer particles

was measured at four different distances from the surface of the sample. The values were used to determine the surface zeta potential by the Zetasizer software. Three measurements were carried out for each sample.

Atomic force microscopy (AFM)

The surface topography of polymer samples was studied with an Agilent 5500 SPM system (Agilent Technologies, USA). All measurements were carried out in tapping mode in air and PBS.

X-ray photoelectron spectroscopy (XPS)

The XPS experiments were performed on a Kratos Axis Ultra DLD instrument equipped with a monochromatic Al K α x-ray source ($h\nu = 1486.6$ eV) operated at a power of 150 W and under UHV conditions in the range of $\sim 10^{-9}$ mbar. All spectra were recorded in hybrid mode using electrostatic and magnetic lenses and an aperture slot of $300\ \mu\text{m} \times 700\ \mu\text{m}$. The survey and high-resolution spectra were acquired at fixed analyzer pass energies of 160 eV and 20 eV, respectively. The samples were mounted in floating mode in order to avoid differential charging. The spectra were acquired using charge neutralization and referenced by using neutral carbon (C 1s) at 284.8 eV. The background subtraction was carried out by Tougaard method and convolution of all component peaks were fitted by Gaussian and Lorentzian method.

Results and discussion

Monitoring the formation of supported lipid membranes

It is well known that lipid bilayers spontaneously assemble on siliceous substrates via vesicle fusion. Though not completely

understood, vesicle fusion on solid substrate is thought to follow a two-phase process (Fig. 1a).^{5, 29} The vesicles first adsorb onto the substrate. When a critical coverage of adsorbed vesicles is reached, they start to deform, rupture and fuse, forming bilayer patches on the substrate. The edges of SLBs spread and further induce adjacent vesicles to rupture forming a continuous bilayer.⁹

To mimic the natural biomembrane, a key property is the two-dimensional mobility of lipid molecules within the bilayer. The fluidity of lipid membrane is a critical factor for interactions between membrane constituents, membrane transport and enzyme activities.^{37, 38} For instance, the integral membrane enzymes such as Ca²⁺-ATPase, Na, K-ATPase and cytochrome oxidase are less active when the lipid membrane becomes less fluid, consequently affecting the reaction rates.³⁷ We, therefore, firstly characterize SLBs using FRAP which allows for estimating the homogeneity and lateral mobility of the layer formed upon vesicle fusion. Fig. 1b shows the typical fluorescent images of lipid membranes assembled from zwitterionic vesicles, DPhPC and DPhPE, on PEDOT:PSS films over time after photobleaching. DPhPC and DPhPE belong to a class of phospholipids known as phytanoyl lipids which are derived from archaeobacterial membranes.³⁹ Due to their high mechanical and chemical stability and low ion permeability,⁴⁰ they are commonly used to mimic the cell membranes for ion-channel characterization^{41, 42} and investigating molecule/peptide-lipid interactions.^{43, 44} For the bilayers formed with the particular composition of DPhPC mixed with DPhPE, high electrical resistances varying between 2–10 G Ω have been reported.⁴⁵ High resistance is necessary for studying small ionic fluctuations across the bilayer as in the case of functional ion channels. The recovery of the fluorescence indicated the formation of the lipid bilayer on all of these surfaces. Next, we investigate the properties of the lipid bilayer and its correlation to the EG content.

Fig. 1 (a) schematics of vesicle fusion, (b) FRAP images of lipid membranes DPhPC/DPhPE (7:3) assembled on PEDOT:PSS films cast from dispersions containing various EG concentrations (0 vol%, 5 vol%, 10 vol% and 20 vol%). These images are treated to extract diffusion coefficients (c), and mobile fractions (d) of membrane lipids; Scale bar = 20 μm

Fig. 2. QCM-D monitoring of zwitterionic SLB formation on PEDOT:PSS surfaces. The vesicles are injected after the baseline buffer (PBS) stabilization followed by two sets of water shocks each ending with buffer injection. The net effect of water is a rapid increase in frequency and a decrease in dissipation. Data presented here are recorded at the 7th overtone. From a to d, the EG content increases from 0 to 20 vol%.

The diffusion coefficient (D) and mobile fraction (MF) for each sample were determined based on the imaging data and plotted in Fig. 1c and d, respectively. The diffusion coefficient gives an estimation of how fast the lipid molecules diffuse within the membrane. The mobile fraction is indicative of whether the lipid molecules are bound to the surface and hence are unable to diffuse.

The lipid membrane formed on the PEDOT:PSS film cast from the dispersion containing 5 vol% EG exhibited the highest diffusion coefficient ($D = 1.67 \mu\text{m}^2/\text{s}$) among all samples. The lowest coefficient was observed for the film with 20 vol% EG ($D = 1.13 \mu\text{m}^2/\text{s}$), similar to diffusion properties of the bilayer on the film that does not contain EG. We found that at least 91% of the labelled lipid molecules were laterally mobile in membranes formed on all PEDOT:PSS films, regardless of the EG content, suggesting continuity of the bilayers. The mobility of the SLB formed on glass was measured for comparison (Fig. S2). The mobile fraction of the SLB on glass was 97% and the diffusion coefficient was determined to be $1.5 \pm 0.1 \mu\text{m}^2/\text{s}$, comparable to the values reported for the PEG-cushioned DPhPC bilayer.⁴⁶ We note that the addition of DPhPE lipids to the composition has been shown to reduce the fluidity further.⁴⁷ The diffusion coefficient of the bilayer on glass is similar to those measured for the lipid membrane formed on PEDOT:PSS with 5 vol% and 10 vol% EG, validating our analysis.

To further confirm vesicle fusion on the bilayers and monitor its dynamics, we used the QCM-D technique. QCM-D is a surface sensitive technique which allows for real-time monitoring of the interactions between adsorbed vesicles and the film and for quantifying mass changes in the film associated with vesicle fusion.³⁰

For instance, a decrease in the oscillation frequency of the quartz crystal coated with the polymer film accompanied with an increase in dissipation of its energy (dampening of the crystal) indicates that the film up-takes mass. Figure 2 shows the QCM-D signals of PEDOT:PSS films upon introduction of vesicles - once they are completely swollen in PBS. For all films, we observe a decrease in frequency upon addition of the lipid vesicles ($\Delta f_{\text{average}} = -245 \text{ Hz}$), the value of which is highest for 5 vol% sample (Table S2). The dissipation change, on the other hand, is lowest for this sample. The high dissipation changes of PEDOT:PSS films ($\Delta D_{\text{average}} = 85 \times 10^{-6}$) suggest that the adsorbed vesicles enhance the viscoelasticity of the surfaces. Such high Δf and ΔD values were reported for SLBs formed on polyelectrolyte coated surfaces, attributed to extensive hydration of waterborne regions.⁴⁸

It was shown that incubating intact vesicles on PEDOT:PSS films in DI water creates an osmotic pressure which then triggers vesicle fusion.²⁷ We therefore applied two consecutive water shocks to rupture the vesicles adsorbed on the surface. For all the films, we observe that these two waves of DI water additions lead to a rapid increase in frequency (loss of mass), as well as a decrease of dissipation (reduced viscoelasticity) (Fig. 2). For 0 and 5 vol% EG sample, while most of the fusion happens during the first water injection, for 10 and 20 vol% EG, the 2nd water shock seems to be more effective. Table S2 summarizes the variations in the QCM-D signatures in terms of initial adsorption of vesicles and the vesicle rupture with subsequent bilayer formation after the 1st and final water shock. These variations indicate vesicle rupture on PEDOT:PSS surfaces, as evidenced by FRAP measurements. The QCM-D signals of all the films, higher than those are reported for inorganic

Paper

Journal of Materials Chemistry C

surfaces,²⁷ and the complex nature of vesicle-surface interactions suggest that the bilayers that are formed are not defect-free, in fact comprising a population of intact vesicles and bilayer patches, in agreement with the previous study with PEDOT:PSS.²⁷ The low final ΔD of 5 vol% EG film however shows that the bilayer formed therein is reflecting of a relatively more rigid and less water containing layer when compared to other films under investigation.

To be able to compare the sealing properties of the SLBs, we coupled an electrochemical impedance spectrometer to the QCM-D sensor. The impedance properties of the films are not significantly affected when going from pristine PEDOT:PSS film to that after bilayer formation, except that for the formulation with 5 vol% EG, we observe an increase in the magnitude of impedance with the bilayer (Fig. S3). We attribute this to the large area of the films studied (area of the EQCM-D sensor is 0.79 cm²), i.e., parts of the film that may not be covered with vesicles or bilayers and therefore solution ions are not impeded by a continuous lipid bilayer. Nonetheless, in order to understand the impact of this particular EG concentration (5 vol%) on vesicle fusion and the peculiar trend of lipid bilayer fluidity with EG, we sought to investigate the physicochemical characteristics of these film surfaces.

Surface hydrophilicity and zeta potential

Surface hydrophilicity is a prerequisite for the rupture of vesicles and subsequent formation of bilayers.⁴⁹ Fully fluid lipid membranes are noted to form on only highly hydrophilic surfaces,^{8, 29, 50} albeit a fluid bilayer could as well be assembled on a plasma-modified PDMS surface with a contact angle as high as 30°. Note that all our films were immersed in DI water overnight, followed by O₂ plasma activation before depositing vesicles on the films. In fact, we do not observe fluorescence recovery when lipids are deposited on the as-prepared films. We soak the films in DI water over night to remove any low molecular mass components from the film, inherent to the commercially available dispersion of PEDOT:PSS as these might intervene with the accuracy of the electrical recordings that require long term exposure of the films to water. Additionally, PEDOT:PSS uptakes a considerable amount of water,⁵¹ which softens the film, envisaged to make the substrate surface more hydrophilic and therefore more suitable for integration with lipids. We determine the wettability of our polymer films via water contact angle measurements. The films after water treatment have a higher contact angle (Table S2). This is in agreement with previous reports demonstrating a water rinse⁵² or water immersion⁵³ to remove excess PSS moieties from the surface of PEDOT:PSS films.

The increased hydrophobicity, which is not favored for vesicle fusion, is counteracted by O₂ plasma treatment, which improves the wettability of polymer surfaces by introducing polar functional groups containing oxygen.⁵⁴⁻⁵⁶ Ohayon *et al.* demonstrated that the water contact angle of a PEDOT:PSS film (identically prepared to the ones studied here) reduced from 45° to less than 5° after O₂ plasma activation as a result of the introduction of -OH groups at the surface.²⁸ After this "fusion treatment", i.e., water immersion and plasma activation, proven to be essential to drive vesicle fusion on PEDOT:PSS, all of our films become superhydrophilic (contact angle = 0°) (Table S2). However, a hydrophilic surface by itself is insufficient

Fig. 3 Surface zeta potential measurements of PEDOT:PSS films with various EG concentrations before (A: black squares) and after (B: red dots) fusion treatment, i.e. immersion of the films in DI water and O₂ plasma activation, before incubating the samples with vesicles. Also shown are the surface zeta potential measurements of electropolymerized PEDOT:PSS (blue triangle) and p(OH-gNDI-gT2) (pink hexagon) films exposed to the same treatment

to induce bilayer formation through vesicle fusion,^{29, 57} and does not guarantee a high quality (e.g. high lateral mobility) of the bilayer formed as seen for PEDOT:PSS films. Previous studies showed adsorption of intact vesicles on hydrophilic TiO₂ surfaces,^{31, 58, 59} which is ascribed to weak vesicle-surface interactions. On the other hand, the SLB formation is highly influenced by electrostatic interactions between vesicles and the substrate.⁶⁰⁻⁶⁴ Cha and coworkers investigated the role of electrostatic interactions in the rupture of zwitterionic liposomes on charged surfaces, demonstrating the critical role of surface charge density in controlling the fusion.⁶⁵

To evaluate the charge density on the film surfaces, zeta potentials of the samples were measured using a Malvern Zetasizer Nano ZS system. Figure 3 shows the surface zeta potential for spin-cast PEDOT:PSS films with various EG concentrations before and after the fusion treatment. As-prepared films had negative surface potentials varying between -74.5 mV and -46.4 mV, indicating that the anionic PSS-rich layers are at the outmost surface (Fig. 3, A). After the treatment, the surface zeta potential decreases for all samples (Fig. 3, B). Negatively charged surfaces such as mica, silica and glass are widely used for forming zwitterionic lipid bilayers via vesicle fusion,⁶⁶ suggesting that all of these films are potentially suitable for bilayer formation from the zwitterionic vesicles.

The PEDOT:PSS film with 5 vol% EG has the highest surface zeta potential of -58.4 ± 3.3 mV, being the most negatively charged surface among all samples. It is interesting to note however that although the zeta potentials do not vary broadly (from -61.7 mV to -43 mV), this most negatively charged surface is also the one that enables the most mobile lipid bilayer (Fig. 1c). However, we would like to understand the effect of surface charges on vesicle fusion itself. For this purpose, we fabricated an electropolymerized PEDOT:PSS film which is an alternative conducting polymer surface to test vesicle fusion without altering the chemical structure. The

Fig. 4 (a) AFM topography images of PEDOT:PSS films in PBS at pH 7.4. The films were cast from dispersions with various EG concentrations and the images were taken after DI water immersion and O₂ plasma activation. Scale bar = 500 nm; (b) Surface roughness of hydrated films with varying EG content (A: black squares) and that of the electropolymerized PEDOT:PSS (blue triangle) and p(OH-gNDI-gT2) (pink hexagon) after treatment; (c) AFM topography image of p(OH-gNDI-gT2) film in PBS at pH 7.4 after water immersion and O₂ plasma activation. The FRAP images show no recovery of fluorescence when lipids deposited on such polymer surface.

zeta potential of this electropolymerized film is -44.8 ± 3.4 mV after the water and plasma treatment (Fig. 3, blue triangle). Although this value is only slightly less than the film cast from 10 vol% EG containing PEDOT:PSS dispersion, we observe no bilayer formation on the electropolymerized film (Fig. S4a). It is most likely that intact vesicles are adsorbed on the polymer surface. This result is intriguing as this negatively charged surface is also hydrophilic with a contact angle ca. 10°. Neither the surface charge nor the wettability solely determines the vesicle fusion, therefore we analyze the topography of the films.

Surface roughness

We characterized the surface topography of hydrated PEDOT:PSS films with tapping-mode AFM in PBS as the films have undergone fusion treatment. Large domains were observed for PEDOT:PSS films cast from EG-containing dispersions (Fig. 4a). It is suggested that EG addition leads to partial removal of PSS from the surface, accompanied with reorientation of PEDOT chains from coiled to linear structure and formation of denser PEDOT aggregates.^{67–69} These drastic morphological changes enable better transport pathways for charges, and as such EG improves the electrical conductivity of PEDOT:PSS films.^{68, 70} The surface roughness (root mean square), S_q , was determined for each sample based on the AFM images with a scan area of $2 \mu\text{m} \times 2 \mu\text{m}$. PEDOT:PSS with 5 vol% EG shows the greatest roughness ($S_q = 3.1$ nm) while PEDOT:PSS without EG has the smoothest surface ($S_q = 2.2$ nm) (Fig. 4b, A). Despite these differences, surfaces with such roughness values are deemed to be smooth.⁷¹ On the other hand, the S_q for electropolymerized PEDOT:PSS in PBS is 7.2 nm (Fig. 4b, blue triangle, and see Fig. S4b for the AFM image of this film). Although roughness was considered to be strongly influential in the adsorption of vesicles⁷² and spreading of lipid membranes,^{61, 62} several groups reported formation of lipid bilayers on rough surfaces.^{19, 73–75} In fact, for such rough surfaces, if the vesicle-substrate interactions are strong enough, roughness no longer plays a predominant role in vesicle fusion. The electropolymerized PEDOT:PSS film presents surface charges and the wettability in favor of vesicle fusion. However, the interactions between vesicle and the film are inadequate (note that the zeta

potential is at the lowest end of the range tested) to overcome the adverse influence of a rough surface.

In order to distinguish the combined effects of roughness and surface charges, we also evaluated a semiconducting polymer, p(OH-gNDI-gT2), which is a negatively charged analogue of p(gNDI-gT2),³³ recently demonstrated as the first electron transporting polymer used in an OECT.³³ The accumulation mode OECTs comprising this n-type polymer exhibits a high signal ON/OFF response (translating into high gain) and a low-power operation in common aqueous electrolytes. Working in the opposite regime to PEDOT:PSS based devices (i.e. depletion mode, signal ON to OFF upon application of a gate voltage), the n-type channel of this OECT becomes conducting only when cations from the solution enter the film, rendering the system a very promising platform to sense the bilayer functionality, e.g., opening of an ion channel for transport of cations. For the synthesis of p(OH-gNDI-gT2), the ester group was cleaved to form free -OH groups (see chemical structure in ESI, and Fig. S1 for NMR spectrum), resulting in an increase in surface hydrophilicity. P(OH-gNDI-gT2) exhibits similar roughness to PEDOT:PSS films cast from dispersions (2.4 nm, see AFM image in Fig. 4c) and has a contact angle of 21–22° after water and plasma treatment. However, the lipids deposited on this polymer were immobile, deduced from the FRAP experiment (Fig. 4c). The corresponding surface zeta potential for p(OH-gNDI-gT2) polymer film was measured to be -35.6 ± 4.4 mV (Fig. 3, pink hexagon), which is the lowest among all the samples investigated so far. We postulate that the vesicles are intact on the surface due to weak vesicle-substrate interactions incapable of overcoming the bending energy of the vesicle membrane. These findings are in agreement with Cha *et al.* who reported the critical role of surface charge density on the rupture of adsorbed zwitterionic vesicles to form SLBs.⁶⁵ On either positively or negatively charged self-assembled monolayer surfaces, there is a critical charge density below which charge neutral vesicles readily fuse into SPBs. Above this value, (for our work, this would correspond to a zeta potential value higher than ca. -40 mV), the zwitterionic vesicles do not rupture no matter how smooth or hydrophilic the surface is.

XPS characterization

We used XPS to characterize the chemical composition of PEDOT:PSS surfaces. We particularly assessed the spectra S 2p as shown in Fig. 5. In the spectra, the high binding energy region (B.E.= ca. 169 eV) is attributed to the sulfur atoms in the PSS, whereas the lower binding energy area (B.E.= ca. 164 eV) is associated with the sulfur atoms in the thiophene ring of the PEDOT chains.⁷⁶ The S 2p core level of PEDOT and PSS chains consists of a spin-split component of S 2p_{1/2} and S 2p_{3/2}. Doublet peaks residing around 168 eV and 169 eV originate from sulfonate groups (ionic species, S 2p_{3/2}) and from sulfonic acids of PSS (neutral species, S 2p_{1/2}), respectively.⁷⁷ We first investigate the surface composition of PEDOT:PSS films as they are exposed to the fusion treatment, i.e., water immersion and plasma treatment. After the fusion treatment of the film cast from the dispersion with 5 vol% EG, we observe a significant decrease in the measured area of PSS to PEDOT (Fig. S5a and Fig. 5b, respectively). Moreover, ionic sulfur atoms of PSS become weaker compared to the neutral sulfur atoms due to the treatment. This is due to removal of excess PSS in the treated films, supporting the results obtained from the surface zeta potential and contact angle measurements above.

Next, we investigate the effect of EG on the surface composition of the films. The relative area of deconvoluted components of these spectra are summarized in Table S3. The film with 5 vol% EG has the highest fraction (area) of S 2p_{3/2} (24.3%), meaning that there are more ionic species of PSS in the surface of this film. The S 2p_{3/2} area decreases for the 10 vol% EG film (22.1%), followed by 20 vol% and 0 vol% EG films (20.8% and 19.5%, respectively). This trend is identical to the relationship of EG content with the diffusion

coefficient of the bilayers: PSS contributes to the fluidity of the lipid bilayer, while the 5 vol% in the dispersion renders the film optimal. The largest fraction of S 2p_{3/2} PSS from 5 vol% EG, which corresponds to the highest negative charge on the surface, is also in complete agreement with our zeta potential measurements. On the other hand, the XPS spectrum of electropolymerized PEDOT:PSS film shows clear differences (Fig. S5b). PEDOT is dominating the surface composition of this film. For instance, for the 5% EG sample, PEDOT to PSS ratio is 0.397, and this ratio increases up to 1.322 for the electropolymerized sample. The higher crystallinity of PEDOT compared to PSS and the relatively more rigid surface due to lack of PSS makes the electropolymerized film surfaces much rougher compared to spin cast samples. We suggest that such a surface accumulated by PEDOT is incompatible for triggering the fusion of vesicles and does not support the assembly of lipid bilayer.

Conclusions

In this work, we aim to understand the basic surface properties that control vesicle rupture on conjugated polymers and investigate the formation of SLBs via fusion of zwitterionic vesicles on a variety of conjugated polymer films including a n-type semiconductor and the PEDOT:PSS prepared either via electrospinning or cast from different dispersion formulations. Among the two major types of conjugated polymers studied (PEDOT:PSS and p(OH-gNDI-gT2)), we could, first of all, form bilayers only on PEDOT:PSS films cast from the commercially

Fig. 5 XPS S 2p spectra of PEDOT:PSS films prepared from various compositions of EG (a: 0 vol%, b: 5 vol%, c: 10 vol%, d: 20 vol%). The spectra have been normalized to the maximum intensity and the binding energies were referenced to C 1s core level at 284.8 eV. The S 2p spectra (black lines) were deconvoluted into four distinct peaks (dashed curves), representing two types of sulfur atoms, one is on the thiophene of PEDOT (ca. 164 eV) and the other is on the sulfonate group in PSS (ca. 169 eV). The red and blue dashed curves correspond to S 2p_{3/2} and S 2p_{1/2} PEDOT, whereas the pink and green dashed curves correspond to S 2p_{3/2} and S 2p_{1/2} PSS.

available dispersion. The surface properties of these films were modified using different concentrations of a co-solvent additive, EG, in the dispersion. The resulting films showed interesting correlations between their surface charge density (modulated by the EG content) and the diffusion coefficient and the viscoelasticity of the bilayers assembled on top. In particular, the lipid membrane formed on PEDOT:PSS cast from the dispersion containing 5 vol% EG exhibits the highest bilayer diffusion coefficient and sealing behaviour. The underlying characteristic of this film is its high negative charge density due to a high contribution of the ionic PSS. Moreover, although the electropolymerized PEDOT:PSS film has the same chemical composition with spin cast films, the uppermost surface comprises of mostly PEDOT-rich regions, which leads to increased roughness. Vesicles do not rupture on such rough surfaces although the overall hydrophilicity and surface charge are comparable to spin-cast PEDOT:PSS samples. In the case of the hydrophilic and smooth surface of the semiconductor p(OH-gNDI-gT2), the surface charge density was inadequate to promote vesicle fusion. Overall, we find that surface hydrophilicity, charge, roughness and chemical composition play crucial roles in determining the efficiency of vesicle fusion. Although the bilayers formed contain defects, tuning the EG content in PEDOT:PSS dispersions influence the properties of the SLB. A hydrophilic, smooth and highly negatively charged conjugated polymer surface is promising for the fusion of zwitterionic vesicles and formation of fluid lipid bilayers. This materials design guideline to tune the communication between the vesicles and supporting surfaces will lead to effective SLB formation on organic electronic materials.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors thank Dr. Nimer Wehbe at Surface Analysis Laboratory for conducting XPS measurements.

Notes and references

- J. E. Alouf, *Folia Microbiologica*, 2003, **48**, 5.
- K. S. Phillips and Q. Cheng, *Analytical Chemistry*, 2005, **77**, 327-334.
- V. Kiessling, M. K. Domanska, D. Murray, C. Wan, L. K. Tamm and T. P. Begley, in *Wiley Encyclopedia of Chemical Biology*, John Wiley & Sons, Inc., 2007, DOI: 10.1002/9780470048672.webc663.
- Y.-H. M. Chan and S. G. Boxer, *Current Opinion in Chemical Biology*, 2007, **11**, 581-587.
- E. T. Castellana and P. S. Cremer, *Surface Science Reports*, 2006, **61**, 429-444.
- C.-Y. Hsia, M. J. Richards and S. Daniel, *Analytical Methods*, 2015, **7**, 7076-7094.
- K. L. Weirich, J. N. Israelachvili and D. K. Fygenson, *Biophysical Journal*, 2010, **98**, 85-92.
- R. P. Richter and A. R. Brisson, *Biophysical Journal*, 2005, **88**, 3422-3433. DOI: 10.1039/C8TC00370J
- T. H. Anderson, Y. Min, K. L. Weirich, H. Zeng, D. Fygenson and J. N. Israelachvili, *Langmuir*, 2009, **25**, 6997-7005.
- J. M. Moran-Mirabal, J. B. Edel, G. D. Meyer, D. Throckmorton, A. K. Singh and H. G. Craighead, *Biophysical Journal*, 2005, **89**, 296-305.
- H. Schönherr, J. M. Johnson, P. Lenz, C. W. Frank and S. G. Boxer, *Langmuir*, 2004, **20**, 11600-11606.
- B. Seantier and B. Kasemo, *Langmuir*, 2009, **25**, 5767-5772.
- A. B. Dahlin, N. J. Wittenberg, F. Höök and S.-H. Oh, *Nanophotonics*, 2013, **2**, 83-101.
- S. Terrettaz, M. Mayer and H. Vogel, *Langmuir*, 2003, **19**, 5567-5569.
- M. Tanaka and E. Sackmann, *Nature*, 2005, **437**, 656-663.
- W. Zhou, Y. Y. Wang, T.-S. Lim, T. Pham, D. Jain and P. J. Burke, *Scientific Reports*, 2015, **5**, 9208.
- R. Naumann, S. M. Schiller, F. Giess, B. Grohe, K. B. Hartman, I. Kärcher, I. Köper, J. Lübken, K. Vasilev and W. Knoll, *Langmuir*, 2003, **19**, 5435-5443.
- S. Gritsch, P. Nollert, F. Jahnig and E. Sackmann, *Langmuir*, 1998, **14**, 3118-3125.
- Y. Shao, Y. Jin, J. Wang, L. Wang, F. Zhao and S. Dong, *Biosensors and Bioelectronics*, 2005, **20**, 1373-1379.
- S. Inal, G. G. Malliaras and J. Rivnay, *Nature Communications*, 2017, **8**, 1767.
- D. Khodagholy, T. Doublet, P. Quilichini, M. Gurfinkel, P. Leleux, A. Ghestem, E. Ismailova, T. Hervé, S. Sanaur, C. Bernard and G. G. Malliaras, *Nature Communications*, 2013, **4**, 1575.
- W. Lee, D. Kim, J. Rivnay, N. Matsuhisa, T. Lonjaret, T. Yokota, H. Yawo, M. Sekino, G. G. Malliaras and T. Someya, *Advanced Materials*, 2016, **28**, 9722-9728.
- X. T. Cui and D. D. Zhou, *IEEE Transactions on Neural Systems and Rehabilitation Engineering*, 2007, **15**, 502-508.
- P. Lin, F. Yan, J. Yu, H. L. W. Chan and M. Yang, *Advanced Materials*, 2010, **22**, 3655-3660.
- L. H. Jimison, S. A. Tria, D. Khodagholy, M. Gurfinkel, E. Lanzarini, A. Hama, G. G. Malliaras and R. M. Owens, *Advanced Materials*, 2012, **24**, 5919-5923.
- J. Rivnay, S. Inal, A. Salleo, R. M. Owens, M. Berggren and G. G. Malliaras, *Nature Reviews Materials*, 2018, **3**, 17086.
- Y. Zhang, S. Inal, C.-Y. Hsia, M. Ferro, M. Ferro, S. Daniel and R. M. Owens, *Advanced Functional Materials*, 2016, **26**, 7304-7313.
- D. Ohayon, C. Pitsalidis, A.-M. Pappa, A. Hama, Y. Zhang, L. Gallais and R. M. Owens, *Advanced Materials Interfaces*, 2017, **4**, 1700191-n/a.
- C. A. Keller and B. Kasemo, *Biophysical Journal*, 1998, **75**, 1397-1402.
- N.-J. Cho, C. W. Frank, B. Kasemo and F. Hook, *Nat. Protocols*, 2010, **5**, 1096-1106.
- E. Reimhult, F. Höök and B. Kasemo, *Langmuir*, 2003, **19**, 1681-1691.
- R. Tero, *Materials*, 2012, **5**.
- A. Giovannitti, C. B. Nielsen, D.-T. Sbircea, S. Inal, M. Donahue, M. R. Niazi, D. A. Hanifi, A. Amassian, G. G. Malliaras, J. Rivnay and I. McCulloch, *Nature Communications*, 2016, **7**, 13066.
- D. Axelrod, D. E. Koppel, J. Schlessinger, E. Elson and W. W. Webb, *Biophysical Journal*, 1976, **16**, 1055-1069.

Paper

Journal of Materials Chemistry C

35. D. E. Koppel, D. Axelrod, J. Schlessinger, E. L. Elson and W. W. Webb, *Biophysical Journal*, 1976, **16**, 1315-1329.
36. D. M. Soumpasis, *Biophysical Journal*, 1983, **41**, 95-97.
37. T. Heimburg and D. Marsh, in *Biological Membranes: A Molecular Perspective from Computation and Experiment*, eds. K. M. Merz and B. Roux, Birkhäuser Boston, Boston, MA, 1996, DOI: 10.1007/978-1-4684-8580-6_13, pp. 405-462.
38. E. J. M. Helmreich, *Biophysical Chemistry*, 2002, **100**, 519-534.
39. J. L. C. M. van de Vossenberg, A. J. M. Driessen and W. N. Konings, *Extremophiles*, 1998, **2**, 163-170.
40. T. Baba, Y. Tushima, H. Minamikawa, M. Hato, K. Suzuki and N. Kamo, *Biochimica et Biophysica Acta (BBA) - Biomembranes*, 1999, **1421**, 91-102.
41. M. Raja and E. Vales, *Biophysical Chemistry*, 2009, **142**, 46-54.
42. M. Andersson, H. M. Keizer, C. Zhu, D. Fine, A. Dodabalapur and R. S. Duran, *Langmuir*, 2007, **23**, 2924-2927.
43. F.-Y. Chen, M.-T. Lee and H. W. Huang, *Biophysical Journal*, 2002, **82**, 908-914.
44. A. V. Sokolov, V. S. Sokolov, T. B. Feldman and M. A. Ostrovsky, *Biochemistry (Moscow) Supplement Series A: Membrane and Cell Biology*, 2008, **2**, 404-411.
45. M. Andersson, J. Jackman, D. Wilson, P. Jarvoll, V. Alfredsson, G. Okeyo and R. Duran, *Colloids and Surfaces B: Biointerfaces*, 2011, **82**, 550-561.
46. J. Lin, J. Szymanski, P. C. Searson and K. Hristova, *Langmuir*, 2010, **26**, 3544-3548.
47. K. J. Seu, L. R. Cambrea, R. M. Everly and J. S. Hovis, *Biophysical Journal*, 2006, **91**, 3727-3735.
48. M. Wlodek, M. Szuwarzynski and M. Kolasinska-Sojka, *Langmuir*, 2015, **31**, 10484-10492.
49. P. Lenz, C. M. Ajo-Franklin and S. G. Boxer, *Langmuir*, 2004, **20**, 11092-11099.
50. A. A. Brian and H. M. McConnell, *Proceedings of the National Academy of Sciences*, 1984, **81**, 6159-6163.
51. M. ElMahmoudy, S. Inal, A. Charrier, I. Uguz, G. G. Malliaras and S. Sanaur, *Macromolecular Materials and Engineering*, 2017, **302**, 1600497-n/a.
52. D. M. DeLongchamp, B. D. Vogt, C. M. Brooks, K. Kano, J. Obrzut, C. A. Richter, O. A. Kirillov and E. K. Lin, *Langmuir*, 2005, **21**, 11480-11483.
53. C. Duc, A. Vlandas, G. G. Malliaras and V. Senez, *Soft Matter*, 2016, **12**, 5146-5153.
54. A. Mata, A. J. Fleischman and S. Roy, *Biomedical Microdevices*, 2005, **7**, 281-293.
55. J. Chai, F. Lu, B. Li and D. Y. Kwok, *Langmuir*, 2004, **20**, 10919-10927.
56. F. D. Egitto and L. J. Matienzo, *IBM Journal of Research and Development*, 1994, **38**, 423-439.
57. J. T. Groves, N. Ulman and S. G. Boxer, *Science*, 1997, **275**, 651-653.
58. E. Reimhult, F. Höök and B. Kasemo, *The Journal of Chemical Physics*, 2002, **117**, 7401-7404.
59. I. Reviakine, F. F. Rossetti, A. N. Morozov and M. Textor, *The Journal of Chemical Physics*, 2005, **122**, 204711.
60. P. Nollert, H. Kiefer and F. Jähnig, *Biophysical Journal*, 1995, **69**, 1447-1455.
61. P. S. Cremer and S. G. Boxer, *The Journal of Physical Chemistry B*, 1999, **103**, 2554-2559.
62. J. Raedler, H. Strey and E. Sackmann, *Langmuir*, 1995, **11**, 4539-4548.
DOI: 10.1039/C8TC00370J
63. C. Hennesthal and C. Steinem, *Journal of the American Chemical Society*, 2000, **122**, 8085-8086.
64. Y.-H. Kim, M. M. Rahman, Z.-L. Zhang, N. Misawa, R. Tero and T. Urisu, *Chemical Physics Letters*, 2006, **420**, 569-573.
65. T. Cha, A. Guo and X. Y. Zhu, *Biophysical Journal*, 2006, **90**, 1270-1274.
66. G. J. Hardy, R. Nayak and S. Zauscher, *Current Opinion in Colloid & Interface Science*, 2013, **18**, 448-458.
67. J. Ouyang, Q. Xu, C.-W. Chu, Y. Yang, G. Li and J. Shinar, *Polymer*, 2004, **45**, 8443-8450.
68. Q. Wei, M. Mukaida, Y. Naitoh and T. Ishida, *Advanced Materials*, 2013, **25**, 2831-2836.
69. H. Shi, C. Liu, Q. Jiang and J. Xu, *Advanced Electronic Materials*, 2015, **1**, 1500017-n/a.
70. J. Rivnay, S. Inal, B. A. Collins, M. Sessolo, E. Stavrinidou, X. Strakosas, C. Tassone, D. M. DeLongchamp and G. G. Malliaras, *Nature Communications*, 2016, **7**, 11287.
71. N. P. Mellott, S. L. Brantley, J. P. Hamilton and C. G. Pantano, *Surface and Interface Analysis*, 2001, **31**, 362-368.
72. A. A. Duarte, S. L. Filipe, L. M. G. Abegão, P. J. Gomes, P. A. Ribeiro and M. Raposo, *Microscopy and Microanalysis*, 2013, **19**, 867-875.
73. S. Nirasay, A. Badia, G. Leclair, J. Claverie and I. Marcotte, *Materials*, 2012, **5**, 2621.
74. K. C. Weng, J. J. R. Stålgren, D. J. Duval, S. H. Risbud and C. W. Frank, *Langmuir*, 2004, **20**, 7232-7239.
75. K. Mulligan, Z. J. Jakubek and L. J. Johnston, *Langmuir*, 2011, **27**, 14352-14359.
76. K. Z. Xing, M. Fahlman, X. W. Chen, O. Inganäs and W. R. Salaneck, *Synthetic Metals*, 1997, **89**, 161-165.
77. J. Y. Kim, J. H. Jung, D. E. Lee and J. Joo, *Synthetic Metals*, 2002, **126**, 311-316.

This work explores the design rules that govern vesicle fusion and bilayer formation on organic electronic material surfaces.