Dear Author,

Please correct your galley proofs carefully and return them no more than four days after the page proofs have been received.

Please limit corrections to errors already in the text; cost incurred for any further changes or additions will be charged to the author, unless such changes have been agreed upon by the editor.

The editors reserve the right to publish your article without your corrections if the proofs do not arrive in time.

Note that the author is liable for damages arising from incorrect statements, including misprints.

Please note any queries that require your attention. These are indicated with a Q in the PDF and a question at the end of the document.

Reprints may be ordered by filling out the accompanying form.

Return the reprint order form by fax or by e-mail with the corrected proofs, to Wiley-VCH : advmat@wiley.com

To avoid commonly occurring errors, **please ensure that the following important items are correct** in your proofs (please note that once your article is published online, no further corrections can be made):

- **Names** of all authors present and spelled correctly
- **Titles** of authors correct (Prof. or Dr. only: please note, Prof. Dr. is not used in the journals)
- **Addresses** and **postcodes** correct
- **E-mail address** of corresponding author correct (current email address)
- **Funding bodies** included and grant numbers accurate
- **Title** of article OK
- All **figures** included
- **Equations** correct (symbols and sub/superscripts)

Corrections should be made directly in the PDF file using the PDF annotation tools. If you have questions about this, please contact the editorial office. The corrected PDF and any accompanying files should be uploaded to the journal's Editorial Manager site.

Author Query Form

WILEY

Journal ADMA
Article adma201906806

Dear Author,

During the copyediting of your manuscript the following queries arose.

Please refer to the query reference callout numbers in the page proofs and respond to each by marking the necessary comments using the PDF annotation tools.

Please remember illegible or unclear comments and corrections may delay publication.

Many thanks for your assistance.

Query No.	Description	Remarks
Q-OO	<p>Open access publication of this work is possible via Wiley OnlineOpen. Information about this is available at: https://authorservices.wiley.com/author-resources/Journal-Authors/licensing-open-access/open-access/onlineopen.html.</p> <p>The cost of publishing your manuscript OnlineOpen may be covered by one of Wiley's national agreements. To find out more, visit https://authorservices.wiley.com/author-resources/Journal-Authors/open-access/affiliation-policies-payments/index.html.</p> <p>Note that eligibility for fee coverage is determined by the affiliation of the primary corresponding author designated at submission. Please log in to your Wiley Author Services account at https://authorservices.wiley.com/ and confirm your affiliation to see if you are eligible.</p> <p>Instructions for placing an OnlineOpen order can be found at: https://authorservices.wiley.com/author-resources/Journal-Authors/open-access/how-to-order-onlineopen.html.</p> <p>To publish your article open access, please complete the order process before completing your proof corrections.</p>	
Q1	The orcid identifier 0000-0002-7580-0403 does not match with the author Prof. Xiaodan Zhang. Please check and confirm the correct orcid identifier.	
Q2	Please confirm that forenames/given names (blue) and surnames/family names (vermillion) have been identified correctly.	
Q3	Please provide the highest academic title (either Dr. or Prof.) for all authors, where applicable.	
Q4	Please check edits in affiliation 6.	
Q5	We have used the PDF file for TOC image. Please check.	
Q6	Please define all acronyms at their first appearance in the abstract, text and table of contents, respectively. Only expanded forms are allowed if the elements are cited only once in the article.	
Q7	Please check all equations have been correctly typeset.	
Q8	Please verify the publisher location added in ref. 42.	

Author: Please confirm that Funding Information has been identified correctly.

Please confirm that the funding sponsor list below was correctly extracted from your article: that it includes all funders and that the text has been matched to the correct FundRef Registry organization names. If a name was not found in the FundRef registry, it may not be the canonical name form, it may be a program name rather than an organization name, or it may be an organization not yet included in FundRef Registry. If you know of another name form or a parent organization name for a "not found" item on this list below, please share that information.

FundRef Name	FundRef Organization Name
Ontario Research Fund – Research Excellence Program	
Natural Sciences and Engineering Research Council of Canada	Natural Sciences and Engineering Research Council of Canada
Ministry of Science and Technology	Ministry of Science and Technology
National Natural Science Foundation of China	National Natural Science Foundation of China
Tianjin Research Key Program of Science and Technology	
Fundamental Research Funds	
Ministry of Science and Technology	Ministry of Science and Technology
National Natural Science Foundation of China	National Natural Science Foundation of China
Shanghai Institutions of Higher Learning and Science and Technology Commission of Shanghai Municipality	

N. Wang, Z. Cao, X. Zheng, B. Zhang,*
S. M. Kozlov, P. Chen, C. Zou, X. Kong,
Y. Wen, M. Liu, Y. Zhou, C. T. Dinh,
L. Zheng, H. Peng, Y. Zhao, L. Cavallo,
X. Zhang,* E. H. Sargent* 1906806

**Hydration-Effect-Promoting Ni-Fe
Oxyhydroxide Catalysts for Neutral
Water Oxidation**

Water oxidation is key to the production of chemical fuels from electricity. Now, both the simulations and experimental characterizations illustrate that incorporating the hydration-effect-promoting metal cations into the Ni-Fe framework can improve water molecules adsorption functionality proximate to the active sites and the subsequent oxygen evolution reaction catalytic activity in pH-neutral electrolyte.

Q5

Hydration-Effect-Promoting Ni–Fe Oxyhydroxide Catalysts for Neutral Water Oxidation

Ning Wang, Zhen Cao, Xueli Zheng, Bo Zhang,* Sergey M. Kozlov, Peining Chen, Chengqin Zou, Xiangbin Kong, Yunzhou Wen, Min Liu, Yansong Zhou, Cao Thang Dinh, Lirong Zheng, Huisheng Peng, Ying Zhao, Luigi Cavallo, Xiaodan Zhang,* and Edward H. Sargent*

Oxygen evolution reaction (OER) catalysts that function efficiently in pH-neutral electrolyte are of interest for biohybrid fuel and chemical production. The low concentration of reactant in neutral electrolyte mandates that OER catalysts provide both the water adsorption and dissociation steps. Here it is shown, using density functional theory simulations, that the addition of hydrated metal cations into a Ni–Fe framework contributes water adsorption functionality proximate to the active sites. Hydration-effect-promoting (HEP) metal cations such as Mg^{2+} and hydration-effect-limiting Ba^{2+} into Ni–Fe frameworks using a room-temperature sol–gel process are incorporated. The Ni–Fe–Mg catalysts exhibit an overpotential of 310 mV at 10 mA cm^{-2} in pH-neutral electrolytes and thus outperform iridium oxide (IrO_2) electrocatalyst by a margin of 40 mV. The catalysts are stable over 900 h of continuous operation. Experimental studies and computational simulations reveal that HEP catalysts favor the molecular adsorption of water and its dissociation in pH-neutral electrolyte, indicating a strategy to enhance OER catalytic activity.

Water oxidation is of prime importance in electrochemical water splitting and CO_2 reduction technologies.^[1] Thanks to an intensive worldwide effort, its performance has advanced continuously in recent years.^[2–4] Since a pH-neutral environment is required for biological growth, water oxidation should function efficiently in neutral pH if it is to enable ever-higher-performing biohybrid systems for the synthesis of fuels and chemicals using renewable energy.^[5,6]

Unfortunately, the overpotential for the oxygen evolution reaction (OER) is in general very high ($>460 \text{ mV}$ at 10 mA cm^{-2})^[7–10] under neutral pH. As a result, bioelectrolysis systems have exhibited low power conversion efficiencies. The neutral OER problem is particularly challenging since, in pH-neutral electrolytes, the reactant concentration

N. Wang, X. Kong, Y. Zhao, X. Zhang
Institute of Photoelectronic Thin Film Devices
and Technology of Nankai University
Tianjin 300350, P. R. China
E-mail: xdzhang@nankai.edu.cn

N. Wang, X. Kong, Y. Zhao, X. Zhang
Key Laboratory of Photoelectronic Thin Film Devices
and Technology of Tianjin
Tianjin 300350, P. R. China

N. Wang, X. Kong, Y. Zhao, X. Zhang
Collaborative Innovation Center of Chemical Science and Engineering
Tianjin 300350, P. R. China

N. Wang, X. Kong, Y. Zhao, X. Zhang
Renewable Energy Conversion and Storage Center of Nankai University
Tianjin 300072, P. R. China

N. Wang, X. Zheng, P. Chen, C. Zou, M. Liu, Y. Zhou, C. T. Dinh,
E. H. Sargent
Department of Electrical and Computer Engineering
University of Toronto
35 St George Street, Toronto, Ontario M5S 1A4, Canada
E-mail: ted.sargent@utoronto.ca

Z. Cao, S. M. Kozlov, L. Cavallo
Physical Sciences and Engineering Division (PSE)
KAUST Catalysis Center (KCC)
King Abdullah University of Science and Technology (KAUST)
Thuwal 23955-6900, Saudi Arabia

B. Zhang, P. Chen, Y. Wen, H. Peng
State Key Laboratory of Molecular Engineering of Polymers
Department of Macromolecular Science and Laboratory
of Advanced Materials
Fudan University
Shanghai 200438, China
E-mail: bozhang@fudan.edu.cn

L. Zheng
Beijing Synchrotron Radiation Facility
Institute of High Energy Physics
Chinese Academy of Sciences
Beijing 100049, China

The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/adma.201906806>.

DOI: 10.1002/adma.201906806

is several orders of magnitude lower than in the alkaline electrolyte.^[11] OER in pH-neutral electrolyte therefore requires additional water adsorption and dissociation processes to provide the adsorbed water molecules (H_2O^*)—and the OER steps under neutral-pH conditions^[12]

Catalysts including iridium oxide (IrO_2)^[13] as well as Co-based,^[14] Ni-based,^[15,16] and Mn-based^[17] materials, have each shown recent progress in OER performance in pH-neutral electrolytes. Nevertheless, these catalysts have yet to fulfill the requirement of sub-350 mV overpotentials and prolonged durability (≥ 500 h typically for initial stability studies).^[18]

We took the view that efficiently capturing and dissociating water molecules at the catalyst/water interface could improve OER performance in pH-neutral electrolytes. Prior studies have shown that noncovalent interactions between hydrated metal cations (M^{n+}) and *OH form $\text{OH}_{\text{ad}}\text{-M}^{n+}(\text{H}_2\text{O})_x$ and enhance the adsorption of OH^- at the catalyst/electrolyte interface. These methods can accelerate the oxygen reduction reaction.^[19–24] Mg^{2+} is an example of a metal that can support another beneficial strategy: it possesses a high hydration energy that offers the prospect of enhancing the bond strength between the catalyst surface and molecular water.^[23] We hypothesized that introducing ions of this kind into the catalyst framework could lead to a higher hydration level of the system, improving thereby the OER rate.

Theoretical studies of the hydration effect on Ni-Fe based catalyst. Using the Ni-Fe system as a prototypical framework,^[25,26] we investigated the effect of introducing metal cations with strong hydration capacity and small atomic diameters. We focus on whether water adsorption onto the surface of Ni-Fe catalyst can be enhanced.

We first studied the effect of Mg^{2+} (a relatively small size cation) and compared it with Ba^{2+} (a relatively large size cation) doping (Figure 1). In each case we examined the water adsorption properties of the doped Ni-Fe catalyst.

Starting from a stable metal oxyhydroxide model, we constructed the slab $\beta\text{-NiOOH}$ as the catalyst framework (Figure S1, Supporting Information).^[27,28] Mg atoms remain at the catalyst surface, and are directly exposed to the aqueous solution during OER (Figure S2, Supporting Information).

We then considered the immersion of this catalyst into aqueous solution: we assumed that two (015) facets were exposed to interfacial water. One of the two (015) facets was modified to replace half of the surface Ni^{2+} with the relatively small Mg^{2+} or the larger Ba^{2+} cations (Figure 1a,d), while the other facets of the catalyst were kept the same as controls. Water adsorption on each catalyst was investigated using molecular dynamic simulations in the canonical ensemble at 300 K (details in the Supporting Information). We accumulated a 12 ps trajectory and recorded the final 10 ps trajectory to produce a map of the water-catalyst distance under dynamic conditions. Specifically, we report $\left\langle \frac{1}{d\sqrt{\pi}} \exp\left(-\frac{(a_0 - a_i)^2}{\xi^2}\right) \right\rangle$, where d is the shortest distance between the interfacial water oxygen and any metal ion at slab surface, a_0 is the x - y coordinate of this water oxygen, a_i is the grid on the surface, and $\xi = 1.0$ Å determines the resolution of the map (Figure 1b,c,e,f).

In the absence of the Mg^{2+} cation, the surface OH terminal groups of the Ni-Fe catalyst determine the interfacial water

Figure 1. DFT simulation of hydration on simplified Ni-Fe framework surfaces with Mg^{2+} versus Ba^{2+} doping. a) Snapshot of Ni-Fe-Mg catalyst emerged in aqueous solution: the framework was constructed using the Ni-Fe-OOH catalyst, and four Mg^{2+} were inserted into one (015) facet. b,c) The closer water–oxygen–metal cation distance. d) Snapshot of Ni-Fe-Ba catalyst emerged in aqueous solution: the framework was constructed using the Ni-Fe-OOH catalyst, and four Ba^{2+} were inserted into one (015) facet. e,f) The water maps above the catalyst with or without surface Ba^{2+} .

Figure 2. Performance of Ni-Fe-Mg catalyst and controls in a three-electrode configuration in CO₂ saturated 0.5 M KHCO₃ aqueous electrolyte. a) OER polarization curves for catalysts loaded on GCE. The data were obtained using 1 mV s⁻¹ scan rate and are presented without *iR* correction (catalyst loading 0.21 mg cm⁻²). b) Tafel plot of catalysts loaded on GCE. c) Electrochemical impedance spectroscopy (EIS) data for Ni-Fe-Mg catalysts and controls in three-electrode configuration in CO₂ saturated 0.5 M KHCO₃ aqueous electrolyte. The data were collected for the electrodes under 1.6 V versus RHE. The inset provides the equivalent circuit: *R*_s: series resistance; *R*_{ct}: charge-transfer resistance; CPE: constant-phase element related to the double-layer capacitance. d) Activation energy of samples on Ni foam obtained from the Arrhenius relationship. e) The OER polarization curves of Ni-Fe-Mg catalysts and controls loaded on Au-coated Ni foam in a three-electrode configuration in CO₂ saturated 0.5 M KHCO₃ aqueous electrolyte. f) Chronopotentiometric curves obtained from the Ni-Fe-Mg catalyst on Ni foam electrode with constant current densities of 10 mA cm⁻², and the corresponding Faradaic efficiency from gas chromatography measurement of evolved O₂.

distribution via hydrogen-bonding interactions. When surface Mg²⁺ is added, it attracts interfacial water molecules, leading to a shorter distance between the oxygen atom in water and the metal ions (red patches in Figure 1c). These interfacial water molecules no longer reflect the structure of surface OH terminal groups. By contrast, when Ba²⁺ is introduced, the water-catalyst distance is dominated by the hydrogen-bonding network (Figure 1f).

Using this simple model, we are able to suggest a trend: pursuing experimental doping using cations having a high hydration capacity could potentially offer more water molecules for dissociation reactions.

Synthesis and OER activity of hydration-effect catalysts. We synthesized hydration-effect-promoting (HEP) oxyhydroxides and hydration-effect-limiting (HEL) Ni-Fe-Ba oxyhydroxides. We used a room-temperature sol-gel process previously reported.^[29] Energy-dispersive X-ray spectroscopy mapping shows a uniform distribution of Ni, Fe, and Mg (Figure S3, Supporting Information). From inductively coupled plasma optical emission spectra, we determined the molar ratio of Ni:Fe:Mg to be 7:1:0.2 (Figure S4, Supporting Information). The catalysts present a porous structure (Figure S5, Supporting Information) without evidence of crystallinity (Figure S6, Supporting Information).

We evaluated catalytic properties using a three-electrode electrochemical cell containing CO₂-saturated 0.5 M KHCO₃

electrolyte. Compared with the HEL catalyst, the HEP exhibited a significant improvement in catalytic activity on glass carbon electrode (GCE). Linear sweep voltammetry (LSV) polarization measurements indicate that optimized Ni-Fe-Mg requires only 514 mV overpotential to reach 10 mA cm⁻² on GCE, which outperforms the best oxide catalysts previously reported (Figure 2a; Table S1 and Figure S7, Supporting Information). The decreased Tafel slope (210 mV dec⁻¹ → 150 mV dec⁻¹, Table S2, Supporting Information) indicates a higher OER reaction rate when Mg²⁺ is incorporated (Figure 2b). Charge-transfer resistance (*R*_{ct}), determined using electrochemical impedance spectroscopy (Figure 2c), shows that incorporating Mg²⁺ decreases the *R*_{ct} (580 → 480 Ω) and gives rise to faster electrode kinetics. The Ni is in an oxidation state higher than 3+ as seen in previous reports (Figure S8, Supporting Information).^[30,31]

Next, we investigated further electrochemical behaviors of the best catalysts compared to controls in order to characterize intrinsic activity. First, we normalized the current density using the electrochemically active surface area (ECSA) obtained using the double-layer capacitance (*C*_{dl}) technique.^[32,33] The ECSA-normalized current density of the HEP catalyst is fully 1.3-times and 1.8-times higher than those of reference Ni-Fe catalyst and HEL Ni-Fe-Ba catalyst, respectively, at 1.7 V versus RHE (Figure S9, Table S3, Supporting Information). The activation energy (Figure 2d) and turnover frequency^[29,31,34–36]

Figure 3. OER polarization curves of Ni-Fe-Mg catalyst and relevant controls. The materials were loaded on GCE in a) 0.5 M KHCO₃ (pH ≈ 8.5) and b) 1 M KOH electrolyte (pH ≈ 14). c) The corresponding Tafel curves of Ni-Fe-Mg catalyst in 0.5 M KHCO₃ (pH ≈ 8.5) and 0.5 M KOH electrolyte (pH ≈ 14). d) Arrhenius plot of the inverse temperature versus the log of the exchange current for Ni-Fe-Mg and Ni-Fe-Ba catalyst in electrolyte with H₂O and D₂O.

(TOF, Figure S10 and Table S4, Supporting Information) confirm the same trend: the HEP catalyst exhibits the lowest activation energy of 64 kJ mol⁻¹ and the highest TOF of 0.3 s⁻¹.

We also built and compared the catalysts on Au-coated Ni foam and Ni foam. In neutral electrolyte, the HEP catalyst outperforms both IrO₂ and other relevant controls (Figure 2e; Table S1 and Figure S11, Supporting Information). The HEP catalyst on Au-coated Ni foam achieves a 310 mV at current density 10 mA cm⁻² compared to 344 mV for Ni-Fe and 360 mV for HEL Ni-Fe-Ba. We measured R_s and R_{ct} to identify the effect of supports on catalytic performance. The Au-coated Ni foams have the lowest R_s and R_{ct} , consistent with the view that it provides faster charge transfer (Table S5 and Figure S12, Supporting Information).

We further tested the iR -corrected LSV curves on GCE and Au-coated Ni foam to exclude the effects of cell geometry measurement and conductivity on performance (Figure S13, Supporting Information). The HEP Ni-Fe-Mg catalyst requires of 290 mV overpotential at 10 mA cm⁻² on Au-coated Ni foam after iR -correction, which is 35 mV lower than that of Ni-Fe catalyst and 50 mV lower than that of HEL Ni-Fe-Ba catalyst). Ni and Fe K-edge X-ray absorption near-edge structure spectroscopy and Fourier-transformed extended X-ray absorption fine structure spectra of catalysts showed no obvious change for Ni-Fe-Mg versus relevant controls (Figures S8c-f and S14 and Table S6, Supporting Information). This indicates that the effects of dopants on the electronic structure of Ni and Fe sites do not play a principal role in the observed catalytic enhancement.

We characterized the operating stability of the HEP catalyst at 10 mA cm⁻² and found that it retained its overpotential to within 10 mV following 900 h of continuous water splitting operation (Figure 2f). The Faradaic efficiency for oxygen production remained at 98% ± 2% throughout.

Investigations of the HEP effect. To explore further the relationship between the hydration effect and catalyst activity, we examined the role of Mg and Ba in water adsorption and water dissociation. When we increase pH, the catalytic advantage from HEP Ni-Fe-Mg is reduced, consistent with the abundance of OH⁻ at high pH (Table S7, Supporting Information; Figure 3a,b), and also in accordance with the viewpoint that alkaline earth cations cannot improve the alkaline catalytic performance.^[37,38] The Tafel slope decreased from 150 mV dec⁻¹ (pH = 7.2) to 120 mV dec⁻¹ (pH = 8.5) and 80 mV dec⁻¹ (pH = 14, Figure 3c), which again supports the view that the HEP advantage is occurred in neutral electrolyte.^[39-41]

We then characterized the activation energy (E_a) for HEP and HEL catalysts in H₂O and D₂O to evaluate the role of OH/OD bond breaking throughout the OER process based. We leveraged the kinetic isotope effect in these studies. We found that reactions in D₂O present a larger activation energy compared to those in H₂O ($E_a(\text{D}_2\text{O}) \approx 1.4 E_a(\text{H}_2\text{O})$, Figure 3d). This difference in the E_a indicates that OH (or OD) bond breaking is the rate-limiting step in the neutral OER process.^[42]

We next proceeded to characterize the effect of HEP/HEL metal cations on water adsorption. Fourier transform infrared (FTIR) spectroscopy and X-ray photoelectron spectroscopy

Figure 4. Experimental data regarding the hydration effect. a) FTIR spectra of Ni-Fe-Mg catalyst and relevant controls. b) O1s XPS of Ni-Fe-Mg catalyst and relevant controls. We used the Gaussian fitting to obtain the contribution of the adsorbed water to the XPS spectrum. High magnitude of the H₂O peak in Ni-Fe-Mg spectrum demonstrates higher water adsorption ability of this material. c) This plot reports the distance between single metal ions (Mg, Ca, Sr, and Ba) and one water molecule. The plot reports these distances as a function of the overpotential at 10 mA cm⁻² current density on Au-coated Ni foam. The correlation was obtained based on a least-square fit. The coefficient of the determinant R^2 was calculated through $R^2 = 1 - SS^{res}/SS^{tot}$, where SS^{res} is the residual sum of squares and SS^{tot} is the total sum of squares.

(XPS) were used to compare the adsorbed water on HEP Ni-Fe-Mg and relevant controls (Figure 4a,b). The enhanced peak intensity at ~3400 cm⁻¹ indicates that the HEP Ni-Fe-Mg catalyst favors water molecule adsorption (Figure 4a; Figure S15, Supporting Information).^[43] XPS curves indicate large quantities of water adsorbed on the HEP catalyst (Figure 4b).^[44,45] Contact angles measurements results show that the addition of Mg²⁺ improves the contact between the electrolyte and the catalyst surface, resulted by the enhanced water-adsorption ability (Figure S16, Supporting Information).

To challenge the role of hydration effect metal cations, we doped other alkaline earth metals into the Ni-Fe framework and characterized OER catalytic activity under identical conditions. The doping concentration of M (Mg, Ca, Sr, and Ba) ratio was fixed at similar value to avoid the effect of dopant concentration on electrochemical activity and water adsorption (Table S8, Supporting Information). The HEP Ni-Fe-Mg and Ni-Fe-Ca catalysts exhibit better performance than HEL Ni-Fe-Sr and Ni-Fe-Ba (Figure 4c). To investigate the hydration-promotion effect further, we performed FTIR and XPS of Ni-Fe-Ca catalyst. The obtained results indicate that the Ni-Fe-Ca catalyst provides improved water-adsorption ability compared to Ni-Fe (Figure 4a,b). Its overpotential of 330 mV at the current density of 10 mA cm⁻² on Au-coated Ni foam is also lower than that of reference sample (345 mV) (Figure S17, Supporting Information).

In summary, a series of Ni-Fe based catalysts were prepared via a sol-gel method at room temperature, and then used as electrocatalysts for OER in neutral electrolyte. By combining electrochemical characterization with density functional theory (DFT) studies, we found that incorporating hydration effect metal cations into a Ni-Fe framework—namely, the Ni-Fe-Mg catalysts—influences water adsorption and enhances OER performance in neutral electrolytes. Specifically, OER activities on the RHE scale for Ni-Fe based catalysts are increased when we decrease the metal-oxygen distance, consistent with the view that the hydration-effect-promoting water adsorption triggers more favorable OER reaction pathways. In the future, the hydration-effect-promoting phenomenon can be extended to provide enhanced water adsorption for other electrochemical reactions, such as in CO₂ reduction to hydrocarbons, N₂ reduction to ammonia, and other reactions involving water molecules.

Experimental Section

See the details in the Supporting Information.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

N.W., Z.C., and X.Z. contributed equally to this work. This work was supported by the Ontario Research Fund – Research Excellence Program, the Natural Sciences and Engineering Research Council of Canada, and the CIFAR Bio-Inspired Solar Energy program. N.W. and X.D.Z. acknowledge support from International Cooperation Projects of the Ministry of Science and Technology (2014DFE60170), National Natural Science Foundation of China (61474065), and (61674084), Tianjin Research Key Program of Science and Technology (18ZXJMTG00220), 111 Project (B16027), and Fundamental Research Funds for the Central Universities. B.Z. and H.S.P. acknowledge funding from Ministry of Science and Technology (2016YFA0203302), the National Natural Science Foundation of China (21503079 and 21875042), and the Program for Professor of Special Appointment (Eastern Scholar) at Shanghai Institutions of Higher Learning and Science and Technology Commission of Shanghai Municipality (18QA1400800). This work benefited from access to the 1W1B beamline at Beijing Synchrotron Radiation Facility. The TEM studies in this work were supported by Jingshan Luo. The simulations were performed using the KAUST supercomputer (HPC).

Conflict of Interest

The authors declare no conflict of interest.

Keywords

hydration effect, neutral electrolyte, Ni–Fe, oxygen evolution reaction

Received: October 16, 2019

Revised: December 11, 2019

Published online:

- [1] B. M. Hunter, H. B. Gray, A. M. Muller, *Chem. Rev.* **2016**, *116*, 14120.
- [2] J. Suntivich, K. J. May, H. A. Gasteiger, J. B. Goodenough, Y. Shao-Horn, *Science* **2011**, *334*, 1383.
- [3] A. Grimaud, O. Diaz-Morales, B. Han, W. T. Hong, Y.-L. Lee, L. Giordano, K. A. Stoerzinger, M. T. M. Koper, Y. Shao-Horn, *Nat. Chem.* **2017**, *9*, 457.
- [4] R. Subbaraman, D. Tripkovic, K. C. Chang, D. Strmcnik, A. P. Paulikas, P. Hirunsit, M. Chan, J. Greeley, V. Stamenkovic, N. M. Markovic, *Nat. Mater.* **2012**, *11*, 550.
- [5] C. Liu, B. C. Colón, M. Ziesack, P. A. Silver, D. G. Nocera, *Science* **2016**, *352*, 1210.
- [6] M. W. Kanan, D. G. Nocera, *Science* **2008**, *321*, 1072.
- [7] K. S. Joya, Y. F. Joya, H. J. M. De Groot, *Adv. Energy Mater.* **2014**, *4*, 1301929.
- [8] K. Li, J. Zhang, R. Wu, Y. Yu, B. Zhang, *Adv. Sci.* **2016**, *3*, 1500426.
- [9] H. Schäfer, D. M. Chevrier, P. Zhang, J. Stangl, K. Müller-Buschbaum, J. D. Hardege, K. Küpper, J. Wollschläger, U. Krupp, S. Dühnen, *Adv. Funct. Mater.* **2017**, *26*, 6402.
- [10] Z. Zhang, J. Hao, W. Yang, J. Tang, *RSC Adv.* **2016**, *6*, 9647.
- [11] K. Xu, C. Han, L. Liu, H. Lv, X. Wu, C. Wu, Y. Xie, *Nano Lett.* **2017**, *17*, 578.
- [12] M. Bajdich, M. Garcia-Mota, A. Vojvodic, J. K. Nørskov, A. T. Bell, *J. Am. Chem. Soc.* **2013**, *135*, 13521.
- [13] M. Schreier, L. Curvat, F. Giordano, L. Steier, A. Abate, S. M. Zakeeruddin, J. Luo, M. T. Mayer, M. Grätzel, *Nat. Commun.* **2015**, *6*, 7326.

- [14] P. Chen, K. Xu, T. Zhou, Y. Tong, J. Wu, H. Cheng, X. Lu, H. Ding, C. Wu, Y. Xie, *Angew. Chem., Int. Ed.* **2016**, *55*, 2488.
- [15] A. M. Smith, L. Trotochaud, M. S. Burke, S. W. Boettcher, *Chem. Commun.* **2015**, *51*, 5261.
- [16] B. Zhang, Y. H. Lui, H. Ni, S. Hu, *Nano Energy* **2017**, *38*, 553.
- [17] A. Yamaguchi, R. Inuzuka, T. Takashima, T. Hayashi, K. Hashimoto, R. Nakamura, *Nat. Commun.* **2014**, *5*, 4256.
- [18] R. D. L. Smith, M. S. Prevot, R. D. Fagan, Z. Zhang, P. A. Sedach, K. J. S. Man, S. Trudel, C. P. Berlinguette, *Science* **2013**, *340*, 60.
- [19] D. T. Limmer, A. P. Willard, P. Madden, D. Chandler, *Proc. Natl. Acad. Sci. USA* **2013**, *110*, 4200.
- [20] C. Zhen, R. Kumar, Y. Peng, G. A. Voth, *J. Phys. Chem. C* **2015**, *119*, 14675.
- [21] J. Carrasco, A. Hodgson, A. Michaelides, *Nat. Mater.* **2012**, *11*, 667.
- [22] D. Strmcnik, K. Kodama, D. Van Der Vliet, J. Greeley, V. R. Stamenkovic, N. M. Markovic, *Nat. Chem.* **2009**, *1*, 466.
- [23] C. Stoffelsma, P. Rodriguez, G. Garcia, N. Garciaaraz, D. Strmcnik, N. M. Marković, M. T. M. Koper, *J. Am. Chem. Soc.* **2010**, *132*, 16127.
- [24] Z. Shen, Y. Liu, P. E. Brown, I. Szlufarska, H. Xu, *J. Phys. Chem. C* **2014**, *118*, 15716.
- [25] Y. Elbaz, M. C. Toroker, *J. Phys. Chem. C* **2017**, *121*, 16819.
- [26] J. C. Conesa, *J. Phys. Chem. C* **2016**, *120*, 18999.
- [27] V. Fidelsky, M. C. Toroker, *Phys. Chem. Chem. Phys.* **2017**, *19*, 7491.
- [28] M. Bajdich, M. García-A-Mota, A. Vojvodic, J. K. Nørskov, A. T. Bell, *J. Am. Chem. Soc.* **2013**, *135*, 13521.
- [29] B. Zhang, X. Zheng, O. Voznyy, R. Comin, M. Bajdich, M. García-Melchor, L. Han, J. Xu, M. Liu, L. Zheng, F. P. García de Arquer, C. T. Dinh, F. Fan, M. Yuan, E. Yassitepe, N. Chen, T. Regier, P. Liu, Y. Li, P. De Luna, A. Janmohamed, H. L. Xin, H. Yang, A. Vojvodic, E. H. Sargent, *Science* **2016**, *352*, 333.
- [30] X. Ji, L. Cui, D. Liu, S. Hao, J. Liu, F. Qu, Y. Ma, G. Du, A. M. Asiri, X. Sun, *Chem. Commun.* **2017**, *21*, 3070.
- [31] X. Zheng, B. Zhang, P. D. Luna, Y. Liang, R. Comin, O. Voznyy, L. Han, F. P. G. d. Arquer, M. Liu, C. T. Dinh, T. Regier, J. Dines, S. He, H. L. Xin, H. S. Peng, D. Prendergast, X. W. Du, E. H. Sargent, *Nat. Chem.* **2018**, *10*, 149.
- [32] H. Li, S. Chen, X. Jia, B. Xu, H. Lin, H. Yang, L. Song, X. Wang, *Nat. Commun.* **2017**, *8*, 15377.
- [33] C. C. McCrory, S. Jung, J. C. Peters, T. F. Jaramillo, *J. Am. Chem. Soc.* **2013**, *135*, 16977.
- [34] M. S. Burke, L. J. Enman, A. S. Batchellor, S. Zou, S. W. Boettcher, *Chem. Mater.* **2016**, *47*, 7549.
- [35] M. B. Stevens, L. J. Enman, A. S. Batchellor, M. R. Cosby, A. E. Vise, C. D. M. Trang, S. W. Boettcher, *Chem. Mater.* **2017**, *29*, 120.
- [36] A. S. Batchellor, S. W. Boettcher, *ACS Catal.* **2015**, *5*, 6680.
- [37] L. J. Enman, M. S. Burke, A. S. Batchellor, S. W. Boettcher, *ACS Catal.* **2016**, *6*, 2416.
- [38] J. Zaffran, M. B. Stevens, C. D. M. Trang, M. Nagli, M. Shehadéh, S. W. Boettcher, M. C. Toroker, *Chem. Mater.* **2017**, *29*, 4761.
- [39] J. M. Hu, J. Q. Zhang, C. N. Cao, *Int. J. Hydrogen Energy* **2004**, *29*, 791.
- [40] L. M. D. Silva, J. F. C. Boodts, L. A. D. Faria, *Electrochim. Acta* **2001**, *46*, 1369.
- [41] I. M. Sadiq, A. M. Mohammad, M. E. El-Shakre, M. S. El-Deab, *Int. J. Hydrogen Energy* **2012**, *37*, 68.
- [42] L. Melander, W. H. Saunders, Wiley, New York **1980**.
- [43] H. A. Al-Hosney, V. H. Grassian, *Phys. Chem. Chem. Phys.* **2005**, *7*, 1266.
- [44] G. Gaggiotti, A. Galdikas, S. Kačiulis, G. Mattogno, A. Šetkus, *J. Appl. Phys.* **1994**, *76*, 4467.
- [45] Y. Nagasawa, T. Choso, T. Karasuda, *Surf. Sci.* **1999**, *433*, 226.

Manuscript No. _____

Please send me and bill me for

no. of **reprints** via ☐ airmail (+ 25 Euro)
☐ surface mail

no. of **copies of this issue**
(1 copy: 28 Euro)
via ☐ airmail (+ 25 Euro)
☐ surface mail

☐ **high-resolution PDF file** (330 Euro).

My e-mail address:

Please note: It is not permitted to present the PDF file on the internet or on company homepages

★**Special Offer**★ If you order 200 or more reprints you will get a PDF file for half price.

Information regarding VAT

Please note that from German sales tax point of view, the charge for **Reprints, Issues or Posters** is considered as "supply of goods" and therefore, in general, such delivery is a subject to German sales tax. However, this regulation has no impact on customers located outside of the European Union. Deliveries to customers outside the Community are automatically tax-exempt. Deliveries within the Community to institutional customers outside of Germany are exempted from the German tax (VAT) only if the customer provides the supplier with his/her VAT number. The VAT number (value added tax identification number) is a tax registration number used in the countries of the European Union to identify corporate entities doing business there. It starts with a country code (e.g. FR for France, GB for Great Britain) and follows by numbers.

Cover Posters

Posters are available of all the published covers and frontispieces in two sizes

- ☐ DIN A2 42 x 60 cm / 17 x 24in (one copy: **39 Euro**)
☐ DIN A1 60 x 84 cm / 24 x 33in (one copy: **49 Euro**)

Postage for shipping posters overseas by airmail:
+ 25 Euro

Postage for shipping posters within Europe by surface mail:
+ 15 Euro

Mail reprints /cover posters / copies of the issue to:

Invoice address:

Date, Signature

Stamp

VAT no.: _____
(institutes / companies in EU countries only)

Purchase Order No.: _____

Credit Card Payment

VISA, MasterCard, AMERICAN EXPRESS

Please use the Credit Card Token Generator located at the website below to create a token for secure payment. The token will be used instead of your credit card number.

Credit Card Token Generator:

https://www.wiley-vch.de/editorial_production/index.php

Please transfer your token number to the space below.

Credit Card Token Number:

--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

Price list for reprints (The prices include mailing and handling charges. All Wiley-VCH prices are exclusive of VAT)

No. of pages	Price (in Euro) for orders of					
	50 copies	100 copies	150 copies	200 copies	300 copies	500 copies
1-4	345	395	425	445	548	752
5-8	490	573	608	636	784	1077
9-12	640	739	786	824	1016	1396
13-16	780	900	958	1004	1237	1701
17-20	930	1070	1138	1196	1489	2022
for every additional 4 pages	147	169	175	188	231	315

★ **Special Offer** ★ If you order 200 or more reprints you will get a PDF file for half price.