Dear Author,

Please correct your galley proofs carefully and return them no more than four days after the page proofs have been received.

Please limit corrections to errors already in the text; cost incurred for any further changes or additions will be charged to the author, unless such changes have been agreed upon by the editor.

The editors reserve the right to publish your article without your corrections if the proofs do not arrive in time.

Note that the author is liable for damages arising from incorrect statements, including misprints.

Please note any queries that require your attention. These are indicated with a Q in the PDF and a question at the end of the document.

Reprints may be ordered by filling out the accompanying form.

Return the reprint order form by fax or by e-mail with the corrected proofs, to Wiley-VCH : afm@wiley.com

Corrections should be made directly in the PDF file using the PDF annotation tools. If you have questions about this, please contact the editorial office. The corrected PDF and any accompanying files should be uploaded to the journal's Editorial Manager site.

To avoid commonly occurring errors, **please ensure that the following important items are correct** in your proofs (please note that once your article is published online, no further corrections can be made):

- **Names** of all authors present and spelled correctly
- **Titles** of authors correct (Prof. or Dr. only: please note, Prof. Dr. is not used in the journals)
- **Addresses** and **postcodes** correct
- **E-mail address** of corresponding author correct (current email address)
- **Funding bodies** included and grant numbers accurate
- **Title** of article OK
- All **figures** included
- **Equations** correct (symbols and sub/superscripts)

Author Query Form

WILEY

Journal ADFM
Article adfm201908040

Dear Author,

During the copyediting of your manuscript the following queries arose.

Please refer to the query reference callout numbers in the page proofs and respond to each by marking the necessary comments using the PDF annotation tools.

Please remember illegible or unclear comments and corrections may delay publication.

Many thanks for your assistance.

Query No.	Description	Remarks
Q-OO	<p>Open access publication of this work is possible via Wiley OnlineOpen. Information about this is available at: https://authorservices.wiley.com/author-resources/Journal-Authors/licensing-open-access/open-access/onlineopen.html.</p> <p>The cost of publishing your manuscript OnlineOpen may be covered by one of Wiley's national agreements. To find out more, visit https://authorservices.wiley.com/author-resources/Journal-Authors/open-access/affiliation-policies-payments/index.html.</p> <p>Note that eligibility for fee coverage is determined by the affiliation of the primary corresponding author designated at submission. Please log in to your Wiley Author Services account at https://authorservices.wiley.com/ and confirm your affiliation to see if you are eligible.</p> <p>Instructions for placing an OnlineOpen order can be found at: https://authorservices.wiley.com/author-resources/Journal-Authors/open-access/how-to-order-onlineopen.html.</p> <p>To publish your article open access, please complete the order process before completing your proof corrections.</p>	
Q1	Please confirm that forenames/given names (blue) and surnames/family names (vermillion) have been identified correctly.	
Q2	Please provide the highest academic title (either Dr. or Prof.) for all authors, where applicable.	
Q3	Please provide page number in ref. [28].	
Q4	The orcid identifier 0000-0001-5029-2142 does not match with the author Prof. Husam N. Alshareef. Please check and confirm the correct orcid identifier.	

Please confirm that Funding Information has been identified correctly.

Please confirm that the funding sponsor list below was correctly extracted from your article: that it includes all funders and that the text has been matched to the correct FundRef Registry organization names. If a name was not found in the FundRef registry, it may not be the canonical name form, it may be a program name rather than an organization name, or it may be an organization not yet included in FundRef Registry. If you know of another name form or a parent organization name for a "not found" item on this list below, please share that information.

FundRef Name	FundRef Organization Name
King Abdullah University of Science and Technology	King Abdullah University of Science and Technology

X. Xu, C. Zhang, M. K. Hota,
Z. Liu, X.-X. Zhang,
H. N. Alshareef* 1908040

Enhanced Quality of Wafer-Scale MoS₂ Films by a Capping Layer Annealing Process

Sulfurization of as-deposited epitaxial MoO₂ films with high density of defects results in textured MoS₂ films. A capping layer annealing process is developed to improve the MoO₂ precursor film quality, resulting in lower defect density and better surface roughness. Sulfurization of the improved MoO₂ precursor film results in single-crystalline MoS₂ film instead of textured films, with much better device performance.

Enhanced Quality of Wafer-Scale MoS₂ Films by a Capping Layer Annealing Process

Xiangming Xu, Chenhui Zhang, Mrinal K. Hota, Zhixiong Liu, Xixiang Zhang, and Husam N. Alshareef*

Wafer-scale, single-crystalline 2D semiconductors without grain boundaries and defects are needed for developing reliable next-generation of integrated 2D electronics. Unfortunately, few literature reports exist on the growth of 2D semiconductors with single-crystalline structure at the wafer scale. It is shown that direct sulfurization of as-deposited epitaxial MoO₂ films (especially, with thickness more than ≈5 nm) produces textured MoS₂ films. This texture is inherited from the high density of defects present in the as-prepared epitaxial MoO₂ film. In order to eliminate the texture of the converted MoS₂ films, a new capping layer annealing process (CLAP) is introduced to improve the crystalline quality of as-deposited MoO₂ film and minimize its defects. It is demonstrated that sulfurization of the CLAP-treated MoO₂ films leads to the formation of single-crystalline MoS₂ films, instead of textured films. It is shown that the single-crystalline MoS₂ films exhibit field-effect mobility of 6.3 cm² V⁻¹ s⁻¹, which is 15 times higher than that of textured MoS₂. These results can be attributed to the smaller concentration of defects in the single-crystalline films.

1. Introduction

The 2D MoS₂ is one of the most promising semiconductors for next generation electronics due to its tunable bandgap,^[1–5] favorable electronic mobility,^[6–8] excellent optoelectronic properties,^[9–13] and good thermal and chemical and mechanical stabilities.^[13–16] Scalable fabrication of 2D films is the precondition for manufacturing of post-Moore's law large-scale integrated devices. Researchers have already realized wafer-scale growth of MoS₂ films through chemical vapor deposition,^[17–19] metal organic chemical vapor deposition^[20] and vapor-solid reaction process.^[21–24] However, up to date, almost all the above growth processes could only realize polycrystalline MoS₂ films. Thus, most of these reported wafer-scale 2D MoS₂ films showed inferior electronic properties compared to single-crystalline

flakes.^[17,18,20,25] In order to bring wafer-scale 2D MoS₂ electronic properties close to theoretical levels, it is necessary to explore new approaches to obtain single-crystalline structures at the wafer scale.

It has been reported that the structure and properties of wafer-scale MoS₂ films, grown by the two-step process, can be engineered by modifying the structure of the precursor film. For example, an epitaxial MoO₂ film resulted in quasi single-crystalline MoS₂ films after sulfurization.^[26] However, still small angle grain boundaries and texture were observed in these MoS₂ films through direct sulfurization of the as-grown epitaxial precursor film. Here we show that thicker (>5 nm) precursor MoO₂ films lead to heavier texture in the converted MoS₂ films. The reason for using MoO₂ as a precursor film is because of its ability to grow continuous ultrathin film epitaxially on high-tem-

perature stable substrates.^[26–28] In order to eliminate texture from the MoS₂ films and achieve single-crystalline MoS₂, we developed a new process to improve the crystalline quality of the epitaxial precursor MoO₂ film. This annealing process is henceforth referred to as the capping layer annealing process (CLAP). Through the sulfurization of the CLAP-treated epitaxial MoO₂ film, wafer-scale single-crystalline MoS₂ films were obtained without texture. Transistor performance showed that MoS₂ film with single-crystalline structure exhibits field effect mobility almost 15 times higher than that of the textured MoS₂. We demonstrate that the process of sulfurization using high-quality epitaxial precursors can be a general growth method for wafer-scale single-crystalline chalcogenide films.

2. Results and Discussions

2.1. MoS₂ Converted from CLAP-Treated Epitaxial MoO₂ Films

Texture in MoS₂ films derived from epitaxial MoO₂ precursor films is caused by a large number of defects such as misfit dislocations present in the as-grown epitaxial precursor MoO₂ film.^[29–31] Direct thermal annealing process has normally been used to reduce the defects and improve the crystalline quality of epitaxial precursor films.^[31–33] However, this approach usually produces noncontinuous films or films with rough surfaces

X. Xu, C. Zhang, Dr. M. K. Hota, Z. Liu, Prof. X.-X. Zhang, Prof. H. N. Alshareef
Materials Science and Engineering
Physical Science and Engineering Division
King Abdullah University of Science and Technology (KAUST)
Thuwal 23955-6900, Saudi Arabia
E-mail: husam.alshareef@kaust.edu.sa

The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/adfm.201908040>.

DOI: 10.1002/adfm.201908040

Figure 1. a) Flow diagram showing the synthesis of single-crystal MoS_2 films converted from CLAP-treated precursor MoO_2 films. Optical image of b) as-deposited epitaxial MoO_2 film, c) MoO_2 film with Si_3N_4 capping layer, d) annealed MoO_2 film after removing the capping layer, e) single-crystalline MoS_2 film converted from sample (d).

due to recrystallization,^[34–36] which we also observe upon direct-annealing our epitaxial MoO_2 films in this report. Thus, direct thermal annealing of the precursor epitaxial MoO_2 film is not a good approach for growing high-quality 2D MoS_2 films. To improve crystalline quality of the ultrathin epitaxial MoO_2 precursor film without losing the continuity and surface flatness, we have developed a new CLAP. This process has the capability of improving the quality of epitaxial precursor films without degrading their flat surface.^[37]

In order to clarify the preparation process of wafer-scale single-crystalline MoS_2 film, a process flow diagram is shown in Figure 1a. First, a 2'' (001) sapphire wafer was cleaned and placed in a pulsed laser deposition (PLD) chamber for MoO_2 deposition. The epitaxial film was realized with optimized PLD parameters, with film thickness of more than 4.5 nm, as shown in Figure 1b. Besides, the thickness could be controlled

by adjusting the number of laser shots. After PLD, but before annealing, a transparent capping layer of Si_3N_4 (50 nm thick) was deposited on the MoO_2 film uniformly by plasma enhanced chemical vapor deposition. Then the Si_3N_4 -protected MoO_2 sample was annealed at 900 °C for 1 h in Ar atmosphere. This CLAP-treated MoO_2 film is shown in Figure 1c. After CLAP, the sample was cooled down to room temperature naturally. After cooling, a buffered oxide etch (BOE) (20:1) solution was used to etch the Si_3N_4 capping layer. After removing the capping layer, a higher quality epitaxial MoO_2 film was obtained, with outstanding uniformity and continuity as shown in Figure 1d. Then, the MoS_2 sample was obtained after the sulfurization, as shown in the optical picture in Figure 1e. The above describes the process for the single-crystalline film preparation process. In contrast, only a textured MoS_2 film (Instead of a single-crystalline structure) could be obtained through direct sulfurizing

of the as-deposited epitaxial MoO₂ film without CLAP. Detailed analysis of these two types of films is shown next.

2.2. Comparison of Directly-Annealed and CLAP-Treated Epitaxial MoO₂ Films

Epitaxial MoO₂ film was obtained by PLD using MoO₃ as target, 10 mTorr O₂ atmosphere, and 400 °C substrate temperature. Initially, we attempted to reduce the defects of the as-deposited MoO₂ film by direct thermal annealing (without capping layer) at different temperatures in Argon atmosphere. The sharpening of the X-ray diffraction (XRD) pattern and Raman peaks of the directly-annealed samples indicated an improved crystalline quality, as depicted in Figures S1 and S2 in the Supporting Information. But this direct annealing process degraded surface roughness and/or induced discontinuity in the MoO₂ films (Figure S3, Supporting Information), which is not acceptable for wafer-scale 2D film conversion. Thus, we developed the CLAP by introducing a protective layer to prevent film surface morphology from deteriorating. The protective layers used in CLAP, such as SiO₂ or Si₃N₄, are designed to be high-temperature stable and removable by BOE, a chemical that does not etch the MoO₂ film (Figure S4, Supporting Information). However, using SiO₂ capping layer did not perform as well as Si₃N₄ because some residual SiO₂ always remained on the MoO₂ film surface. The Si₃N₄ layer was easier to be totally removed, as indicated by the atomic force microscopy (AFM) phase images in Figure S5 in the Supporting Information. In addition, the Si₃N₄ capping layer resulted in smoother MoO₂ film surface, as depicted in Figure S6 in the Supporting Information.

The impact of the annealing process on the crystalline structure of epitaxial MoO₂ film was studied by XRD and Raman spectroscopy, as demonstrated in Figure 2a–c. Note that the crystal orientation of MoO₂ was not changed after the thermal treatment (with or without CLAP), as depicted in Figure 2a. The Rocking curve results are shown in Figure 2b. The full width at half maximum (FWHM) of the (200) peak was reduced from 0.085 to 0.072 as a result of the CLAP, meaning that the crystal quality of the epitaxial film was improved because of the thermal treatment. The slight peak shift to lower angle might be due to strain released during the annealing process. Figure 2c shows the Raman spectra of pristine, directly-annealed (uncapped) and CLAP-annealed MoO₂ films. The sharper peaks of both annealed MoO₂ films confirm their improved crystal quality. However, the Raman peak intensity of the CLAP-treated film at position 202 nm is stronger than that of directly-annealed (uncapped) film (position shift to 204 nm). In contrast, the peak intensity of CLAP-treated film at position 491.5 nm is much weaker (the peak position of the directly-annealed film shift to 498.5 nm). The reason might be that the vibration mode of the 202 peak is parallel to the (200) MoO₂ lattice plane, but the 491.5 peak is not in the same lattice plane. Since the CLAP resulted in continuous MoO₂ films (Figure 2f), an enhanced vibration mode was observed in the (200) lattice plane.^[38] The Raman peak position shifts shown in Figure 2c (from 202 and 491.5 for CLAP film to 204 and 498.5 for directly-annealed uncapped film) might be due to two reasons: one is the different degree of phonon confinement

in between the ultrathin CLAP-treated continuous film and the direct-annealed isolated MoO₂ grains;^[39] the other reason is the different amount of strain^[40] released from these two films. Figure 2d–f shows the AFM images of pristine (as-deposited), directly-annealed (uncapped), and CLAP-treated epitaxial MoO₂ film, respectively. It is apparent from Figure 2e that film annealing with no capping layer results in discontinuous micrograins. The film treated by the CLAP in Figure 2f remains continuous and flat (room mean square (RMS) roughness = 0.342 nm). This value slightly increases compared to 0.167 nm of the pristine film (Figure 2d). This roughness might result from the plasma surface treatment during the capping layer deposition^[41] or from enhanced atomic movement during the high-temperature annealing process.^[42] Figure 2g shows a schematic of the MoO₂ film morphology variation with increasing direct annealing temperature. The as-prepared MoO₂ film is full of misfit dislocations or mosaic disorientation defects, as indicated in the enlarged lattice structure figure I: The MoO₂ film initially becomes rough at lower annealing temperature. II: Further increasing the temperature induces MoO₂ film recrystallization and forms interconnected micrograins. III: When the direct annealing temperature reaches 900 °C, the micrograins become isolated. Figure 2h shows a schematic of the different stages of the CLAP. Nondifferently, the as-deposited MoO₂ film has a higher density of defects such as dislocation and mosaicity. ① Before the thermal annealing process, a capping layer (e.g., Si₃N₄) is deposited on top of the MoO₂ film. ② A thermal annealing process is then carried out which sharply annihilates defects and improves the epitaxial quality of the MoO₂ film. Meanwhile, mass transfer on the film surface caused by recrystallization is effectively prevented by the capping layer, leading to smoother and continuous films. ③ After the thermal treatment, the capping layer is removed by an acid solution, and a high-quality precursor MoO₂ film with smooth surface is obtained, also with fewer defects, indicated by the relevant enlarged lattice structure figure. Notably, verified by experiment, the CLAP process is not practical for atomically-thin film with thickness less than ≈5 nm. The reason might be that atomically-thin film is with much higher surface activity, thus it is easily damaged by any post-treatment process.^[43]

2.3. Microscopic Characterization of MoS₂ Films

In order to analyze the influence of the quality of the epitaxial precursor MoO₂ films on the quality of the converted MoS₂ films, the conversion process was carried out at fixed conditions. The conversion process detail is provided in the Experimental Section. The transmission electron microscopy (TEM) and scanning TEM (STEM) images shown in Figure 3 were all obtained from MoS₂ films with thickness of ≈5 nm. Low magnitude TEM image characterization was performed on the MoS₂ film converted from the CLAP-treated MoO₂ film; the three areas marked by red circles (Figure 3a) show selected area electron diffraction (SAEDs). The dark area indicated by the yellow arrow is the Cu grid, and the gray network indicated by the red arrow is the lacey carbon region. Figure 3b shows the low magnification STEM image of the MoS₂ film converted from CLAP-treated MoO₂ film. From Figure 3b we could find that the whole

Figure 2. Improved crystal quality of precursor MoO₂ film by CLAP. a) XRD pattern of pristine MoO₂ films and CLAP-treated MoO₂ films. b) XRD (200) rocking curve measurement of epitaxial MoO₂ film before and after CLAP. c) Raman spectra of pristine MoO₂ film and CLAP-treated MoO₂ films. AFM height images of d) pristine MoO₂ film, e) directly-annealed (uncapped) MoO₂ at 900 °C. f) MoO₂ film treated by CLAP at 900 °C. Scale bar: 200 nm. Schematic diagrams of g) uncapped MoO₂ film morphology change with increasing annealing temperature; h) CLAP treatment process of MoO₂ film with improved quality. The schematic drawing is not to scale for lustration purposes.

continuous MoS₂ film has only one or two discontinuous monolayers on the top surface. Figure 3c shows a high magnification STEM image focused on the edge area of the top discontinuous

monolayers. The inset fast Fourier transform (FFT) pattern shows a single-crystal like pattern, indicating that the crystalline orientation of the top discontinuous monolayers is consistent

Figure 3. (S)TEM characterization of MoS₂ converted from pristine and CLAP-treated 4.5 nm thick MoO₃ film. a) Low magnification TEM (scale bar: 10 μ m); b) LR-STEM of MoS₂ film (scale bar: 100 nm); c) HR-STEM HAADF image of MoS₂ film at the top monolayer flake edge area (scale bar: 5 nm), inset is the relevant FFT. d) HR-STEM HAADF images with atomic resolution of MoS₂ film converted from CLAP-treated MoO₃ film (scale bar: 1 nm). e) Side view, f) top view of the single crystalline MoS₂ film structure. g) Side and top view of the MoS₂ AA' and AB layer stacking mode. h, i) SAEDs of MoS₂ converted from CLAP-treated MoO₃ film (selected area marked in panel (a) with red circles). k) SAED of MoS₂ converted from pristine film.

with that of underneath continuous film. The morphology of this kind of film is further illustrated with side and top views in Figure 3e,f, respectively. The HR STEM high-angle annular dark-field (HAADF) image (Figure 3d) of the stable single-crystalline MoS₂ film depicts the honeycomb structure with AA' stacking order of the 2H MoS₂ phase.^[44] The comparison between AA' and AB stacking mode is shown with side and top views in Figure 3g. Figure 3h–j displays the SEADs taken at three locations marked (1, 2, and 3) in Figure 3a. All diffraction patterns exhibit hexagonally arranged diffraction spots, demonstrating the single-crystalline structure of the MoS₂ films. Since these three selected areas were all set within a diameter of about 20 μ m (the upper limit of our TEM instrument), they illustrate that the single-crystalline structure uniformity is exhibited at the wafer scale. Figure 3k shows the SAED pattern (location marked with red circle in Figure S7 in the Supporting Information) of the MoS₂ converted from pristine precursor epitaxial MoO₃ film without any postannealing treatment. The ring-like pattern consists of quasi discrete elongated light spots, indicating the preferred orientation and the texture structure in the 2D MoS₂ film. Several researchers have demonstrated that these kind of structures have great influence on the mechanical,

optical, and electronic properties of thin films.^[45–48] However, this is probably the first time that textured morphology has been observed in 2D chalcogenide films. We believe that the reason for forming the texture in 2D films is the presence of high density of defects in the precursor MoO₃ films. Achievement of the single-crystalline structure can be attributed to the high-quality precursor film obtained after the CLAP treatment. TEM characterization of thicker (15 nm) MoS₂ films converted from pristine and CLAP-treated precursor were also performed, as depicted in Figure S8 in the Supporting Information. The SAED (Figure S8b, Supporting Information) of the 15 nm thick film from pristine precursor displayed textured structure, with diffraction pattern that resembles the ring pattern of textured films shown in Figure 3k. However, the thicker MoS₂ films converted from the CLAP-treated precursor retain a perfect single-crystalline structure (Figure S8d, Supporting Information).

2.4. Spectral Characterization

The Raman, photoluminescence (PL), and X-ray photoelectron spectroscopy (XPS) measurements were performed on the

Figure 4. a) Raman, b) PL, c) XPS-Mo 3d, d) XPS-S 2p spectra of single-crystalline and textured MoS₂ films converted from CLAP-treated and pristine MoO₃ films with different thickness.

MoS₂ films converted from the CLAP-treated or pristine MoO₃ films. The intensity-normalized Raman spectra in Figure 4a show that no peak shift between textured and single-crystalline MoS₂. Further, no peak shift is observed among single-crystalline films with different thickness. The peak differences between E_{2g} and A_{1g} peaks all are 25.4 cm⁻¹, which means that all the films mentioned above show bulk film structure (film with more than five layers or 3 nm) and no strain difference. A total of 33 locations on the 4.5 nm thick MoS₂ film wafer (Figure S9a, Supporting Information) were tested by Raman. All tested locations show the same E_{2g} and A_{1g} peak positions (Figure S9b, Supporting Information). This result confirms the film uniformity across the 2" wafer. In Figure 4b, The PL spectra of 15 nm MoS₂ films reveal that the FWHM of PL peak at 676 nm position of single-crystalline film is smaller than that textured films, which means single-crystalline MoS₂ films exhibit better quality. Typical XPS spectra of textured MoS₂ with thickness 4.5, 6, and 9 nm are shown in Figure 4c–d. Figure 4c shows XPS peaks at 235.88, 232.73, 232.83, 229.67, and 226.87 corresponding to Mo⁶⁺ 3d_{3/2}, Mo⁶⁺ 3d_{5/2}, Mo⁶⁺ 3d_{3/2}, Mo⁶⁺ 3d_{5/2}, and S 2s, respectively. Figure 4d shows S 2p_{1/2} and S 2p_{3/2} peaks at 163.70 and 162.51 eV. These peak positions are consistent with those reported for crystalline MoS₂ films.^[21] All the single-crystalline and textured MoS₂

films with different thickness actually show the same XPS peak positions as illustrated above. Through careful Lorentzian–Gaussian fitting of XPS, The Mo/S elemental ratio in films with thickness 4.5, 6, and 9 nm were calculated to be 1/1.92, 1/1.91, and 1/1.89, respectively. This data indicates that the thicker precursor MoO₃ films are more difficult to sulfurize, hence the resultant MoS₂ films contained more defects. This effect originate from the difficulty of sulfur elements replacing oxygen (defined as S-O-exchange defects) deeper in the thick MoO₃ films.

2.5. Transfer Process and Transistor Performance

The MoS₂ films deposited with different thicknesses on 2" wafers could be uniformly transferred onto both rigid and flexible substrates using PDMS stamp transfer combined with wet chemical etching process. The image in Figure 5a shows transferred films with thickness 4.5 and 6 nm (as shown by the inset AFM images and line scan) on SiO₂(300 nm)/Si⁺⁺ substrates. The films were also successfully transferred onto flexible paper substrate as displayed in Figure 5b. The transfer process above demonstrates the potential for our wafer-scale MoS₂ films to be used in Si-based, flexible, and paper electronics.

Figure 5. Transfer process and TFT performance of single-crystalline and textured MoS₂ films. a) MoS₂ film with a thickness of 4.5 and 6 nm transferred onto SiO₂ (300 nm)/Si⁺⁺ substrate. b) MoS₂ film with a thickness of 9 nm transferred to flexible paper. c) Schematic of top-gated TFT fabricated using MoS₂ as a channel, d) Output characteristics, e) Logarithm plot transfer curves, and f) Field-effect mobility of single-crystalline and textured MoS₂ of different thickness.

Top-gated thin film transistors (TFTs) were fabricated, as shown in Figure 5c, to characterize the electronic properties of the MoS₂. The S/D (source and drain) and top gate Au/Ti (50/10 nm) contacts were deposited by e-beam evaporation at room temperature in high vacuum. HfO₂ gate dielectric (60 nm thick) was deposited using atomic layer deposition (ALD). Details of the TFT fabrication are explained in the Experimental section. The output curves of TFTs fabricated using single-crystalline and textured MoS₂ films (both 6 nm thick) are shown in Figure 5d, where Ohmic-like behavior with S/D electrodes could be observed. Transfer curves of TFTs fabricated using both single-crystalline MoS₂ (red curves) and textured MoS₂ (black curves) channel with different thicknesses (4.5, 6, and 9 nm) are plotted along with conductivity on a logarithmic scale (Figure 5e). All the transfer curves were measured under the same S/D voltage (1 V) for a fair comparison. The results shown in Figure 5f (also Figure S10a,b in the Supporting Information) indicate that the single-crystalline MoS₂ based TFTs always show higher mobility than textured MoS₂ based TFTs, no matter the channel thickness. Especially, when the MoS₂ film thickness was 4.5 nm, the single-crystalline MoS₂ film showed a mobility of 6.3 cm² V⁻¹ s⁻¹ (this result is better than that of the MoS₂ films converted from the other Mo-based precursors),^[22–24,49] which is 15 times higher than that of the

textured MoS₂. This result is likely due to the high concentration of defects in the textured films which can scatter the channel electrons. Subthreshold swing values (Figure S10c, Supporting Information) did not show any clear trend, probably because of fluctuations in the TFT fabrication process. As the films become thicker, the TFT performance with both films (single-crystalline MoS₂ and textured MoS₂) show significant degradation, and the mobility differences between the single-crystalline and textured MoS₂ become smaller. The degraded mobilities and current on/off ratios measured for thicker MoS₂ film devices are in contrast to the trend normally observed in mechanically-exfoliated or CVD-grown flakes.^[50,51] The reason for this difference might be that at larger MoS₂ film thickness both the single-crystalline and textured MoS₂ films have more S-O-exchange defects. These defects could act as electrons-scattering centers, but more experimental work is needed to confirm this hypothesis.

3. Conclusion

Single-crystalline MoS₂ films were grown on 2" wafers by sulfurization of capp-annealed MoO₃ films. Our CLAP could eliminate defects present in the as-deposited epitaxial MoO₃

precursor films, which resulted in single-crystalline MoS₂ films. However, the direct sulfurization of as-deposited epitaxial MoO₃ films (without capping layer) resulted in textured MoS₂ films. The distinction between the single-crystalline and textured MoS₂ films was clarified through TEM characterization. The wafer-scale MoS₂ films of different thickness were successfully transferred onto rigid SiO₂ (300 nm)/Si⁺⁺ and flexible paper substrates. Electronic properties of the single-crystalline and textured MoS₂ films were compared. Transistors fabricated single-crystalline films showed 15 times higher field effect mobility than their textured counterparts.

4. Experimental Section

Epitaxial MoO₃ PLD Deposition: (001) Al₂O₃ substrate was precleaned and thermally annealed in vacuum for 2 h to improve surface quality. The MoO₃ deposition process was carried out at 400 °C in O₂ ambient at a pressure of 10 mTorr. Thickness of MoO₃ was controlled by the number of laser shots and by laser energy. This process is similar to the previous report.^[26]

CLAP Process: Pristine (as deposited) epitaxial MoO₃ sample was covered with protective capping layer, such as SiO₂ or Si₃N₄ with thickness of 50 nm. The SiO₂ layer was deposited at room temperature by sputtering process. Si₃N₄ layer was deposited at 250 °C by plasma-enhanced chemical vapor deposition. The protective capping layer was thermally stable without crystallization even at temperature up to 900 °C. The MoO₃ sample with capping layer with annealed in the PLD chamber at 900 °C for 1 h in Argon at a pressure of 50 mtorr. The annealing time cannot be prolonged to more than 2 h, as this would cause serious film uniformity issues. After the annealing process, the sample was cooled down to room temperature, and then put into BOE (20:1) for 2 h to totally remove the capping layer. It is made sure the selected capping layer etchant did not damage the MoO₃. The bare MoO₃ samples were then cleaned in DI water three times. Finally, the high-quality epitaxial MoO₃ films with fewer defects were ready for the sulfurization process.

Sulfurization Process: Three zone chemical vapor deposition system is used to do the sulfurization. During the sulfurization process, Argon carrier gas with flow rate of 100 sccm and pressure 5–10 torr was used. Sulfur powder source with 500 mg was put in the up-stream heating zone with temperature 150 °C. The MoO₃ sample was put in the down-stream heating zone. After the temperature of the sulfur source stabilized at 150 °C, MoO₃ sample was heated at a heating rate of 20 °C min⁻¹. The sulfurization temperature was carried out at 900 °C for 1 h. Once the process finished, the system was naturally cooled down.

Top-Gated TFT Device Fabrication: The MoS₂ films were used as channel layer and patterned by dry etching. An Au/Ti film with thickness (50/10 nm) was deposited by electron beam evaporation and used as S/D contact and top gate electrodes, patterned by lift-off process. HfO₂ high-k dielectric layer, with thickness of 60 nm, was deposited using atomic layer deposition. The via hole was patterned by dry etching.

Characterization: θ -2 θ scans and Rocking curves X-ray diffraction patterns of the epitaxial MoO₃ films were obtained using X-Ray Diffractometer (Bruker, D8 DA Vinci) with Cu K α (λ = 1.5418 Å). Raman and PL measurement was realized with Horiba Aramis Raman spectrometer (Horiba Scientific) equipment, excited by visible light with wavelength 473 nm. AFM (Bruker, Dimension Icon SPM) was for the surface morphologies characterization of pristine, thermally-treated epitaxial MoO₃, and transferred MoS₂ films. TEM images and selected area electron diffraction patterns were obtained by transmission electron microscope (Titan Cs Probe, FEI). HR TEM images were performed in a Cs-corrected FEI Titan Themis microscope. The free-standing MoS₂ film was obtained through 2 h etching in aqueous alkali solution, then was transferred onto TEM grids with lacey carbon film. XPS spectra were measured in a Kratos Axis Ultra DLD spectrometer equipped with a monochromatic Al K α X-ray source ($h\nu$ = 1486.6 eV) operating at

150 W. All spectra were recorded using an aperture slot of 300 μ m $\times$ 700 μ m, while high-resolution spectra were measured with a pass energy of 20 eV and a step size 0.1 eV. Performance of top-gated TFTs was measured using an Agilent B1500A analyzer.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

Research reported in this publication was supported by King Abdullah University of Science and Technology (KAUST).

Conflict of Interest

The authors declare no conflict of interest.

Keywords

MoS₂, single crystalline, texture, transistor, wafer scale

Received: September 28, 2019

Revised: November 28, 2019

Published online:

- [1] Y. Chen, J. Xi, D. O. Dumcenco, Z. Liu, K. Suenaga, D. Wang, Z. Shuai, Y.-S. Huang, L. Xie, *ACS Nano* **2013**, 7, 4610.
- [2] A. Ramasubramaniam, D. Naveh, E. Towe, *Phys. Rev. B* **2011**, 84, 205325.
- [3] J. Mann, Q. Ma, P. M. Odenthal, M. Isarraraz, D. Le, E. Preciado, D. Barroso, K. Yamaguchi, G. von Son Palacio, A. Nguyen, *Adv. Mater.* **2014**, 26, 1399.
- [4] Y. Y. Hui, X. Liu, W. Jie, N. Y. Chan, J. Hao, Y.-T. Hsu, L.-J. Li, W. Guo, S. P. Lau, *ACS Nano* **2013**, 7, 7126.
- [5] H. J. Conley, B. Wang, J. I. Ziegler, R. F. Haglund Jr., S. T. Pantelides, K. I. Bolotin, *Nano Lett.* **2013**, 13, 3626.
- [6] W. Bao, X. Cai, D. Kim, K. Sridhara, M. S. Fuhrer, *Appl. Phys. Lett.* **2013**, 102, 042104.
- [7] S. Das, H.-Y. Chen, A. V. Penumatcha, J. Appenzeller, *Nano Lett.* **2013**, 13, 100.
- [8] M. M. Perera, M.-W. Lin, H.-J. Chuang, B. P. Chamlagain, C. Wang, X. Tan, M. M.-C. Cheng, D. Tománek, Z. Zhou, *ACS Nano* **2013**, 7, 4449.
- [9] Z. Yin, H. Li, H. Li, L. Jiang, Y. Shi, Y. Sun, G. Lu, Q. Zhang, X. Chen, H. Zhang, *ACS Nano* **2012**, 6, 74.
- [10] X. Wang, P. Wang, J. Wang, W. Hu, X. Zhou, N. Guo, H. Huang, S. Sun, H. Shen, T. Lin, *Adv. Mater.* **2015**, 27, 6575.
- [11] S. H. Yu, Y. Lee, S. K. Jang, J. Kang, J. Jeon, C. Lee, J. Y. Lee, H. Kim, E. Hwang, S. Lee, *ACS Nano* **2014**, 8, 8285.
- [12] D. Kufer, G. Konstantatos, *Nano Lett.* **2015**, 15, 7307.
- [13] M. Calandra, *Phys. Rev. B* **2013**, 88, 245428.
- [14] Y. Gong, B. Li, G. Ye, S. Yang, X. Zou, S. Lei, Z. Jin, E. Bianco, S. Vinod, B. I. Yakobson, *2D Mater.* **2017**, 4, 021028.
- [15] M. Wang, S. Cai, C. Pan, C. Wang, X. Lian, Y. Zhuo, K. Xu, T. Cao, X. Pan, B. Wang, S.-J. Liang, J. J. Yang, P. Wang, F. Miao, *Nat. Electron.* **2018**, 1, 130.

- [16] W. G. Song, H. J. Kwon, J. Park, J. Yeo, M. Kim, S. Park, S. Yun, K. U. Kyung, C. P. Grigoropoulos, S. Kim, *Adv. Funct. Mater.* **2016**, 26, 2426.
- [17] P. Yang, X. Zou, Z. Zhang, M. Hong, J. Shi, S. Chen, J. Shu, L. Zhao, S. Jiang, X. Zhou, *Nat. Commun.* **2018**, 9, 979.
- [18] H. Yu, M. Liao, W. Zhao, G. Liu, X. Zhou, Z. Wei, X. Xu, K. Liu, Z. Hu, K. Deng, *ACS Nano* **2017**, 11, 12001.
- [19] Z. Dai, Z. Wang, X. He, X. X. Zhang, H. N. Alshareef, *Adv. Funct. Mater.* **2017**, 27, 1703119.
- [20] K. Kang, S. Xie, L. Huang, Y. Han, P. Y. Huang, K. F. Mak, C.-J. Kim, D. Muller, J. Park, *Nature* **2015**, 520, 656.
- [21] H. Yang, A. Giri, S. Moon, S. Shin, J.-M. Myoung, U. Jeong, *Chem. Mater.* **2017**, 29, 5772.
- [22] S. Xiongfei, Z. Wu, X. Hu, D. Shijin, Z. Peng, B. Wenzhong, Z. David Wei, *2D Mater.* **2017**, 4, 025051.
- [23] K.-K. Liu, W. Zhang, Y.-H. Lee, Y.-C. Lin, M.-T. Chang, C.-Y. Su, C.-S. Chang, H. Li, Y. Shi, H. Zhang, C.-S. Lai, L.-J. Li, *Nano Lett.* **2012**, 12, 1538.
- [24] Y. C. Lin, W. J. Zhang, J. K. Huang, K. K. Liu, Y. H. Lee, C. T. Liang, C. W. Chu, L. J. Li, *Nanoscale* **2012**, 4, 6637.
- [25] W. Chen, J. Zhao, J. Zhang, L. Gu, Z. Yang, X. Li, H. Yu, X. Zhu, R. Yang, D. Shi, *J. Am. Chem. Soc.* **2015**, 137, 15632.
- [26] X. Xu, Z. Wang, S. Lopatin, M. Quevedo-Lopez, H. N. Alshareef, *2D Mater.* **2019**, 6, 015030.
- [27] E. Ahn, Y. S. Seo, J. Cho, I. Lee, J. Hwang, H. Jeon, *RSC Adv.* **2016**, 6, 60704.
- [28] C. H. Ma, J. C. Lin, H. J. Liu, T. H. Do, Y. M. Zhu, T. D. Ha, Q. Zhan, J. Y. Juang, Q. He, E. Arenholz, P. W. Chiu, Y. H. Chu, *Appl. Phys. Lett.* **2016**, 108.
- [29] J. Lee, H. Shichijo, H. Tsai, R. Matyi, *Appl. Phys. Lett.* **1987**, 50, 31.
- [30] F. LeGoues, M. Copel, R. Tromp, *Phys. Rev. Lett.* **1989**, 63, 1826.
- [31] J.-S. Park, J. Bai, M. Curtin, B. Adekore, M. Carroll, A. Lochtefeld, *Appl. Phys. Lett.* **2007**, 90, 052113.
- [32] Y.-W. Cheng, H.-Y. Wu, Y.-Z. Lin, C.-C. Lee, C.-F. Lin, *Thin Solid Films* **2015**, 577, 17.
- [33] K. H. Lee, S. Bao, G. Y. Chong, Y. H. Tan, E. A. Fitzgerald, C. S. Tan, *APL Mater.* **2015**, 3, 016102.
- [34] V. Valliyil Sasi, A. Iqbal, K. Chaik, A. Iacopi, F. Mohd-Yasin, *Micromachines* **2017**, 8, 148.
- [35] M. Nieminen, S. Lehto, L. Niinistö, *J. Mater. Chem.* **2001**, 11, 3148.
- [36] W. Wang, L. Li, Q. Zhou, J. Pan, Z. Zhang, E. S. Tok, Y.-C. Yeo, *Appl. Surf. Sci.* **2014**, 321, 240.
- [37] J. Greenlee, A. Nath, T. Anderson, B. Feigelson, A. Koehler, K. Hobart, R. Dupuis, T. Detchprohm, S. Shen, F. Kub, *ECS J. Solid State Sci.* **2017**, 6, Q3067.
- [38] F. A. Akgul, G. Akgul, N. Yildirim, H. E. Unalan, R. Turan, *Mater. Chem. Phys.* **2014**, 147, 987.
- [39] L. Kumari, Y.-R. Ma, C.-C. Tsai, Y.-W. Lin, S. Y. Wu, K.-W. Cheng, Y. Liou, *Nanotechnology* **2007**, 18, 115717.
- [40] S. Mar, C. Chen, Y. Huang, K. Tiong, *Appl. Surf. Sci.* **1995**, 90, 497.
- [41] A. Zendehtnam, J. Ghasemi, A. Zendehtnam, *Int. Nano Lett.* **2018**, 8, 157.
- [42] F. Meriche, T. Touam, A. Chelouche, M. Dehimi, J. Solard, A. Fischer, A. Boudrioua, L.-H. Peng, *Electron. Mater. Lett.* **2015**, 11, 862.
- [43] Y. Chen, J. Hu, H. Diao, W. Luo, Y. F. Song, *Chem. - Eur. J.* **2017**, 23, 4010.
- [44] S. Yang, J. Kang, Q. Yue, K. Yao, *J. Phys. Chem. C* **2014**, 118, 9203.
- [45] K.-D. Liss, A. Bartels, A. Schreyer, H. Clemens, *Textures Microstruct.* **2003**, 35, 219.
- [46] M. Birkholz, B. Selle, F. Fenske, W. Fuhs, *Phys. Rev. B* **2003**, 68, 205414.
- [47] M. Birkholz, *J. Appl. Crystallogr.* **2007**, 40, 735.
- [48] U. F. Kocks, C. N. Torné, H.-R. Wenk, A. J. Beaudoin, *Texture and Anisotropy: Preferred Orientations in Polycrystals and their Effect on Materials Properties*, Cambridge University Press, Cambridge, UK **2000**.
- [49] Y. Kim, A. R. Kim, G. Zhao, S. Y. Choi, S. C. Kang, A. R. Kim, G. Zhao, S. Y. Choi, S. C. Kang, S. K. Lim, K. E. Lee, J. Park, B. H. Lee, M. Gwa, *ACS Appl. Mater. Interfaces* **2017**, 9, 37146.
- [50] B. Radisavljevic, A. Radenovic, J. Brivio, V. Giacometti, A. Kis, *Nat. Nanotechnol.* **2011**, 6, 147.
- [51] J. Zheng, X. Yan, Z. Lu, H. Qiu, G. Xu, X. Zhou, P. Wang, X. Pan, K. Liu, L. Jiao, *Adv. Mater.* **2017**, 29, 1604540.

Reprint Order Form

Charges for Reprints in Euro (excl. VAT), prices are subject to change. Minimum order 50 copies; single issues for authors at a reduced price.

No. of pages	50 copies	100 copies	150 copies	200 copies	300 copies	500 copies
1–4	345,—	395,—	425,—	445,—	548,—	752,—
5–8	490,—	573,—	608,—	636,—	784,—	1077,—
9–12	640,—	739,—	786,—	824,—	1016,—	1396,—
13–16	780,—	900,—	958,—	1004,—	1237,—	1701,—
17–20	930,—	1070,—	1138,—	1196,—	1489,—	2022,—
every additional 4 pages	147,—	169,—	175,—	188,—	231,—	315,—

Manuscript No.: _____
Customer No.: (if available) _____
Purchase Order No.: _____
Author: _____

Information regarding VAT: The charges for publication of *cover pictures* / *reprints/issues/poster/Video abstracts* are considered to be “supply of services” and therefore subject to German VAT. However, if you are an institutional customer outside Germany, the tax can be waived if you provide us with the valid VAT number of your company. Non-EU customers may have a VAT number starting with “EU” instead of their country code, if they are registered with the EU tax authorities. If you do not have a valid EU VAT number and you are a taxable person doing business in a non-EU country, please provide a certification from your local tax authorities confirming that you are a taxable person under local tax law. Please note that the certification must confirm that you are a taxable person and are conducting an economic activity in your country. **Note:** certifications confirming that you are a tax-exempt legal body (non-profit organization, public body, school, political party, etc.) in your country do not exempt you from paying German VAT.

Please send me send bill me for

☐ no. of reprints

☐ no. of issue
(1 copy: 28 Euro)

☐ high-resolution PDF file (330 Euro excl. VAT)
E-mail address: _____

❖ Special Offer:

If you order 200 or more reprints you will get
a PDF file for half price.

*Please note: It is not permitted to present the PDF file on
the internet or on company homepages.*

Cover Posters (prices excl. VAT)

Posters of published covers are available in two sizes:

☐ DIN A2 42 x 60 cm / 17 x 24in (one copy: 39 Euro)

☐ DIN A1 60 x 84 cm / 24 x 33in (one copy: 49 Euro)

Postage for shipping (prices excl. VAT)

overseas +25 Euro
within Europe +15 Euro

VAT number: _____

Mail reprints / copies of the issue to:

Send bill to:

☐ I will pay by bank transfer

☐ I will pay by credit card

VISA, Mastercard and AMERICAN EXPRESS

For your security please use this link (Credit Card
Token Generator) to create a secure code Credit
Card Token and include this number in the form
instead of the credit card data. Click here:

https://www.wiley-vch.de/editorial_production/index.php

CREDIT CARD TOKEN NUMBER

						V													
--	--	--	--	--	--	---	--	--	--	--	--	--	--	--	--	--	--	--	--

Date, Signature _____