Dear Author,

Please correct your galley proofs carefully and return them no more than four days after the page proofs have been received.

Please limit corrections to errors already in the text; cost incurred for any further changes or additions will be charged to the author, unless such changes have been agreed upon by the editor.

The editors reserve the right to publish your article without your corrections if the proofs do not arrive in time.

Note that the author is liable for damages arising from incorrect statements, including misprints.

Please note any queries that require your attention. These are indicated with a Q in the PDF and a question at the end of the document.

Reprints may be ordered by filling out the accompanying form.

Return the reprint order form by fax or by e-mail with the corrected proofs, to Wiley-VCH : advmat@wiley.com

To avoid commonly occurring errors, **please ensure that the following important items are correct** in your proofs (please note that once your article is published online, no further corrections can be made):

- **Names** of all authors present and spelled correctly
- **Titles** of authors correct (Prof. or Dr. only: please note, Prof. Dr. is not used in the journals)
- **Addresses** and **postcodes** correct
- **E-mail address** of corresponding author correct (current email address)
- **Funding bodies** included and grant numbers accurate
- **Title** of article OK
- All **figures** included
- **Equations** correct (symbols and sub/superscripts)

Corrections should be made directly in the PDF file using the PDF annotation tools. If you have questions about this, please contact the editorial office. The corrected PDF and any accompanying files should be uploaded to the journal's Editorial Manager site.

Author Query Form

WILEY

Journal ADMA
Article adma201908392

Dear Author,

During the copyediting of your manuscript the following queries arose.

Please refer to the query reference callout numbers in the page proofs and respond to each by marking the necessary comments using the PDF annotation tools.

Please remember illegible or unclear comments and corrections may delay publication.

Many thanks for your assistance.

Query No.	Description	Remarks
Q-OO	<p>Open access publication of this work is possible via Wiley OnlineOpen. Information about this is available at: https://authorservices.wiley.com/author-resources/Journal-Authors/licensing-open-access/open-access/onlineopen.html.</p> <p>The cost of publishing your manuscript OnlineOpen may be covered by one of Wiley's national agreements. To find out more, visit https://authorservices.wiley.com/author-resources/Journal-Authors/open-access/affiliation-policies-payments/index.html.</p> <p>Note that eligibility for fee coverage is determined by the affiliation of the primary corresponding author designated at submission. Please log in to your Wiley Author Services account at https://authorservices.wiley.com/ and confirm your affiliation to see if you are eligible.</p> <p>Instructions for placing an OnlineOpen order can be found at: https://authorservices.wiley.com/author-resources/Journal-Authors/open-access/how-to-order-onlineopen.html.</p> <p>To publish your article open access, please complete the order process before completing your proof corrections.</p>	
Q1	Please confirm that forenames/given names (blue) and surnames/family names (vermillion) have been identified correctly.	
Q2	Please provide the highest academic title (either Dr. or Prof.) for all authors, where applicable.	
Q3	Please add postal code in affiliation 4.	
Q4	Refs. (49) and (54) were identical, so the latter instance has been deleted and renumbered remaining list and their citations. Please check.	

Please confirm that Funding Information has been identified correctly.

Please confirm that the funding sponsor list below was correctly extracted from your article: that it includes all funders and that the text has been matched to the correct FundRef Registry organization names. If a name was not found in the FundRef registry, it may not be the canonical name form, it may be a program name rather than an organization name, or it may be an organization not yet included in FundRef Registry. If you know of another name form or a parent organization name for a "not found" item on this list below, please share that information.

FundRef Name	FundRef Organization Name
King Abdullah University of Science and Technology	King Abdullah University of Science and Technology

Y.-P. Zhu, J. K. El-Demellawi, J. Yin,
S. Lopatin, Y. Lei, Z. Liu,
X. Miao, O. F. Mohammed,
H. N. Alshareef*1908392

**Unprecedented Surface Plasmon
Modes in Monoclinic MoO₂
Nanostructures**

Plasmonics control at nanoscale. Monoclinic MoO₂ nanostructures have been studied as promising substrates with a strong surface plasmon effect, along with controllable plasmonic energies through tuning nanostructures both chemically and in situ. Theoretical simulation and experimental measurements reveal that the surface plasmon is from the abundant free electrons in Mo d orbitals.

Unprecedented Surface Plasmon Modes in Monoclinic MoO₂ Nanostructures

Yun-Pei Zhu, Jehad K. El-Demellawi, Jun Yin, Sergei Lopatin, Yongjiu Lei, Zhixiong Liu, Xiaohu Miao, Omar F. Mohammed, and Husam N. Alshareef*

Developing stable plasmonic materials featuring earth-abundant compositions with continuous band structures, similar to those of typical metals, has received special research interest. Owing to the metal-like behavior, monoclinic MoO₂ nanostructures are recently found to support stable and intense surface plasmon (SP) resonances. However, no progress has been made on their energy and spatial distributions over individual nanostructures, nor the origin of their possibly existing specific SP modes. Here, various MoO₂ nanostructures are designed via polydopamine chemistry and managed to visualize multiple longitudinal and transversal SP modes supported by the monoclinic MoO₂, along with intrinsic interband transitions, using scanning transmission electron microscopy coupled with ultrahigh-resolution electron energy loss spectroscopy. The identified geometry-depending SP energies are tuned by either controlling the shape and thickness of MoO₂ nanostructures through their well-designed chemical synthesis, or by altering their length using a developed electron-beam patterning technique. Theoretical calculations reveal that the strong plasmonic behavior of the monoclinic MoO₂ is associated with the abundant delocalized electrons in the Mo d orbitals. This work not only provides a significant improvement in imaging and tailoring SPs of nonconventional metallic nanostructures, but also highlights the potential of MoO₂ nanostructures for micro-nano optical and optoelectronic applications.

Surface plasmon (SP) is the quantum of elementary excitation involving coherent oscillation of delocalized electrons, which originates from the matter–electromagnetic field (e.g., light) interaction at the matter–dielectric interface.^[1–4] However,

harvesting the full potential of SPs is highly limited to the ability to probe and control them at the interface of single nanostructures (e.g., nanorods, nanospheres, nanotubes).^[5–7] By virtue of the rapid development of nanotechnology that made it now possible to synthesize functional nanostructures with sizes smaller than the wavelength of the incident light, direct access to subwavelength spatial information has become essential. In stark contrast to conventional diffraction-limited optical techniques (e.g., optical near-field microscopy), which cannot provide such information,^[6,8,9] electron energy-loss spectroscopy (EELS) in a scanning transition electron microscope (STEM) can realize a uniquely high spectral- and spatial-resolution studies of an individual nanostructure.^[10,11] This technical superiority relates to the atomic-level spatial resolution of STEM and confined electromagnetic field induced by the swift electrons, while the electromagnetic field is spatially localized and spectrally broadband.

In spite of the dominance of the metallic nanostructures (e.g., Ag, Au, Cu, Al) that support propagating and localized plasmonic excitations, the ongoing research focuses on the development of new and superior plasmonic materials featuring low cost and substantial density of free conduction-band electrons.^[1,12,13] In this regard, highly doped semiconductors, perovskites, transparent metal oxides, and metal nitrides/dichalcogenides have been demonstrated as promising alternatives with strong SP resonance (SPR) effect,^[14–17] though the existence of energy gaps in these newly designed materials prohibits the continuous adjustment of plasmon polaritons. Several strategies including defective engineering and dimensional tuning have, however, been exploited to regulate the electronic band structures.^[18–21] For example, oxygen vacancies in transition metal oxides can deliver abundant outer d-orbital free electrons, leading to an improved SPR effect that can even compete with noble metals.^[20,21] Unfortunately, the easy removal of oxygen vacancies upon exposure to air under ambient conditions or light excitation in optical spectrometers can drastically lessen the SPR effect.^[21,22]

On the other hand, owing to their intrinsic quantum-confined electrons, excellent light confinement at the surfaces, and coexistence of quasi-2D surfaces and nanometer-scale edges, 2D nanostructures can potentially afford a rich set of

Dr. Y.-P. Zhu, J. K. El-Demellawi, Y. Lei, Z. Liu, Prof. H. N. Alshareef
Materials Science and Engineering
King Abdullah University of Science and Technology (KAUST)
Thuwal 23955-6900, Saudi Arabia
E-mail: husam.alshareef@kaust.edu.sa

Dr. J. Yin, Prof. O. F. Mohammed
Division of Physical Science and Engineering
King Abdullah University of Science and Technology (KAUST)
Thuwal 23955-6900, Saudi Arabia

Dr. S. Lopatin
King Abdullah University of Science and Technology (KAUST)
Core Labs
Thuwal 23955-6900, Saudi Arabia

Dr. X. Miao
Westlake University
Xihu District, Hangzhou, Zhejiang, China

The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/adma.201908392>.

DOI: 10.1002/adma.201908392

resonance modes. Therefore, a detailed investigation of all the possible SP modes supported by 2D nanostructures is of both theoretical and practical importance. To date, several 2D nanomaterials like MXenes, black phosphorus, graphene, and hexagonal boron nitride have been studied for plasmonic applications.^[23–26] The spectral and spatial characteristics of their plasmonic modes can be further tuned by tailoring their nanostructural morphology, i.e., geometry, size, and thickness.^[11] Thus far, most of the plasmon-related characterizations have dealt with chemically synthesized 2D nanostructures. However, those chemical synthesis strategies do not offer sufficient control over the shape, size, or the separation of the produced nanostructures.^[27,28] Beyond classical van der Waals layered materials like MXenes and graphene, the design of new 2D plasmonic nanostructures with favorable electronic structures and precisely controlled morphologies has been scarcely reported.

Monoclinic MoO₂ is an unusual transition metal oxide due to its metallic conductivity and high chemical stability. Accordingly, MoO₂ nanostructures hold a great promise for applications in electrochemical energy storage, electrocatalysis, sensing, and electrochromic displays.^[29–31] Because of the existence of a large number of free electrons at its surface, MoO₂ exhibits a strong SPR effect upon excitation, which endows it with improved detectivity when used as a substrate material for surface-enhanced Raman spectroscopy (SERS).^[32,33] Compared to the classical metallic nanostructures, monoclinic MoO₂ shows many superior properties, such as high chemical and thermal stability, increased melting point, and improved electronic conductivity. These features make MoO₂ a promising candidate for SPR-related practical applications due to its strong and stable SPR effect.^[32,33] Nevertheless, to the best of our knowledge, specific SPR modes possibly supported by the 2D MoO₂-based nanostructures have not been studied before, neither their shape- nor their size-dependence, let alone their spatial variability over the nanostructures.

Herein, we design a series of 2D MoO₂ nanostructures based on rational polydopamine chemistry, followed by altering their size using a well-controlled electron beam patterning technique. By employing state-of-the-art monochromated aberration-corrected STEM and high-resolution low-loss EELS, the fundamental SP mode, i.e., dipole, supported by single MoO₂ nanostructures (i.e., nanoribbons and nanoflakes), along with other higher-order modes spanning the visible–infrared regime, were visualized. Well-localized spatial distributions are generated by the STEM-EELS method on account of the absence of background blurring of the SP modes and artificial extension during the analysis. The dependence of the longitudinal SP modes, both optically forbidden and active, on the size and shape of monoclinic MoO₂ nanostructures is investigated systematically. A combination of density-functional theory (DFT) calculations and X-ray photoelectron spectroscopy (XPS) further illustrates the origin of SPs in monoclinic MoO₂ nanostructures.

The typical synthesis of 2D MoO₂ nanostructures (e.g., nanoribbons, nanoflakes) generally involves tedious chemical methods, for example, the reduction of presynthesized 2D MoO₃ matrixes by high-temperature calcination (>600 °C) in H₂ ambient or hydrothermal treatment using massive reductants (e.g., polymers, alcohol), and the direct growth on target

substrates via chemical vapor deposition (CVD).^[34–36] These strategies usually result in hardly controllable morphologies and large particle sizes. In this work, an alternative strategy relying on dopamine chemistry has been developed to prepare 2D MoO₂ nanoribbons (Figure S1, Supporting Information). The primary advantage of catechol-containing dopamine is its easy attachment to the substrate surfaces.^[37,38] In addition, the mild oxidation ability of the MoO₃ nanoribbons (Figure S2, Supporting Information), synthesized by a hydrothermal process can initiate the deposition of dopamine monomers and their spontaneous self-polymerization at room temperature (Figure S3, Supporting Information).^[39] The whole reaction is mild without involving harsh reaction conditions or additional oxidation catalysts, leaving well-retained nanoribbon morphology even after the polydopamine coating process. A subsequent pyrolysis process in argon atmosphere can reduce MoO₃ to MoO₂ through carbothermal reaction,^[40] finally producing well-structured MoO₂ nanoribbons (Figures S4 and S5, Supporting Information). Importantly, the carbothermal reaction strategy based on polydopamine chemistry can be extended to prepare other MoO₂ nanostructures, e.g., MoO₂ nanoflakes (Figure S6, Supporting Information), indicating the potential versatility of our chemical strategy.

According to its refined X-ray diffraction (XRD) pattern (Figure 1a), the as-synthesized MoO₂ shows a monoclinic structure (space group: *P*₂₁/*c*), along with a monoclinic angle of 120.92° and lattice constants of *a* = 5.5305 Å, *b* = 4.8484 Å, and *c* = 5.6160 Å. In this distorted rutile structure (Figure 1b, viewed along the *a*-axis), O atoms are packed closely into octahedrons with Mo atoms occupying half of the octahedral voids. Noticeably, the Mo coordination does not follow a strict octahedral form, and there are two different series of Mo–O bond lengths (inset of Figure 1a), delivering a local symmetry of *D*_{2h}.^[32] The Mo–Mo distances along the *a*-axis of the deformed rutile alternate give rise to two Mo-to-Mo bond lengths of 2.578 and 3.063 Å (Figure 1c, viewed along the *b*-axis). This atomic configuration leads to two distinct O coordination environments (inset of Figure 1a), similar to the cases found in the metallic phases of TcO₂, WO₂, and α-ReO₂.^[41] The monoclinic nature of the synthesized MoO₂ was further evidenced by the corresponding Raman spectrum displayed in Figure S7 (Supporting Information). The two peaks located at 739 and 572 cm^{−1} are assigned to the Mo–O bond vibrational modes (i.e., Mo–O₁ and Mo–O₂), while other fingerprint peaks correspond to the photon vibrational modes of the monoclinic-phase MoO₂.^[33,40]

Indeed, the octahedral component of the ligand field induced by the molybdenum cations makes the 4d levels split into e_g and t_{2g} (Figure S8, Supporting Information).^[42] Nonetheless, the chain structure of monoclinic MoO₂ phase makes it probable to distinguish between the in-plane single t_{2g} orbital (referred to the shared octahedral edges and further denoted as the t_{||} orbital) and the other two t_{2g} orbitals that are perpendicular to the plane (correspondingly, denoted as the t_⊥ orbitals).^[42] In the distorted rutile structure, the t_{||} orbital possesses lobes that point along the *c*-axis, while t_⊥ orbitals on the neighboring Mo sites can interact in a σ-like manner to generate antibonding and bonding states. Notably, the band originating from the in-phase t_{||} overlap splits away from the remaining bands, which is related to the t_{2g} levels with less perturbation. For typical

Figure 1. a) Rietveld refined XRD pattern of the synthesized hybrid of MoO_2 and carbon nanosheets. Experimental data: orange circle, calculated pattern: blue line, and difference profile: gray line. Inset of (a) shows a distorted MoO_6 octahedron with the bond ordering and bond length highlighted. b, c) Crystal structure of monoclinic MoO_2 viewed along the a -axis and b -axis. d, e) HAADF-STEM and f) atomic-resolution HAADF-STEM images of the MoO_2 nanoribbons. g) Core-loss EELS spectrum and h) EELS elemental mapping of a single MoO_2 nanoribbon with a thickness of ≈ 62 nm. The dashed lines in (g) are guidelines for the characteristic Mo- $M_{5,4}$, C-K, Mo- $M_{3,2}$, O-K, Mo- $L_{3,2}$, and Mo- L_1 edge onsets at ≈ 227 , 285, 392, 531, 2526, and 2865 eV, respectively.

d^1 compounds like low-temperature VO_2 polymorph,^[41] the σ -bonding $t_{||}$ band is fully occupied, but the other t_{2g} -derived levels are still empty. This electron occupation behavior accounts for the nonmetallic property of these compounds and explains the driving force for structural distortion regarding the stabilization of two electrons per metal pair through the

metal–metal bonding. Differently, for the monoclinic d^2 -type MoO_2 , one extra electron per Mo cation can partially populate the higher $t_{\perp}$ bands, thereby inducing the Mo–Mo bonding and metallic conductivity.

The high-angle annular dark-field (HAADF) scanning transmission electron microscopy (STEM) images show that the

nanoribbon morphology can be well retained after the reduction from MoO₃ to MoO₂ (Figure 1d,e). The atomic-resolution STEM image reveals the well-defined tunnels when viewed from the (100) direction, along with a lattice spacing of 0.33 nm that can be indexed to the (011) planes of monoclinic MoO₂ (Figure 1f). The core-loss EELS spectrum (Figure 1g) of a single MoO₂ nanoribbon shows the characteristic ionization edges of M and O.^[43,44] The corresponding EELS mapping (Figure 1h) highlights the homogeneous elemental distribution over the nanoribbons. The thickness of either the MoO₂ nanoribbons (≈ 60 – 70 nm) or nanoflakes (≈ 15 nm), estimated using the log-ratio method,^[23,45] was found to be systematically uniform (refer to the Supporting Information for more details). The core-loss EELS and XPS spectra (Figure 1g and Figure S5, Supporting Information) confirm the presence of phase-pure MoO₂ without carbon doping or carbon layer coating.

Remarkably, we were able to detect various distinct low-loss signals (with subtracted zero-loss peak (ZLP)) acquired on our MoO₂ nanostructures, at energies as low as 0.1 eV, thanks to the ultrahigh-resolution EELS technique.^[46,47] Figure 2a displays the low-loss EELS spectra of an ≈ 71 nm-thick MoO₂ nanoribbon (inset of Figure 2a) with five features identified at 0.14, 0.24, 0.35, 1.82, and 3.32 eV. The corresponding EELS fitted intensity maps illustrate the spatial distribution of the detected spectral feature maxima, respectively (Figure 2b). The spatial harmonic distribution together with the high energy dissipation of the first three EELS signals indicates the multipolar longitudinal modes arising from the free electron gas oscillations along the lateral edges of the nanoribbon.^[3,23] The signals at 0.14, 0.24, and 0.35 eV are construed as the dipole, quadrupole, and hexapole longitudinal modes, respectively, of the stationary SPs delivered by the monoclinic MoO₂ nanoribbon. Apparently, the residual, amorphous carbon nanosheets that are randomly distributed between the monoclinic MoO₂ nanoribbons did not contribute to the detected SPR effect as the electron beam was solely focused on isolated single nanoribbons. Analogous

investigations of specific SP modes have been mostly limited to metallic 2D nanostructures.^[8,48,49] Nonetheless, similar multipolar modes have been recently found for nonclassical metallic 2D nanostructures, e.g., MXenes, having sufficient free electron density.^[23,50,51]

The additional signal at 1.82 eV, with its peculiar homogeneous distribution (Figure 2b), is attributed to the transversal SP mode, which is excited by the incident electromagnetic field perpendicular to the main axis of the nanoribbon. In contrast to transversal SP modes, longitudinal multipolar modes are characteristic with their variant energy and spatial distributions across each nanostructure. They strongly depend on the geometrical aspects (i.e., shape, size, and thickness) of the studied nanostructures,^[52,53] which can be confirmed by the EELS fitted intensity maps of other MoO₂ nanoribbons (Figure 3 and Figure S9, Supporting Information) and nanoflakes (Figure S10, Supporting Information). On the other hand, the transversal SP mode is geometrically independent (Figures S9 and S10, Supporting Information), and is mainly related to the inherent free electron gas concentration. Whereas the energy of the longitudinal multipolar modes is noticeably red- and blueshifted for longer and shorter lateral edges, respectively.

Aside from the detected plasmonic features, the absorption edge onset at 3.32 eV is attributed to interband transitions (IBT) within the electronic structure of monoclinic MoO₂. The corresponding EELS map of the IBT (Figure 2b) shows a homogeneous spatial distribution over the entire nanoribbon. Furthermore, it is worth mentioning that we have also conducted in situ heating in conjunction with STEM-EELS to investigate the plasmonic behavior of the MoO₂ nanoribbons at elevated temperatures (590 and 900 °C). Strikingly, the plasmonic features of our nanoribbons remained unaltered after annealing at both temperatures (Figure 3 and Figure S9, Supporting Information), emphasizing the absence of phase transformation throughout the annealing process (Figures S16 and S17, Supporting Information).

Figure 2. a) ZLP-subtracted low-loss EELS spectra acquired on an ≈ 71 nm-thick monoclinic MoO₂ nanoribbon. The signals are normalized to the peak at 1.82 eV and magnified by a factor of 2 above 3 eV. Inset: HAADF-STEM image of the MoO₂ nanoribbon supported by a Si₃N₄ membrane. b) EELS fitted intensity maps of the corresponding longitudinal SP modes, i.e., dipole (0.14 eV), quadrupole (0.24 eV), and hexapole (0.35 eV), in addition to the transversal SP mode at 1.82 eV and the IBT with an onset of 3.32 eV.

Figure 3. a) (i and ii) HAADF-STEM images of an ≈ 63 nm-thick MoO₂ nanoribbon (annealed at 590 °C) before and after being irradiated (at the center) by a 300 kV focused electron beam (50 nA beam current), respectively. (iii) EELS fitted intensity maps of the corresponding longitudinal SP modes, i.e., dipole (0.11 eV), quadrupole (0.22 eV), and hexapole (0.32 eV), transversal SP mode (1.82 eV), and IBT (3.32 eV) supported by the nanoribbon in (ii). Note that no shift has been recorded in the SP energies before and after annealing. (iv) Magnified image of the damaged area denoted by the yellow-dashed rectangle in (ii). (v and vi) SAED patterns obtained from the undamaged and damaged areas marked by the red and greenish-blue squares in (iii), respectively. b) (i) HAADF-STEM image of an ≈ 70 nm-thick MoO₂ nanoribbon. The two orange stripes mark the area subjected to the irradiation. (ii and iii) HAADF-STEM images of the two shorter nanoribbons cut from the nanoribbon in (i), along with the corresponding EELS fitted intensity maps of the independent supported longitudinal SPs, i.e., dipole (0.22 eV) and quadrupole (0.35 eV) for the shorter nanoribbon, and quadrupole (0.26 eV) and hexapole (0.30 eV) for the longer nanoribbon. The white dotted boundaries delineate the edges of the nanoribbons in panels (a) and (b).

Based on the aforementioned discussions, we have demonstrated the spatial and energy distributions of various longitudinal modes, which are related to their confinement on the surfaces and brinks of the 2D nanoribbons. We have also illustrated the geometry dependence of the SP energies of the longitudinal modes supported by the 2D MoO₂ nanostructures (Table S1, Figures S10 and S12–S15, Supporting Information). In the case of the nanoribbons, the increase in the length leads to an obvious redshift in the energy of a given longitudinal SP mode, which is associated with the retardation effect.^[23,48] Likewise, the reduction in the thickness would also induce a redshift in the SP energies.^[48] However, it has not escaped our notice that the control of the energy of the specific SP modes sustained by the MoO₂ nanostructures is vastly limited to their random size distribution owing to the nature of their chemical synthesis route. Thus, there is a need to exploit new strategies to precisely control the energy of the supported SPs, by geometrically manipulating the propagating electromagnetic wave along the edges of the nanoribbons. For that, we intended to slit our nanoribbons to specific lengths by sputtering particular areas of the nanoribbons using a 300 kV high-current-focused electron beam. Ultimately, we believe that after a certain exposure time, the focused electron beam irradiation would be sufficient

to completely cleave the nanoribbons for the sake of controlling the size of the nanostructures. To validate our hypothesis, we irradiated several MoO₂ nanoribbons for different periods of time. The irradiation was performed in STEM mode with a beam current of 50 nA (≈ 1 nm probe size), and an irradiation rate of 0.1 s pixel⁻¹ (pixel size: 1 nm). Figure 3a (i and ii) shows the HAADF images of an ≈ 63 nm-thick MoO₂ nanoribbon, before and after irradiation by a high-energy-focused electron beam for 70 min, along with the low-loss EELS maps of the supported SP modes and IBT (Figure 3a (iii)). A magnified image of the damaged area ($\approx 200 \times 200$ nm²) demonstrates that 70 min of electron beam irradiation (i.e., electron beam dose) were not long enough to destroy the nanoribbon (Figure 3a (iv)), but they were enough to induce an obvious crystalline-to-amorphous phase transformation. This is clearly indicated by the selected area electron diffraction (SAED) patterns obtained at each side of the damaged/undamaged interface (Figure 3a (v and vi)), as well as the high-resolution STEM image of the interface (Figure S18, Supporting Information). Interestingly, this irradiation-induced damage did not interrupt the propagation of the stationary SP wave along the edges of the nanoribbon, which is manifested by the inviolate dipole, quadrupole, and hexapole SP modes at 0.11, 0.22, and 0.32 eV, respectively

(Figure 3a (iii)). It, however, resulted in strong damping in the SPs as revealed by the waning intensity acquired over the damaged area. Nevertheless, the energy of the sustained SPs remained unchanged, even for the transversal mode that solely depends on the intrinsic characteristics of monoclinic MoO₂, i.e., free electron gas density.

To progress with the resizing of the synthesized nanoribbons, we irradiated another nanoribbon (Figure 3b (i)) for longer exposure time using a slower scanning rate (i.e., 1 s pixel⁻¹) until the material was completely sputtered. As a matter of fact, we did not irradiate the whole area ($\approx 500 \times 200$ nm²) between the two shorter nanoribbons. Instead, we only bombarded the nanoribbon at the sides of the removed part as denoted by the horizontal orange stripes in Figure 3b (i), essentially employing a highly focused electron beam as a 1 nm precision cutting tool. Once the irradiated volume was entirely demolished, the isolated intermediate slab ($\approx 500 \times 200$ nm²) instantaneously peeled off the supporting Si₃N₄ membrane, giving rise to two isolated single MoO₂ nanoribbons supporting the oscillation of two distinct sets of SP modes (Figure 3b (ii and iii)). In principle, altering the size, i.e., length in our case, of the nanoribbons has induced a change in the oscillation frequency of the free electron gas,^[46,49,53] leading to a change in the SP energy of the longitudinal modes supported by the nanoribbons. In particular, the shortening of the lateral length has prompted a blueshift in the SP energy of the supported mode. This is clearly manifested in Figure 3b (ii and iii), where each of the nanoribbons sustains a quadrupole mode, with its ubiquitous localization at the middle of the lateral sides,^[48] yet at different SP energy; the shortest one (Figure 3b (ii)) allows for a quadrupole mode at 0.35 eV, while that of the longer appears at 0.26 eV.

Fundamentally, the gradual irradiation-induced slitting of the MoO₂ nanoribbon has been attained as follows: the high-energy-focused electron beam irradiation generated a defect clustering in the monoclinic structure accompanied by the nucleation of amorphous islands within the irradiated volume. The onset of both irradiation-generated defect clustering and the solid-state amorphization appears to be stimulated by local energy and the elastic instabilities between the amorphous islands and the crystal. Hence, the interaction of the electron-beam-generated defects with the interfaces between the crystal and these islands could either induce their shrinkage or growth depending on the electron beam flux.^[54] Such a dependence on the electron beam flux is related to the competition between defect accretion in the collision cascade and the shrinkage associated with the defect annihilation from the damaged volume. Thus, when the nanoribbons are irradiated for a shorter period of time (i.e., 70 min using a faster rate of 0.1 s pixel⁻¹), the defect clustering in the amorphized region has led to an increase in the thickness of the damaged volume (obtained at the center) from ≈ 63 to ≈ 75 nm, which explains the blurriness of the HAADF image obtained at the unirradiated crystalline areas (Figure 3a (ii and iv)). However, after longer exposure time (i.e., 1 s pixel⁻¹), the balance was tilted in favor of the shrinkage of the amorphized volume owing to the gradual annihilation of the defects.^[55]

Next, to further dissect the origin of the aforementioned SPR effect arising from the collective oscillations of free electron

gas confined at the material surface,^[1–11] we conducted DFT calculations for the monoclinic MoO₂. Figure 4a displays the imaginary (ϵ_1) and real (ϵ_2) parts of the dielectric function of the monoclinic MoO₂. The ϵ_2 turns negative at wavelengths above 200 nm, indicating the onset of free electron gas oscillations.^[3,6,23] This correlates very well with our interpretation of the experimental low-loss EELS results. Furthermore, the electron localization function (ELF) was calculated and the corresponding free electron gas distribution are depicted in Figure 4b, showing that the high free electron gas density clearly favors the formation of nonpolar metallic Mo–Mo bonds. The existence of abundant free electrons has endowed monoclinic MoO₂ with the ability to exhibit a strong SPR effect. The electronic band structure of monoclinic MoO₂ was computed to further illustrate its electronic states (Figure 4c and Figure S19, Supporting Information). Of note, we can observe two Mo-4d states lying below the Fermi energy (E_F) level across the entire Brillouin zone, which results from the split-off bonding $t_{||}$ states. Two more Mo-4d bands are located below the E_F along the E–A–B–D and Γ –Y–C directions, but these two bands push through the E_F along the directions of C–E, Z–D, and Γ –Z. The effect of these crossings leads to the metallic nature of the monoclinic MoO₂.

We further calculated the projected density of states (PDOS) of monoclinic MoO₂ to study the orbital contributions of Mo and O to the band structure. The PDOS can be separated into three regions, marked as I–III in Figure 4d. Both regions I (above the E_F level) and II (between -2 eV and E_F) are mainly composed of Mo d orbitals with two sharp peaks at -1.32 and -0.51 eV appeared in region II. The lone orbitals fully occupied by Mo- d_{xz} and Mo- d_{yz} help to generate the peak situated at -1.32 eV, while the PDOS peak at -0.51 eV is a result of the non-bonding state dominated by the Mo- $d_{x^2-y^2}$ orbital.^[56] In region III (ranging from -8 to -2 eV), the occupied states are dominated by O p orbitals, together with some significant hybridization with Mo d orbitals. The PDOS in regions II and III are related to the partially occupied conduction band (CB) and fully occupied B₋₁ band, respectively.^[57] The B₋₁ band is from low-lying Mo–O₁ and Mo–O₂ bonding states, which is consistent with the analysis of the XRD pattern and Raman spectrum that prove the existence of two types of Mo–O bonding (Figure 1a and Figure S6, Supporting Information).

The valence-band XPS (VB-XPS) spectrum is in good agreement with the simulated PDOS (Figure 4e). An intense and relatively narrow peak shows up above the O 2p VB (i.e., below -2.5 eV) as in the PDOS computation. This is related to the π - and σ -bonding states: the π -bonding has limited capability to completely split off the $t_{||}$ (π) bands from the rest of the unoccupied Mo 4d orbitals to generate an insulator. Importantly, the E_F level is situated in a remarkable trough in the DOS. Notably, there are two signals at 1.51 and 0.53 eV below the E_F level within the region of Mo 4d band, which are almost equal to the corresponding calculated values of 1.32 and 0.51 eV, respectively.

The Mo 3d core level of monoclinic MoO₂ nanoribbons appears to consist of an intrinsic feature of MoO₂, and a spin-orbit doublet attributed to Mo⁶⁺ (232.5 and 235.6 eV). The doublets at 233.3 and 229.4 eV (marked as s in Figure 4f) correspond to well-screened Mo⁴⁺ states, wherein the localized level

Figure 4. a) Calculated dielectric function of monoclinic MoO₂. b) 2D ELF mapping of monoclinic MoO₂. The gradual color change of the bar from blue to red indicates increased charge localization. c) Calculated electronic band structure, d) projected density of states, e) valence-band XPS spectrum, and f) Mo 3d core level of the monoclinic MoO₂. The red lines in (c)–(e) denote the Fermi energy (E_F).

is occupied by itinerant conduction electrons. The relatively broader and weaker deconvoluted components at 234.1 and 231.2 eV are assigned to unscreened final states of Mo⁴⁺ (labeled *u* in Figure 4f), in which the localized level stays empty.^[58] The energy difference between unscreened and screened Mo 3d_{5/2} is 1.8 eV, which is, indeed, close to the plasmonic energy of 1.82 eV for the monoclinic MoO₂ nanoribbons determined by low-loss EELS spectrum (Figure 2a). Therefore, the unscreened peaks may be considered as strong plasmonic satellites, similar to the model first raised by Chazalviel.^[59] In most cases, the intrinsic satellites have been associated with Mo⁵⁺ species (i.e., Mo₂O₅) as a result of ignoring the narrow-band metallic nature of monoclinic MoO₂ as well as the nonexistence of Mo⁵⁺ oxide bulk phase, especially under ambient conditions.^[50,60] The feature of satellites in the Mo 3d region of our monoclinic MoO₂ nanostructures is similar to the case of Ru 3d core level of conductive, metallic RuO₂.^[61] This typical metallic behavior of metal oxide showed an angular variation in the satellite intensity, which also mirrored the main peak. This result confirmed that the satellites were derived from the Ru ions that occupied the identical sites to those responsible for the main peaks. Therefore, the Ru 3d core level of RuO₂ has possessed the intrinsic satellite structure, which was not associated with the ill-defined surface states featuring valences higher than 5+.

More evidence for the aforementioned interpretations can be found in the O 1s core level of our monoclinic MoO₂ nanoribbons (Figure S20, Supporting Information). The

corresponding O 1s core level exhibits an energy gap of 1.45 eV between the main peak and the strong satellite, which is lower compared to the satellite energy for the Mo 3d core level. However, it is reasonable to see this difference since the conduction band of monoclinic MoO₂ is mainly comprised of Mo d orbitals (Figure 4c,d). Accordingly, the screening response upon forming an O 1s core hole would be different compared to that of the formation of a Mo 3d core hole. Importantly, the similar O 1s core level can be found for other metallic transition-metal oxides like defective PbO_{2-x},^[59] Sb-doped SnO₂,^[62] and sodium tungsten bronze (Na_xWO₃).^[63]

In line with the substantial resemblance between the above-mentioned theoretical calculations and XPS measurements, monoclinic MoO₂ was confirmed to be metallic due to the abundance of free electrons from the Mo d orbitals. Importantly, the Fermi level of monoclinic MoO₂ is found to be located in a deep trough in the density of states. This behavior is reminiscent of frequently studied plasmonic metal nanostructures,^[1–13] allowing for continuous tuning of the plasmon polaritons because of the absence of energy bandgaps (Figures 2 and 3).

In summary, we have accomplished a rational synthesis protocol of different monoclinic MoO₂ nanostructures using a simple chemical strategy. More importantly, by using a spatially resolved low-loss STEM-EELS, we managed, for the first time, to the extent of our knowledge, to map several distinctive multipolar SP modes supported by single MoO₂ nanostructures. Moreover, the SP energy of the detected modes was

tuned by precisely controlling the length of the MoO₂ nano-ribbons using a potentially promising electron beam patterning technique. The pronounced SPR effect was confirmed, both theoretically and experimentally, to be related to the presence of abundant free electrons in Mo d orbitals. We believe that our findings hold great promise for comprehending plasmon physics of readily controllable metallic nanostructures and open a new avenue for developing plasmonic engineering.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

Y.-P.Z. and J.K.E.-D. contributed equally to this work. The research reported in this publication was supported by King Abdullah University of Science and Technology (KAUST).

Conflict of Interest

The authors declare no conflict of interest.

Keywords

energy mapping, high-resolution EELS, nanostructure patterning, STEM, surface plasmon origin

Received: December 22, 2019
Revised: February 16, 2020
Published online:

- [1] T. Low, P. Avouris, *ACS Nano* **2014**, *8*, 1086.
- [2] A. N. Grigorenko, M. Polini, K. S. Novoselov, *Nat. Photonics* **2012**, *6*, 749.
- [3] M. Kociak, O. Stéphan, *Chem. Soc. Rev.* **2014**, *43*, 3865.
- [4] R. P. Puchert, F. Steiner, G. Plechinger, F. J. Hofmann, I. Caspers, J. Kirschner, P. Nagler, A. Chernikov, C. Schüller, T. Korn, J. Vogelsang, S. Bange, J. M. Lupton, *Nat. Nanotechnol.* **2017**, *12*, 637.
- [5] C. Matricardi, C. Hanske, J. L. Garcia-Pomar, J. Langer, A. Mihi, L. M. Liz-Marzán, *ACS Nano* **2018**, *12*, 8531.
- [6] V. G. Kravets, A. V. Kabashin, W. L. Barnes, A. N. Grigorenko, *Chem. Rev.* **2018**, *118*, 5912.
- [7] J. Tang, J. Xia, M. Fang, F. Bao, G. Cao, J. Shen, J. Evans, S. He, *Nat. Commun.* **2018**, *9*, 1705.
- [8] J. Nelayah, M. Kociak, O. Stéphan, F. J. G. Abajo, M. Tencé, L. Henrard, D. Taverna, I. Pastoriza-Santos, L. M. Liz-Marzán, C. Colliex, *Nat. Phys.* **2007**, *3*, 348.
- [9] A. F. Koenderink, A. Alù, A. Polman, *Science* **2015**, *348*, 516.
- [10] S. Raza, S. Kadkhodazadeh, T. Christensen, M. D. Vece, M. Wubs, N. A. Mortensen, N. Stenger, *Nat. Commun.* **2015**, *6*, 8788.
- [11] Y. Wu, G. Li, J. P. Camden, *Chem. Rev.* **2018**, *118*, 2994.
- [12] X. Yang, Z. Sun, T. Low, H. Hu, X. Guo, F. J. G. Abajo, P. Avouris, Q. Dai, *Adv. Mater.* **2018**, *30*, 1704896.
- [13] C. Zhan, X. J. Chen, J. Yi, J. F. Li, D. Y. Wu, Z. Q. Tian, *Nat. Rev. Chem.* **2018**, *2*, 216.
- [14] C. S. Granerød, S. R. Bilden, T. Aarholt, Y. F. Yao, C. C. Yang, D. C. Look, L. Vines, K. M. Johansen, Ø. Prytz, *Phys. Rev. B* **2018**, *98*, 115301.
- [15] L. Shi, W. Zhou, Z. Li, S. Koul, A. Kushima, Y. Yang, *ACS Nano* **2018**, *12*, 6335.
- [16] S. Butun, S. Tongay, K. Aydin, *Nano Lett.* **2015**, *15*, 2700.
- [17] S. Exarhos, A. Alvarez-Barragan, E. Aytan, A. A. Balandin, L. Mangolini, *ACS Energy Lett.* **2018**, *3*, 2349.
- [18] Y. Liu, C. Xiao, Z. Li, Y. Xie, *Adv. Energy Mater.* **2016**, *6*, 1600436.
- [19] Y. P. Zhu, C. Xia, Y. Lei, N. Singh, U. Schwingenschlögl, H. N. Alshareef, *Nano Energy* **2019**, *56*, 357.
- [20] K. Manthiram, A. P. Alivisatos, *J. Am. Chem. Soc.* **2012**, *134*, 3995.
- [21] S. Cong, Y. Yuan, Z. Chen, J. Hou, M. Yang, Y. Su, Y. Zhang, L. Li, Q. Li, F. Geng, Z. Zhao, *Nat. Commun.* **2015**, *6*, 7800.
- [22] G. Xi, S. Ouyang, P. Li, J. Ye, Q. Ma, N. Su, H. Bai, C. Wang, *Angew. Chem., Int. Ed.* **2012**, *51*, 2395.
- [23] J. K. El-Demellawi, S. Lopatin, J. Yin, O. F. Mohammed, H. N. Alshareef, *ACS Nano* **2018**, *12*, 8485.
- [24] Q. Guo, R. Yu, C. Li, S. Yuan, B. Deng, F. J. G. Abajo, F. Xia, *Nat. Mater.* **2018**, *17*, 986.
- [25] M. A. Huber, F. Mooshammer, M. Plankl, L. Viti, F. Sandner, L. Z. Kastner, T. Frank, J. Fabian, M. S. Vitiello, T. L. Cocker, R. Huber, *Nat. Nanotechnol.* **2017**, *12*, 207.
- [26] A. J. Giles, S. Dai, I. Vurgaftman, T. Hoffman, S. Liu, L. Lindsay, C. T. Ellis, N. Assefa, I. Chatzakis, T. L. Reinecke, J. G. Tischler, M. M. Fogler, J. H. Edgar, D. N. Basov, J. D. Caldwell, *Nat. Mater.* **2018**, *17*, 134.
- [27] Y. Chen, Z. Fan, Z. Zhang, W. Niu, C. Li, N. Yang, B. Chen, H. Zhang, *Chem. Rev.* **2018**, *118*, 6409.
- [28] T. Low, A. Chaves, J. D. Caldwell, A. Kumar, N. X. Fang, P. Avouris, T. F. Heinz, F. Guinea, L. Martin-Moreno, F. Koppens, *Nat. Mater.* **2017**, *16*, 182.
- [29] X. Hu, W. Zhang, X. Liu, Y. Mei, Y. Huang, *Chem. Soc. Rev.* **2015**, *44*, 2376.
- [30] J. K. Shon, H. S. Lee, G. O. Park, J. Yoon, E. Park, G. S. Park, S. S. Kong, M. Jin, J. M. Choi, H. Chang, S. Doo, J. M. Kim, W. S. Yoon, C. Pak, H. Kim, G. D. Stucky, *Nat. Commun.* **2016**, *7*, 11049.
- [31] Y. Jin, H. Wang, J. Li, X. Yue, Y. Han, P. K. Shen, Y. Cui, *Adv. Mater.* **2016**, *28*, 3785.
- [32] Q. Zhang, X. Li, Q. Ma, Q. Zhang, H. Bai, W. Yi, J. Liu, J. Han, G. Xi, *Nat. Commun.* **2017**, *8*, 14903.
- [33] S. H. Lee, H. Nishi, T. Tatsuma, *Chem. Commun.* **2017**, *53*, 12680.
- [34] O. Melo, L. García-Pelayo, Y. González, O. Concepción, M. Manso-Silván, R. López-Nebreda, J. L. Pau, J. C. González, A. Climent-Fontae, V. Torres-Costa, *J. Mater. Chem. C* **2018**, *6*, 6799.
- [35] T. Li, M. Beidaghi, X. Xiao, L. Huang, Z. Hu, W. Sun, X. Chen, Y. Gogotsi, J. Zhou, *Nano Energy* **2016**, *26*, 100.
- [36] N. S. Vorobeva, A. Lipatov, D. S. Muratov, A. Sinitskii, *Nanotechnology* **2018**, *29*, 505707.
- [37] S. Hong, J. Kim, Y. S. Na, J. Park, S. Kim, K. Singha, G.-I. Im, D. K. Han, W. J. Kim, H. Lee, *Angew. Chem., Int. Ed.* **2013**, *52*, 9187.
- [38] T. Liu, K. C. Kim, B. Lee, Z. Chen, S. Noda, S. S. Jang, S. W. Lee, *Energy Environ. Sci.* **2017**, *10*, 205.
- [39] Y. Liu, K. Ai, L. Lu, *Chem. Rev.* **2014**, *114*, 5057.
- [40] C. Zhang, X. Zou, Z. Du, J. Gu, S. Li, B. Li, S. Yang, *Small* **2018**, *14*, 1703960.
- [41] D. B. Rogers, R. D. Shannon, A. W. Sleight, J. L. Gillson, *Inorg. Chem.* **1969**, *8*, 841.
- [42] J. B. Goodenough, *Prog. Solid State Chem.* **1971**, *5*, 145.
- [43] L. Lajaunie, F. Boucher, R. Dessapt, P. Moreau, *Ultramicroscopy* **2015**, *149*, 1.
- [44] B. L. Kaiser, D. Merki, H. Vrubel, S. Gul, V. K. Yachandra, X. Hu, J. Yano, *J. Am. Chem. Soc.* **2015**, *137*, 3141.
- [45] R. F. Egerton, *Electron Energy-Loss Spectroscopy in the Electron Microscope*, 3rd ed., Springer, New York **2011**.

- Q4
- [46] A. A. Govyadinov, A. Konečná, A. Chuvilin, S. Vélez, I. Dolado, A. Y. Nikitin, S. Lopatin, F. Casanova, L. E. Hueso, J. Aizpurua, R. Hillenbrand, *Nat. Commun.* **2017**, 8, 95.
- [47] S. Lopatin, B. Cheng, W.-T. Liu, M.-L. Tsai, J.-H. He, A. Chuvilin, *Ultramicroscopy* **2018**, 184, 109.
- [48] J. Nelayah, M. Kociak, O. Stephan, N. Geuquet, L. Hernard, F. J. G. de Abajo, M. Tencé, I. Pastoriza-Santos, L. M. Liz-Marzan, C. Colliex, *Nano Lett.* **2010**, 10, 902.
- [49] R. G. Hobbs, V. R. Manfrinato, Y. Yang, S. A. Goodman, L. Zhang, E. A. Stach, K. K. Berggren, *Nano Lett.* **2016**, 16, 4149.
- [50] D. B. Velusamy, J. K. El-Demellawi, A. E. El-Zohry, A. Giugni, S. Lopatin, M. N. Hedhili, A. E. Mansour, E. D. Fabrizio, O. F. Mohammed, H. N. Alshareef, *Adv. Mater.* **2019**, 31, 1807658.
- [51] S. Lopatin, J. El-Demellawi, H. Alshareef, *Microsc. Microanal.* **2018**, 24, 1578.
- [52] J. A. Scholl, A. L. Koh, J. A. Dionne, *Nature* **2012**, 483, 421.
- [53] S. Eustis, M. A. El-Sayed, *Chem. Soc. Rev.* **2006**, 35, 209.
- [54] L. Pelaz, L. A. Marqués, J. Barbolla, *J. Appl. Phys.* **2004**, 96, 5947.
- [55] D. Chen, J. Wang, T. Chen, L. Shao, *Sci. Rep.* **2013**, 3, 1450.
- [56] Z. Hu, G. Liu, X. Chen, Z. Shen, J. C. Yu, *Adv. Funct. Mater.* **2016**, 26, 4445.
- [57] X. X. Xu, C. Randorn, P. Efstathiou, J. T. S. Irvine, *Nat. Mater.* **2012**, 11, 595.
- [58] D. O. Scanlon, G. W. Watson, D. J. Payne, G. R. Atkinson, R. G. Egdell, D. S. L. Law, *J. Phys. Chem. C* **2010**, 114, 4636.
- [59] J. N. Chazalviel, M. Campagna, G. K. Wertheim, H. R. Shanks, *Phys. Rev. B* **1977**, 16, 697.
- [60] C. R. Clayton, Y. C. Lu, *Surf. Interface Anal.* **1989**, 14, 66.
- [61] D. J. Morgan, *Surf. Interface Anal.* **2015**, 47, 1072.
- [62] R. G. Egdell, J. Rebane, T. J. Walker, D. S. L. Law, *Phys. Rev. B* **1999**, 59, 1792.
- [63] D. J. Payne, R. G. Egdell, D. S. L. Law, P. A. Glans, T. Learmonth, K. E. Smith, J. H. Guo, A. Walsh, G. W. Watson, *J. Mater. Chem.* **2007**, 17, 267.

Manuscript No. _____

Please send me and bill me for

no. of **reprints** via ☐ airmail (+ 25 Euro)
☐ surface mail

no. of **copies of this issue**
(1 copy: 28 Euro)
via ☐ airmail (+ 25 Euro)
☐ surface mail

☐ **high-resolution PDF file** (330 Euro).

My e-mail address:

Please note: It is not permitted to present the PDF file on the internet or on company homepages

★**Special Offer**★ If you order 200 or more reprints you will get a PDF file for half price.

Information regarding VAT

Please note that from German sales tax point of view, the charge for **Reprints, Issues or Posters** is considered as "supply of goods" and therefore, in general, such delivery is a subject to German sales tax. However, this regulation has no impact on customers located outside of the European Union. Deliveries to customers outside the Community are automatically tax-exempt. Deliveries within the Community to institutional customers outside of Germany are exempted from the German tax (VAT) only if the customer provides the supplier with his/her VAT number. The VAT number (value added tax identification number) is a tax registration number used in the countries of the European Union to identify corporate entities doing business there. It starts with a country code (e.g. FR for France, GB for Great Britain) and follows by numbers.

Cover Posters

Posters are available of all the published covers and frontispieces in two sizes

- ☐ DIN A2 42 x 60 cm / 17 x 24in (one copy: **39 Euro**)
☐ DIN A1 60 x 84 cm / 24 x 33in (one copy: **49 Euro**)

Postage for shipping posters overseas by airmail:
+ 25 Euro

Postage for shipping posters within Europe by surface mail:
+ 15 Euro

Mail reprints /cover posters / copies of the issue to:

Invoice address:

Date, Signature

Stamp

VAT no.: _____
(institutes / companies in EU countries only)

Purchase Order No.: _____

Credit Card Payment

VISA, MasterCard, AMERICAN EXPRESS

Please use the Credit Card Token Generator located at the website below to create a token for secure payment. The token will be used instead of your credit card number.

Credit Card Token Generator:

https://www.wiley-vch.de/editorial_production/index.php

Please transfer your token number to the space below.

Credit Card Token Number:

--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

Price list for reprints (The prices include mailing and handling charges. All Wiley-VCH prices are exclusive of VAT)

No. of pages	50 copies	100 copies	150 copies	200 copies	300 copies	500 copies
1-4	345	395	425	445	548	752
5-8	490	573	608	636	784	1077
9-12	640	739	786	824	1016	1396
13-16	780	900	958	1004	1237	1701
17-20	930	1070	1138	1196	1489	2022
for every additional 4 pages	147	169	175	188	231	315

★ **Special Offer** ★ If you order 200 or more reprints you will get a PDF file for half price.