April 11th, 2020

**Tuning the Metal Support Interaction and Enhancing the Stability of Titania
Supported Cobalt Fischer-Tropsch Catalysts via Carbon Nitride Coating**

Jingping Hong^{1,*}, Bo Wang¹, Guiqin Xiao¹, Ning Wang^{2,*}, Yuhua Zhang¹, Andrei Y.
Khodakov^{3*} and Jinlin Li¹

¹Key Laboratory of Catalysis and Energy Materials Chemistry of Ministry of Education
& Hubei Key Laboratory of Catalysis and Materials Science, South-Central University
for Nationalities, Wuhan 430074, China

²Advanced Membranes and Porous Materials Center Physical Sciences and
Engineering Division, King Abdullah University of Science and Technology Thuwal
23955, Saudi Arabia.

³Univ. Lille, CNRS, Centrale Lille, Univ. Artois, UMR 8181 – UCCS – Unité de
Catalyse et Chimie du Solide, F-59000 Lille, France.

* Corresponding authors: Email: jingpinghong@mail.scuec.edu.cn (Jingping Hong);
ning.wang.1@kaust.edu.sa (Ning Wang); andrei.khodakov@univ-lille.fr (Andrei Y.
Khodakov)

Abstract

Supported metal catalysts have found numerous applications in many catalytic reactions, including Fischer-Tropsch synthesis. Metal dispersion, metal reducibility, catalytic performance and catalyst stability are usually strongly affected by the interaction of active phase and support. A strong metal support interaction has been previously reported for titania supported catalysts.

In this work, a series of titania supported cobalt catalysts promoted via deposition of a layer of carbon nitride were prepared, characterized and tested in Fischer-Tropsch synthesis. The catalytic performance of freshly activated catalysts was an interplay of cobalt dispersion and reducibility. Deposition of carbon nitride on the surface of titania resulted in a noticeable enhancement of cobalt dispersion, while it hindered to some extent cobalt reducibility. The non-promoted cobalt catalysts exhibited noticeable deactivation in Fischer-Tropsch synthesis. The catalyst deactivation was due to the progressive encapsulation of cobalt active phase by TiO_2 during the reaction. A carbon nitride layer on the TiO_2 surface stabilized cobalt nanoparticles and prevented encapsulation of active sites by TiO_2 species. The stability was significantly enhanced on all titania supported cobalt catalysts promoted with carbon nitride.

Keywords: Fischer-Tropsch synthesis; cobalt catalyst; TiO_2 ; carbon nitride; stability

1. Introduction

With the rapid depletion of petroleum reserves and new environmental requirements, Fischer-Tropsch (FT) synthesis has become an important and promising process to convert coal-, biomass- or natural gas-derived syngas into valuable fuels and chemicals¹⁻⁶. Cobalt-based catalysts are preferred for the production of heavy long-chain paraffins. They have a number of advantages such as high activity, high selectivity to linear hydrocarbons, low activities for the water-gas shift reaction⁷⁻⁹ and better stability compared to the iron counterparts.

For cobalt nanoparticles larger than 6-8 nm, both TOF and selectivities to long-chain hydrocarbons were reported to be constant, while those values decreased when the cobalt particle size got smaller than 6 nm¹⁰⁻¹³. Catalyst deactivation is also a major challenge of FT synthesis. The deactivation of cobalt-based catalysts may include metal particle oxidation, sintering, cobalt carbide formation, poisoning, diffusional constraints, strong metal-support interaction, cobalt-support mixed compound formation, surface reconstruction¹⁴⁻²⁰. Cobalt particle growth (sintering) and coking were identified as key deactivation phenomena¹⁶⁻¹⁹ on many supported cobalt catalysts.

The performance of cobalt catalysts in FT synthesis is a function of the number, intrinsic activity and stability of surface metal sites. All these catalytic parameters are strongly affected by the interaction between the metal nanoparticles and support. Interaction of metal and support can take different forms. First, this interaction can affect the metal dispersion. Higher cobalt dispersion is usually observed in the alumina supported catalysts, while using silica and titania as support can lead to somewhat larger cobalt oxide and metal nanoparticles. Higher cobalt dispersion can be also obtained by encapsulation of cobalt nanoparticles in the porous support, for example inside carbon nanotubes²¹. If the cobalt smaller metal nanoparticles have been produced on a specific

support, this would modify the number of active sites and in some particular cases, the intrinsic activity of surface sites. Second, metal support interaction can result in formation of metal support mixed compounds (cobalt aluminates, cobalt silicates etc.). Higher fraction of metal support mixed compounds is usually observed in alumina supported catalysts. Cobalt support mixed compounds have difficult reducibility; they are inert in FT reaction. Third, electronic interaction between metal nanoparticles and support can lead to the modifications of intrinsic activity of cobalt surface sites.

Several reports have addressed use of carbon materials for supporting cobalt FT catalysts^{21, 22}. Carbon materials exhibit weak metal–support interaction and usually do not form barely reducible mixed compounds with cobalt species such as aluminates or silicates (in the case of alumina or silica supports). In addition, carbon based cobalt catalysts often exhibit higher turnover frequencies and higher selectivities to the C₅₊ hydrocarbons compared to their counterparts supported by refractory oxides. Insufficient mechanical strength and inability to be regenerated in air are major drawbacks of carbon materials, which limit their application in the industry^{23, 24}. In addition, carbon materials are usually more expensive than the oxide supports (SiO₂, Al₂O₃, TiO₂).

Metal catalysts supported by titania exhibit a particular type of metal support interaction often called as “Strong Metal Support Interaction (SMSI)”, which has been observed for the metals of the VIII group on TiO₂. SMSI was first uncovered in the 70s of last century by Tauster et al.²⁵ and was further confirmed by the works of Vannice and Garten²⁶⁻²⁸. SMSI originates from the reducibility of titania. The chemical interaction between reduced support and metallic species may lead to the formation of intermetallic compounds and electron transfer^{29, 30} between partially reduced titania and metal species. Partial reduction of catalytic supports, such as titania, niobia and ceria

may also result in formation of oxide layer over the surface of active phase³¹⁻³³. This layer may affect chemisorption over metal species, modify their intrinsic activity and stability of supported metal nanoparticles.

Functional carbon–oxide hybrid materials and doping of supported catalysts with heteroatoms are regarded as effective strategies to overcome limitations of carbon or oxide supports and to combine the advantages of oxide supports such as rigidity and mechanical strength and those of carbon materials such as higher intrinsic activity and absence of inactive metal-support compounds. Deposition of carbon layer also allows modification and optimization of the active metal – support interaction^{23, 34-37}. In our previous work²³, the silica support was coated by carbon species via fructose pyrolysis. In another work²⁴, a hydrothermal treatment was used to prepare carbon - coated TiO₂ supported cobalt catalysts. The protection of the TiO₂ surface by hydrothermal carbon coating improved both cobalt dispersion and reducibility. Much higher activity and higher C₅₊ selectivity were obtained. However, the catalysts still underwent the activity decrease in the initial reaction stage, and the hydrothermal carbon layer has been consumed during reaction. Cheng et al.³⁵ synthesized N-doped carbon nanospheres to support cobalt nanoparticles. Nitrogen dopants were found to significantly strengthen the interaction between cobalt species and supports via electron donation from N atoms, while the catalytic performance and stability were enhanced.

In this work, a series of carbon nitride coated TiO₂ composites were prepared using urea as a source of carbon and nitrogen. The additional N dopant was aimed to adjust the interaction between cobalt and carbon nitride-TiO₂ composite materials. The effects of coating TiO₂ by carbon nitride on the structure and FT performance of supported cobalt nanoparticles were thoroughly investigated. The properties of the uncoated Co/TiO₂ catalyst were also studied for comparison.

2. Experimental

2.1 Preparation of $\text{TiO}_2@\text{xCN}$ supports

Degussa P25 TiO_2 was used as a raw TiO_2 material. The carbon nitride coated TiO_2 was synthesized through the following procedure: a required amount of urea ($\text{CO}(\text{NH}_2)_2$) was dissolved in deionized water and added dropwise to P25 TiO_2 via incipient wetness impregnation (IWI) method. The urea- TiO_2 mixture was transferred into a hermetically closed Teflon flask and hydrothermally treated in an oven at 100 °C for 12 h. The dried powder was then ground into 60 – 150 μm , and calcined in a muffle furnace at 550 °C for 2 h with a ramping rate of 15 °C·min⁻¹. The as-prepared materials were named as $\text{TiO}_2@\text{xCN}$, where x stood for Urea/P25 TiO_2 weight ratio (x =1, 1.5, 2, 3 in this work).

2.2 Preparation of the $\text{Co}/\text{TiO}_2@\text{xCN}$ catalysts

Cobalt based catalysts were prepared by conventional incipient wetness impregnation, using cobalt nitrate as precursor. The impregnated samples were dried in air at 100 °C for 12 h, and calcined in flowing N_2 at 350 °C for 5h. The obtained catalysts were named as $\text{Co}/\text{TiO}_2@\text{xCN}$ (x =1, 1.5, 2, 3), and the nominal cobalt loading in all catalysts were 10 wt.%. The detailed information about the support and catalyst preparation is listed in **Table S1, Supporting Information (Supp Info)**.

2.3 Characterization

The structure and properties of supports and cobalt-based catalysts were characterized by a combination of techniques: Fourier transform infrared (FT-IR) spectroscopy, thermogravimetric analysis (TGA), transmission electron microscopy

(TEM), high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) and energy dispersive X-ray spectroscopy (EDS) elemental mapping, X-ray photoelectron spectroscopy (XPS), X-ray diffraction (XRD), low temperature nitrogen adsorption, hydrogen temperature programmed reduction (H_2 -TPR), hydrogen or CO temperature programmed desorption (H_2/CO -TPD) and temperature programmed hydrogenation - mass spectroscopy (TPH-MS).

FT-IR spectra of supports and catalysts were collected on a Nicolet NEXUS-470 Spectrometer ($400\text{--}4000\text{ cm}^{-1}$). TGA of $\text{TiO}_2@\text{xCN}$ supports was carried out on a NETZSCH 209F3 apparatus, the data were recorded during temperature ramping from $50\text{ }^\circ\text{C}$ to $750\text{ }^\circ\text{C}$ in flowing air. TEM measurements were performed on a FEI-Titan Super-Twin (ST) electron microscope operated at 300 kV and a Tecnai G2F20 microscope (FEI Co., Holland) operated at 200 kV. HAADF-STEM and EDS elemental mapping were carried out with a FEI Titan 80-300 microscope equipped with a monochromator and a probe Cs corrector operated at 300 kV. XRD patterns were acquired on a D8 Advance diffractometer (Bruker Co., Ltd, Germany) equipped with a Ni - filtered Cu - K α radiation source ($\lambda = 1.54056\text{ \AA}$) with a scanning rate of $0.02\text{ }^\circ/\text{s}$. XPS spectra were recorded on a VG Multilab 2000 (Thermal Electron, Inc., USA) photoelectron spectrometer using Al (K α) radiation as the excitation source. H_2 - TPR profiles of catalysts were obtained on a catalyst multifunctional characterization instrument (AMI - 200, Altamira Instruments, Inc., USA). H_2 -TPR & MS measurements of fresh catalysts were performed on a Quanta Chemstar chemisorption instrument equipped with a Tilon LC - D200M mass spectroscopy. Typically, 200 mg of fresh prepared catalyst was pretreated in flowing Ar at $150\text{ }^\circ\text{C}$ for 30 min to remove the adsorbed water. After cooling down to $50\text{ }^\circ\text{C}$, the gas was switched to a 5 vol. % H_2/Ar flow (30 ml/min), then the temperature was raised to $800\text{ }^\circ\text{C}$ with a ramping rate

of 10 °C /min for H₂-TPR & MS measurements. H₂ consumption was monitored by a TCD, and MS signal channels of m/z = 2, 16, 17, 18, 30, 46 corresponding to H₂, CH₄, OH, H₂O, NO and NO₂ were recorded at the same time. H₂ and CO-TPD were performed on a Microtrac BEL BELCAT-B chemisorption instrument, the catalysts were pre-reduced at 350 °C in flowing H₂ before adsorption and desorption procedures. TPH-MS of spent catalysts was performed on MicrotracBEL AutochemII 2920 and InProcess Instruments GAM 200 apparatus, before measurement, the spent catalysts were thoroughly washed by CS₂ and ethanol. More detailed characterization information can be found in our previous work^{38, 39}.

2.4 FT catalytic tests

The performance of the cobalt-based catalysts in FT synthesis was tested in a four-tube fixed bed stainless steel tubular reactor (i.d. 6 mm). Before catalytic tests, the calcined catalysts were in-situ reduced in flowing H₂ at 350 °C for 10 h. After cooling down to 100 °C, the syngas (H₂/CO = 2, GHSV = 3 NL·h⁻¹·g⁻¹) was directed into reactors, and the system pressure was gradually increased to 1.0 MPa. The reaction was conducted at 220 °C and 250°C. The average CO conversion and reaction selectivity were measured after 20 h time on stream. The effluent gaseous products were analyzed online by a gas chromatograph. Solid and liquid products were respectively gathered in a hot and a cold traps, respectively. They were analyzed offline, after the reaction has been finished. The catalytic performance was characterized as CO conversion, cobalt-time yield (FT reaction rate) and selectivities to selected hydrocarbons. Cobalt time yields were expressed as moles of CO converted per gram of total cobalt per second. The product selectivities were reported as percentage of CO converted into a given product, respectively, and expressed on carbon basis.

Figure 1: (a) Photographs of supports prepared using different urea amounts. (b) FT-IR spectra of TiO_2 and $\text{TiO}_2@x\text{CN}$ supports. (c) XRD patterns of calcined urea, TiO_2 and $\text{TiO}_2@1\text{CN}$ materials. (d) TG curves of $\text{TiO}_2@x\text{CN}$ supports in air atmosphere. (e) TEM images of $\text{TiO}_2@x\text{CN}$ supports.

3 Results and discussion

3.1 Support properties

Figure 1a displays photographs of the calcined $\text{TiO}_2@x\text{CN}$ supports. Pure titanium dioxide is a white powder. The color of the carbon nitride- TiO_2 composite supports was a function of the amount of added urea. With increasing the urea/P25 TiO_2 ratio, the color evolves from the white, light yellow to dark yellow color, indicating the increase in the amount of residual C or N species on the TiO_2 material. The urea residual

species on TiO₂ after calcination were examined by FT-IR. Only the O-H stretching vibration absorption band at 1651 cm⁻¹ originated from the adsorbed water was observed on TiO₂ (**Figure 1b**). In the spectra of the TiO₂@xCN materials, besides the O-H band, the C-N stretching vibration band at 1612 cm⁻¹ and aromatic C-N stretching vibration bands at 1387 cm⁻¹ and 1311 cm⁻¹ were observed. They indicate the presence of carbon nitride species⁴⁰⁻⁴⁵.

The crystalline structure of calcined urea, pure P25 TiO₂ and TiO₂@1CN materials was analyzed by XRD. Pure P25 TiO₂ was a mixture of mostly anatase phase (JCPDS 71-1166) with a small fraction of rutile phase (JCPDS 21-1276). The residues of urea calcined at 550 °C for 2 h in muffle furnace present a characteristic diffraction peak at $2\theta = 27.3^\circ$ assigned to hexagonal g-C₃N₄ (JCPDS 87-1526, **Figure 1c**). This intense peak was ascribed to the (002) plane formed by stacking of the conjugated aromatic system^{46, 47}. Overlapping diffraction peaks of g-C₃N₄ (002) plane and rutile TiO₂ (110) plane at 27.3-27.4° makes it difficult, identification of carbon nitride in TiO₂@xCN. Thus, the peak intensities of anatase TiO₂ (101) plane at $2\theta = 25.3^\circ$ ($I_\bullet$) and that at $2\theta = 27.4^\circ$ (I_∇) attributed to TiO₂ (110) in pure TiO₂ and TiO₂@1CN were compared. The peak ratios of $I_\bullet/I_\nabla$ in pure TiO₂ and TiO₂@1CN supports were 8.1 and 4.8, respectively. Much stronger signal at $2\theta = 27.4^\circ$ (I_∇) in the XRD patterns of TiO₂@1CN indicated the presence of hexagonal g-C₃N₄ in this sample.

The morphology of the TiO₂@xCN supports was examined by TEM. **Figure 1e** shows that the TiO₂ surface is covered by carbon nitride. High resolution TEM demonstrates that the thickness of carbon nitride layer is proportional to the amount of added urea. Thicker, but non-uniform layers were observed on the samples prepared using a higher urea/P25 TiO₂ weight ratio.

Surface carbon and nitrogen species in the TiO₂@xCN supports were measured

by XPS. The results are shown in **Figure S1** and **Tables S2-S3, Supp Info**. The N 1s XPS spectrum (**Figure S1a, Supp Info**) was composed by three peaks at 399.0 eV, 400.0 eV and 401.0 eV. The peak at 399.0 eV could be assigned to N sp^2 -species bonded to carbon, characteristic of triazine rings, while the other two peaks were related to the C-N-H and C-N bondings⁴⁸. The N 1s XPS peaks were quantitatively analyzed, the data are listed in **Table S2, Supp Info**. The relative fractions of triazine rings, and thus, C-N-H and C-N bonds were the same in all the catalysts. The C 1s spectra (**Figure S1b, Supp Info**) of four supports can be deconvoluted into three peaks. The main peak at 284.6 eV was ascribed to sp^2 C-C bonds in graphitic carbon, two small peaks at 286.2 eV and 288.4 eV were attributed to sp^3 -coordinated C-N bonds and sp^2 -bonded carbon in N-containing aromatic rings(N-C=N)⁴⁹⁻⁵¹, respectively. Both C 1s and N 1s XPS spectra are consistent with FT-IR and XRD results. They are indicative of the presence of carbon nitride in the catalysts. Besides, in agreement with TEM results, the surface N/Ti XPS ratio increased with increasing carbon nitride coating thickness (**Table S3, Supp Info**).

The carbon nitride doping contents in the four $TiO_2@xCN$ supports were evaluated from TGA in flowing air (**Figure 1d**). When increasing the temperatures up to 750 °C, the weight loss percentages on $TiO_2@1CN$, $TiO_2@1.5CN$, $TiO_2@2CN$ and $TiO_2@3CN$ were 2.7 %, 5.4 %, 10 % and 14.3 %, respectively. This suggests that the amount of carbon nitride in final calcined supports is also directly proportional to the urea/P25 TiO_2 weight ratio. The more urea is added, the more C_3N_4 is on the support surface.

The low temperature nitrogen adsorption data measured for TiO_2 , $TiO_2@1CN$ and $TiO_2@2CN$ are shown in **Figure S2** and **Table S4, Supp Info**. All three samples show type IV isotherms according to the IUPAC classification, with non-standard hysteresis

loop (**Figure S2a, Supp Info**), suggesting the presence of irregular mesopores. After coating with carbon nitride, the N_2 adsorption-desorption isotherms were not much altered. $TiO_2@1CN$ and $TiO_2@2CN$ have shown broader BJH pore distribution curves (**Figure S2b, Supp Info**) at 20-60 nm, and more notably, smaller pores in the diameter range of 2-3 nm. These smaller pores can arise from the C_3N_4 layers on the TiO_2 surface. Note that the carbon nitride deposition also results in higher BET surface area (**Table S4, Supp Info**).

3.2 Characterization of the $Co/TiO_2@xCN$ catalysts

Figure S3a, Supp Info shows FT-IR spectra of the calcined Co/TiO_2 and $Co/TiO_2@xCN$ catalysts. The peak at 1612 cm^{-1} ascribed to C-N stretching and the peaks at 1387 cm^{-1} , 1311 cm^{-1} attributed to aromatic C-N stretching vibration were observed⁵². Compared with the FT-IR spectra of corresponding supports (**Figure 1b**), no apparent change was found after cobalt loading and thermal calcination at $350\text{ }^\circ\text{C}$ in N_2 , indicating good overall thermal stability of the deposited carbon nitride.

XRD patterns of five catalysts (**Figure S3b, Supp Info**) exhibit the peaks at $2\theta = 59.3^\circ$ and 65.2° ascribed to (511) and (440) planes of Co_3O_4 . Co_3O_4 was the only cobalt phase detected in the calcined catalysts. Interestingly, the Co_3O_4 XRD peaks were broadened and less intense after the carbon nitride coating. This is indicative of higher cobalt dispersion on $Co/TiO_2@xCN$ than on Co/TiO_2 . The average Co_3O_4 particle sizes calculated using the Scherrer equation from the diffraction peak at $2\theta = 65.2^\circ$, are listed in **Table 1**. Carbon nitride coating of titania seems beneficial for enhancing cobalt dispersion, the average Co_3O_4 particle size decreases with increasing the coating thickness, from 20 nm to 12 nm.

Table 1: Atomic ratios of calcined and plasma treated Co/TiO₂ and Co/TiO₂@xCN catalysts obtained from XPS as well as cobalt particle size from XRD and TEM.

Catalysts	BE Co _{2p}	SES (eV) ^a	Co/Ti	N/Ti	Co ³⁺ / Co ²⁺	Co particle size (nm) in fresh catalysts		Co particle size (nm) in spent catalysts (XRD) ^c
						TEM	XRD ^b (Co ₃ O ₄)	
Co/TiO ₂	779.6	15.3	0.077	-	1.8	13.9	20	17.3
Co/TiO ₂ -1CN	778.2	15.0	0.22	0.039	1.7	12.1	14.9	13.2
Co/TiO ₂ -1.5CN	778.3	15.0	0.18	0.035	1.6	11.9	14.7	12.8
Co/TiO ₂ -2CN	778.4	15.1	0.28	0.045	1.2	11.3	13.5	12.7
Co/TiO ₂ -3CN	778.8	15.0	0.23	0.041	0.9	10.3	12	12.5

^a The spin-energy separation (SES) of Co 2p_{3/2} and Co 2p_{1/2} binding energy. ^b Particle size of Co₃O₄ was calculated by Scherrer equation; ^cCo metal particle size was calculated by Scherrer equation

To confirm further the promotion effect of carbon nitride layer on cobalt dispersion, the Co/TiO₂ and Co/TiO₂@xCN precursors were calcined at 350 °C for 5 h in a muffle furnace in air. FT-IR spectra were measured in order to confirm, whether the carbon nitride species have been gasified during calcination. **Figure S4, Supp Info** shows disappearance of the bands in the range of 1300 -1400 cm⁻¹ assigned to aromatic C-N stretching vibration after calcination in air, indicating the complete removal of carbon nitride species. XRD patterns of Co/TiO₂ and Co/TiO₂@xCN calcined in air are plotted in **Figure S5, Supp Info**. Only characteristic diffraction peaks of Co₃O₄ at 2θ

= 59.4° and 65.4° were detected. The Co₃O₄ crystallite sizes calculated from the width of the peak at 65.4° using the Scherrer equation are listed in **Table S5, Supp Info**. Calcination of Co/TiO₂ in air seems to result in smaller Co₃O₄ nanoparticles than calcination in N₂. At the same time, similar Co₃O₄ particle size (15-16 nm) was observed in the Co/TiO₂ and Co/TiO₂@xCN catalysts calcined in air. This suggests that the presence of carbon nitride layer on TiO₂ surface could indeed enhance cobalt dispersion in supported catalysts. Note that cobalt dispersion enhancement was not observed, when the carbon nitride coating has been completely removed from the catalysts after the calcination in air.

The morphology and microstructures of the Co/TiO₂@xCN catalysts were investigated by TEM, HAADF-STEM and EDS elemental mapping (**Figure 2**). Note that cobalt particles were darker than TiO₂ in the bright field TEM images and brighter in the HAADF-STEM micrographs. **Figure 2a, c, e** and **Figure S6, Supp Info** show histograms of cobalt nanoparticle size distributions in the TiO₂@xCN supported catalysts. More than >250 spots were counted in the TEM images. The calculated average particle size is given in **Table 1**. The cobalt nanoparticles size (measured by TEM) decreases from 13.9 nm in Co/TiO₂ to 10.3 nm in the Co/TiO₂-3CN sample with the highest carbon nitride content. Thus, TEM analysis is consistent with the XRD data and confirms that the C₃N₄ layer on the surface of TiO₂ improves cobalt dispersion. The N, O, Ti and Co EDS elemental mappings of three calcined Co/TiO₂@xCN catalysts are shown in **Figure 2b, d, f**. Nitrogen along with titanium and oxygen show uniform distribution on all samples. In agreement with the XRD and TEM results, much higher cobalt dispersion was observed by Co EDS in Co/TiO₂@1CN and Co/TiO₂@2CN than on Co/TiO₂.

Figure 2: TEM images and corresponding Co₃O₄ size distribution of (a) Co/TiO₂, (c) Co/TiO₂@1CN and (e) Co/TiO₂@2CN catalysts. HAADF-STEM and EDX-Mapping images of (b) Co/TiO₂, (d) Co/TiO₂@1CN and (f) Co/TiO₂@2CN catalysts.

The chemical composition and oxidation state of the calcined Co/TiO₂@xCN catalysts were investigated by XPS. Only Co, O, Ti, N, and C XPS signals were

detected (**Figure 3a**). Both C 1s and N 1s XPS spectra of four CN coated catalysts (**Figure 3b and c**) were almost identical to those of corresponding supports.

Figure 3: XPS spectra of Co/TiO₂ and Co/TiO₂@xCN catalysts: (a) overview spectra, (b) C 1s, (c) N 1s, (d) Co 2p XPS spectra.

This suggests that after cobalt loading and calcination, carbon nitride was maintained on the surface of the Co/TiO₂@1-3CN catalysts. The Co 2p_{3/2} XPS spectra of the Co/TiO₂@xCN catalysts are shown in **Figure 3d**. The uncoated Co/TiO₂ catalyst presents a very weak Co 2p_{3/2} signal, while much stronger Co 2p_{3/2} bands are observed on the catalysts supported on TiO₂@xCN. Higher cobalt XPS concentrations in the catalysts coated with carbon nitride are consistent with higher cobalt dispersion. The surface Co/Ti ratio for Co/TiO₂@xCN catalysts was in the range of 0.18 - 0.28 (**Table 1**), more than twice higher than that of pure TiO₂ supported counterpart (0.077). Besides the peak intensity, the binding energy (BE) of Co 2p_{3/2} peak also varied as a function

of the support structure. The BE of Co $2p_{3/2}$ on Co/TiO₂ was 779.6 eV, and this peak can be fitted into two peaks assigned to the Co³⁺ and Co²⁺ species. The Co³⁺/Co²⁺ area ratio was 1.8, demonstrating that Co₃O₄ was the main component on the surface of this catalyst. Surprisingly, besides the Co³⁺ and Co²⁺ XPS peaks, a new peak centered at ~778.0 eV assigned to Co⁰ appeared in the XPS spectra of all four Co/TiO₂@xCN catalysts⁵³. Since no Co⁰ was detected by XRD, the presence of surface Co⁰ might be originated from surface cobalt oxide reduction by carbon species²².

Figure 4: TPR profiles of Co/TiO₂ and Co/TiO₂@xCN catalysts.

The reducibility of the Co/TiO₂@xCN catalysts was investigated by H₂-TPR (Figure 4). All catalysts had three reduction peaks at 320, 360-385 and 437 °C attributed respectively to the reduction of Co₃O₄ to CoO, CoO to Co⁰ and the Co-species interacting with the support. No TPR peaks were observed at higher temperatures. Interestingly, the positions of the first peak (~320 °C) and third peak (~440°C) are not affected by the presence of carbon nitride coating, while the second reduction peak (CoO to Co⁰) shifts towards higher temperature with increasing the carbon nitride content. Note that the intensity of third reduction peak increases and that of second peak

decreases with higher carbon nitride content. The fraction of metallic cobalt in catalysts the reduced before the catalytic test could be therefore, a function of the intensity of the second TPR peak situated at 360-380°C. Our results show that, with increasing carbon nitride content, both the area of second reduction peak (CoO to Co⁰) decreases and the reduction temperature of this peak shifts to higher temperatures. This indicates that cobalt reducibility has been to some extent hindered on the C₃N₄ coated TiO₂ supported catalysts. To better compare the reducibility of five catalysts, quantitative analysis of the reduction degree has been performed using the H₂-TPR profiles. The cobalt reduction degree was calculated from the hydrogen consumption in the second and third reduction peaks attributed to the reduction of CoO to Co⁰. The values of the catalyst reduction degrees measured by TPR at 400 °C and 500°C (**Table S6, Supp Info**) indicate more difficult cobalt reduction in the TiO₂ supported catalysts with C₃N₄ coating.

Figure 5: H₂-TPR & MS profiles of the fresh Co/TiO₂, Co/TiO₂@1CN and Co/TiO₂@2CN catalysts.

To investigate the stability of the carbon nitride species during reduction, the combined H₂-TPR & MS measurements were conducted for the Co/TiO₂, Co/TiO₂@1CN and Co/TiO₂@2CN catalysts (**Figure 5**).

Note that the H₂-TPR experiments were performed with 10 vol. % H₂/Ar, while for the TPR & MS, the 5 vol. % H₂/Ar gas mixture was used. This explains slight differences in the obtained results. **Figures 5 a-d** show that the shape of TCD signals of all three catalysts coincides well with the shape of hydrogen consumption profiles measured by MS. The main product is H₂O, originating from the reduction of cobalt oxides. Besides H₂O, a weak CH₄ and CO₂ peaks were also observed by MS for all three catalysts. These peaks may be due to the gasification of carbon species. Meanwhile, a very tiny NO (m/z=30) signal was detected on two Co/TiO₂@1CN and Co/TiO₂@2CN catalysts. Since CH₄ signals on both Co/TiO₂ and Co/TiO₂@xCN catalysts are comparable, and nitrogen oxide signals detected on Co/TiO₂@xCN samples were very weak, we can deduce that methane is mainly produced from gasification of surface carbon or carbonate species present in similar amounts in both non-promoted TiO₂ and carbon nitride promoted catalysts. This suggests that only small amount of surface carbon nitride has been gasified in the TPR-MS measurements.

TPD of the reactants (H₂ and CO) was performed to further understand the properties of catalyst active sites (**Figure S7, Supp Info**). The H₂-TPD profiles (**Figure S7a, Supp Info**) show intense low temperature desorption peaks at 180-220°C and weaker peaks at 400°C. With the increase in the carbon nitride coating thickness, the intensity of the H₂ desorption peaks at 400 °C was significantly increased, while the intensity of the low temperature was almost unaffected. The CO-TPD curves of both Co/TiO₂ and Co/TiO₂@xCN catalysts (**Figure S7b, Supp Info**) exhibit desorption

peaks below 200 °C. The intensity of CO desorption peaks increases with higher carbon nitride coating amount, while the CO desorption peak shifts to lower temperature region. These results are consistent with higher cobalt dispersion and higher amount of cobalt surface sites in the Co/TiO₂@xCN catalysts. At the same time, the CO adsorption strength seems to decrease with increasing coating thickness of carbon nitride on the TiO₂ surface.

Figure 6: (a) CO conversion as a function of time on stream (TOS) and (b) Average CO conversion of Co/TiO₂ and Co/TiO₂@xCN catalysts at 220°C.

3. 3. Catalytic performance

The results of catalytic evaluation of the Co/TiO₂@xCN in FT synthesis are shown in **Figure 6** and **Table 2**. In agreement with ref. 19, the non-coated Co/TiO₂ catalyst showed the highest initial carbon monoxide conversion (15.0 %). However, this catalyst exhibited rapid and continuous deactivation in first 70 h of reaction, the deactivation rate reached 0.44 %/h. The initial FT reaction rates over the Co/TiO₂@xCN catalysts slightly decreased with increasing carbon nitride coating thickness. Lower FT reaction rate can be due to more difficult cobalt reduction in the presence of the carbon nitride layer. Surprisingly, no deactivation was observed over all these four catalysts promoted

with carbon nitride. The catalytic results clearly showed that carbon nitride coating on the surface of TiO₂ could significantly improve the catalyst stability. Small amount of carbon nitride was already sufficient for maintaining of both high FT activity and good reaction stability. **Table 2** showed that the hydrocarbon selectivity was also affected by carbon nitride addition. Compared with Co/TiO₂, the CH₄ selectivity decreased, whereas the C₅₊ selectivity was enhanced over the Co/TiO₂@xCN catalysts. The observed differences in the selectivity to the C₅₊ hydrocarbons might be related to the N doping. This is consistent with the finding of Yang et al.⁵⁴, the N-doped carbon could improve the selectivity to the long-chain hydrocarbons.

Table 2: FT performance and particle size of cobalt species on Co/TiO₂ and Co/TiO₂@xCN catalysts^a.

Catalyst	Initial CO Conv. (%)	CO Conv. ^b (%)	Cobalt-time yield ^c (10 ⁻⁴ mol _{CO} mol _{Co} ⁻¹ s ⁻¹)	Products selectivity (%)			
				CO ₂	CH ₄	C ₂ - C ₄	C ₅₊
Co/TiO ₂	15.0	9.8	7.2	1.3	13.8	10.6	75.6
Co/TiO ₂ @1CN	13.8	13.8	10.1	2.0	6.5	5.6	87.9
Co/TiO ₂ @1.5CN	12.1	12.0	8.8	1.7	10.9	7.5	83.1
Co/TiO ₂ @2CN	8.8	8.7	6.4	1.7	8.6	7.1	84.3
Co/TiO ₂ @3CN	8.3	8.3	6.1	2.1	7.6	5.5	87.0

^a Reduction conditions: 350 °C, H₂, 3 L·g_{cat}⁻¹·h⁻¹, 10 h; reaction conditions: 1 MPa,

H₂/CO=2:1, 3 L·g_{cat}⁻¹·h⁻¹, 220°C; ^b Average CO conversion after 20 hours; ^c Cobalt-time yield expresses in moles of converted CO (steady state conversion) per second divided by the total amount of cobalt (in moles) loaded into the reactor.

To better understand the catalytic behavior at higher CO conversion level, FT performance of the Co/TiO₂ and Co/TiO₂@1CN catalysts was evaluated at elevated temperature (250 °C). The catalytic test with the Co/TiO₂@1CN catalyst calcined in air was also performed for comparison. The CO conversion as a function of time on stream for these three catalysts is plotted in **Figure 7**.

Figure 7: CO conversion as a function of time on stream (TOS) for Co/TiO₂, Co/TiO₂@1CN and air calcined Co/TiO₂@1CN catalysts reacting at 250 °C.

Co/TiO₂@1CN presents the best stability, when the CO conversion reaches 60 %. The deactivation rate of Co/TiO₂ (0.37 %/h) was 30 times higher than that of Co/TiO₂@1CN (0.012 %/h). The Co/TiO₂@1CN catalyst calcined in air exhibited much slower deactivation rate compared to Co/TiO₂ but still 20 times higher than that of Co/TiO₂@1CN. Interestingly, Co/TiO₂@1CN reached its maximum reaction rate in ~2h, while the other two samples, 4 h and 7h were needed to reach their maximum activity. The characterization results showed that the carbon nitride species were

completely removed after thermal treatment of this catalyst in air at 350 °C for 5h. The catalytic results therefore, suggest that the presence of carbon nitride coating is indispensable for better stability of Co/TiO₂ catalysts.

Figure 8: (a) CH₄ signal of spent Co/TiO₂ and Co/TiO₂@1CN catalysts during TPH-MS experiments, (b) XRD patterns of spent Co/TiO₂ and Co/TiO₂@xCN catalysts.

3.4. Characterization of spent catalysts

In order to provide further insights into the mechanisms responsible for the catalyst deactivation, Co/TiO₂ and Co/TiO₂@xCN after the FT catalytic test were extensively characterized by TPH-MS, XRD, STEM-EDX and TEM. Deposition of carbon species on the catalyst surface during FT reaction was evaluated by TPH-MS. The m/z signals of 2, 15, 16, 17, 18, 28, 40 were recorded during heating of the spent catalysts in hydrogen. Besides H₂O (m/z = 17 and 18), only methane signal was detected. **Figure 8a** shows broad methane peaks in the temperature range of 200 – 800 °C. The presence of several peaks in the TPH-MS profiles can be attributed to different types of carbon species on the catalyst surface⁵⁵. Both the shape and intensity of methane signals observed over Co/TiO₂ and Co/TiO₂@1CN were quite similar. This suggests the presence of similar deposited carbon species on these two catalysts. It should also be

noted that the absolute value of methane TPH-MS signal was quite low, the concentration of carbon species was around $0.7 \mu\text{mol/g}$ for both catalysts. Such low concentration of carbon species determined by TPH indicates that the observed deactivation of Co/TiO_2 cannot be solely assigned to carbon deposition.

The XRD patterns of the spent catalysts are shown in **Figure 8b**. Besides the diffraction peaks of anatase and rutile TiO_2 , a peak at 44.2° attributed to *fcc* Co^0 was detected. The average Co^0 particle sizes calculated by the Scherrer equation are displayed in **Table 1**. In the spent catalysts, cobalt was mostly present as metallic species, while Co_3O_4 was observed in the freshly calcined counterparts. The cobalt metal nanoparticles have the diameter 25% smaller^{56, 57} than the diameter of the parent oxide nanoparticles. The slight decrease in the average cobalt metal particle size in the spent catalysts in comparison with the oxide nanoparticles in the fresh samples indicates absence of cobalt sintering during the FT reaction.

Figure 9: HAADF-STEM images of spent (a) Co/TiO_2 and (c) $\text{Co/TiO}_2@1\text{CN}$. EDX-Mapping images of spent (b) Co/TiO_2 and (d) $\text{Co/TiO}_2@1\text{CN}$.

Localization of the cobalt, titanium, carbon and nitrogen elements in the spent Co/TiO₂ and Co/TiO₂@1CN catalysts was examined by STEM-EDX (**Figure 9**). The STEM-EDX of the spent Co/TiO₂@1CN catalyst indicates the presence of carbon and nitrogen elements, which remain uniformly dispersed on the TiO₂ support. This suggests that the carbon nitride coating has not been removed under the reaction conditions. Cobalt species were also uniformly dispersed in the spent Co/TiO₂ and Co/TiO₂@1CN catalysts.

Figure 10: Comparison of Ti 2p XPS spectra between fresh and spent Co/TiO₂ and Co/TiO₂@xCN catalysts.

Further information about the deactivation phenomena was extracted from the XPS data. Since the surface of spent catalysts was covered by wax products, the XPS peak intensity may not give precise information about the surface chemical composition. **Figure 10** shows almost identical Ti 2p BE (~ 458.2 eV) in the freshly calcined and spent Co/TiO₂@xCN catalysts. Over non-coated Co/TiO₂, the BE of Ti 2p shifts by 0.4

eV from 458.2 eV to higher values, which suggests a change of titania-cobalt interaction during FT synthesis. The shift of BE may indicate electronic effects arising from cobalt species and affecting electronic structure of titania. The effect can be due to the catalyst restructuring during the reaction.

Figure 11: TEM images of spent Co/TiO₂ (a) and Co/TiO₂@1CN (c) catalysts; (b) high resolution HAADF-STEM images and EDX-Mapping images of spent Co/TiO₂ catalyst.

The TEM images of the spent Co/TiO₂ and Co/TiO₂@1CN catalysts are shown in **Figure 11**. TEM clearly shows that the cobalt particles are covered with a layer of TiO₂ (**Figure 11a**) in the spent Co/TiO₂ catalyst, while this phenomenon was not observed in spent Co/TiO₂@1CN. This could explain why the Ti 2p XPS BE shifted on the Co/TiO₂ catalyst after the reaction (**Figure 10**). The severe and continuous deactivation of the Co/TiO₂ catalyst in FT synthesis may be therefore, due to the cobalt encapsulation by TiO₂ during FT reaction. The encapsulation of cobalt species by TiO₂ was not observed in the Co/TiO₂@1CN samples. This suggests that the C₃N₄ layer on the TiO₂ support could slow down the titania migration to cobalt nanoparticles and thus, stabilize cobalt surface sites for catalytic reaction.

3.5. Metal support interaction and stability of titania supported cobalt catalysts

In this paper, deposition of a layer of carbon nitride was used to modify the performance and stability of titania supported catalysts. Characterization suggests that this layer covers titania support and remains almost intact under the conditions of catalyst activation and FT synthesis. The presence of carbon nitride layer leads on the one hand, to the noticeable enhancement of cobalt dispersion. Cobalt particle size measured by XRD decreases from 20 in Co/TiO₂ to 12-13 nm in the samples with higher carbon nitride contents (**Table 1**). On the other hand, more difficult cobalt reducibility was observed by TPR (**Figure 4**) over the catalysts containing higher amounts of carbon nitride. It can be suggested that the presence of this carbon nitride layer leads to the substitution of the interaction of cobalt with titania with the interaction of cobalt with carbon nitride. The interplay of dispersion and reducibility probably determines the initial performance of titania supported cobalt catalysts.

Under the conditions of FT synthesis, we observed noticeable rapid deactivation and evolution of the structure of non-promoted titania supported cobalt catalyst (**Figure 6a**). The catalyst deactivation has been spectacularly slowed down in the presence of a layer of carbon nitride over the surface of titania. The catalysts with the carbon nitride layer over TiO_2 have shown quasi-stable CO conversion for more than 100 h of the reaction (**Figure 6a**). The deactivation of supported cobalt FT catalysts has been investigated in numerous papers^{1, 6, 14-20, 52}. While several mechanisms can contribute to the catalyst deactivation phenomena, cobalt sintering and coke/carbon deposition have been identified¹⁵⁻²⁰ as the most important deactivation phenomena. Most of publications however, have addressed deactivation of cobalt catalysts supported either by alumina or silica. The results of this work clearly show a specificity of the deactivation phenomena, which occur over titania supported catalysts relative to other common catalytic supports. Characterization of the spent catalyst using a combination of techniques indicates that cobalt sintering and carbon deposition cannot explain the rapid and gradual decrease in FT reaction rate observed over the non-promoted Co/TiO_2 sample. Indeed, XRD patterns of the fresh and spent catalysts did not show any noticeable increase in cobalt particle size after the FT reaction (**Table 1 and Figures S3, Supp Info and 8b**). This suggests that cobalt dispersion is almost unaffected by the reaction and cannot be a major deactivation mechanism. In addition, TPH-MS shows similar shape and intensity of the methane production curves during hydrogenation of deposited carbon species on both the non-promoted Co/TiO_2 catalyst and $\text{Co/TiO}_2@1\text{CN}$ catalyst with the carbon nitride layer. This suggests that the presence of carbon nitride layer does not affect to any noticeable extent, carbon deposition over TiO_2 supported catalysts.

Further insights into the deactivation of non-promoted Co/TiO_2 were provided by

TEM and XPS. TEM (**Figure 11**) shows coating of cobalt species by the TiO_2 islands in the spent non-promoted Co/TiO_2 catalyst. In addition, XPS of the spent catalysts is indicative of the BE shift for Ti 2p peaks, which is indicative of the electronic interaction of titania and cobalt. The observed modifications of the catalyst structure can be interpreted in terms of SMSI²¹⁻²⁵⁻³³ previously reported for the TiO_2 based catalysts. Usually SMSI occurs in the TiO_2 based catalysts after their reductive treatments at higher temperatures ($>450\text{-}500^\circ\text{C}$). The exposure to higher temperatures causes partial reduction of titania. Interestingly, the particularity of SMSI in non-promoted titania supported cobalt catalysts uncovered in our work is that the formation of TiO_2 coating over cobalt species proceeds during the FT reaction at $220\text{-}250^\circ\text{C}$ in the presence of hydrogen, carbon monoxide, hydrocarbons and water. The modifications of catalyst structure during catalyst activation and FT reaction are summarized in **Figure 12**.

Figure 12: Restructuring of titania supported cobalt catalysts in the absence and in the presence of a carbon nitride layer.

Catalyst restructuring takes place only in the non-promoted titania supported cobalt catalyst, while these deactivation phenomena do not take place in the catalysts

containing a layer of carbon nitride. The presence of carbon nitride layer weakens interaction between cobalt and titania and hinders diffusion of reduced titania species over cobalt nanoparticles during the FT reactions. Consequently, the stability of titania based catalysts has been significantly improved. The proposed methodology to lessen SMSI via the support coating with carbon nitride can be used for other reducible oxide supports (e.g. Nb_2O_5 , V_2O_3 , Ta_2O_5 and CeO_2).

4. Conclusion

The $\text{TiO}_2@\text{xCN}$ composite materials were synthesized using a simple hydrothermal-impregnation method and used as supports for cobalt-based FT catalysts. The carbon nitride species form a uniform coating layer over the TiO_2 support. The carbon nitride coating improves cobalt dispersion over titania, smaller cobalt particles are found on the catalysts with a thicker coating layer. Because of slightly more difficult cobalt reducibility, the initial FT activity was lower in the titania supported cobalt catalysts with higher amounts of deposited carbon nitride compared to the non-promoted catalyst.

More notably, carbon nitride coating of titania significantly improves the catalyst stability. No obvious deactivation was observed on all $\text{Co}/\text{TiO}_2@\text{xCN}$ catalysts, while rapid and continuous deactivation occurred on the Co/TiO_2 sample. The catalyst deactivation over the non-coated titania supported cobalt catalysts was primarily due to the encapsulation of cobalt species by titania. The presence of carbon nitride layer slows down coating of the active cobalt phase by titania, stabilizes cobalt metal nanoparticles and improves the catalyst stability in FT reaction.

ASSOCIATED CONTENT

Supporting information

The supporting information is available free of charge on the ACS Publications website at DOI:

Catalyst preparation parameters; Textural properties, atomic ratios, surface N analysis as well as N 1s and C 1s XPS spectra of supports; N₂ adsorption-desorption isotherms and pore size distribution, FT-IR spectra and XRD patterns, TEM images and corresponding Co₃O₄ size distributions, H₂-TPD and CO-TPD profiles of Co/TiO₂ and Co/TiO₂@xCN catalysts; Co₃O₄ particle size, XRD patterns and FT-IR spectra of air calcined catalysts.

Acknowledgements

We thank the financial support by National Natural Science foundation of China (21203255, 21473259), Hubei Natural Science Foundation (2018CFB556), Technology Foundation for Selected Overseas Chinese Scholar, Ministry of Personnel of China (BZY14037), Fundamental Research Funds for the Central Universities (South-Central University for Nationalities, CZY19006). AK thanks the South Central University for Nationalities for funding his research stay in Wuhan.

References

1. Khodakov, A. Y.; Chu, W.; Fongarland, P., Advances in the development of novel cobalt Fischer-Tropsch catalysts for synthesis of long-chain hydrocarbons and clean fuels. *Chem. Rev.* **2007**, *107*, 1692-1744.
2. Torres Galvis, H. M.; Bitter, J. H.; Khare, C. B.; Ruitenbeek, M.; Dugulan, A. I.; de Jong, K. P., Supported iron nanoparticles as catalysts for sustainable production of lower olefins. *Science* **2012**, *335*, 835-838.
3. Jiao, F.; Li, J.; Pan, X.; Xiao, J.; Li, H.; Ma, H.; Wei, M.; Pan, Y.; Zhou, Z.; Li, M.; Miao, S.; Li, J.; Zhu, Y.; Xiao, D.; He, T.; Yang, J.; Qi, F.; Fu, Q.; Bao, X., Selective conversion of syngas to light olefins. *Science* **2016**, *351* (6277), 1065-1068.
4. Cheng, K.; Virginie, M.; Ordonsky, V. V.; Cordier, C.; Chernavskii, P. A.; Ivantsov, M. I.; Paul, S.; Wang, Y.; Khodakov, A. Y., Pore size effects in high-temperature Fischer-Tropsch synthesis over supported iron catalysts. *J. Catal.* **2015**, *328*, 139-150.
5. Liu, C.; Zhang, Y.; Zhao, Y.; Wei, L.; Hong, J.; Wang, L.; Chen, S.; Wang, G.; Li, J., The effect of the nanofibrous Al₂O₃ aspect ratio on Fischer-Tropsch synthesis over cobalt catalysts. *Nanoscale* **2017**, *9* (2), 570-581.
6. Cheng, K.; Kang, J.; King, D. L.; Subramanian, V.; Zhou, C.; Zhang, Q.; Wang, Y., Chapter three - Advances in catalysis for syngas conversion to hydrocarbons. In *Advances in Catalysis*, Song, C., Ed. Academic Press: San Diego, 2017; Vol. 60, pp 125-208.
7. Chen, S.; Wang, C.; Li, J.; Zhang, Y.; Hong, J.; Wen, X.; Liu, C., ZSM-5 seed-grafted SBA-15 as a high performance support for cobalt Fischer-Tropsch synthesis catalysts. *Catal. Sci. Technol.* **2015**, *5* (11), 4985-4990.
8. Hong, J.; Du, J.; Wang, B.; Zhang, Y.; Liu, C.; Xiong, H.; Sun, F.; Chen, S.; Li, J., Plasma-assisted preparation of highly dispersed cobalt catalysts for enhanced Fischer-Tropsch synthesis performance. *ACS Catal.* **2018**, *8*, 6177-6185.
9. Hong, J.; Marceau, E.; Khodakov, A. Y.; Griboval-Constant, A.; La Fontaine, C.; Briois, V., A Time-Resolved In Situ Quick-XAS Investigation of Thermal Activation of Fischer-Tropsch Silica-Supported Cobalt Catalysts. *Chem.-Eur. J.* **2012**, *18* (10), 2802-2805.
10. Bezemer, G. L.; Bitter, J. H.; Kuipers, H. P. C. E.; Oosterbeek, H.; Holeyijn, J. E.; Xu, X.; Kapteijn, F.; van Dillen, A. J.; de Jong, K. P., Cobalt particle size effects in the Fischer-Tropsch reaction studied with carbon nanofiber supported catalysts. *J. Am. Chem. Soc.* **2006**, *128* (12), 3956-3964.
11. den Breejen, J. P.; Radstake, P. B.; Bezemer, G. L.; Bitter, J. H.; Frøseth, V.; Holmen, A.; Jong, K. P. d., On the origin of the cobalt particle size effects in Fischer-Tropsch catalysis. *J. Am. Chem. Soc.* **2009**, *131* (20), 7197-7203.
12. Prieto, G.; Martínez, A.; Concepción, P.; Moreno-Tost, R., Cobalt particle size effects in

- Fischer–Tropsch synthesis: structural and in situ spectroscopic characterisation on reverse micelle-synthesised Co/ITQ-2 model catalysts. *J. Catal.* **2009**, *266* (1), 129-144.
13. Iglesia, E.; Soled, S. L.; Fiato, R. A., Fischer-Tropsch synthesis on cobalt and ruthenium. Metal dispersion and support effects on reaction rate and selectivity. *J. Catal.* **1992**, *137* (1), 212-224.
14. Jacobs, G.; Patterson, P. M.; Zhang, Y.; Das, T.; Li, J.; Davis, B. H., Fischer–Tropsch synthesis: Deactivation of noble metal-promoted Co/Al₂O₃ catalysts. *Appl. Catal. A: Gen.* **2002**, *233* (1–2), 215-226.
15. Moodley, D. J.; van de Loosdrecht, J.; Saib, A. M.; Overett, M. J.; Datye, A. K.; Niemantsverdriet, J. W., Carbon deposition as a deactivation mechanism of cobalt-based Fischer–Tropsch synthesis catalysts under realistic conditions. *Appl. Catal. A: Gen.* **2009**, *354* (1), 102-110.
16. Saib, A. M.; Moodley, D. J.; Ciobîcă, I. M.; Hauman, M. M.; Sigwebela, B. H.; Weststrate, C. J.; Niemantsverdriet, J. W.; van de Loosdrecht, J., Fundamental understanding of deactivation and regeneration of cobalt Fischer–Tropsch synthesis catalysts. *Catal. Today* **2010**, *154* (3–4), 271-282.
17. Tsakoumis, N. E.; Rønning, M.; Borg, Ø.; Rytter, E.; Holmen, A., Deactivation of cobalt based Fischer–Tropsch catalysts: A review. *Catal. Today* **2010**, *154* (3–4), 162-182.
18. Sadeqzadeh, M.; Chambrey, S.; Piché, S.; Fongarland, P.; Luck, F.; Curulla-Ferré, D.; Schweich, D.; Bousquet, J.; Khodakov, A. Y., Deactivation of a Co/Al₂O₃ Fischer–Tropsch catalyst by water-induced sintering in slurry reactor: Modeling and experimental investigations. *Catal. Today* **2013**, *215* (0), 52-59.
19. Eschemann, T. O.; de Jong, K. P., Deactivation behavior of Co/TiO₂ catalysts during Fischer–Tropsch synthesis. *ACS Catal.* **2015**, *5* (6), 3181-3188.
20. Sadeqzadeh, M.; Chambrey, S.; Hong, J.; Fongarland, P.; Luck, F.; Curulla-Ferré, D.; Schweich, D.; Bousquet, J.; Khodakov, A. Y., Effect of different reaction conditions on the deactivation of alumina-supported cobalt Fischer–Tropsch catalysts in a milli-fixed-bed reactor: Experiments and modeling. *Ind. Eng. Chem. Res.* **2014**, *53* (17), 6913-6922.
21. Xing, C.; Yang, G.; Wang, D.; Zeng, C.; Jin, Y.; Yang, R.; Suehiro, Y.; Tsubaki, N., Controllable encapsulation of cobalt clusters inside carbon nanotubes as effective catalysts for Fischer–Tropsch synthesis. *Catal. Today* **2013**, *215*, 24-28.
22. Luo, Q.-X.; Guo, L.-P.; Yao, S.-Y.; Bao, J.; Liu, Z.-T.; Liu, Z.-W., Cobalt nanoparticles confined in carbon matrix for probing the size dependence in Fischer-Tropsch synthesis. *J. Catal.* **2019**, *369*, 143-156.
23. Cheng, K.; Subramanian, V.; Carvalho, A.; Ordonsky, V. V.; Wang, Y.; Khodakov, A. Y., The role of carbon pre-coating for the synthesis of highly efficient cobalt catalysts for Fischer–Tropsch synthesis. *J. Catal.* **2016**, *337*, 260-271.
24. Liu, C.; He, Y.; Wei, L.; Zhang, Y.; Zhao, Y.; Hong, J.; Chen, S.; Wang, L.; Li, J., Hydrothermal carbon-coated TiO₂ as support for Co-based catalyst in Fischer–Tropsch synthesis. *ACS Catal.* **2018**, *8* (2), 1591-1600.
25. Tauster, S. J.; Fung, S. C.; Garten, R. L., Strong metal-support interactions. Group 8 noble

- metals supported on titanium dioxide. *J. Am. Chem. Soc.* **1978**, *100* (1), 170-175.
26. Bradford, M. C. J.; Vannice, M. A., Catalytic reforming of methane with carbon dioxide over nickel catalysts I. Catalyst characterization and activity. *Appl. Catal. A: Gen.* **1996**, *142* (1), 73-96.
27. Vannice, M. A.; Garten, R. L., Metal-support effects on the activity and selectivity of Ni catalysts in CO H₂ synthesis reactions. *J. Catal.* **1979**, *56* (2), 236-248.
28. Baker, R. T. K.; Prestidge, E. B.; Garten, R. L., Electron microscopy of supported metal particles II. Further studies of Pt/TiO₂. *J. Catal.* **1979**, *59* (2), 293-302.
29. Chien, S.-H.; Shelimov, B. N.; Resasco, D. E.; Lee, E. H.; Haller, G. L., Characterization of the interaction between rhodium and titanium oxide by XPS. *J. Catal.* **1982**, *77* (1), 301-303.
30. Sexton, B. A.; Hughes, A. E.; Foger, K., XPS investigation of strong metal-support interactions on Group IIIa–Va oxides. *J. Catal.* **1982**, *77* (1), 85-93.
31. Santos, J.; Phillips, J.; Dumesic, J. A., Metal-support interactions between iron and titania for catalysts prepared by thermal decomposition of iron pentacarbonyl and by impregnation. *J. Catal.* **1983**, *81* (1), 147-167.
32. Bowker, M.; Stone, P.; Morrall, P.; Smith, R.; Bennett, R.; Perkins, N.; Kvon, R.; Pang, C.; Fourre, E.; Hall, M., Model catalyst studies of the strong metal–support interaction: Surface structure identified by STM on Pd nanoparticles on TiO₂(110). *J. Catal.* **2005**, *234* (1), 172-181.
33. van de Loosdrecht, J.; van der Kraan, A. M.; van Dillen, A. J.; Geus, J. W., Metal-support interaction: Titania-supported and silica-supported nickel catalysts. *J. Catal.* **1997**, *170* (2), 217-226.
34. Taghavi, S.; Asghari, A.; Tavasoli, A., Enhancement of performance and stability of graphene nano sheets supported cobalt catalyst in Fischer–Tropsch synthesis using graphene functionalization. *Chem. Eng. Res. Des.* **2017**, *119*, 198-208.
35. Cheng, Q.; Zhao, N.; Lyu, S.; Tian, Y.; Gao, F.; Dong, L.; Jiang, Z.; Zhang, J.; Tsubaki, N.; Li, X., Tuning interaction between cobalt catalysts and nitrogen dopants in carbon nanospheres to promote Fischer-Tropsch synthesis. *Appl. Catal. B: Environ.* **2019**, *248*, 73-83.
36. Nikulshin, P. A.; Salnikov, V. A.; Mozhaev, A. V.; Minaev, P. P.; Kogan, V. M.; Pimerzin, A. A., Relationship between active phase morphology and catalytic properties of the carbon–alumina-supported Co(Ni)Mo catalysts in HDS and HYD reactions. *J. Catal.* **2014**, *309*, 386-396.
37. Xiong, H.; Schwartz, T. J.; Andersen, N. I.; Dumesic, J. A.; Datye, A. K., Graphitic-carbon layers on oxides: Toward stable heterogeneous catalysts for biomass conversion reactions. *Angew. Chem. Int. Ed.* **2015**, *54* (27), 7939-7943.
38. Gao, S.; Hong, J.; Xiao, G.; Chen, S.; Zhang, Y.; Li, J., Evolution of cobalt species in glow discharge plasma prepared CoRu/SiO₂ catalysts with enhanced Fischer-Tropsch synthesis performance. *J. Catal.* **2019**, *374*, 246-256.
39. Wang, B.; Xiong, Y.; Han, Y.; Hong, J.; Zhang, Y.; Li, J.; Jing, F.; Chu, W., Preparation of stable and highly active Ni/CeO₂ catalysts by glow discharge plasma technique for glycerol steam reforming. *Appl. Catal. B: Environ.* **2019**, *249*, 257-265.
40. Jiang, J.; Zou, J.; Wee, A. T. S.; Zhang, W., Use of single-layer g-C₃N₄/Ag hybrids for surface-

- enhanced Raman scattering (SERS). *Scientific Reports* **2016**, 6, 34599.
41. Li, Y. G.; Wee, A. T. S.; Huan, C. H. A.; Li, W. S.; Pan, J. S., Reactive atom synthesis and characterization of C₃N₄ crystalline films. *Surf. Interface Anal.* **1999**, 28 (1), 221-225.
42. Wei, J.; Hing, P.; Mo, Z. Q., TEM, XPS and FTIR characterization of sputtered carbon nitride films. *Surf. Interface Anal.* **1999**, 28 (1), 208-211.
43. Li, H.; Jing, Y.; Ma, X.; Liu, T.; Yang, L.; Liu, B.; Yin, S.; Wei, Y.; Wang, Y., Construction of a well-dispersed Ag/graphene-like g-C₃N₄ photocatalyst and enhanced visible light photocatalytic activity. *RSC Adv.* **2017**, 7 (14), 8688-8693.
44. Chen, X.; Kuo, D.-H.; Lu, D., Nanonization of g-C₃N₄ with the assistance of activated carbon for improved visible light photocatalysis. *RSC Adv.* **2016**, 6 (71), 66814-66821.
45. Ojha, N.; Bajpai, A.; Kumar, S., Visible light-driven enhanced CO₂ reduction by water over Cu modified S-doped g-C₃N₄. *Catal. Sci. Technol.* **2019**, 9, 4598-4613.
46. Ge, L.; Han, C.; Liu, J.; Li, Y., Enhanced visible light photocatalytic activity of novel polymeric g-C₃N₄ loaded with Ag nanoparticles. *Appl. Catal. A: Gen.* **2011**, 409-410, 215-222.
47. Shalom, M.; Gimenez, S.; Schipper, F.; Herraiz-Cardona, I.; Bisquert, J.; Antonietti, M., Controlled Carbon Nitride Growth on Surfaces for Hydrogen Evolution Electrodes. *Angew. Chem. Int. Ed.* **2014**, 53 (14), 3654-3658.
48. Chang, F.; Xie, Y.; Li, C.; Chen, J.; Luo, J.; Hu, X.; Shen, J., A facile modification of g-C₃N₄ with enhanced photocatalytic activity for degradation of methylene blue. *Appl. Surf. Sci.* **2013**, 280, 967-974.
49. Guo, F.; Shi, W.; Wang, H.; Han, M.; Li, H.; Huang, H.; Liu, Y.; Kang, Z., Facile fabrication of a CoO/g-C₃N₄ p-n heterojunction with enhanced photocatalytic activity and stability for tetracycline degradation under visible light. *Catal. Sci. Technol.* **2017**, 7 (15), 3325-3331.
50. Long, B.; Lin, J.; Wang, X., Thermally-induced desulfurization and conversion of guanidine thiocyanate into graphitic carbon nitride catalysts for hydrogen photosynthesis. *J. Mater. Chem. A* **2014**, 2 (9), 2942-2951.
51. Thaweesak, S.; Lyu, M.; Peerakiatkhajohn, P.; Butburee, T.; Luo, B.; Chen, H.; Wang, L., Two-dimensional g-C₃N₄/Ca₂Nb₂TaO₁₀ nanosheet composites for efficient visible light photocatalytic hydrogen evolution. *Appl. Catal. B: Environ.* **2017**, 202, 184-190.
52. Qin, J.; Huo, J.; Zhang, P.; Zeng, J.; Wang, T.; Zeng, H., Improving the photocatalytic hydrogen production of Ag/g-C₃N₄ nanocomposites by dye-sensitization under visible light irradiation. *Nanoscale* **2016**, 8 (4), 2249-2259.
53. Wang, Y.; Lu, Y.; Cao, Q.; Fang, W., A magnetic CoRu-CoO_x nanocomposite efficiently hydrogenates furfural to furfuryl alcohol at ambient H₂ pressure in water. *Chem. Comm.* **2020**, 56, 3765-3768.
54. Yang, Y.; Jia, L.; Hou, B.; Li, D.; Wang, J.; Sun, Y., The effect of nitrogen on the autoreduction of cobalt nanoparticles supported on nitrogen-doped ordered mesoporous carbon for the Fischer-Tropsch synthesis. *ChemCatChem* **2014**, 6 (1), 319-327.

- 1
2
3 55. Carvalho, A.; Ordonsky, V. V.; Luo, Y.; Marinova, M.; Muniz, A. R.; Marcilio, N. R.;
4 Khodakov, A. Y., Elucidation of deactivation phenomena in cobalt catalyst for Fischer-Tropsch
5 synthesis using SSITKA. *J. Catal.* **2016**, *344*, 669-679.
6
7 56. Hao, Q.-Q.; Wang, G.-W.; Liu, Z.-T.; Liu, Z.-W., Insights into structural and chemical
8 properties of activated montmorillonite for Fischer-Tropsch synthesis over supported cobalt
9 catalysts. In *Nanocatalysis for Fuels and Chemicals*, American Chemical Society: 2012; Vol. 1092,
10 pp 167-193.
11
12 57. Ahn, C.-I.; Koo, H. M.; Jo, J. M.; Roh, H.-S.; Lee, J.-B.; Lee, Y.-J.; Jang, E. J.; Bae, J. W.,
13 Stabilized ordered-mesoporous Co₃O₄ structures using Al pillar for the superior CO hydrogenation
14 activity to hydrocarbons. *Appl. Catal. B: Environ.* **2016**, *180*, 139-149.
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60