Self-assembled Monolayer Enables HTL-free Organic Solar Cells with 18% Efficiency and Improved Operational Stability

Yuanbao Lin,[†] Yuliar Firdaus,^{†,} Furkan H. Isikgor,[†] Mohamad Insan Nugraha,[†] Emre Yengel,[†] George T. Harrison,[†] Rawad Hallani,[†] Abdulrahman El-Labban,[†] Hendrik Faber,[†] Chun Ma,[†] Xiaopeng Zheng,[§] Anand Subbiah,[†] Calvyn T. Howells,[†] Osman M. Bakr,[§] Iain McCulloch,[†] Stefaan De Wolf,[†] Leonidas Tsetseris,[‡] Thomas D. Anthopoulos[†]*

[†] King Abdullah University of Science and Technology (KAUST), KAUST Solar Center (KSC), Thuwal 23955, Saudi Arabia

[§] King Abdullah University of Science and Technology (KAUST), Physical Science and Engineering Division (PSE), Thuwal 23955, Saudi Arabia.

‡ Department of Physics, National Technical University of Athens, Athens GR-15780,
Greece

AUTHOR INFORMATION

Corresponding Author

* Email: thomas.anthopoulos@kaust.edu.sa

* Email: yuliar.firdaus@kaust.edu.sa

TOC GRAPHICS

HTL-free OPV with 18% PCE

ABSTRACT

We report on bulk-heterojunction (BHJ) organic photovoltaics (OPVs) using the self-assembled monolayer (SAM) 2PACz as a hole-selective interlayer functionalized directly onto the indium tin oxide (ITO) anode. The 2PACz is found to change the work function of ITO while simultaneously affecting the morphology of the BHJ deposited atop. Cells with PM6:N3 BHJ and ITO-2PACz anode exhibit a power conversion efficiency (PCE) of 16.6%, which is higher than that measured for bare ITO (6.45%) and ITO/PEDOT:PSS (15.94%) based devices. The enhanced performance is attributed to lower contact-resistance, reduced bimolecular recombination losses, and improved charge transport within the BHJ. Importantly, the ITO-2PACz-based OPVs show a dramatically improved operational stability when compared with PEDOT:PSS-based cells. When the ITO-2PACz anode is combined with the ternary PM6:BTP-eC9:PC₇₁BM BHJ, the resulting cells exhibit a maximum PCE of 18.03%, further highlighting the potential of engineered SAMs for use in hole-selective contacts in high-performance OPVs.

Main Text

Focused research efforts in recent years have propelled the power conversion efficiencies (PCEs) of organic photovoltaics (OPVs) to over 18%.¹⁻⁵ Despite the exceptional progress, however, the achieved performance still lags behind the recently predicted PCE values

of over 20%.⁶⁻⁷ To achieve this level of performance further advances in donor and acceptor materials are needed. Equally important is the development of improved interfacial materials, not only for reaching the predicted PCE, but also for enhancing the operational stability of OPVs.⁸ To this end, many studies have focused on novel interfacial materials, particularly electron transport layers (ETLs) such as ZnO,⁹ poly[9,9-bis(6'-bromohexyl)fluorene-alt-*co*-1,4-phenylene (PFN-Br),¹⁰ perylene diimide amino N-oxide (PDINO),¹¹ 3-[6-(diphenylphosphinyl)-2-naphthalenyl]-1,10-phenanthroline (Phen-NaDPO),¹² and Phen-NaDPO:Sn(SCN)₂.¹³ In contrast, progress in hole transport layers (HTLs) currently lags behind that of ETL materials. PEDOT:PSS and its derivatives are still widely used as HTLs for standard structure OPVs¹⁴⁻¹⁵, offering multiple attractive features in terms of processability, good layer coverage, high work function (WF)¹⁶, and tunable wettability that makes them compatible with a diverse range of bulk-heterojunction (BHJ) systems.¹⁷ Despite the promising characteristics of PEDOT:PSS, however, its high acidity and hygroscopicity are known to compromise the long term operational stability of the devices.¹⁸⁻¹⁹

1
2
3 HTL-free structures are widely used nowadays to enhance both the efficiency and
4
5
6 stability of metal halide perovskite solar cells (PSCs), with some additional advantages
7
8
9 including low cost, simpler fabrication, decreased parasitic absorption, and high
10
11
12 reproducibility of PSCs.²⁰ Recently, self-assembled monolayers (SAMs) of organic
13
14
15 molecules such as [2-(9*H*-Carbazol-9-yl)ethyl]phosphonic acid (2PACz) have been
16
17
18 studied and successfully used as hole-selective contacts for HTL-free p-i-n PSCs.²⁰ The
19
20
21 2PACz SAM offers a well-suited energetic alignment and a significantly reduced non-
22
23
24 radiative recombination at the contact/perovskite interface, leading to HTL-free PSCs with
25
26
27 a PCE of 20.9%. These devices outperform those based on the benchmark HTL
28
29
30 poly[bis(4-phenyl)(2,4,6-trimethylphenyl)amine] (PTAA).
31
32
33
34
35
36
37
38

39 Despite the demonstrated potential in PSCs, the SAM-based HTL-free approach has
40
41
42 yet to be fully exploited in state-of-the-art OPVs.²¹ To date, most studies on the use of
43
44
45 SAMs in OPVs rely on their application as interfacial modifiers for electron-collecting
46
47
48 cathode electrodes (see the summary of relevant literature in **Table S1**).²²⁻³³ A notable
49
50
51 example is the C₆₀-SAM-modified ZnO nanoparticles (NPs) interlayer used in non-
52
53
54
55
56
57
58
59
60

fullerene OPVs for which simultaneous improvement of the device's PCE and photostability were achieved; the T_{80} lifetime (the time required to reach 80% of initial performance) of optimized devices was estimated to exceed 20 years.²⁹ In contrast, only a handful of studies have explored SAM modification of anode electrodes as a mean to improve the performance of OPVs (**Table S1**). The lack of interest is most likely the result of low PCEs (<4%) for SAM-based OPVs as compared to state-of-the-art PEDOT:PSS-based cells.²⁵⁻²⁶

Here we show that 2PACz-modified ITO (ITO-2PACz) can be used as an efficient hole-collecting anode in standard architecture OPVs based on poly[(2,6-(4,8-bis(5-(2-ethylhexyl-3-fluoro)thiophen-2-yl)-benzo[1,2-b:4,5-b']dithiophene))-alt-(5,5-(1',3'-di-2-thienyl-5',7'-bis(2-ethylhexyl)benzo[1',2'-c:4',5'-c']dithiophene-4,8-dione)] (PM6) and N3, as the donor polymer and non-fullerene molecular acceptor, respectively. The ensuing devices show an impressive PCE of 16.6% which is higher than control cells based on bare ITO (6.45%) and optimized ITO/PEDOT:PSS-based (15.94%) anodes. We show that the presence of 2PACz increases the WF of ITO aiding hole extraction. We also find that the cells based on 2PACz-modified ITO exhibit a longer carrier lifetime, larger carrier

densities, and lower bimolecular recombination compared to bare ITO and ITO/PEDOT:PSS-based OPVs. Furthermore, optical simulation of the ITO-2PACz-based cells suggests that the higher current density is due to enhanced optical field intensity within the BHJ of the device. Importantly, SAM-based OPVs also show a major improvement in their operational stability as compared to control ITO/PEDOT:PSS-based cells. To this end, our analysis shows that in comparison to ITO/PEDOT:PSS-based cells, aged ITO-2PACz-based devices retain their charge carrier mobilities and charge trapping/detrapping characteristics, ultimately leading to the limited performance degradation observed. Moreover, when the ITO-2PACz electrode is combined with the ternary PM6:BTP-eC9:PC₇₁BM BHJ, the resulting cells exhibit a remarkable maximum PCE of 18.03%, which is significantly higher than control cells based on PEDOT:PSS (17.52%).

The chemical structure of 2PACz and a schematic illustration of the SAM on ITO (ITO-SAM) are shown in **Figure 1a**. The SAM molecules attach to the metal oxide surfaces via coordination of a phosphoryl oxygen to a metallic Lewis acid.³⁴ In this study,

the 2PACz solution (1 mg/ml in ethanol) was spin-coated directly on oxygen plasma-treated ITO resulting in strong chemisorption on its surface (**Figure 1a**).³⁵ From the UV-Vis absorbance spectra in **Figure 1b** it is evident that the ITO-2PACz exhibits lower absorbance than the conventional ITO/PEDOT:PSS anode electrode in the range from 350 to 415 nm and 500 to 1000 nm, which could be beneficial for application in OPVs and will be discussed later.

With the aid of Density Functional Theory (DFT) calculations, we confirmed that there exist several chemisorption configurations, with bidentate or tridentate types of binding between the 2PACz molecules and the ITO surface, as shown in **Figure S1**. Based on the calculated energies, the most stable chemisorbed structure is shown in **Figure S1a** and entails a tridentate pattern with covalent bonds between all three acidic O atoms of a 2PACz molecule and an underlying substrate atom. In an effort to detect direct evidence of the presence of atomic species related to 2PACz on the surface of ITO, we utilized X-ray photoelectron spectroscopy (XPS). **Figure S2a** shows the XPS data in the whole scan region (0-700 eV). The existence of signals related to N and P can directly be attributed

to the presence of 2PACz molecules, while the strong presence of In originates from the ITO electrode beneath due to the monolayer nature of the 2PACz SAM.

Figure 1c shows the high resolution C1s binding energy region for the ITO-2PACz electrode, showing a characteristic signal of the 2PACz and its carbazole component.³⁶⁻
³⁷ The measured spectra can be satisfactory fit with five main peaks (287-282 eV) with a mixed Lorentzian/Gaussian line shape and a Shirley background. The additional peaks between 288-293 eV originate from π - π^* shake-up satellite loss.³⁷ The peak at 284.7 eV with a relative peak area of 0.155, is assigned to the C=N bond in the carbazole unit of the 2PACz, while the peak at 285.8 eV with a relative area of 0.074 is attributed to the C-N bond in the aliphatic linking chain.³⁷ The peak at 285.2 eV with a relative peak area of 0.071, on the other hand, is assigned to the C-P bond in agreement with the literature.³⁸⁻
³⁹ The scaling of relative peak areas is in line with the number of relevant atoms present in 2PACz (**Figure 1a**). Small contribution from adventitious C-O ($\approx$ 286 eV) cannot be excluded and most likely overlap with signal originating from C-N.

The coverage of 2PACz on ITO can be estimated using different methods including cyclic voltammetry⁴⁰ and XPS.⁴¹⁻⁴² In the present study we employed the XPS technique due to its availability in our laboratory. As explained in detail in supporting information, the ratio of P(2p)/In(3d_{5/2}) signal is predicted for a close-packed 2PACz ($\theta=1$) overlayer on an ITO surface after accounting for electron attenuation, atomic density and core level sensitivity (**Figure S2** and **Table S2**).⁴³ Overall an average coverage of $0.92 \theta \pm 0.1 \theta$ is determined, equating to $\approx 4.05 \times 10^{14}$ molecules/cm². The latter value is in line with that measured by Paniagua *et al.* for a saturated phosphonic acid/ITO surface.⁴¹ This analysis supports the facile formation of a highly dense coverage of 2PACz and a suitable hole contact interface. Further evidence of the presence of 2PACz on the ITO surface was obtained by energy-dispersive X-ray spectroscopy (EDX) measurements (**Figure 1d**). The measured distribution of P (EDX: P) on ITO suggests a high coverage by the 2PACz SAM, as would be expected for a dense monolayer, and is qualitatively similar to that observed for the S distribution in the ITO/PEDOT:PSS (EDX: S) electrode. All aforementioned results suggest that 2PACz functionalized on the surface of ITO, forming a dense monolayer.

Figure 1. (a) Chemical structure of 2PACz and schematic illustration of the ITO-2PACz electrode. (b) UV-Vis absorbance spectra of ITO, ITO-2PACz, and ITO/PEDOT:PSS films. (c) X-ray photoelectron spectroscopy (XPS) of the C1s region of ITO-2PACz. (d) Elemental mapping of In (red) for ITO, P (yellow) for 2PACz, and S (blue) for PEDOT:PSS obtained using EDX (scale bar: 2 μ m). (e) Surface height histograms of ITO, ITO-2PACz, and ITO/PEDOT:PSS films obtained by AFM.

Atomic force microscopy (AFM) was also used to study the surface topography of ITO, ITO-2PACz, and ITO/PEDOT:PSS anode electrodes. **Figure S3** shows the AFM images, while **Figure 1e** displays the corresponding surface height histograms extracted from those images. The ITO-2PACz electrode exhibits a smoother surface than bare ITO, which is manifested in the slightly lower root-mean-square (RMS) surface roughness

value of 1.3 nm (ITO = 1.6 nm) and shifts the entire distribution towards smaller height values. The ITO/PEDOT:PSS electrode appears significantly smoother with a surface RMS of 0.89 nm due to the narrower height distribution.

Next, we used photoelectron spectroscopy in air (PESA) to determine the WF of ITO electrode before and after 2PACz functionalization (**Figure S4** and **Table S3**). As shown in **Figure 2a**, the WF of ITO-2PACz (-5.45 eV) is significantly deeper than the value measured for the bare ITO (-4.86 eV) and ITO/PEDOT:PSS (-5.15 eV) electrodes. Kelvin probe measurements confirm the WF trend revealed by the PESA measurements (see comparison in **Table S3**). We have also evaluated the WF for all pertinent electrode structures using DFT calculations (**Figures 2b-c**). For the bare (111) ITO surface we derive a WF of -4.70 eV, which is in good agreement with the experimentally determined value i.e. -4.86 eV. For the same ITO surface functionalized with 2PACz in the configuration shown in **Figure S1a**, and considering a surface coverage of 5.04×10^{13} molecules/cm², we calculate a WF of -4.90 eV. The latter value agrees with the trend of an increased WF upon functionalization, albeit to a lesser extent compared to the

experimentally measured change described above. We note, however, that previous studies of Hotchkiss *et al.* found a monotonic increase of the absolute values of the WF as a function of the coverage of ITO surfaces functionalized with phosphonic acids.⁴⁴ Hence, our calculated WF (-4.90 eV) for the relative low 2PACz coverage (5.04×10^{13} molecules/cm²) is consistent with the measured WF (-5.45 eV) at higher coverages (4.05×10^{14} molecules/cm²).

Figure 2. (a) The work function of ITO, ITO-2PACz, ITO/PEDOT:PSS, and HOMO level of PM6 measured via the photoelectron spectroscopy in air (PESA) technique. Calculated electrostatic potentials for (b) the (111) surface of ITO and (c) the surface of ITO with a

2PACz SAM (results obtained with DFT slab calculations on supercells with stoichiometry $\text{In}_{60}\text{Sn}_4\text{O}_{96}$). The inset shows side views of the structures. (In: gray, Sn: blue, O: red, C: light gray, N: blue, P: orange, H: white spheres). (d) The dark current through a hole-only device based on ITO, 2PACz, PEDOT:PSS. The inset shows the schematic of the hole-only cell's architecture.

To investigate the impact of 2PACz functionalization on the characteristics of hole-injection from an ITO electrode into an organic semiconductor, we fabricated hole-only devices. **Figure 2d** shows the dark current-voltage curves for a hole-only device based on the donor polymer PM6, while the inset shows the schematic of the device architecture employed. Here, PM6 is sandwiched between either ITO, ITO/PEDOT:PSS or ITO-2PACz, and an Ohmic hole-injecting Ag/MoO₃ contact. Since the PM6 is characterized by a moderately deep highest occupied molecular orbital (HOMO) energy level of 5.18 eV (**Figure 2a**), hole injection from ITO (WF = -4.86 eV) is expected to be suppressed due to the presence of a substantial potential barrier of ≈ 0.32 eV. As evident from **Figure 2d**, the current injected from bare ITO (forward bias) is indeed significantly lower than that injected from the Ohmic hole-injecting Ag/MoO₃ contact under reverse bias. The hole injection improves drastically upon inserting either a 40-nm-thick layer PEDOT:PSS

between ITO and PM6 or by functionalizing the 2PACz SAM onto ITO. In both cases, a remarkable transition from highly asymmetric (bare ITO) to nearly symmetric forward and reverse $J-V$ curves occurs highlighting the hole-transport enabling role of PEDOT:PSS and 2PACz. Importantly, devices utilizing ITO-2PACz as the hole-injecting electrode exhibit slightly higher current than those based on PEDOT:PSS, especially at lower biasing levels, possibly indicating an improved Ohmic contact as compared to PEDOT:PSS. In addition, the maximum hole mobility (μ_h), calculated via the space-charge limited current (SCLC) method, for the 2PACz-based device is slightly higher ($1.1 \times 10^{-3} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$) than PEDOT:PSS-based devices ($9.1 \times 10^{-4} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$), further supporting the existence of an improved hole-injecting contact in the case of ITO-2PACz.

The surface energy of ITO/HTL is another significant parameter that affects the morphology of the BHJ layer in OPVs. We performed contact-angle measurements for ITO and ITO-2PACz (**Figure S5**), from which the surface energies were inferred using the Owens equation⁴⁵

$$\gamma_1(1 + \cos\theta) = 2(\gamma_s^D\gamma_1^D)^{1/2} + 2(\gamma_s^P\gamma_1^P)^{1/2} \quad (\text{Eq. 1})$$

here γ_l is the surface energy of liquid, which is composed of dispersion component γ and polarity component γ_p . Similarly, γ_s is the surface energy of solid, which is composed of dispersion component γ and polarity component γ_p . The results are summarized in **Table S4** and show that the ITO-2PACz has a higher surface energy (68.7 mN/m) than both the bare ITO (57.9 mN/m) and ITO/PEDOT:PSS (59.8 mN/m) electrodes suggesting the possibility of a stronger interaction between the BHJ solution and the ITO-2PACz surface during spin-coating. To probe this further we used AFM to measure the surface morphology of PM6:N3 layer. The chemical structure and energy levels of the materials are shown in **Figure S6**, while **Figure S7** presents the AFM images and surface height histogram for the BHJ deposited onto the various surfaces. The PM6:N3 BHJ deposited on bare ITO exhibit a relatively broad rough surface (RMS = 2.3 nm). In contrast, ITO/PEDOT:PSS and ITO-2PACz show more homogeneous morphologies and lower surface roughness of 1.5 and 1.2 nm, respectively. This trend is better illustrated in the surface height histograms of **Figure S7d**, where the height distribution for the BHJ on ITO-2PACz undergoes a clear shift towards lower heights indicating surface smoothing. Moreover, both the topography and phase images reveal the existence of a nanofiber

structure in the PM6:N3 BHJ layer, deposited onto ITO-2PACz electrodes. The latter is most likely the result of a particular interaction between the semiconductor solution and the ITO-2PACz electrode surface during spin coating. The different BHJ morphology is expected to lead to different optoelectronic properties, which are discussed later.

To explore the potential of 2PACz as a possible replacement for PEDOT:PSS in OPVs, we fabricated HTL-free cells based on the standard architecture shown in **Figure 3a** using PM6:N3 as the BHJ. The experimental conditions used to functionalize the 2PACz onto ITO e.g. (annealing temperatures, plasma cleaning time) were carefully optimized and the results are summarized in **Figures S8-S10** and **Tables S5-S7**. Representative $J-V$ curves obtained from the resulting OPV cells are shown in **Figure 3b** while a summary of the key device parameters is provided in **Table 1**. Cells with bare ITO exhibit a maximum PCE of 6.45% with a short-circuit current (J_{SC}) of 23.32 mA/cm², an open circuit voltage (V_{OC}) of 0.515 V, a fill factor (FF) of 53.7%, and series resistance (R_S) of 5.30 Ω cm². OPVs based on ITO/PEDOT:PSS show improved performance with a maximum PCE of 15.94% which is comparable to the published result for PM6:N3 BHJ

OPVs (15.98%) based on the standard device architecture.⁴⁶ Remarkably, when 2PACz SAM was applied atop of ITO (ITO-2PACz), the PCE increases to 16.6%, accompanied by an increased J_{SC} (26.53 mA/cm²), an improved FF (74.5%), and a reduced R_S (2.47 Ω cm²).

Figure 3. (a) Schematic of the standard cell architectures employed. (b) $J-V$ curves of PM6:N3 solar cells based on ITO, ITO-2PACz, and ITO/PEDOT:PSS. (c) external quantum efficiency (EQE) curves of same OPV. (d) Optical simulations for the exciton generation rate profiles in the studied SAM and PEDOT:PSS-based OPV devices. Light intensity dependence of (f) V_{OC} , and (e) bimolecular recombination rate constant (k_{rec}) for the same cells. (f) Nyquist plots of ITO, 2PACz, and PEDOT:PSS-based devices.

Table 1. Summary of key operating parameters of OPVs based on PM6:N3 BHJs with different anode electrode systems measured under illumination of AM 1.5G (100 mW/cm²).

Anode electrode	V_{OC} [V]	J_{SC} [mA/cm ²]	J_{cal} [mA/cm ²]	FF [%]	PCE [%]	R_s [Ω cm ²]
ITO (bare)	0.515	23.32	23.15	53.7	6.45 (5.93±0.38) ^a	5.30
ITO-2PACz	0.840	26.53	26.14	74.5	16.60 (16.30±0.22)	2.47
ITO/PEDOT:PSS	0.842	25.64	25.28	73.9	15.94 (15.72±0.14)	2.94

^aPCE_{avg} values in brackets represent averages from 15 devices.

Figure 3c displays the external quantum efficiency (EQE) spectra of the PM6:N3-based OPV cells. For all devices, the integrated current density (J_{cal}) deduced from the EQE spectra matches well the values obtained from the J - V measurements within $\pm 1.5\%$ (**Table 1**). The ultrathin nature of the 2PACz SAM functionalized on ITO enables cells with a higher photoresponse in the range of 345-440 nm and 510-860 nm, as compared to ITO/PEDOT:PSS-based cells, ultimately resulting in higher J_{cal} (**Figure 3c**). This significant enhancement likely arises from the lower absorbance of the ITO-2PACz compared to ITO/PEDOT:PSS anodes (**Figure 1b**). **Figure S11** overlays internal quantum efficiency (IQE) spectra, removing the dependence on optical absorption. The average IQEs of an OPV with ITO-2PACz equal to 90.5% for the spectra range 450 - 850 nm,

reaching up to 98.8% at 570 nm. In comparison, the average IQEs for the OPV with PEDOT:PSS is 85.9% in the same range. The higher average IQEs from SAM-based devices suggests that most of the absorbed photons are converted to free carriers with higher efficiency and then collected at the corresponding electrodes.

To better understand the influence of 2PACz and PEDOT:PSS on the optical properties of the cells, we simulated the optical field intensity across the device using the transfer-matrix formalism.⁴⁷ The optical constants (refractive index n and extinction coefficient k) for all layers in the device were measured independently using spectroscopic ellipsometry (**Figure S12a-b**). As shown in **Figure 3d** and **Figure S12c-e**, the cell based on ITO-2PACz exhibits a higher optical electric field intensity and exciton generation rate within the BHJ, and a lower parasitic absorption than the ITO/PEDOT:PSS device. These calculations corroborate the experimental results and further highlight the potential of ITO-2PACz for application in high-performance OPVs. The calculated maximum J_{SC} (IQE=100%) of SAM-based devices (**Figure 12f**) exceeds

PEDOT:PSS-based cell when BHJ thickness over 80 nm, in agreement with $J-V$ results in Figure 3b.

Next, the impact of 2PACz on charge-carrier recombination in the devices was studied via light-intensity dependent $J-V$ measurements, transient photovoltage (TPV), and charge-extraction (CE) measurements (Figure S13a-c). Figure 3e shows the variation of V_{OC} vs. light intensity plotted on a semi-logarithmic scale with the data fitted to $V_{OC} \propto SkT/q \ln(I)$, where S , k , T , q , and I are the slope, Boltzmann constant, the temperature, the elementary charge, and light intensity, respectively. If trap-assisted recombination is involved, a stronger dependence of V_{OC} on the light intensity with a slope greater than kT/q will be observed.⁴⁸ The dependence of V_{OC} on the light intensity for the ITO-2PACz cells exhibits a slope of $1.04 kT/q$, which is significantly smaller than the $1.59 kT/q$ measured for bare ITO-based devices, and still lower than $1.18 kT/q$ measured for the optimized ITO/PEDOT:PSS-based cell. These results highlight the ability of the ITO-2PACz anode to reduce the trap-assisted recombination, which partly reflects in the improved PCE.

Further insights into the charge carrier dynamics were obtained by measuring the charge carrier lifetime (τ) and carrier density using TPV and CE measurements, respectively, under varying light intensity conditions (**Figure S13d-e**).⁴⁹ The carrier lifetime in ITO-2PACz-based devices is found to be consistently longer across the entire light intensity range investigated. Representative values include those measured at 200 mW/cm² yielding 2.7 μ s for ITO-2PACz, 1.8 μ s for ITO/PEDOT:PSS, and 0.4 μ s for bare ITO (**Figure S13d**). The consistently larger τ for ITO-2PACz-based cells is indicative of a lower carrier recombination. Interestingly, higher carrier densities are also measured for OPVs with ITO-2PACz as compared to ITO/PEDOT:PSS and bare ITO-based cells, in line with the higher J_{SC} (**Table 1**). We also inferred the bimolecular recombination rate constants (k_{rec}) from the carrier lifetime and densities according to $k_{rec} = 1/[(\lambda+1)n\tau]$, where λ is the recombination order.⁵⁰ As shown in **Figure 3f**, k_{rec} for the ITO-2PACz device is lower than that measured for the bare ITO and ITO/PEDOT-PSS-based cells at all light densities investigated.

Electrochemical Impedance Spectroscopy (EIS) measurements were performed to examine the interface resistance in the various OPVs in the dark while applying a bias voltage equal to

V_{OC} .⁵¹ Nyquist plots shown in **Figure S14** were fitted by using the equivalent circuit model following a previous report⁵² and the relevant data are summarized in **Table S8**. The interface resistances (R_2) of the devices with bare ITO, ITO-2PACz, and ITO/PEDOT:PSS are estimated to be 540.4, 37.8, and 43.5 Ω , respectively. The results show the advantage of ITO-2PACz to enable a lower interface resistance thanks to its deeper WF, ultimately leading to cells with higher FF and overall PCE.^{16, 53} Furthermore, the average carrier transition time (τ_{avg}) of the equivalent circuit was calculated using:⁵²

$$\tau_{avg} = R_1 \times C_1 \quad (2)$$

where R_1 and C_1 are the resistance and capacitance of the active layer, respectively. The calculated τ_{avg} values for OPVs based on bare ITO, ITO-2PACz, and ITO/PEDOT:PSS anodes are 0.4, 3.1, and 2.1 μs , respectively, and are consistent with the τ values calculated from TPV measurements.

We have also investigated the operational stability of optimized PM6:N3 OPVs based on different anode electrodes given its paramount importance for any practical application of the technology.⁵⁴⁻⁵⁵ We performed maximum power point tracking (MPPT) measurements while storing the devices under vacuum. A tracking step of 60 s was used while the device was subjected to continuous illumination supplied by a white colour light-

emitting diode (LED) with a light intensity of 200 mW/cm². The normalized PCE plotted as a function of light-soaking time is presented in **Figure 4a**. After 120 h of continuous light-soaking, the ITO-2PACz-based cell retains 74% of its initial PCE, while the performance of the PEDOT:PSS-based cell deteriorates rapidly to ≈20% of its initial PCE after 50 h. Although preliminary, the results indicate that ITO-2PACz could potentially help to enhance the lifetime of state-of-the-art OPVs.

To gain better insight into the device degradation mechanism, both fresh and aged devices were analyzed using transient photocurrent (TPC) measurements, a highly versatile technique often used to study space-charge effects, carrier trapping and de-trapping in OPVs. Here, cells are excited with a square-shaped light pulse of varying intensity (5-200 mW/cm²) and long enough (200 μs) for the photocurrent to reach a steady state. The recorded TPC traces can then be analyzed according to three key features: (i) the initial rapid rise time, (ii) the time needed for the photocurrent to reach a quasi-steady-state, and (iii) the fall time of the photocurrent. Freshly prepared ITO/PEDOT:PSS devices exhibit fast rise and fall time response to the light pulse (**Figure 4b**). Following aging,

1
2
3 however, the same device exhibits significantly slower rise & fall times, an effect
4
5
6 particularly pronounced at illumination intensities of $< 30 \text{ mW/cm}^2$ (**Figure 4c**). The latter
7
8
9 suggests the presence of a higher number of deep electron trap states that have been
10
11
12 formed during device aging.^{56,57} In contrast, no obvious change in the characteristic
13
14
15 features of the TPC traces measured for fresh (**Figure 4d**) and aged (**Figure 4e**) ITO-
16
17
18 2PACz-based cells was found. The only noticeable difference is the slight current
19
20
21 overshoots seen at high light intensity measurements for the aged ITO-2PACz-based
22
23
24 OPV, a feature previously attributed to a change in the BHJ morphology.⁵⁸ Nevertheless,
25
26
27 the changes in the TPC traces for ITO-2PACz-based cells is negligible when compared
28
29
30 to ITO/PEDOT:PSS devices, which explains the enhanced operational stability of ITO-
31
32
33 2PACz-based OPV cells.
34
35
36
37
38
39
40
41
42

43 We also studied the impact of aging on the charge carrier mobility (μ) using the
44
45 photogenerated charge extraction by a linearly increasing voltage (photo-CELIV)
46
47
48 technique.⁵⁹ From the measured photocurrent transients (**Figure 4f**) the carrier mobility
49
50
51 can be calculated using:
52
53
54
55
56
57
58
59
60

$$\mu = 2 \frac{d^2}{3At_{max}^2 \left(1 + 0.36 \Delta j / j_0 \right)} \quad (3)$$

where d is BHJ thickness, A is the voltage rise speed of the applied voltage pulse, t_{max} is the time to reach the extraction current maximum, Δj and j_0 are the displacement and initial currents, respectively. The photo-CELIV extracted mobilities for the fresh ITO-2PACz and PEDOT:PSS-based cells are 2.55×10^{-4} and $1.87 \times 10^{-4} \text{ cm}^2 \text{V}^{-1} \text{s}^{-1}$, respectively. The higher device mobility in ITO-2PACz-based device most likely originates from the difference in the BHJ morphology and particularly to the presence of fibre-like features seen in the AFM images of **Figure S7b**. Following aging, the μ value in ITO-2PACz-based cells decreases slightly to $1.98 \times 10^{-4} \text{ cm}^2 \text{V}^{-1} \text{s}^{-1}$, while for aged ITO/PEDOT:PSS devices the drop is significantly larger ($8.78 \times 10^{-5} \text{ cm}^2 \text{V}^{-1} \text{s}^{-1}$). Once again, the results highlight the superiority of ITO-2PACz-based cells over ITO/PEDOT:PSS-based devices.

To elucidate the origin of the improved stability of SAM-based cells, EIS measurements were used to study the electrical properties of the aged ITO-2PACz/BHJ and PEDOT:PSS/BHJ interfaces (**Figure S14** and **Table S8**).⁵² Both ITO-2PACz and ITO/PEDOT:PSS-based cells exhibit similar trends of increased BHJ resistances and decreased BHJ capacitances, suggesting that the degradation of the active layer is not the primary reason for

the differences seen in the operational stability between the two cells (**Figure 4a**). However, the significantly increased interface ($43.5\ \Omega$ vs. $306.4\ \Omega$) and electrode ($17.4\ \Omega$ vs. $57.8\ \Omega$) resistance values observed for the PEDOT:PSS-based OPVs following MPPT measurements, indicate that the interface has deteriorated. In contrast, for ITO-2PACz based OPVs subjected to MPPT testing, the interface and electrode resistance changes are significantly smaller ($37.8\ \Omega$ vs. $42.1\ \Omega$ and $15.6\ \Omega$ vs. $31.8\ \Omega$, respectively), suggesting the existence of a more stable ITO-2PACz/BHJ interface.

Figure 4. (a) Evolution of normalized PCEs of PM6:N3-based BHJ OPVs based on ITO-2PACz and ITO/PEDOT:PSS anodes under maximum power point tracking (MPPT) testing. Transient short-circuit photocurrent of fresh and aged OPVs based on ITO/PEDOT:PSS (b, c) and ITO-2PACz-based cell (d-e). (f) Photo-CELIV traces measured for fresh and aged ITO-2PACz and ITO/PEDOT:PSS-based cells.

Recently, the nonfullerene acceptor BTP-eC9 has helped to increase the PCE of single junction OPV cells close to 18%.¹ The chemical structure, HOMO, and LUMO energies *via* DFT of BTP-eC9 is presented in **Figure 5a**.¹ To study the compatibility of the proposed ITO-2PACz anode with PM6:BTP-eC9:PC₇₁BM, we prepared a series of OPV cells based on ITO/PEDOT:PSS and ITO-2PACz anodes. **Figure S15** and **Table S9** summarize the different weight ratio (wt%) used for optimizing the PM6:BTP-eC9:PC₇₁BM system. As shown in **Figure 5b** and **Table 2**, cells with PEDOT:PSS HTL yield V_{OC} of 0.854 V, J_{SC} of 26.28 mA/cm², and a FF of 78.2%, resulting in a maximum PCE of 17.52%. Remarkably, OPVs based on ITO-2PACz anodes show a higher maximum PCE value of 18.03%, accompanied by a slightly lower V_{OC} (0.845 V), an increased J_{SC} (26.94 mA/cm²) and an enhanced FF (79.2%). The PCE of 18.03% is the highest PCE reported to date for OPVs utilizing SAMs either as part of the hole- or the electron-collecting electrode (see summary in **Figure 5c** and **Table S1**).²²⁻³³ The statistical PCE values from 15 devices (see insert in **Figure 5b**) demonstrate the reproducibility of these high PCE devices.

Moreover, the EQE spectra (**Figure 5d**) exhibits a higher photoresponse in the range of 380-430 nm and 500-800 nm, compared to ITO/PEDOT:PSS-based cells, ultimately contributing to the higher J_{cal} (26.65 mA/cm² vs. 26.02 mA/cm²) in **Table 2**. This trend of enhanced EQE response is similar to that measured for PM6:N3 cells employing ITO-2PACz anodes (**Figure 3c**).

Figure 5. (a) Molecular structure of BTP-eC9, and its HOMO and LUMO calculated via DFT. (b) J - V curves of PM6:BTP-eC9:PC₇₁BM solar cells based on ITO-2PACz, and ITO/PEDOT:PSS. The inset figure in (b) shows the histogram and Gaussian fit (solid lines) of PCEs measured for OPVs with ITO-2PACz (red) and ITO/PEDOT:PSS (green). (c) A summary of reported PCE values for SAM modified OPVs.²²⁻³³ (d) EQE curves of same OPV devices.

Table 2. Summary of key operating parameters of OPVs based on PM6:BTP-eC9:PC₇₁BM BHJs with different anode electrode systems measured under illumination of AM 1.5G (100 mW/cm²).

Anode electrode	V_{oc} [V]	J_{sc} [mA/cm ²]	J_{cal} [mA/cm ²]	FF [%]	PCE [%]	R_s [Ω cm ²]
ITO-2PACz	0.845	26.94	26.65	79.2	18.03 (17.70±0.16) ^a	1.52
ITO/PEDOT:PSS	0.854	26.28	26.02	78.2	17.52 (17.52±0.15)	2.23

^aPCE_{avg} values in brackets represent averages from 15 devices.

In conclusion, we have successfully integrated the 2PACz SAM as a hole-selective interlayer in HTL-free BHJ OPVs. The functionalization of 2PACz from solution directly onto ITO was found to increase its work function and decrease the contact resistance with the BHJ layer. AFM analysis showed that solution-processing of the PM6:N3 BHJ onto ITO-2PACz anode electrodes affects the BHJ layer morphology resulting in a nano-fibrous surface texture. Solar cells based on PM6:N3 BHJ and 2PACz-modified ITO yielded a maximum PCE of 16.60%; a higher value than control cells based on PEDOT:PSS (15.94%). Analysis of the carrier recombination dynamics revealed that the enhanced performance is primarily due to improved optical absorption within the BHJ and enhanced charge extraction. Importantly, the ITO-2PACz-based OPVs showed

1
2
3
4 remarkably enhanced operational stability as compared to ITO/PEDOT:PSS-based cells.
5
6

7 The ITO-2PACz-based cell retained 74% of its initial performance after 120 hours MPPT,
8
9
10 while the ITO/PEDOT:PSS devices degraded to 20% of their pre-aging performance level
11
12
13 after 50 hours MPPT. The improved stability was attributed to negligible change in the
14
15
16 interface between ITO-2PACz and the BHJ, as well as the ability of the cells to maintain
17
18
19 the high charge-carrier mobility before and after photo-aging. Finally, the broader
20
21
22 applicability of the ITO-2PACz anode was demonstrated with its application in OPVs
23
24
25 based on PM6:BTP-eC9:PC₇₁BM as the BHJ, exhibiting a PCE of 18.03%, which is the
26
27
28 highest reported to date for SAM-based OPVs. Our work highlights ITO-2PACz as a cost-
29
30
31 effective hole-selective contact technology for application in stable, high-efficiency OPVs.
32
33
34
35
36
37
38
39
40
41
42
43

44 ASSOCIATED CONTENT

45
46
47

48 **Supporting Information Available:** Fabrication and characterization details of OPVs,
49
50
51 methodology for DFT calculations, XPS analysis, AFM measurements, PESA
52
53
54
55
56
57
58
59
60

measurements, contact angle and surface energy characteristics, optimization of 2PACz-based OPVs, optical simulation, light intensity characterization of OPVs.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENT

This publication is based upon work supported by the King Abdullah University of Science and Technology (KAUST) Office of Sponsored Research (OSR) under Award No: OSR-2018-CARF/CCF-3079. L. T. acknowledges support for the computational time granted from GRNET in the National HPC facility -ARIS - under project STEM-2.

REFERENCES

- (1) Cui, Y.; Yao, H.; Zhang, J.; Xian, K.; Zhang, T.; Hong, L.; Wang, Y.; Xu, Y.; Ma, K.; An, C.; He, C.; Wei, Z.; Gao, F.; Hou, J., Single-Junction Organic Photovoltaic Cells with Approaching 18% Efficiency. *Adv. Mater.* **2020**, *32* (19), 1908205.
- (2) Liu, Q. S.; Jiang, Y. F.; Jin, K.; Qin, J. Q.; Xu, J. G.; Li, W. T.; Xiong, J.; Liu, J. F.; Xiao, Z.; Sun, K.; Yang, S. F.; Zhang, X. T.; Ding, L. M., 18% Efficiency organic solar cells. *Sci. Bull.* **2020**, *65* (4), 272-275.
- (3) Liu, L.; Kan, Y. Y.; Gao, K.; Wang, J. X.; Zhao, M.; Chen, H.; Zhao, C. J.; Jiu, T.; Jen, A. K. Y.; Li, Y. L., Graphdiyne Derivative as Multifunctional Solid Additive in Binary Organic Solar Cells with 17.3% Efficiency and High Reproducibility. *Adv. Mater.* **2020**, *32* (11), 1907604.
- (4) Lin, Y.; Firdaus, Y.; Nugraha, M. I.; Liu, F.; Karuthedath, S.; Emwas, A. H.; Zhang, W.; Seitkhan, A.; Neophytou, M.; Faber, H.; Yengel, E.; McCulloch, I.; Tsetseris, L.; Laquai, F.; Anthopoulos, T. D., 17.1% Efficient Single-Junction Organic Solar Cells Enabled by n-Type Doping of the Bulk-Heterojunction. *Adv. Sci.* **2020**, *7* (7), 1903419.
- (5) Lin, Y.; Adilbekova, B.; Firdaus, Y.; Yengel, E.; Faber, H.; Sajjad, M.; Zheng, X.; Yarali, E.; Seitkhan, A.; Bakr, O. M.; El-Labban, A.; Schwingenschlogl, U.; Tung, V.; McCulloch, I.; Laquai, F.; Anthopoulos, T. D., 17% Efficient Organic Solar Cells Based on Liquid Exfoliated WS₂ as a Replacement for PEDOT:PSS. *Adv. Mater.* **2019**, *31* (46), 1902965.
- (6) Firdaus, Y.; Le Corre, V. M.; Khan, J. I.; Kan, Z.; Laquai, F.; Beaujuge, P. M.; Anthopoulos, T. D., Key Parameters Requirements for Non-Fullerene-Based Organic Solar Cells with Power Conversion Efficiency > 20%. *Adv. Sci.* **2019**, *6* (9), 1802028.
- (7) Li, S.; Li, C.-Z.; Shi, M.; Chen, H., New Phase for Organic Solar Cell Research: Emergence of Y-Series Electron Acceptors and Their Perspectives. *ACS Energy Lett.* **2020**, *5* (5), 1554-1567.
- (8) Duan, C.; Zhong, C.; Huang, F.; Cao, Y., Interface Engineering for High Performance Bulk-Heterojunction Polymeric Solar Cells. In *Organic Solar Cells: Materials and Device Physics*, Choy, W. C. H., Ed. Springer London: London, 2013; pp 43-79.

- (9) Small, C. E.; Chen, S.; Subbiah, J.; Amb, C. M.; Tsang, S.-W.; Lai, T.-H.; Reynolds, J. R.; So, F., High-efficiency inverted dithienogermole–thienopyrrolodione-based polymer solar cells. *Nat. Photonics* **2011**, *6* (2), 115-120.
- (10) Huang, F.; Wu, H. B.; Wang, D.; Yang, W.; Cao, Y., Novel electroluminescent conjugated polyelectrolytes based on polyfluorene. *Chem. Mater.* **2004**, *16* (4), 708-716.
- (11) Zhang, Z. G.; Qi, B. Y.; Jin, Z. W.; Chi, D.; Qi, Z.; Li, Y. F.; Wang, J. Z., Perylene diimides: a thickness-insensitive cathode interlayer for high performance polymer solar cells. *Energ. Environ. Sci.* **2014**, *7* (6), 1966-1973.
- (12) Tan, W. Y.; Wang, R.; Li, M.; Liu, G.; Chen, P.; Li, X. C.; Lu, S. M.; Zhu, H. L.; Peng, Q. M.; Zhu, X. H.; Chen, W.; Choy, W. C. H.; Li, F.; Peng, J. B.; Cao, Y., Lending Triarylphosphine Oxide to Phenanthroline: a Facile Approach to High-Performance Organic Small-Molecule Cathode Interfacial Material for Organic Photovoltaics utilizing Air-Stable Cathodes. *Adv. Funct. Mater.* **2014**, *24* (41), 6540-6547.
- (13) Seitkhan, A.; Neophytou, M.; Kirkus, M.; Abou-Hamad, E.; Hedhili, M. N.; Yengel, E.; Firdaus, Y.; Faber, H.; Lin, Y.; Tsetseris, L., Use of the Phen-NaDPO: Sn (SCN) 2 Blend as Electron Transport Layer Results to Consistent Efficiency Improvements in Organic and Hybrid Perovskite Solar Cells. *Adv. Funct. Mater.* **2019**, *29* (49), 1905810.
- (14) Zeng, M.; Wang, X.; Ma, R.; Zhu, W.; Li, Y.; Chen, Z.; Zhou, J.; Li, W.; Liu, T.; He, Z.; Yan, H.; Huang, F.; Cao, Y., Dopamine Semiquinone Radical Doped PEDOT:PSS: Enhanced Conductivity, Work Function and Performance in Organic Solar Cells. *Adv. Energy Mater.* **2020**, 2000743.
- (15) Zheng, Z.; Hu, Q.; Zhang, S.; Zhang, D.; Wang, J.; Xie, S.; Wang, R.; Qin, Y.; Li, W.; Hong, L.; Liang, N.; Liu, F.; Zhang, Y.; Wei, Z.; Tang, Z.; Russell, T. P.; Hou, J.; Zhou, H., A Highly Efficient Non-Fullerene Organic Solar Cell with a Fill Factor over 0.80 Enabled by a Fine-Tuned Hole-Transporting Layer. *Adv. Mater.* **2018**, *30* (34), 1801801.
- (16) Tan, J. K.; Png, R. Q.; Zhao, C.; Ho, P. K. H., Ohmic transition at contacts key to maximizing fill factor and performance of organic solar cells. *Nat. Commun.* **2018**, *9* (1), 3269.

- (17) Li, G.; Shrotriya, V.; Huang, J. S.; Yao, Y.; Moriarty, T.; Emery, K.; Yang, Y., High-efficiency solution processable polymer photovoltaic cells by self-organization of polymer blends. *Nat. Mater.* **2005**, *4* (11), 864-868.
- (18) Wijeyasinghe, N.; Regoutz, A.; Eisner, F.; Du, T.; Tsetseris, L.; Lin, Y.-H.; Faber, H.; Pattanasattayavong, P.; Li, J.; Yan, F.; McLachlan, M. A.; Payne, D. J.; Heeney, M.; Anthopoulos, T. D., Copper(I) Thiocyanate (CuSCN) Hole-Transport Layers Processed from Aqueous Precursor Solutions and Their Application in Thin-Film Transistors and Highly Efficient Organic and Organometal Halide Perovskite Solar Cells. *Adv. Funct. Mater.* **2017**, *27* (35), 1701818.
- (19) de Jong, M. P.; van Ijzendoorn, L. J.; de Voigt, M. J. A., Stability of the interface between indium-tin-oxide and poly(3,4-ethylenedioxythiophene)/poly(styrenesulfonate) in polymer light-emitting diodes. *Appl. Phys. Lett.* **2000**, *77* (14), 2255-2257.
- (20) Al-Ashouri, A.; Magomedov, A.; Ross, M.; Jost, M.; Talaikis, M.; Chistiakova, G.; Bertram, T.; Marquez, J. A.; Kohnen, E.; Kasparavicius, E.; Levenco, S.; Gil-Escrig, L.; Hages, C. J.; Schlattmann, R.; Rech, B.; Malinauskas, T.; Unold, T.; Kaufmann, C. A.; Korte, L.; Niaura, G.; Getautis, V.; Albrecht, S., Conformal monolayer contacts with lossless interfaces for perovskite single junction and monolithic tandem solar cells. *Energ. Environ. Sci.* **2019**, *12* (11), 3356-3369.
- (21) Zhou, Z. M.; Pang, S. P., Highly efficient inverted hole-transport-layer-free perovskite solar cells. *J. Mater. Chem. A* **2020**, *8* (2), 503-512.
- (22) Yip, H. L.; Jen, A. K. Y., Recent advances in solution-processed interfacial materials for efficient and stable polymer solar cells. *Energ. Environ. Sci.* **2012**, *5* (3), 5994-6011.
- (23) Monson, T. C.; Lloyd, M. T.; Olson, D. C.; Lee, Y. J.; Hsu, J. W. P., Photocurrent Enhancement in Polythiophene- and Alkanethiol-Modified ZnO Solar Cells. *Adv. Mater.* **2008**, *20* (24), 4755-4759.
- (24) Zhang, S. H.; Zhan, L. L.; Li, S. X.; Li, C. Z.; Chen, H. Z., Enhanced performance of inverted non-fullerene organic solar cells through modifying zinc oxide surface with self-assembled monolayers. *Org. Electron.* **2018**, *63*, 143-148.

- (25) Kim, J. S.; Park, J. H.; Lee, J. H.; Jo, J.; Kim, D. Y.; Cho, K., Control of the electrode work function and active layer morphology via surface modification of indium tin oxide for high efficiency organic photovoltaics. *Appl. Phys. Lett.* **2007**, *91* (11), 112111.
- (26) Das, S.; Joslin, J.; Alford, T. L., Self-assembled monolayer modified ITO in P3HT:PC61BM organic solar cells with improved efficiency. *Sol. Energ. Mat. Sol. C.* **2014**, *124*, 98-102.
- (27) Li, A. Y.; Nie, R. M.; Deng, X. Y.; Wei, H. X.; Zheng, S. Z.; Li, Y. Q.; Tang, J. X.; Wong, K. Y., Highly efficient inverted organic solar cells using amino acid modified indium tin oxide as cathode. *Appl. Phys. Lett.* **2014**, *104* (12), 123303.
- (28) Hains, A. W.; Liu, J.; Martinson, A. B. F.; Irwin, M. D.; Marks, T. J., Anode Interfacial Tuning via Electron-Blocking/Hole-Transport Layers and Indium Tin Oxide Surface Treatment in Bulk-Heterojunction Organic Photovoltaic Cells. *Adv. Funct. Mater.* **2010**, *20* (4), 595-606.
- (29) Xu, X.; Xiao, J.; Zhang, G.; Wei, L.; Jiao, X.; Yip, H.-L.; Cao, Y., Interface-enhanced organic solar cells with extrapolated T80 lifetimes of over 20 years. *Sci. Bull.* **2020**, *65* (3), 208-216.
- (30) Yip, H. L.; Hau, S. K.; Baek, N. S.; Jen, A. K. Y., Self-assembled monolayer modified ZnO/metal bilayer cathodes for polymer/fullerene bulk-heterojunction solar cells. *Appl. Phys. Lett.* **2008**, *92* (19), 193313.
- (31) Yip, H. L.; Hau, S. K.; Baek, N. S.; Ma, H.; Jen, A. K. Y., Polymer solar cells that use self-assembled-monolayer-modified ZnO/Metals as cathodes. *Adv. Mater.* **2008**, *20* (12), 2376.
- (32) Wong, W. W. H.; Rudd, S.; Ostrikov, K.; Ramiasa-MacGregor, M.; Subbiah, J.; Vasilev, K., Plasma deposition of organic polymer films for solar cell applications. *Org. Electron.* **2016**, *32*, 78-82.
- (33) Stubhan, T.; Salinas, M.; Ebel, A.; Krebs, F. C.; Hirsch, A.; Halik, M.; Brabec, C. J., Increasing the Fill Factor of Inverted P3HT:PCBM Solar Cells Through Surface Modification of Al-Doped ZnO via Phosphonic Acid-Anchored C60 SAMs. *Adv. Energy Mater.* **2012**, *2* (5), 532-535.

- (34) Pujari, S. P.; Scheres, L.; Marcelis, A. T.; Zuilhof, H., Covalent surface modification of oxide surfaces. *Angew, Chem, Int, Ed, Engl*, **2014**, *53* (25), 6322-56.
- (35) Hotchkiss, P. J.; Jones, S. C.; Paniagua, S. A.; Sharma, A.; Kippelen, B.; Armstrong, N. R.; Marder, S. R., The modification of indium tin oxide with phosphonic acids: mechanism of binding, tuning of surface properties, and potential for use in organic electronic applications. *Acc. Chem. Res.* **2012**, *45* (3), 337-46.
- (36) Chastain, J., Handbook of X-ray photoelectron spectroscopy. *Perkin-Elmer Corporation* **1992**, *40*, 221.
- (37) Beamson, G., High resolution XPS of organic polymers. *The Scienta ESCA 300 Database* **1992**.
- (38) Wagstaffe, M.; Thomas, A. G.; Jackman, M. J.; Torres-Molina, M.; Syres, K. L.; Handrup, K., An experimental investigation of the adsorption of a phosphonic acid on the anatase TiO₂ (101) surface. *J. Phys. Chem. C* **2016**, *120* (3), 1693-1700.
- (39) Davies, P. R.; Newton, N. G., The chemisorption of organophosphorus compounds at an Al (1 1 1) surface. *Appl. Surf. Sci.* **2001**, *181* (3-4), 296-306.
- (40) Kang, M.-S.; Ma, H.; Yip, H.-L.; Jen, A. K. Y., Direct surface functionalization of indium tin oxide via electrochemically induced assembly. *J. Mater. Chem.* **2007**, *17* (33), 3489-3492.
- (41) Paniagua, S. A.; Li, E.; Marder, S. R., Adsorption studies of a phosphonic acid on ITO: film coverage, purity, and induced electronic structure changes. *Phys. Chem. Chem. Phys* **2014**, *16* (7), 2874-2881.
- (42) Paniagua, S. A.; Hotchkiss, P. J.; Jones, S. C.; Marder, S. R.; Mudalige, A.; Marrikar, F. S.; Pemberton, J. E.; Armstrong, N. R., Phosphonic acid modification of indium– tin oxide electrodes: combined XPS/UPS/contact angle studies. *J. Phys. Chem. C* **2008**, *112* (21), 7809-7817.
- (43) Seah, M., Simple universal curve for the energy-dependent electron attenuation length for all materials. *Surf. Interface Anal.* **2012**, *44* (10), 1353-1359.
- (44) Hotchkiss, P. J.; Li, H.; Paramonov, P. B.; Paniagua, S. A.; Jones, S. C.; Armstrong, N. R.; Bredas, J. L.; Marder, S. R., Modification of the Surface Properties of Indium Tin Oxide with Benzylphosphonic Acids: A Joint Experimental and Theoretical Study. *Adv. Mater.* **2009**, *21* (44), 4496.

- (45) Owens, D. K.; Wendt, R. C., Estimation of the surface free energy of polymers. *J. Appl. Polym. Sci.* **1969**, *13* (8), 1741-1747.
- (46) Jiang, K.; Wei, Q. Y.; Lai, J. Y. L.; Peng, Z. X.; Kim, H.; Yuan, J.; Ye, L.; Ade, H.; Zou, Y. P.; Yan, H., Alkyl Chain Tuning of Small Molecule Acceptors for Efficient Organic Solar Cells. *Joule* **2019**, *3* (12), 3020-3033.
- (47) Pettersson, L. A. A.; Roman, L. S.; Inganas, O., Modeling photocurrent action spectra of photovoltaic devices based on organic thin films. *J. Appl. Phys.* **1999**, *86* (1), 487-496.
- (48) Kyaw, A. K.; Wang, D. H.; Gupta, V.; Leong, W. L.; Ke, L.; Bazan, G. C.; Heeger, A. J., Intensity dependence of current-voltage characteristics and recombination in high-efficiency solution-processed small-molecule solar cells. *ACS Nano* **2013**, *7* (5), 4569-77.
- (49) Firdaus, Y.; Maffei, L. P.; Cruciani, F.; Muller, M. A.; Liu, S. J.; Lopatin, S.; Wehbe, N.; Ndjawa, G. O. N.; Amassian, A.; Laquai, F.; Beaujuge, P. M., Polymer Main-Chain Substitution Effects on the Efficiency of Nonfullerene BHJ Solar Cells. *Adv. Energy Mater.* **2017**, *7* (21), 1700834.
- (50) Shuttle, C. G.; O'Regan, B.; Ballantyne, A. M.; Nelson, J.; Bradley, D. D. C.; Durrant, J. R., Bimolecular recombination losses in polythiophene: Fullerene solar cells. *Phys. Rev. B* **2008**, *78* (11), 113201.
- (51) Yao, E. P.; Chen, C. C.; Gao, J.; Liu, Y. S.; Chen, Q.; Cai, M.; Hsu, W. C.; Hong, Z. R.; Li, G.; Yang, Y., The study of solvent additive effects in efficient polymer photovoltaics via impedance spectroscopy. *Sol. Energ. Mat. Sol. C.* **2014**, *130*, 20-26.
- (52) Braun, S.; Salaneck, W. R.; Fahlman, M., Energy-Level Alignment at Organic/Metal and Organic/Organic Interfaces. *Adv. Mater.* **2009**, *21* (14-15), 1450-1472.
- (53) Yao, E.-P.; Chen, C.-C.; Gao, J.; Liu, Y.; Chen, Q.; Cai, M.; Hsu, W.-C.; Hong, Z.; Li, G.; Yang, Y., The study of solvent additive effects in efficient polymer photovoltaics via impedance spectroscopy. *Sol. Energ. Mat. Sol. C.* **2014**, *130*, 20-26.

- (54) Park, S.; Ahn, H.; Kim, J.-y.; Park, J. B.; Kim, J.; Im, S. H.; Son, H. J., High-Performance and Stable Nonfullerene Acceptor-Based Organic Solar Cells for Indoor to Outdoor Light. *ACS Energy Lett.* **2019**, *5* (1), 170-179.
- (55) Zhao, Q. Q.; Xiao, Z.; Qu, J. F.; Liu, L. Z.; Richter, H.; Chen, W.; Han, L.; Wang, M. J.; Zheng, J. M.; Xie, Z. Q.; Ding, L. M.; He, F., Elevated Stability and Efficiency of Solar Cells via Ordered Alloy Co-Acceptors. *Acs Energy Lett.* **2019**, *4* (5), 1106-1114.
- (56) McNeill, C. R.; Hwang, I.; Greenham, N. C., Photocurrent transients in all-polymer solar cells: Trapping and detrapping effects. *J. Appl. Phys.* **2009**, *106* (2), 024507.
- (57) Xiao, J. Y.; Ren, M. R.; Zhang, G. C.; Wang, J. B.; Zhang, D. L.; Liu, L. L.; Li, N.; Brabec, C. J.; Yip, H. L.; Cao, Y., An Operando Study on the Photostability of Nonfullerene Organic Solar Cells. *Solar Rrl* **2019**, *3* (7), 1900077.
- (58) Tremolet de Villers, B. J.; MacKenzie, R. C.; Jasieniak, J. J.; Treat, N. D.; Chabiny, M. L., Linking Vertical Bulk-Heterojunction Composition and Transient Photocurrent Dynamics in Organic Solar Cells with Solution-Processed MoO_x Contact Layers. *Adv. Energy Mater.* **2014**, *4* (5), 1301290.
- (59) Clarke, T. M.; Lungenschmied, C.; Peet, J.; Drolet, N.; Mozer, A. J., A Comparison of Five Experimental Techniques to Measure Charge Carrier Lifetime in Polymer/Fullerene Solar Cells. *Adv. Energy Mater.* **2015**, *5* (4), 1401345.